



Designation: ~~C897-00~~ Designation: C 897 - 05

Standard Specification for Aggregate for Job-Mixed Portland Cement-Based Plasters¹

This standard is issued under the fixed designation C 897; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers natural or manufactured aggregate for use in job-mixed base and finish-coat full thickness portland cement, portland cement-lime and modified portland cement plasters.

1.2 The values stated in inch-pound units are to be regarded as the standard. The SI (metric) values given in parentheses are approximate and are provided for information purposes only.

1.3 The text of this specification references notes and footnotes that provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the specification.

2. Referenced Documents

2.1 ASTM Standards:²

C 11 Terminology Relating to Gypsum and Related Building Materials and Systems

C 40 Test Method for Organic Impurities in Fine Aggregates for Concrete

C 87 Test Method for Effect of Organic Impurities in Fine Aggregate on Strength of Mortar

C 88 Test Method for Soundness of Aggregates by Use of Sodium Sulfate or Magnesium Sulfate

C 117 Test Method for Material Finer than 75-Micrometre (75- μm) (No. 200) Sieve in Mineral Aggregates by Washing

C 123 Specification for Lightweight Pieces in Aggregate³ Test Method for Lightweight Particles in Aggregate

C 125 Terminology Relating to Concrete and Concrete Aggregates

C 136 Test Method for Sieve Analysis of Fine and Coarse Aggregates

C 142 Test Method for Clay Lumps and Friable Particles in Aggregates

D 75 Practice for Sampling Aggregates

3. Terminology

3.1 *Definitions*—Definitions used in this standard shall be in accordance with Terminologies C 11 and C 125.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *aggregate, n*—a granular material such as natural or manufactured sand used with a cementing medium to form plaster (stucco).

3.2.2 *manufactured sand* *manufactured sand, n*—the fine material resulting from the crushing and classification by screening, or otherwise, of rock, gravel, or blast furnace slag.

3.2.3 *natural sand* *natural sand, n*—the fine granular material resulting from the natural disintegration of rock.

4. Composition

4.1 *Deleterious Substances*—The amount of deleterious substances in aggregates, each determined on independent samples complying with the grading requirements of Section 6, shall not be more than the following:

Item	Maximum Permissible Weight, %
Friable particles	1.0
Light weight particles, floating on liquid having a specific gravity of 2.0	0.5

4.2 Organic Impurities:

¹ This specification is under the jurisdiction of ASTM Committee C11 on Gypsum and Related Building Materials and Systems, and is the direct responsibility of Subcommittee C 11.02 on Specifications and Test Methods for Accessories and Related Products.

Current edition approved May 10, 2000. Published July 2000. Originally published as C897-78. Last previous edition C897-96.

Current edition approved Dec. 1, 2005. Published December 2005. Originally approved in 1978. Last previous edition approved in 2000 as C 897 - 00.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.