
**Metallic and other inorganic coatings —
Cleaning and preparation of metal
surfaces —**

**Part 1:
Ferrous metals and alloys**

*Revêtements métalliques et autres revêtements inorganiques —
Nettoyage et préparation des surfaces métalliques —
Partie 1. Métaux ferreux et alliages*

[ISO 27831-1:2008](https://standards.iteh.ai/catalog/standards/sist/226d5240-5aed-49ee-9f6b-dabebf69d811/iso-27831-1-2008)

<https://standards.iteh.ai/catalog/standards/sist/226d5240-5aed-49ee-9f6b-dabebf69d811/iso-27831-1-2008>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 27831-1:2008](https://standards.iteh.ai/catalog/standards/sist/226d5240-5aed-49ee-9f6b-dabebf69d811/iso-27831-1-2008)

<https://standards.iteh.ai/catalog/standards/sist/226d5240-5aed-49ee-9f6b-dabebf69d811/iso-27831-1-2008>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	vi
Introduction	vii
1 Scope	1
2 Normative references	2
3 Terms and definitions.....	2
4 Essential information to be supplied by the purchaser to the processor	3
5 Requirements	3
6 Standard cleaning methods.....	4
7 Non-corrosion-resisting steels, cast irons and pure irons	5
7.1 Non-corrosion-resisting steels.....	5
7.1.1 Selection of method of cleaning	5
7.1.2 Stress relief heat treatment	5
7.1.3 General degreasing and cleaning	5
7.1.3.1 Steels of tensile strength up to 1 000 MPa	5
7.1.3.2 Steels of tensile strength in the range 1 000 MPa to 1 400 MPa	5
7.1.3.3 Steels of tensile strength in the range 1 400 MPa to 1 800 MPa	5
7.1.3.4 Steels of tensile strength over 1 800 MPa	6
7.1.4 Preparation prior to electroplating.....	6
7.1.5 Preparation prior to autocatalytic nickel plating.....	7
7.1.6 Preparation prior to phosphate treatment.....	7
7.1.7 Preparation prior to sherardizing.....	7
7.1.8 Preparation prior to hot-dip galvanizing	8
7.1.8.1 Steel items other than castings	8
7.1.8.2 Steel castings	8
7.1.9 Preparation prior to metal spraying.....	8
7.1.9.1 Spraying for protection against corrosion and high-temperature oxidation.....	8
7.1.9.2 Spraying for reclamation (recycling) purposes	8
7.1.10 Preparation prior to the application of diffusion coatings	8
7.1.11 Preparation prior to vitreous enamelling	9
7.1.11.1 Conventional enamelling method.....	9
7.1.11.2 Alternative enamelling method.....	9
7.1.12 Preparation prior to hot tinning.....	10
7.1.12.1 Preparation for ordinary mild-steel surfaces	10
7.1.12.2 Preparation of non-reactive mild-steel surfaces (TRI process)	10
7.1.13 Preparation prior to physical vapour deposition of cadmium and aluminium.....	10
7.2 Cast irons	10
7.2.1 General degreasing and cleaning	10
7.2.2 Preparation prior to electroplating.....	10
7.2.3 Preparation prior to autocatalytic nickel plating	10
7.2.4 Preparation prior to phosphating and the application of other conversion coatings.....	10
7.2.5 Preparation prior to hot tinning.....	11
7.2.5.1 “Direct chloride” method (TRI process)	11
7.2.5.2 Preparation prior to electroplating with a readily tin-platable metal	11
7.2.6 Preparation prior to hot-dip galvanizing	11
7.2.7 Preparation prior to metal spraying.....	11
7.2.8 Preparation prior to diffusion coating	12
7.2.9 Preparation prior to vitreous enamelling	12
8 Corrosion-resisting and heat-resisting steels	12

8.1	Corrosion-resisting steels.....	12
8.1.1	Stress-relieving heat treatment	12
8.1.2	General degreasing and cleaning	12
8.1.3	Preparation prior to electroplating	12
8.1.4	Preparation prior to autocatalytic nickel plating	12
8.1.5	Preparation prior to metal spraying	12
8.1.5.1	Preparation for metal spraying	12
8.1.5.2	Spraying for reclamation (recycling) purposes.....	13
8.1.6	Preparation prior to vitreous enamelling — Austenitic steels	13
8.2	Heat-resisting steels	13
9	Pretreatment of metals prior to powder coating.....	14
9.1	General degreasing and cleaning	14
9.2	Preparation of non-corrosion-resisting steels.....	14
9.3	Preparation of corrosion-resisting steels.....	14
10	Cleaning and preparation processes	14
10.1	Process A — Organic-solvent degreasing and cleaning	14
10.1.1	General	14
10.1.2	Method A1 — Hot solvent, not water-rinsable	15
10.1.3	Method A2 — Cold solvent, not water-rinsable	15
10.1.4	Method A3 — Hot solvent, water-rinsable	15
10.1.5	Method A4 — Cold solvent, water-rinsable	15
10.1.6	Method A5 — Petroleum fuel based mixtures containing emulsifying agents	15
10.1.7	Method A6 — Ultrasonic cleaning	16
10.2	Process B — Alkaline degreasing	16
10.2.1	General	16
10.2.2	Method B1 — General-purpose alkaline degreasing.....	16
10.2.3	Method B2 — Mild alkaline degreasing	16
10.2.4	Method B3 — Cathodic alkaline degreasing	16
10.3	Process C — Acid emulsion cleaning	16
10.4	Process D — Abrasive cleaning	17
10.4.1	General	17
10.4.2	Method D1 — Coarse-abrasive blasting	17
10.4.3	Method D2 — Fine-abrasive blasting	17
10.4.4	Method D3 — Scouring	17
10.4.5	Method D4 — Tumbling	17
10.4.6	Method D5 — Wire brushing	17
10.5	Process E — Caustic-alkali descaling	18
10.5.1	Method E1 — Sodium hydride descaling	18
10.5.2	Method E2 — Alkali permanganate descaling	18
10.6	Process F — Acid pickling without electrolysis	18
10.6.1	General	18
10.6.2	Method F1	18
10.6.3	Method F2	18
10.6.4	Method F3	18
10.6.5	Method F4	19
10.6.6	Method F5	19
10.7	Process G — Acid dipping	19
10.7.1	General	19
10.7.2	Method G1	19
10.7.3	Method G2	19
10.8	Process H — Anodic pickling	20
10.8.1	General	20
10.8.2	Method H1	20
10.8.3	Method H2	20
10.8.4	Method H3	20
10.9	Process J — Acid de-rusting	20
10.10	Process K — Alkaline de-rusting.....	21
10.10.1	General	21
10.10.2	Method K1 (for light rust)	21

10.10.3 Method K2 (for heavy rust)	21
10.10.4 Method K3 (for heavy rust)	22
10.11 Process L — Chemical smoothing and electropolishing of steels	22
10.11.1 Method L1 — Chemical smoothing process (for non-corrosion-resisting steels)	22
10.11.2 Method L2 — Electropolishing of corrosion-resisting steels	22
10.12 Process M — Passivation and removal of surface contamination from corrosion-resisting steels and surface preparation prior to electroplating	23
10.12.1 Method M1 — Passivation	23
10.12.2 Method M2 — Test for surface contamination	23
10.12.3 Method M3 — Alternative test for surface contamination	23
10.12.4 Method M4 — Preparation of corrosion-resisting steels prior to electroplating	24
Annex A (informative) Maintenance of organic and vapour degreasing baths	25
Annex B (informative) The control of acidity in vapour cleaning baths	26
Annex C (normative) Method for the determination of oxidizable material in sulfuric acid	27
Bibliography	28

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 27831-1:2008](https://standards.iteh.ai/catalog/standards/sist/226d5240-5aed-49ee-9f6b-dabebf69d811/iso-27831-1-2008)

<https://standards.iteh.ai/catalog/standards/sist/226d5240-5aed-49ee-9f6b-dabebf69d811/iso-27831-1-2008>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 27831-1 was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*, Subcommittee SC 3, *Electrodeposited coatings and related finishes*.

ISO 27831 consists of the following parts, under the general title *Metallic and other inorganic coatings — Cleaning and preparation of metal surfaces*:

— Part 1: *Ferrous metals and alloys*

[ISO 27831-1:2008](https://standards.iteh.ai/catalog/standards/sist/226d5240-5aed-49ee-9f6b-dabebf69d811/iso-27831-1-2008)

— Part 2: *Non-ferrous metals and alloys*

<https://standards.iteh.ai/catalog/standards/sist/226d5240-5aed-49ee-9f6b-dabebf69d811/iso-27831-1-2008>

Introduction

The adhesion of deposited coatings depends upon the efficiency of degreasing and cleaning processes used on the substrate surface. The removal of grease, oil and dirt and all other forms of contamination left from fabrication processes or due to corrosion/erosion of surfaces in storage or in service is essential for successful production of a pristine, chemically clean active surface for deposition of coatings.

The surface contaminants can be

- corrosion products, mould sand or mould release agents on ferrous and non-ferrous castings;
- corrosion products and mill scales on hot-rolled steel sheet, girders, etc. (broken mill scale is cathodic to the underlying substrate);
- oil and rolling lubricant on cold-rolled steel sheet;
- rolling lubricant on e.g. cold-rolled aluminium sheet;
- corrosion products on delivery or during storage on hot-dip-galvanized steel sheet or angle bars/brackets;
- other undesirable materials from storage and handling.

The difficulty of coating these surfaces is well known.

Cleaning processes for removing surface contaminants are varied, depending, among other things, on the identification and classification of the soil as well as the size and shape of the substrate, the degree of cleanliness required, the availability of the facilities needed, the cost of the processes used and their impact on the environment, and the nature of subsequent processes to which the substrate is going to be subjected.

ISO 27831 includes cleaning processes ranging from mechanical methods (which give the least degree of cleanliness) to chemical and ultrasonic methods (which give a higher degree of surface preparation) and substrate conditioning by glow discharge plasma (sputter cleaning) for vapour deposition.

ISO 27831 describes practices for cleaning a variety of metals and metal alloys prior to the application of a range of coatings or without any coating requirements.

The cleaning processes described in ISO 27831-1 and ISO 27831-2 are indicative only of those most commonly used in practice. However, there are numerous formulations of solutions and numerous proprietary processes available which are not included in ISO 27831-1 or ISO 27831-2. Wherever possible, references to particular processes have been made. For references concerning all other processes included in either part of ISO 27831, the publications given in the Bibliography in the respective part should be consulted.

ISO 27831-1 covers ferrous metals and their alloys, whilst ISO 27831-2 covers non-ferrous metals and their alloys. For ISO 27831-2 to be usable, as far as possible, as a “stand-alone” document, Clauses 1 to 6 of ISO 27831-1 have been included in it as Clauses 1 to 6 and the numbering of the other clauses follows the same sequence as in ISO 27831-1. Additionally, since some of the cleaning and preparation processes specified for ferrous materials in ISO 27831-1 can also be used for non-ferrous metals, the cleaning and preparation processes follow the same sequence, using the same designations, as in ISO 27831-1.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 27831-1:2008

<https://standards.iteh.ai/catalog/standards/sist/226d5240-5aed-49ee-9f6b-dabebf69d811/iso-27831-1-2008>

Metallic and other inorganic coatings — Cleaning and preparation of metal surfaces —

Part 1: Ferrous metals and alloys

WARNING — This part of ISO 27831 may not be compliant with some countries' health, safety and environmental legislation. It calls for the use of substances and/or procedures that may be injurious to health if adequate safety measures are not taken. This part of ISO 27831 does not address any health hazards, safety or environmental matters, or legislation associated with its use. It is the responsibility of the user of this part of ISO 27831 to establish appropriate health, safety and environmentally acceptable practices and take appropriate action to comply with any national, regional and/or international regulations. Compliance with this part of ISO 27831 does not, of itself, confer immunity from legal obligations.

1 Scope

iTeh STANDARD PREVIEW

This part of ISO 27831 specifies processes for the cleaning of the surfaces of ferrous metals and their alloys to remove any irrelevant or unwanted deposits or other material at any stage of manufacture, storage or service and for the preparation of these surfaces for further treatment. It does not cover cleaning operations associated with the preliminary removal of heavy deposits of oil, grease or dirt accumulated during operational service, preparations for welding or the cleaning of electrical contacts. However, many of the processes included in this part of ISO 27831 may be used for these operations at the discretion of the users of this part of ISO 27831.

This part of ISO 27831 covers processes which are needed for the preparation of metal surfaces prior to the application of the following surface coatings:

- electrodeposited metal coatings;
- autocatalytic metal coatings (autocatalytic and displacement types);
- conversion coatings;
- hot-dipped coatings;
- sprayed metal coatings;
- diffusion coatings;
- coatings produced by vitreous enamelling;
- coatings produced by physical vapour deposition of aluminium and cadmium;
- powder coatings.

ISO 27831-1:2008(E)

This part of ISO 27831 describes processes for carrying out the following treatments:

- degreasing;
- descaling;
- pickling;
- de-rusting;
- chemical smoothing;
- electropolishing.

This part of ISO 27831 relates the processes described above to the following metals:

- non-corrosion-resisting steels, cast irons and pure irons;
- corrosion-resisting and heat-resisting steels.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2064, *Metallic and other inorganic coatings — Definitions and conventions concerning the measurement of thickness*

<https://standards.iteh.ai/catalog/standards/sist/226d5240-5aed-49ee-9f6b-dabebf69d811/iso-27831-1-2008>

ISO 2080, *Metallic and other inorganic coatings — Surface treatment, metallic and other inorganic coatings — Vocabulary*

ISO 4527, *Metallic coatings — Autocatalytic (electroless) nickel-phosphorus alloy coatings — Specification and test methods*

ISO 9587, *Metallic and other inorganic coatings — Pretreatment of iron or steel to reduce the risk of hydrogen embrittlement*

ISO 9588, *Metallic and other inorganic coatings — Post-coating treatments of iron or steel to reduce the risk of hydrogen embrittlement*

ISO 22778, *Metallic coatings — Physical vapour-deposited coatings of cadmium on iron and steel — Specification and test methods*

ISO 22779, *Metallic coatings — Physical vapour-deposited coatings of aluminium — Specification and test methods*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 2064, ISO 2080, ISO 9587, ISO 9588, ISO 22778 and ISO 22779 apply.

4 Essential information to be supplied by the purchaser to the processor

When ordering articles to be processed in accordance with this part of ISO 27831, the purchaser shall provide the following information in writing, e.g. in the contract, in the purchase order or on the engineering drawing:

- a) the number of this part of ISO 27831 (ISO 27831-1);
- b) the specification and metallurgical condition of the material of which the item is made;
- c) the tensile strength of the steel components and the requirements for stress relief and post-cleaning embrittlement relief heat treatments of the steel to reduce the risk of hydrogen embrittlement (see 7.1);
- d) the cleaning method or methods given in this part of ISO 27831 which are to be used, and any deviation from these methods (e.g. the use of a proprietary method for health or safety reasons);
- e) details of any particular requirements for special surfaces;
- f) details of any special procedures (e.g. process H, method H1);
- g) details of any particularly difficult surface condition and any special information regarding coatings to be removed or coatings or inserts to be protected;
- h) where appropriate, details of the surface coating which is to be subsequently applied.

5 Requirements

iTeh STANDARD PREVIEW
(standards.iteh.ai)

5.1 Any materials used for cleaning and preparation shall contain not more than a mass fraction of 5×10^{-6} of mercury (Hg). Where items can be regarded as susceptible to degradation by residual arsenic and/or antimony, the following maximum limitations shall also apply:

for arsenic (As): a mass fraction of 15×10^{-6} ;

for antimony (Sb): a mass fraction of 15×10^{-6} .

NOTE 1 The presence of arsenic, reduced sulfur or reduced phosphorous compounds in an acid bath will promote absorption of hydrogen by steel and may reduce the adhesion of subsequently applied coatings.

NOTE 2 Contamination of steel components can occur when antimony-inhibited solutions are used. The resultant deposit of antimony on exposed surfaces can adversely affect the properties of the steel and subsequent processing of the item. If processing solutions become contaminated, this can lead to further items being similarly affected.

5.2 When assembled items are being processed, the treatments chosen shall be suitable for each constituent material and the combination of materials.

5.3 Items will often require a sequence of several degreasing and cleaning treatments. Solvent cleaning may occasionally leave traces of soil after evaporation of the solvent and care shall be taken to remove such contamination. Inorganic contamination may not always be removed by organic solvents. It may therefore be necessary to use additional aqueous processes after final degreasing and cleaning.

5.3.1 The surfaces shall be free from grease, oil, oxide, scale and other foreign matter and shall be in a chemically clean condition, i.e. fully receptive to any subsequent processing.

To test for surface cleanliness, the cleaned surface may be sprayed with, or immersed in, cool, clean water. On clean surfaces, the water will form a uniform film whereas, in the presence of oily soils, the water film will break away from contaminated areas. In cases of gross contamination, the entire film may break down into discrete globules. If the surface to be tested has any residue of cleaning agent containing surface-active agent, a continuous film may be obtained even in the presence of grease. This false effect can be overcome by dipping the surface in dilute acid and rinsing before carrying out the test. Subsequent specified treatments shall be applied without delay.

5.3.2 Abrasives used on any metal or alloy shall not also be used on any dissimilar metal or alloy. Separate abrasive cleaning media shall be used for different alloy families, for example iron and its alloys, aluminium and its alloys. Thus alumina, for example, used for abrasive cleaning of aluminium surfaces, shall not have been used for any other type of material, such as steel or copper-rich alloys, or been otherwise externally contaminated.

Shot peening of the basis metal or substrate, if required, shall be performed before final cleaning and the application of the coating.

5.3.3 The mechanical properties shall not be impaired except where they may be recovered by subsequent heat, or other, treatments forming part of the normal processing sequence.

5.3.4 The dimensions and surface finish shall be such as to enable the finished (e.g. electroplated) items to be within the required drawing or specification limits.

5.4 Where solvent cleaning is used, corrosion of items, particularly those made from light alloys, may occur if they are subjected to heat before all the solvent has disappeared from the surfaces. Thus, solvents which thermally degrade with the liberation of corrosive products shall not be used. Care shall also be taken to ensure that all traces of liquid are removed from items of complex form or containing blind holes. Bundles of items intended for immediate heat treatment shall be shaken to ensure that liquid is not retained by capillary attraction between surfaces in contact. In any event, after removal from the degreaser, items shall not be immersed in a molten salt bath until they are completely dry and have reached room temperature.

It is not good practice to allow an interval between treatments. It shall be borne in mind that degreasing and cleaning procedures produce a surface whose resistance to corrosive attack is low. Consequently, readily corrodible materials need to be protectively coated or further processed immediately.

5.5 Immediately after each treatment in an aqueous solution, the items shall be thoroughly rinsed in clean hot and/or clean cold water, as appropriate, paying special attention to items containing crevices. Immediately after the final rinsing, the metal surface shall not exhibit a water break. Water used for final rinsing after processing shall be discarded or retreated when the conductivity exceeds 10 $\mu\text{S}/\text{cm}$.

5.6 After the final rinsing or other final preparatory treatment, items to be given a protective treatment in aqueous solutions shall be transferred immediately, without drying, to the treatment bath.

5.7 Items to be given further treatment by dry processes and items which are not to be subjected to further processing shall be thoroughly dried.

5.7.1 Where drying in a draught of warm air is recommended, the air shall be free from oil and other contaminants.

5.7.2 The use of chlorinated solvents for drying purposes is not permitted.

5.8 All stages of the degreasing and cleaning procedures shall follow each other without delay.

5.9 The acid and alkaline solutions used in some of the cleaning and preparation processes can have a deleterious effect on unstable materials. When an item is for use with unstable materials, particular care shall be taken to ensure that all such solutions are completely removed by thorough washing with clean water. Special attention shall be paid to irregularly shaped items and to blind holes and crevices.

5.10 Where limits of composition of solutions are known, they are quoted in this part of ISO 27831. Where limits are not quoted, other proportions may be used provided they are within a tolerance of $\pm 10\%$.

6 Standard cleaning methods

6.1 The processes and methods described in this part of ISO 27831 are indicative only of those most commonly used in practice. However, there are numerous formulations of solutions and proprietary processes available which are not included in this part of ISO 27831. Throughout this part of ISO 27831, the process and method designations in brackets which follow references to cleaning treatments refer to the processes and methods in Clause 10.