

SLOVENSKI STANDARD SIST ISO 427:1995

01-november-1995

Zlitine bakra s kositrom, primerne za gnetenje - Kemična sestava in oblike izdelkov, preoblikovanih z gnetenjem

Wrought copper-tin alloys -- Chemical composition and forms of wrought products

Alliages cuivre-étain corroyés - Composition chimique et formes des produits corroyés (standards.iteh.ai)

Ta slovenski standard je istoveten z: ISO 427:1983

660640cbe85e/sist-iso-427-1995

ICS:

77.150.30 Bakreni izdelki Copper products

SIST ISO 427:1995 en

SIST ISO 427:1995

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST ISO 427:1995

https://standards.iteh.ai/catalog/standards/sist/e36c10de-3d6f-4a2e-b9ea-660640cbe85e/sist-iso-427-1995

International Standard



427

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION●МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ●ORGANISATION INTERNATIONALE DE NORMALISATION

Wrought copper-tin alloys — Chemical composition and forms of wrought products

Alliages cuivre-étain corroyés — Composition chimique et formes des produits corroyés

Second edition - 1983-10-15 STANDARD PREVIEW (standards.iteh.ai)

SIST ISO 427:1995 https://standards.iteh.ai/catalog/standards/sist/e36c10de-3d6f-4a2e-b9ea-660640cbe85e/sist-iso-427-1995

UDC 669.35.6-13 Ref. No. ISO 427-1983 (E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been authorized has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 427 was developed by Technical Committee ISO/TC 26, Copper and copper alloys, and was circulated to the member bodies in November 1981.

It has been approved by the member bodies of the following countries: 1995

https://standards.iteh.ai/catalog/standards/sist/e36c10de-3d6f-4a2e-b9ea-

Austria Germany, F.R.

Germany, F.R. 660640cbe South Africa, Rep. of

Belgium Hungary
Brazil Italy
Bulgaria Japan
Canada Korea, D

ary Spain Sweden Switzerland

China Czechoslovakia Korea, Dem. P. Rep. of Turkey
Netherlands United Kingdom

Czechoslovakia Egypt, Arab Rep. of Norway USA Poland USSR

Finland Romania

The member body of the following country expressed disapproval of the document on technical grounds:

France

This second edition cancels and replaces the first edition (i.e. ISO 427-1973).

Wrought copper-tin alloys — Chemical composition and forms of wrought products

1 Scope and field of application

This International Standard specifies the chemical composition of wrought copper-tin alloys and lists the forms of wrought products in which they are currently available in commercial S 11 quantities.

For the purpose of this International Standard, the definitions given in ISO 197/1 and ISO 197/3 apply.

ISO 6957, Wrought copper alloys — Strip for springs. 1)

 $\frac{1}{1000} \frac{1}{1000} \frac{1}{1000$

Definitions

2 References

https://standards.iteh.ai/catalog/standards/sist/e36c10de-3d6f-4a2e-b9ea-660640cbe85e/sist-iso**4**¹²⁷**Chemical composition**

ISO 197, Copper and copper alloys — Terms and definitions Part 1: Materials.

Part 3: Wrought products.

ISO 1190/1, Copper and copper alloys — Code of designation — Part 1: Designation of materials.

ISO 1634/1, Wrought copper and copper alloys — Mechanical properties — Part 1: Plate, sheet and strip for general purposes. 1)

ISO 1635, Wrought copper and copper alloys — Round tubes for general purposes — Mechanical properties. 1)

ISO 1637, Wrought copper and copper alloys — Rod and bar — Mechanical properties. ²⁾

ISO 1638, Wrought copper and copper alloys — Wire — Mechanical properties. ²⁾

ISO 4382/2, Plain bearings — Copper alloys — Part 2: Wrought copper alloys for solid plain bearings.

The chemical composition of the copper alloys is given in tables 1 and 2. The composition limits do not preclude the possible presence of other elements not specified. If the purchaser's requirements necessitate limits for any other element not specified, these shall be agreed upon between the supplier and the purchaser. Percentage content of elements shown as "remainder" is usually calculated by difference from 100 %.

The designations used are in accordance with the principles laid down in ISO 1190/1.

5 Forms of wrought products and mechanical properties

The forms of wrought products in which these copper alloys are available are given in table 3. The mechanical properties for all forms of wrought products for which the symbol X is given, are defined in the following International Standards:

ISO 1634/1, ISO 1635, ISO 1637, ISO 1638, ISO 6957.

¹⁾ At present at the stage of draft.

²⁾ Under revision.

ISO 427-1983 (E)

Table 1 — Copper-tin alloys

Designation	Element	Chemical composition by mass, %							
		Cu	Fe	Ni	P	Pb	Sn	Zn	density kg/dm ³
CuSn2	min. max.	Rem.	_ 0,1	_ 0,3	0,01 0,3	 0,05	1,0 2,5	_ 0,3	8,9
CuSn4	min. max.	Rem.	_ 0,1	0,3	0,01 0,4	_ 0,05	3,5 4,5	_ 0,3	8,9
CuSn5	min. max.	Rem.	_ 0,1	_ 0,3	0,01 0,4	_ 0,05	4,5 5,5	_ 0,3	8,9
CuSn6	min. max.	Rem.	0,1	0,3	0,01 0,4	0,05	5,5 7,5	0,3	8,8
CuSn8	min. max.	Rem.	_ 0,1	0,3	0,01 0,4	_ 0,05	7,5 9,0	_ 0,3	8,8
CuSn8P1)	min. max.	Rem.	_ 0,1	0,3	0,1 0,4	_ 0,05	7,5 9,0	0,3	8,8

¹⁾ Mainly for wear resistance applications, e.g. plain bearings according to ISO 4382/2.

Table 2 — Special copper-tin alloys

Designation	Element	Chemical composition by mass, %							
		Cu	Fe	Ni	Р	Pb	Sn	Zn	density kg/dm ³
CuSn4Zn2	min. max.	Tem. S) PRI	0,05	3,0 5,0	1,0 3,0	8,9
CuSn4Pb4Zn3	min. max.	Rem.	stand 0,10	lards.	ite <u>o</u> n.a	3,5 4,5	3,5 4,5	1,5 4,5	8,9

SIST ISO 427:1995

https://standards.itels.ai/crtalog/standards/sist/e36c10de_3d6f-4a2e-b9ea-

KEY:

X - main manufactured forms.

(X) — forms manufactured in smaller quantities, for example in certain countries only or for special purposes.

NOTE — Where no symbol is given, the form is not considered of importance for that type of copper alloy, but it does not necessarily indicate that such a product cannot be manufactured.

Designation	Plate, sheet		Strip		Tubes					
	General purpose	Boilers	General purpose	Springs	General purpose	Condenser	Rod, bar	Wire	Extruded profiles 1)	Forgings
Copper-tin allo	ys							·		
CuSn2			(X)		(X)		(X)	(X)		
CuSn4	(X)		×	Х	(X)		(X)	(X)		
CuSn5	(X)		X	Х	(X)		Х	×		
CuSn6	Х		Х	Х	(X)		Х	Х		
CuSn8	Х		X	Х	Х		Х	Х		
CuSn8P			(X) ²⁾		(X) ²⁾		(X) ²⁾			
Special copper	tin alloys									
CuSn4Zn2	X3)		X3)		1					ĺ
CuSn4Pb4Zn3	X3)		X3)		X3)		(X)			

¹⁾ Made by extruding or by combination of extruding and drawing.

²⁾ Mainly for wear resistance applications, e.g. plain bearings according to ISO 4382/2.

³⁾ Mechanical properties to be defined later, i.e. in course of revision of ISO 1634/1 and ISO 1635.