

---

---

**Rubber and plastics hoses and tubing —  
Textile-reinforced types — Sub-ambient  
temperature crush test**

*Tuyaux et tubes en caoutchouc et en plastique — Types avec armature textile — Essai d'écrasement à température inférieure à la température ambiante*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 28702:2008](https://standards.iteh.ai/catalog/standards/sist/bf3fce69-18e7-43d4-bee9-a097ef7e6f53/iso-28702-2008)

<https://standards.iteh.ai/catalog/standards/sist/bf3fce69-18e7-43d4-bee9-a097ef7e6f53/iso-28702-2008>



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 28702:2008

<https://standards.iteh.ai/catalog/standards/sist/bf3fce69-18e7-43d4-bee9-a097ef7e6f53/iso-28702-2008>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 28702 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Hoses (rubber and plastics)*.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 28702:2008](https://standards.iteh.ai/catalog/standards/sist/bf3fce69-18e7-43d4-bee9-a097ef7e6f53/iso-28702-2008)

<https://standards.iteh.ai/catalog/standards/sist/bf3fce69-18e7-43d4-bee9-a097ef7e6f53/iso-28702-2008>

## Introduction

This International Standard can be used to test the low-temperature properties of hoses whereby the brittle temperature of materials used for the lining and cover can be assessed.

The method does not measure the flexibility of hoses at the test temperature.

Other sub-ambient temperature tests for hoses and hose assemblies are given in ISO 4672, *Rubber and plastics hoses — Sub-ambient temperature flexibility tests* [to be replaced by ISO 10619-2 (in preparation)].

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 28702:2008](https://standards.iteh.ai/catalog/standards/sist/bf3fce69-18e7-43d4-bee9-a097ef7e6f53/iso-28702-2008)

<https://standards.iteh.ai/catalog/standards/sist/bf3fce69-18e7-43d4-bee9-a097ef7e6f53/iso-28702-2008>

# Rubber and plastics hoses and tubing — Textile-reinforced types — Sub-ambient temperature crush test

## 1 Scope

This International Standard specifies a test method for measuring the low-temperature brittleness of rubber and plastics hoses with a textile reinforcement and tubing at sub-ambient temperatures by crushing a test piece of the hose.

This International Standard is only applicable to hoses with a nominal bore up to and including 100 mm.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

ISO 28702:2008

<https://standards.iteh.ai/catalog/standards/sist/bf3fce69-18e7-43d4-bee9-a097ef7e6f53/iso-28702-2008>

## 3 Principle

A hose test piece is compressed to 50 % of its inside diameter at the test temperature and, after decompression, is examined on the interior and exterior for the presence of any cracks or other abnormalities.

## 4 Apparatus

**4.1 Compression jig or any other suitable apparatus**, consisting of two flat plates large enough for the hose to be compressed to 50 % of its inside diameter.

**4.2 Conditioning chamber**, capable of being maintained at the specified temperature as selected in Clause 6.

## 5 Test piece

Cut a ring test piece of length approximately 25 mm from the hose under test.

## 6 Test temperature

The test shall be conducted at one of the following temperatures or at another sub-ambient temperature as defined in the relevant product standard.

- 0 °C ± 2 °C;
- 10 °C ± 2 °C;
- 25 °C ± 2 °C;
- 40 °C ± 2 °C;
- 55 °C ± 2 °C.

## 7 Procedure

Condition the test piece and compression jig in the conditioning chamber at the test temperature for 24 h and then hold the test piece between the two plates of the compression jig at the test temperature for at least another 30 min before testing. Guidance on achieving the specified temperature is given in ISO 23529.

After the specified conditioning periods, compress the test piece in the direction at right angles to the plates to 50 % of its inside diameter within a time of 5 s ± 2 s. An example of a compression jig is shown in Figure 1. The test may be carried out on any other suitable mechanical test equipment, however.

In principle, the test shall be carried out in the conditioning chamber. If this is not feasible, remove the test piece from the chamber and perform the test within 15 s.

After testing, leave the test piece to warm up to room temperature.

[ISO 28702:2008](https://standards.iteh.ai/catalog/standards/sist/bf3fce69-18e7-43d4-bee9-a097ef7e6f53/iso-28702-2008)

<https://standards.iteh.ai/catalog/standards/sist/bf3fce69-18e7-43d4-bee9-a097ef7e6f53/iso-28702-2008>


## 8 Examination of test piece after testing

Examine the interior and exterior of test piece with a × 2 magnifier. If any abnormalities such as cracks, fractures, or separation of layers are observed, record them.


## 9 Test report

The test report shall include the following information:

- a) a reference to this International Standard (ISO 28702:2008);
- b) the type of hose tested and its nominal bore;
- c) the test temperature;
- d) whether the test was carried out inside or outside the conditioning chamber;
- e) the results of the examination of the test piece after testing;
- f) the date of the test.



a) Example of a compression jig



b) Before compression

c) Under compression

**Key**

- 1 compression jig
- 2 test piece
- $d$  inside diameter of hose
- $t$  hose wall thickness

**Figure 1 — Crush method for compressing the hose test piece**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 28702:2008

<https://standards.iteh.ai/catalog/standards/sist/bf3fce69-18e7-43d4-bee9-a097ef7e6f53/iso-28702-2008>

---

---

**ICS 23.040.70**

Price based on 3 pages