



Designation: D 7033 – 05

Standard Practice for Establishing Design Capacities for Oriented Strand Board (OSB) Wood-Based Structural-Use Panels¹

This standard is issued under the fixed designation D 7033; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

Oriented strand board (OSB) wood-based structural-use panels have been used in a variety of applications since the 1970s. OSB panels manufactured for use in North America generally comply with U.S. Department of Commerce Standard **PS-2**. Panels that comply with **PS-2** are subjected to various kinds of qualification performance testing and ongoing quality assurance testing. While many panel applications are specified simply on the basis of meeting a given “span rating” as defined in **PS-2**, some construction and specialty applications may require a complete set of engineering design values. Based on the structural tests required by **PS-2** (flexure), along with data for other properties, a set of baseline capacities has been available since 1988. As is customary for structural-use panels, design values will be discussed in this practice in terms of design capacities rather than design properties, where the difference is that a design property is expressed in units of stress (that is, pounds-per-square inch) and a design capacity is expressed in the engineering units of strength (that is, inch-pounds of bending strength capacity, pounds of tensile capacity, and so forth). The term “design values” will be used generically and can apply to either properties or capacities.

As uses for OSB wood-based structural-use panels extend into new applications, it becomes increasingly important that manufacturers, qualified agencies, and regulatory bodies reference a set of common, consensus-based procedures for establishment of design values. The purpose of this practice is to provide these common procedures.

1. Scope

1.1 This practice covers the basis for code recognition of design capacities for OSB structural-use panels. Procedures are provided to establish or re-evaluate design capacities for OSB structural-use panels. Procedures for sampling and testing are also provided. Design values stated as capacity per unit dimension are to be regarded as standard. Design capacities developed in accordance with this practice are applicable to panels intended for use in dry in-service conditions.

NOTE 1—This practice is based on **ICC-ES Acceptance Criteria AC-182—Acceptance Criteria for Wood-Based Structural-Use Panels**. Relative to the scope of AC-182, this practice is limited to OSB panels.

NOTE 2—While this practice makes reference to **PS-2**, this practice applies similarly to products certified to other standards such as **CAN/CSA O325**.

NOTE 3—OSB produced under **PS-2** is rated with the “Exposure 1” bond classification. Exposure 1 panels covered by **PS-2** are intended for dry use applications where the in-service equilibrium moisture content conditions are expected to be less than 16%. Exposure 1 panels are intended to resist the effects of moisture due to construction delays, or

other conditions of similar severity. Guidelines on use of OSB are available from manufacturers and qualified agencies.

2. Referenced Documents

2.1 *ASTM Standards*:²

D 9 Terminology Relating to Wood and Wood-Based Products

D 143 Test Methods for Small Clear Specimens of Timber
D 1037 Test Methods for Evaluating Properties of Wood-Base Fiber and Particle Panel Materials

D 2718 Test Methods for Structural Panels in Planar Shear (Rolling Shear)

D 2719 Test Methods for Structural Panels in Shear Through-the-Thickness

D 2915 Practice for Evaluating Allowable Properties for Grades of Structural Lumber

D 3043 Test Methods for Structural Panels in Flexure

D 3500 Test Methods for Structural Panels in Tension

¹ This practice is under the jurisdiction of ASTM Committee D07 on Wood and is the direct responsibility of Subcommittee D07.03 on Panel Products. Current edition approved Dec. 15, 2005. Published January 2006.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

- D 3501** Test Methods for Wood-Based Structural Panels in Compression
- D 4442** Test Methods for Direct Moisture Content Measurement of Wood and Wood-Base Materials
- D 5456** Specification for Evaluation of Structural Composite Lumber Products
- D 5457** Specification for Computing Reference Resistance of Wood-Based Materials and Structural Connections for Load and Resistance Factor Design
- D 6815** Specification for Evaluation of Duration of Load and Creep Effects of Wood and Wood-Based Products
- 2.2 Other Documents:**
- PS-2** Performance Standard for Wood-Based Structural-Use Panels, U.S. Department of Commerce Voluntary Product Standard³
- NDS** ANSI/AF&PA National Design Specification for Wood Construction⁴
- CAN/CSA O325.0 (R2003)** Construction Sheathing⁵
- CSA O86** Engineering Design in Wood⁵
- ASD/LRFD** Manual for Engineered Wood Construction⁶
- ICC Evaluation Service Acceptance Criteria AC-182** Acceptance Criteria for Wood-Based Structural-Use Panels⁷

3. Terminology

3.1 *Definitions*—For definitions of terms related to wood, refer to Terminology **D 9**.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *baseline capacities*—capacities developed for OSB panels intended for use in applications that are not governed by building codes. As distinct from **PS-2** and proprietary panels, documentation of baseline capacities is on the basis of test reports rather than evaluation reports or code reference. Example applications include, but are not limited to, concrete form and industrial panels.

3.2.2 *characteristic value*—a population mean, confidence interval, or tolerance limit estimated from the test data. The characteristic value is an intermediate value in the development of design values.

3.2.3 *design capacity*—a value that is a function of material design property and design section property.

3.2.4 *design property*—the stress-based design value derived by dividing design capacity by the design section property.

3.2.5 *oriented strand board (OSB)*—a mat-formed panel product with oriented layers resulting in directional properties. Oriented strand board is comprised primarily of wood strands bonded with exterior adhesive formulations under heat and pressure. Design capacities are referenced to the primary and

secondary structural axes, which typically correspond to the manufacturing machine and cross-machine directions, respectively. The primary direction is often referred to as the strength direction.

3.2.6 *primary axis*—the primary axis typically corresponds to the manufacturing machine direction and exhibits higher mechanical properties relative to the secondary axis. The primary axis typically corresponds to the eight-foot dimension of four-foot by eight-foot OSB.

3.2.7 *proprietary panels*—refers to OSB structural-use panels having proprietary design capacities as provided in an evaluation report issued by a code evaluation service.

3.2.8 *PS-2 panels*—refers to panels manufactured in accordance with **PS-2**.

NOTE 4—Design values for OSB certified to **CAN/CSA O325.0** are published in **CSA O86** Engineering Design in Wood. See CSA 086 for specific applications of OSB design values.

3.2.9 *secondary axis*—the secondary axis typically corresponds to the manufacturing cross-machine direction and exhibits lower mechanical properties relative to the primary axis. The secondary axis typically corresponds to the four-foot dimension of four-foot by eight-foot OSB.

3.2.10 *test cell*—the combined test data for a single span rating/property that is intended to characterize that sampling unit.

3.2.11 *tolerance limit*—in this standard, a one-sided tolerance limit is a value about which it may be stated with 75% confidence that a proportion (that is, 90%, 50%, and so forth) of the population has values greater than this tolerance limit.

4. Significance and Use

4.1 The procedures described in this practice are intended to be used to establish design capacity (both strength and stiffness) values based on testing of OSB that, at a minimum, satisfies the performance requirements of **PS-2**.

4.2 Review and reassessment of values derived from this practice shall be conducted on a periodic basis. If a change is found to be significant, retesting or reevaluation, or both, in accordance with the procedures of this practice shall be considered.

5. Minimum Sampling Matrix and Frequency

5.1 Development of design capacities under this practice may be for either a single span rating or a full matrix of span ratings as defined in **PS-2**.

5.2 Panels sampled for testing shall be representative of the population for which design capacities are desired. Panel sampling and grouping procedures shall comply with Section 4 of Specification **D 5457**.

5.3 Each product (span rating, grade, nominal thickness) represents a unique product designation. Grouping within product designations shall comply with Section 4 of Specification **D 5457**.

NOTE 5—Data should be reviewed periodically. Inclusion of data beyond the review period should be supplemented by proof that it represents more recent production.

5.4 *Sampling Matrix for Design Capacities*—For the purpose of developing design capacities, the minimum sampling

³ Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

⁵ Available from Canadian Standards Association (CSA), 178 Rexdale Blvd., Toronto, ON Canada M9W1R3.

⁶ Available from American Forest and Paper Association (AF&PA), 1111 19th St., NW, Suite 800, Washington, DC 20036.

⁷ Available from ICC Evaluation Service, 5360 Workman Mill Rd, Whittier, California 90601

matrix shall include every thickness and span rating for which a design value will be claimed. Alternatively, when supported by a documented model, characteristic values for untested cells are permitted to be established by analytical methods. For each manufacturing facility and product for which design capacities are desired, the minimum number of test replications shall be 30, with the exception of bending stiffness and bending strength capacity, for which the minimum number of test replications shall be 60. A quality assurance program monitored by a qualified agency shall provide verification of continuing compliance with claimed design values.

6. Testing Requirements

6.1 *Bending Stiffness* (EI , $lbf\text{-in.}^2/ft$)—Bending stiffness shall be determined in accordance with Test Methods **D 3043**, Method C—Pure Moment Test. Test panel thickness shall be recorded. Flexural stiffness shall be determined in the primary and secondary panel directions and shall be reported on a per foot of width basis. The applicable moment arm shall be the load bar spacing between points of contact with the test panel.

6.2 *Bending Strength Capacity* ($F_b S$, $lbf\text{-in.}/ft$)—Bending strength capacity shall be determined in accordance with Test Methods **D 3043**, Method C—Pure Moment Test. Bending strength capacity shall be determined for the same panel specimens evaluated under 6.1. Bending strength capacity shall be determined in the primary and secondary panel directions and shall be reported on a per foot of panel width basis. Test panel thickness shall be recorded. The applicable moment arm shall be the load bar spacing between points of contact with the test panel.

6.3 *Strength Capacity in Planar Shear* ($F_s(Ib/Q)$, lbf/ft)—Planar shear strength capacity shall be determined in accordance with Test Methods **D 2718**. Test specimen thickness shall be recorded. Planar shear strength capacities along the primary and secondary axes shall be determined and shall be reported on a per foot of panel width basis.

NOTE 6—Test Methods **D 2718** includes the use of a five-point bending test as an approved method.

6.4 *Strength Capacity in Shear Through-the-Thickness* ($F_{v,t}$, $lbf/in.$)—Shear through-the-thickness shall be determined in accordance with Test Methods **D 2719**, Method B or Method C. Test panel thickness shall be recorded. Shear through-the-thickness shall be determined along the primary and secondary axes and shall be reported on the basis of pound-force per inch of shear-resisting panel length.

6.5 *Shear Rigidity Through-the-Thickness* ($G_{v,t}$, $lbf/in.$)—Shear rigidity through-the-thickness shall be determined in accordance with Test Methods **D 2719**, Method B or Method C. Test panel thickness shall be recorded. Shear rigidity through-the-thickness shall be determined along the primary and secondary axes and shall be reported in units of pound-force per inch of panel depth.

6.6 *Axial Stiffness (in tension and compression, EA, lbf/ft)*—Axial tension and compression stiffness shall be determined in accordance with Test Methods **D 3500**, Method B—Tensile Strength of Large Specimens, and Test Methods **D 3501**, Method B—Compression Test for Large Specimens, respectively. Test panel thickness shall be recorded. Axial stiffness

shall be determined along the primary and secondary axes and shall be reported on a per foot of panel width basis. Specimen dimensions shall be recorded.

6.7 *Axial Strength (in tension and compression, $F_c A$, $F_t A$, lbf/ft)*—Axial tension and compression strength shall be determined in accordance with Test Methods **D 3500**, Method B—Tensile Strength of Large Specimens, and Test Methods **D 3501**, Method B—Compression Test for Large Specimens, respectively. Test panel thickness shall be recorded. Axial strength shall be determined along the primary and secondary axes and shall be reported on a per foot of panel width basis. Specimen dimensions shall be recorded.

6.8 *Fastener Withdrawal Resistance*—Fastener withdrawal resistance tests shall be conducted in accordance with Test Methods **D 1037**, except that 8d common wire (bright, plain-shank medium diamond-point steel nail with a nominal shank diameter of 0.131 in., a nominal length of 2.5 in., and a head diameter of $\frac{3}{32}$ in.) nails shall be used. Specimen thickness and density shall be recorded. Results shall be reported as tested and as normalized to a per inch of thickness basis for determination or equivalent specific gravity in accordance with Annex A2 of Specification **D 5456**. Fastener specifications shall be recorded and shall include actual diameter.

6.9 *Lateral Fastener Resistance*—The equivalent specific gravity of the OSB shall be determined on the basis of dowel-bearing performance in accordance with Annex A2.7 of Specification **D 5456** except that the test fasteners shall include 8d and 10d common wire nails as defined in Specification **D 5456**, Annex A2. Lateral fastener capacity shall be determined along the primary and secondary axes. For each panel directional axis, the equivalent specific gravity shall be the minimum value determined for the fasteners tested. Specimen thickness and density shall be recorded.

6.10 *Nail-Head Pull-Through Resistance*—To measure the resistance of a panel to having the head of a nail or other fastener pulled through the board, nail-head pull-through tests shall be conducted in accordance with Test Methods **D 1037**, except that 8d common wire nails with a nominal head diameter of $\frac{3}{32}$ in. shall be used. Specimen thickness and density shall be recorded. Fastener specifications shall be recorded and shall include actual shank diameter and actual nail head diameter. Results shall be reported as-tested.

6.11 *Compression Perpendicular (Bearing) Capacity* (F_{cp} , psi)—Compression perpendicular tests shall be conducted in accordance with principles of Test Methods **D 143**, except that references to placement of growth rings are not applicable. Specimen dimensions shall be 1.5 in. (minimum) by 6 in. by panel thickness. The compressive load shall be applied perpendicular to the surface of the specimen through a 2-in. wide bearing plate aligned across the width of the specimen. Stress at 0.04-in. deformation shall be recorded. Specimen dimensions and density shall be recorded.

7. Determination of Design Capacities

7.1 *Allowable Stress Design (ASD)*—Design capacities for allowable stress design shall be determined in accordance with ASD/LFRD procedures established in this practice or through soft conversion from reliability-based design capacities developed in accordance with Specification **D 5457** (7.2 of this