

---

---

**Rubber compounding ingredients —  
Carbon black — Determination of  
individual pellet crushing strength**

*Ingrédients de mélange du caoutchouc — Noir de carbone —  
Détermination de la force d'écrasement des granules individuels*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 8942:2010](https://standards.iteh.ai/catalog/standards/sist/413d3671-3f35-412d-bd6f-b65e13462086/iso-8942-2010)

<https://standards.iteh.ai/catalog/standards/sist/413d3671-3f35-412d-bd6f-b65e13462086/iso-8942-2010>



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 8942:2010

<https://standards.iteh.ai/catalog/standards/sist/413d3671-3f35-412d-bd6f-b65e13462086/iso-8942-2010>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Contents

Page

Foreword .....	iv
Introduction.....	v
1 Scope .....	1
2 Normative references .....	1
3 Terms and definitions .....	1
4 Principle .....	1
5 Method A .....	1
6 Method B .....	2
6.1 Apparatus .....	2
6.2 Sampling and selection of pellets for use as test pieces.....	3
6.3 Procedure .....	3
6.3.1 Manual procedure.....	3
6.3.2 Automatic procedure .....	4
6.4 Calculation and expression of results .....	4
7 Test report.....	4
Annex A (informative) Precision and bias .....	5
Bibliography.....	7

ISO 8942:2010

<https://standards.iteh.ai/catalog/standards/sist/413d3671-3f35-412d-bd6f-b65e13462086/iso-8942-2010>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 8942 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

It cancels and replaces ISO/TR 8942:1988, which has been technically revised.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 8942:2010  
<https://standards.iteh.ai/catalog/standards/sist/413d3671-3f35-412d-bd6f-b65e13462086/iso-8942-2010>

## Introduction

Carbon black for the rubber industry is generally pelletized to reduce dust and facilitate handling. The property of individual pellet crushing strength, among several other properties, may have an influence on the dispersion of carbon black in polymers, on bulk handling and on conveying properties. For these purposes, carbon black is mostly pelletized to around 1 mm in diameter, but the pellet size can reach 1,7 mm. Therefore, in most of the existing test methods used to measure the individual pellet crushing strength, the pellets are selected in sizes ranging from 1 mm to 1,7 mm.

The individual pellet crushing strength is the force necessary to crush one pellet, and the value measured is absolute (i.e. neither per unit volume nor per unit surface area of the pellet). The value varies with the size of the pellet. Therefore, a narrower size range in the sample generally gives a narrower distribution of the measured individual pellet crushing strength.

This International Standard provides two methods for determining the individual pellet crushing strength of carbon black:

- Method A, specified in ASTM D5230, which uses a test sample of a certain pellet size range that is widely used in the industry for typical grades, prepared by passing a sample through a sieve that has an aperture of 1,4 mm to 1,7 mm.
- Method B, which uses a test sample prepared using a sieve that has an aperture of 1,0 mm. This method is used when a more precise result is required, such as in process control or in order to meet a customer's specification.

[ISO 8942:2010](https://standards.iteh.ai/catalog/standards/sist/413d3671-3f35-412d-bd6f-b65e13462086/iso-8942-2010)

<https://standards.iteh.ai/catalog/standards/sist/413d3671-3f35-412d-bd6f-b65e13462086/iso-8942-2010>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 8942:2010

<https://standards.iteh.ai/catalog/standards/sist/413d3671-3f35-412d-bd6f-b65e13462086/iso-8942-2010>

# Rubber compounding ingredients — Carbon black — Determination of individual pellet crushing strength

## 1 Scope

This International Standard specifies two methods for the determination of the individual pellet crushing strength of carbon black for use in the rubber industry:

- method A: using pellets of size ranging from 1,4 mm to 1,7 mm;
- method B: using pellets of size 1 mm.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 565, *Test sieves — Metal wire cloth, perforated metal plate and electroformed sheet — Nominal sizes of openings*

ISO 8942:2010

ISO 1124, *Rubber compounding ingredients — Carbon black shipment sampling procedures*

ASTM D5230, *Standard Test Method for Carbon Black — Automated Individual Pellet Hardness*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

### 3.1

#### individual pellet crushing strength

force required to crush (i.e. fracture) a carbon black pellet under specified conditions

## 4 Principle

A number of pellets within the diameter range 1,4 mm to 1,7 mm (method A) or of diameter 1,0 mm (method B) are selected by sieving a carbon black sample (in method B, this is achieved by selecting only those pellets which, during sieving, become lodged in the apertures of a 1,0 mm aperture sieve). The pellets selected are placed one at a time between two parallel plates of a device capable of applying a force. The force which is being applied when the pellet fractures is recorded.

## 5 Method A

Testing is carried out in accordance with ASTM D5230.

## 6 Method B

### 6.1 Apparatus

Usual laboratory apparatus, plus the following:

#### 6.1.1 Manual pellet hardness tester.

Required is a device capable of applying a force at a constant rate and of measuring the force at which the pellet fractures.

The device shall:

- have two parallel plates (a baseplate and a force-application plate) which remain horizontal throughout the whole of the test;
- be capable of applying a force which increases at a constant rate of between 5 cN/s<sup>1)</sup> and 25 cN/s;
- possess a means of measuring this force with an accuracy of 1 cN;
- be capable of being calibrated using deadweights or a force-measuring device that verifies the accuracy of the equipment over the range being used for the test.

The baseplate and force-application plate shall be firmly fixed in order to prevent the pellet from rolling, or otherwise moving, before the start of the test.

Simple, accurate bench dial scales having a 50 g or 200 g dial and with the force-application plate positioned above the scale pan may be used.

**6.1.2 Automatic pellet hardness tester<sup>2)</sup>**, capable of measuring the crushing force to an accuracy of  $\pm 0,4$  cN and having the following characteristics:

- the ability to load a pellet automatically on to the plate from the pellet feed device;
- the ability to apply the crushing force at a constant rate;
- a control unit which takes the instrument through the test cycle which comprises crushing the pellet under controlled conditions, measuring the crushing force and storing the result and, finally, cleaning the pellet fragments from the plate surface before starting the next cycle;
- an algorithm for detecting the end-point of each individual test, i.e. the maximum force reached before the first occurrence of a reduction in force;
- a software programme for calculating the data required in 6.4 for a specified number of pellets.

---

1) 1 cN = 1,019 gf.

2) The following automatic pellet hardness testers are available commercially:

- AS 2000 from Asahisouken Co. Ltd., 3-13-3 Meikeshinmei chuo-ku, Niigata City, Niigata 950-0943, Japan;
- Individual Pellet Hardness Tester from Jaron Technologies LLC, 2338 Duncan St., Pampa, TX 79065, USA (formerly Titan Specialties);
- IPHT from HITEC Luxembourg, 5 rue de l'Église, L-1458 Luxembourg.

This information is given for the convenience of users of this International Standard and does not constitute an endorsement by ISO of the instruments named.



**6.1.3 Sieve shaker.**

**6.1.4 Sieve**, complying with the requirements of ISO 565, preferably having a nominal aperture size of 1,0 mm. A sieve with an aperture size of 1,4 mm or 1,7 mm (or some other value) may, however, be used by agreement between the interested parties.

NOTE There is a marked tendency for larger particle sizes to have a higher individual crushing strength. The use of a 1 mm sieve to isolate pellets of diameter 1 mm, as described in 6.2.3 and 6.2.4, is intended to avoid this problem.

**6.1.5 Bottom-receiver pan.****6.1.6 Sieve cover.****6.1.7 Sample splitter**, single-stage riffle type.**6.1.8 Shallow container**, e.g. a dish approximately 300 mm long.**6.2 Sampling and selection of pellets for use as test pieces**

**6.2.1** Take samples in accordance with the requirements of ISO 1124.

**6.2.2** Pass a sufficient quantity of carbon black through the sample splitter (6.1.7) to obtain a representative sample of approximately 100 g.

**6.2.3** Assemble the bottom-receiver pan (6.1.5) and sieve (6.1.4) correctly. Transfer the 100 g sample of the riffled carbon black to the sieve, place the sieve cover (6.1.6) on the sieve and transfer the assembly to the sieve shaker (6.1.3). Shake the sieve assembly for  $60^{+10}_0$  s with the minimum of energy input so as to avoid pellet breakdown. If a hammer-type mechanical shaker is used, the hammer shall be at rest.

**6.2.4** Remove the pellets left on the sieve by turning it upside-down. Then hold the sieve upside-down over a shallow container (6.1.8) and tap the sieve gently so that the pellets lodged in the apertures fall into the container. Repeat these operations until about 50, 100 or 150 1 mm pellets, depending how many it is intended to test (see 6.2.5), have been obtained. With these pellets at one end of the container, slightly tilt and gently shake the container so that the most spherical pellets roll to the opposite end. Choose 20, 50 or 100 (see 6.2.5) of the most spherical of these pellets.

**6.2.5** The number of pellets tested is 20 for normal applications, although, by agreement between the interested parties, either 50 or 100 pellets may be tested if a more precise result is required.

**6.3 Procedure****6.3.1 Manual procedure**

**6.3.1.1** Select one pellet and, using a soft brush, position it in the centre of the baseplate, just under the force-application plate (see 6.1.1).

**6.3.1.2** Carefully bring the force-application plate into contact with the pellet. Exercise great care when testing soft pellets which tend to fracture prematurely due to impact on initial contact.

**6.3.1.3** Apply force at a constant rate of 25 cN/s until the pellet fractures. Record the force required.

**6.3.1.4** Clean the baseplate and force-application plate.

**6.3.1.5** Repeat the operations in 6.3.1.1 to 6.3.1.4 until all 20 (or 50 or 100) pellets have been tested.