



Designation: C 125 – 06

## Standard Terminology Relating to Concrete and Concrete Aggregates<sup>1</sup>

This standard is issued under the fixed designation C 125; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope\*

1.1 The following definitions apply to hydraulic cement concrete, although some of them may have wider application.<sup>2</sup>

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>3</sup>

**C 109/C 109M** Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or [50-mm] Cube Specimens)

**C 143/C 143M** Test Method for Slump of Hydraulic-Cement Concrete

**C 219** Terminology Relating to Hydraulic Cement

**C 403/C 403M** Test Method for Time of Setting of Concrete Mixtures by Penetration Resistance

**C 494/C 494M** Specification for Chemical Admixtures for Concrete

**C 939** Test Method for Flow of Grout for Preplaced-Aggregate Concrete (Flow Cone Method)

**C 1074** Practice for Estimating Concrete Strength by the Maturity Method

#### 2.2 American Concrete Institute Publications:<sup>4</sup>

**308** Practice for Curing Concrete

### 3. Terms and Their Definitions

**absorption, *n***—the process by which a liquid is drawn into and tends to fill permeable pores in a porous solid body; also, the

increase in mass of a porous solid body resulting from the penetration of a liquid into its permeable pores.

**DISCUSSION**—In the case of concrete and concrete aggregates, unless otherwise stated, the liquid involved is water, the increase in mass is that which does not include water adhering to the outside surface, the increase in mass is expressed as a percentage of the dry mass of the body and the body is considered to be “dry” when it has been treated by an appropriate process to remove uncombined water, such as drying to constant mass at a temperature between 100 and 110 °C.

**admixture, *n***—a material other than water, aggregates, hydraulic cementitious material, and fiber reinforcement that is used as an ingredient of a cementitious mixture to modify its freshly mixed, setting, or hardened properties and that is added to the batch before or during its mixing.

**accelerating admixture, *n***—admixture that accelerates the setting and early strength development of concrete. (**C 494/C 494M**)

**air-entraining admixture, *n***—admixture that causes the development of a system of microscopic air bubbles in concrete or mortar during mixing.

**chemical admixture, *n***—a nonpozzolanic admixture in the form of a liquid, suspension, or water-soluble solid.

**mineral admixture, *n***—deprecated term.

**DISCUSSION**—This term has been used to refer to different types of water insoluble, finely divided materials such as pozzolanic materials, cementitious materials, and aggregate. These materials are not similar, and it is not useful to group them under a single term. The name of the specific material should be used, for example, use “pozzolan,” “ground granulated blast-furnace slag,” or “finely divided aggregate,” as is appropriate.

**retarding admixture, *n***—admixture that retards the setting of concrete. (**C 494/C 494M**)

**water-reducing admixture, *n***—admixture that either increases the slump of freshly mixed mortar or concrete without increasing the water content or that maintains the slump with a reduced amount of water due to factors other than air entrainment.

**water-reducing admixture, high-range, *n***—a water-reducing admixture capable of producing at least 12 % reduction of

<sup>1</sup> This terminology is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.91 on Terminology.

Current edition approved Feb. 15, 2006. Published March 2006. Originally approved in 1936. Last previous edition approved in 2003 as C 125 – 03.

<sup>2</sup> Terminology **C 219** contains definitions of a number of items in use in standards under the jurisdiction of Committee C09. Definitions of additional terms may be found in *Cement and Concrete Terminology*, 116R American Concrete Institute, P.O. Box 19150, Detroit, MI 48219.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>4</sup> Available from the American Concrete Institute, P.O. Box 9094, Farmington Hills, MI 48333-9094.

\*A Summary of Changes section appears at the end of this standard.

water content when tested in accordance with Specification **C 494/C 494M** and meeting the other relevant requirements of Specification **C 494/C 494M**.

**aggregate, n**—granular material, such as sand, gravel, crushed stone, or iron blast-furnace slag, used with a cementing medium to form hydraulic-cement concrete or mortar.

*coarse aggregate, n*—(1) aggregate predominantly retained on the 4.75-mm (No. 4) sieve; or (2) that portion of an aggregate retained on the 4.75-mm (No. 4) sieve.

DISCUSSION—The definitions are alternatives to be applied under differing circumstances. Definition (1) is applied to an entire aggregate either in a natural condition or after processing. Definition (2) is applied to a portion of an aggregate. Requirements for properties and grading should be stated in the specification.

*fine aggregate, n*—(1) aggregate passing the 9.5-mm ( $\frac{3}{8}$ -in.) sieve and almost entirely passing the 4.75-mm (No. 4) sieve and predominantly retained on the 75- $\mu$ m (No. 200) sieve; or (2) that portion of an aggregate passing the 4.75-mm (No. 4) sieve and retained on the 75- $\mu$ m (No. 200) sieve.

DISCUSSION—The definitions are alternatives to be applied under differing circumstances. Definition (1) is applied to an entire aggregate either in a natural condition or after processing. Definition (2) is applied to a portion of an aggregate. Requirements for properties and grading should be stated in the specifications.

*heavyweight aggregate, n*—see *high-density aggregate*.

*high-density aggregate, n*—aggregate with relative density greater than 3.3, such as: barite, magnetite, limonite, ilmenite, iron, or steel.

*lightweight aggregate, n*—see *low-density aggregate*.

*low-density aggregate, n*—aggregate with bulk density less than 1120 kg/m<sup>3</sup> (70 lb/ft<sup>3</sup>), such as: pumice, scoria, volcanic cinders, tuff, and diatomite; expanded or sintered clay, shale, slate, diatomaceous shale, perlite, vermiculite, or slag; and end products of coal or coke combustion.

*normal-density aggregate, n*—aggregate that is neither high nor low density.

DISCUSSION—This term refers to aggregate with relative density typically ranging between 2.4 and 3.0, or with bulk density typically ranging between 1120 kg/m<sup>3</sup> (70 lb/ft<sup>3</sup>) and 1920 kg/m<sup>3</sup> (120 lb/ft<sup>3</sup>).

*normalweight aggregate, n*—see *normal-density aggregate*.

**air-cooled blast-furnace slag, n**—the material resulting from solidification of molten blast-furnace slag under atmospheric conditions; subsequent cooling may be accelerated by application of water to the solidified surface.

**air content, n**—the volume of air voids in cement paste, mortar, or concrete, exclusive of pore space in aggregate particles, usually expressed as a percentage of total volume of the paste, mortar, or concrete.

**air void, n**—a space in cement paste, mortar, or concrete filled with air; an entrapped air void is characteristically 1 mm or more in width and irregular in shape; an entrained air void is typically between 10 and 1000  $\mu$ m in diameter and spherical or nearly so.

DISCUSSION—The content of the voids may include atmospheric air incorporated into the concrete during mixing of air or other gases released by chemical or other processes within the fresh concrete.

**blast-furnace slag, n**—the nonmetallic product, consisting essentially of silicates and aluminosilicates of calcium and other bases, that is developed in a molten condition simultaneously with iron in a blast furnace.

**bleeding, n**—the autogenous flow of mixing water within, or its emergence from, newly placed concrete or mortar caused by the settlement of the solid materials within the mass, also called water gain.

**bulk density, n**—of *aggregate*, the mass of a unit volume of bulk aggregate material (the unit volume includes the volume of the individual particles and the volume of the voids between the particles).

DISCUSSION—This term replaces the deprecated term **unit weight**—of *aggregate*.

**bulk specific gravity, n**—the ratio of the mass of a volume of a material (including the permeable and impermeable voids in the material, but excluding the voids between particles of the material) at a stated temperature to the mass of an equal volume of distilled water at a stated temperature.

**bulk specific gravity (saturated surface dry), n**—the ratio of the mass of a volume of a material including the mass of water within the pores in the material (but excluding the voids between particles) at a stated temperature, to the mass of an equal volume of distilled water at a stated temperature.

**cellular concrete, n**—a lightweight hydraulic-cement concrete having a homogeneous void or cell structure attained using gas-forming chemicals or foaming agents.

**cementitious material (hydraulic), n**—an inorganic material or a mixture of inorganic materials that sets and develops strength by chemical reaction with water by formation of hydrates and is capable of doing so under water.

**cementitious mixture, n**—a mixture (mortar, concrete, or grout) containing hydraulic cement.

**concrete, n**—a composite material that consists essentially of a binding medium within which are embedded particles or fragments of aggregate; in hydraulic-cement concrete, the binder is formed from a mixture of hydraulic cement and water.

**concrete, self-consolidating, n**—concrete that can flow around reinforcement and consolidate under its own weight without additional effort and without exceeding specified limits of segregation.

DISCUSSION—Project specifications shall indicate the acceptable segregation based upon a specified test method. Although there currently are no ASTM test methods approved to define specified limits of segregation, they are under development; also, there are industry methods available to specifiers.

**consistency, n**—of *fresh concrete, mortar, or grout*, the relative mobility or ability to flow.

DISCUSSION—This characteristic of fresh cementitious mixtures is difficult to quantify and empirical test methods have been adopted to provide indicators of consistency. For example, the slump test described in Test Method **C 143/C 143M** is used for concrete, the flow table method described in Test Method **C 109/C 109M** is used for mortar, and the flow cone method described in Test Method **C 939** is used for grout.