
**Textiles — Yarns from packages —
Determination of single-end breaking
force and elongation at break using
constant rate of extension (CRE) tester**

*Textiles — Fils sur enroulements — Détermination de la force de
rupture et de l'allongement à la rupture des fils individuels à l'aide d'un
appareil d'essai à vitesse constante d'allongement*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 2062:2009

<https://standards.iteh.ai/catalog/standards/sist/8368eb6f-5edc-4ba7-b5cf-c56a4361de5d/iso-2062-2009>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 2062:2009

<https://standards.iteh.ai/catalog/standards/sist/8368eb6f-5edc-4ba7-b5cf-c56a4361de5d/iso-2062-2009>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2009

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2062 was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 23, *Fibres and yarns*.

This third edition cancels and replaces the second edition (ISO 2062:1993), which has been technically revised.

ITEH STANDARD PREVIEW
(standards.iteh.ai)

[ISO 2062:2009](https://standards.iteh.ai/catalog/standards/sist/8368eb6f-5edc-4ba7-b5cf-c56a4361de5d/iso-2062-2009)

<https://standards.iteh.ai/catalog/standards/sist/8368eb6f-5edc-4ba7-b5cf-c56a4361de5d/iso-2062-2009>

Introduction

In the 1950s and 1960s when this International Standard was first prepared, three types of tensile testers were in wide use: constant rate of specimen extension (CRE), constant rate of travel (CRT) and constant rate of loading (CRL). It was therefore advisable to state the rate of operation in a way which would be common to all three types of tester. In addition, the best possible agreement was sought between the test results of the three types of tester. Consequently, the principle of constant time to break was adopted, and 20 s to break was chosen for this International Standard and also for a number of national standards.

In the early 1990s, CRE testers were recognized as the best type. As CRT and CRL testers were still in use internationally, the procedure for using them was included in an informative annex. There is no assurance that the results from the three types of tester will agree. This International Standard considers CRE testers only, so the time-to-break principle was no longer needed and a simpler statement of rate of extension was used. The rate of extension of 100 % per minute has been adopted as standard, but higher rates were permitted by agreement for automatic testers.

CRT and CRL testers are now considered to be obsolete. The methods of using them are deprecated and their inclusion in informative Annex A does not have an influence on the status of this International Standard.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 2062:2009](https://standards.iteh.ai/catalog/standards/sist/8368eb6f-5edc-4ba7-b5cf-c56a4361de5d/iso-2062-2009)

<https://standards.iteh.ai/catalog/standards/sist/8368eb6f-5edc-4ba7-b5cf-c56a4361de5d/iso-2062-2009>

Textiles — Yarns from packages — Determination of single-end breaking force and elongation at break using constant rate of extension (CRE) tester

1 Scope

1.1 This International Standard specifies methods for the determination of the breaking force and elongation at break of textile yarns taken from packages.

Four methods are given:

- A: manual; specimens are taken directly from conditioned packages;
- B: automatic; specimens are taken directly from conditioned packages;
- C: manual; relaxed test skeins are used after conditioning;
- D: manual; specimens are used after wetting.

1.2 Method C is used in cases of dispute regarding elongation at break of the yarn.

NOTE Methods A, B and C are expected to give the same results for yarn strength, but Method C might give somewhat truer (and higher) values of elongation than A or B. Method D is likely to give results differing, for both breaking force and elongation at break, from those obtained by methods A, B or C.

1.3 This International Standard specifies methods using constant rate of specimen extension (CRE) tensile testers. Testing on the now obsolete constant rate of travel (CRT) and constant rate of loading (CRL) instruments is covered, for information, in Annex A, in recognition of the fact that these instruments are still in use and can be used by agreement.

1.4 This International Standard applies to all types of yarns, except glass, elastomeric, aramid, high molecular polyethylene (HMPE), ultra high molecular polyethylene (UHMPE), ceramic and carbon yarns and polyolefin tape.

NOTE A method for the testing of glass yarns is given in ISO 3341.

1.5 This International Standard is applicable to yarns from packages but can be applied to yarns extracted from fabrics, subject to agreement between the interested parties.

1.6 This International Standard is intended for the single-end (single-strand) testing of yarns.

NOTE The skein method of testing is given in ISO 6939.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 139, *Textiles — Standard atmospheres for conditioning and testing*

ISO 2060, *Textiles — Yarn from packages — Determination of linear density (mass per unit length) by the skein method*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 breaking force

maximum force applied to a specimen in a tensile test carried to rupture

NOTE For yarns, the breaking force or load is preferably expressed in centinewtons.

3.2 elongation at break

increase in length of a specimen corresponding to the breaking force

NOTE For yarns, elongation at break is expressed as a percentage of the initial length.

3.3 breaking tenacity

ratio of a yarn's breaking force to its linear density

NOTE For yarns, breaking tenacity is expressed in centinewtons per tex.

3.4 constant rate of specimen extension (CRE) tester

testing machine in which one end of the specimen is held in a virtually stationary clamp and the other end is gripped in a clamp that is driven at a constant speed

NOTE A suitable system is provided for detecting and recording the force applied and the elongation.

3.5 clamp

that part of a tensile testing machine used to grip the specimen by means of suitable jaws

3.6 jaws

those elements of a clamp which grip the specimen

3.7 gauge length

nominal length
distance between the clamping points of the tester

NOTE With bollard or capstan clamps, it is the distance between their gripping points, measured along the path of the yarn.

3.8 initial length

length of a test specimen (between the clamping points) under specified pretension at the beginning of the test

3.9 package

length of yarn in a form suitable for use, handling, storing, etc.

NOTE Packages can be supported (e.g. cones, bobbins) or unsupported (e.g. skeins, balls).

4 Principle

A specimen of yarn is extended until rupture by a suitable mechanical device, and the breaking force and elongation at break are recorded. A constant rate of extension of 100 % per minute (based on the gauge length) is used, but higher or lower rates are permitted by agreement. Two gauge lengths are permitted: usually 500 mm (with a rate of extension of 500 mm/min), and exceptionally 250 mm (with a rate of extension of 250 mm/min).

5 Apparatus and reagents

5.1 Constant rate of specimen extension (CRE) tester, which complies with the following requirements.

The tester shall be capable of being set at gauge lengths of 500 mm \pm 2 mm or 250 mm \pm 1 mm, or preferably both.

The constant rate of extension of the moving clamp shall be 500 mm/min \pm 10 mm/min or 250 mm/min \pm 5 mm/min, to an accuracy of \pm 2 %, with lower or, for automatic testers, higher rates being permitted by agreement.

The maximum error of the indicated force shall not exceed 2 % of the true force.

The tester may be of the manual or automatic type.

The clamps for gripping the specimens shall prevent slipping or cutting of the specimens and breaks at the jaws. Flat-faced unlined jaws shall be the normal type but, if these cannot prevent slippage, then other types of clamps may be used on agreement, such as lined jaws, bollard clamps or other types of snubbing devices. As the type of clamp may influence the reading of the elongation, all interested parties shall use the same type.

The tester shall be equipped with an autographic force/elongation recording device of sufficiently fast response, or with a system directly recording the breaking force and elongation at break.

The tester shall be capable of setting a pretension either by means of a set of pretensioning weights or by using the force-measuring device.

5.2 Reel, for preparing test skeins from the laboratory sample (for methods C and D).

5.3 Swift or similar device, for holding the test skein under zero tension and permitting easy transfer of the yarn to the tensile tester (for Method C).

5.4 Receptacles, for immersing the sample or the specimens in water (for Method D).

5.5 Tap water, at room temperature (for Method D).

5.6 Non-ionic surfactant, 0,1 % (volumetric) aqueous solution (for Method D).

6 Sampling

6.1 Samples shall be taken in accordance with

- a) the directions given in the material specification when available, or
- b) the procedures described in 6.2 to 6.7.

6.2 A bulk sample shall be taken of one or more cases, as representative of the lot to be tested as shown in Table 1.

Table 1 — Sampling frequency

Number of cases	Number of cases selected at random
3 or less	1
4 to 10	2
11 to 30	3
31 to 75	4
76 or more	5

6.3 If only mean values are required, then 10 packages shall be taken from the bulk sample, distributed as evenly as possible among the cases and among the levels in each case.

6.4 Except for the provisions of 6.5, the minimum number of specimens to be tested shall be 50 for single-spun yarns and 20 for other yarns. The specimens shall be distributed as evenly as possible among the 10 packages.

6.5 If the variability of the test is known and only mean values are required, then the number of specimens shall be calculated as $0,17 CV^2$ where CV is the coefficient of variation of the individual breaks (expressed as a percentage) obtained from experience on similar material.

NOTE This number of specimens will give a precision (1,96 times the standard error of the mean) of $\pm 4\%$ at a probability level of 90 %.

ISO 2062:2009

Strength testing is a “one-tail” test; that is “yarn shall not be weaker than...” but “may be stronger than...”. When specifying 90 % probability, one tail of the distribution is 5 %, or exactly the same as the two tails together or the more common 95 % probability appropriate for a “two-tail” test.

6.6 If the coefficient of variation is to be determined in addition to the mean, then 20 packages shall be taken from the bulk sample and at least 200 specimens shall be tested for single-spun yarns and at least 100 specimens for all other types of yarn.

6.7 If specimens are to be extracted from fabrics [not suitable for automatic testers (Method B)], then the fabric sample shall be large enough to furnish a sufficient number and length of specimens. The test specimens shall be taken so that the twist in the yarn is not changed during sampling. In woven fabrics, warp specimens shall be taken from different ends and weft specimens shall be taken at random from several sections of the sample to be as representative of the yarn as possible. In knitted fabrics, specimens shall represent as many different yarns as possible.

7 Preconditioning and conditioning

7.1 The atmospheres for preconditioning, conditioning and testing shall be as specified in ISO 139.

7.2 For methods A to C, the sample packages or test skeins shall be preconditioned for a minimum of 4 h.

NOTE Preconditioning can often be dispensed with if the samples are conditioned directly “from the dry side”.

7.3 After preconditioning, the sample shall be brought to moisture equilibrium under the conditioning atmosphere. For skeins, overnight conditioning is usually sufficient, but for tightly wound packages a minimum of 48 h is necessary.

7.4 Preconditioning and conditioning are not required for wet tests (Method D).

8 Procedure

8.1 General

8.1.1 If more than one condition of testing is permitted, usually by agreement, then all parties interested in the test results shall perform the test under the same conditions (i.e. gauge length, rate of extension, type of clamp, temperature, pretension).

8.1.2 Two gauge lengths are permitted: the usual length of 500 mm, and a length of 250 mm which can be used only if

- a) the extension of the instrument is insufficient to accommodate a 500 mm specimen, or
- b) by agreement between the interested parties.

8.1.3 If a calculation of breaking tenacity is required, determine the linear density of the yarn in accordance with ISO 2060.

8.1.4 Use a rate of extension of 500 mm/min or 250 mm/min at the gauge length of 500 mm or 250 mm. In addition, for automatic testers only (Method B), higher rates are permitted by agreement; 2 000 mm/min and 5 000 mm/min are recommended. Lower extension rates may be used on agreement; e.g. 50 %/min or 20 %/min.

8.1.5 Unwind the yarn from the package as is done in normal use.

8.1.6 Before clamping the specimen, check that the jaws are correctly aligned and parallel, so that the force applied produces no angular deviation.

8.1.7 Insert the specimen in the clamps with a pretension of $0,5 \text{ cN/tex} \pm 0,1 \text{ cN/tex}$ for conditioned specimens, or $0,25 \text{ cN/tex} \pm 0,05 \text{ cN/tex}$ for wet specimens. If the specimen is inserted under unknown tension, the tester must be able to determine its initial length (under specified pretension).

For untwisted technical and industrial multifilament yarns, to ensure that all filaments have the same tension at the beginning of the test and to prevent slippage of individual filaments in the clamps during the test, a twist should be applied prior to the test. A twist of 60 ± 1 turns/m for yarns below 2 200 dtex and a twist of 30 ± 1 turns/m for yarns above 2 200 dtex are recommended. Other twist amounts may be allowed on agreement of the interested parties.

8.1.8 For textured yarns, use a pretension which will remove the crimp but not stretch the yarn. The following pretensions are recommended (unless otherwise agreed), calculated on the nominal linear density of the yarn:

- $2,0 \text{ cN/tex} \pm 0,2 \text{ cN/tex}$, for polyester and polyamide yarns;
- $1,0 \text{ cN/tex} \pm 0,1 \text{ cN/tex}$, for acetate, triacetate and viscose yarns;
- $0,5 \text{ cN/tex} \pm 0,05 \text{ cN/tex}$, for bi-shrinkage and jet-bulked yarns, except for carpet yarns heavier than 50 tex.

8.1.9 Finally, secure the specimen in the clamps.

8.1.10 Perform the test under the standard atmosphere for testing, as specified in 7.1.

8.1.11 During the test, check that the specimen does not slip between the jaws by more than 2 mm. If it does so repeatedly, change the clamps or jaw lining. Discard the results of the tests where slippage occurs. Also discard results involving jaw breaks where breaks occur 5 mm from the jaws or closer, but record the number of specimens for which the results were discarded.