

# INTERNATIONAL STANDARD

**ISO**  
**15783**

First edition  
2002-02-01

**AMENDMENT 1**  
2008-11-01

---

---

## Seal-less rotodynamic pumps — Class II — Specification

### AMENDMENT 1

*Pompes rotodynamiques sans dispositif d'étanchéité d'arbre —  
Classe II — Spécifications*

AMENDEMENT 1

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

[ISO 15783:2002/Amd 1:2008](https://standards.iteh.ai/catalog/standards/sist/0c418b51-7d68-47d3-86c4-5ee0dc98f334/iso-15783-2002-amd-1-2008)

<https://standards.iteh.ai/catalog/standards/sist/0c418b51-7d68-47d3-86c4-5ee0dc98f334/iso-15783-2002-amd-1-2008>



Reference number  
ISO 15783:2002/Amd.1:2008(E)

© ISO 2008

**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 15783:2002/Amd 1:2008](https://standards.iteh.ai/catalog/standards/sist/0c418b51-7d68-47d3-86c4-5ee0dc98f334/iso-15783-2002-amd-1-2008)

<https://standards.iteh.ai/catalog/standards/sist/0c418b51-7d68-47d3-86c4-5ee0dc98f334/iso-15783-2002-amd-1-2008>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 15783:2002 was prepared by Technical Committee ISO/TC 115, *Pumps*, Subcommittee SC 1, *Dimensions and technical specifications of pumps*.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 15783:2002/Amd 1:2008](https://standards.iteh.ai/catalog/standards/sist/0c418b51-7d68-47d3-86c4-5ee0dc98f334/iso-15783-2002-amd-1-2008)  
<https://standards.iteh.ai/catalog/standards/sist/0c418b51-7d68-47d3-86c4-5ee0dc98f334/iso-15783-2002-amd-1-2008>

## **iTeh STANDARD PREVIEW** **(standards.iteh.ai)**

ISO 15783:2002/Amd 1:2008

<https://standards.iteh.ai/catalog/standards/sist/0c418b51-7d68-47d3-86c4-5ee0dc98f334/iso-15783-2002-amd-1-2008>

# Seal-less rotodynamic pumps — Class II — Specification

## AMENDMENT 1

*Pages 40 and 41, Annex F*

Replace the existing “Table F.1 — Internationally and nationally accepted materials for pump parts” by the following:

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 15783:2002/Amd 1:2008](https://standards.iteh.ai/catalog/standards/sist/0c418b51-7d68-47d3-86c4-5ee0dc98f334/iso-15783-2002-amd-1-2008)  
<https://standards.iteh.ai/catalog/standards/sist/0c418b51-7d68-47d3-86c4-5ee0dc98f334/iso-15783-2002-amd-1-2008>

Table F.1 — Internationally and nationally accepted materials for pump parts

Material class	Applications	International Standard ISO	USA		UNS <sup>a</sup>	EN <sup>b</sup>	Europe		Japan JIS
			ASTM				Designation	Number	
Cast iron	Pressure castings	185/ Gr. 250	A 278 Class 30		F12401	EN 1561	EN-GJL-250	JL1040	G 5501, Gr. FC 250
	General castings	185/ Gr. 300	A 48 Class 25/30/40		F11701/ F12101	1561	EN-GJL-250 EN-GJL-300	JL1040 JL1050	G 5501, Gr. FC 250 G 5501, Gr. FC 300
Ductile iron	General castings	1083, 400-18	A 536 Gr 60-40-18		F32800	1563	EN-GJS-400-18	JS1020	G5502, Gr.FCD400-18
Ni-resist	Special castings	2892, L-NiCuCr 15 6 3	A 436 Type 1		F44000	13835	EN-GJLA-XNiCuCr15-6-2	—	G5510, Gr.FCA-NiCuCr1563
		2892, S-NiCr 20 2	A 439 Type D-2		F43000	13835	EN-GJSA-XNiCr20-2		G5510, Gr.FCDA-NiCr202
Carbon steel	Pressure castings	4991 C23-45AH	A 216 Gr WCB		J03002	10213-2	GP 240 GH	1.0619	G 5151, CI SCPL 2
	Low-temperature castings	4991, C23-45BL	A 352 Gr LCB		J 03003	10213-3	G18Mo5	1.5422	G5152, CI SCPL1
		4991, C43E2aL	A 352 Gr LC2		22500	10213-3	G20Mo5	1.6220	G5152, CI SCPL11
		4991, C43L	A 352 Gr LC3		J 31550	10213-3	G9Ni10	1.5636	G5152, CI SCPL21
						10213-3	G9Ni14	1.5638	G5152, CI SCPL31
	Wrought/ forgings	683-18-C25, 9327-2 - PH26-PH31, 9327-4	A 266 Class 2		K03506	10222-2	P 280 GH	1.0426	G 3202, CI SFVC 2A
	Bar stock: pressure	683-18-C 25, 9327-2, PH26-PH31, 9327-4	A 696 Gr B40		G10200	10273	P 295 GH	1.0481	G 4051, CI S25C
	Bar stock: general	683-18-C45e 9327-2 - PH26-PH31, 9327-4	A 576 Gr 1045		G10450	10083-2	C 45	1.0503	G 4051, CI S45C
	Bolts and studs (general)	9327-2-F31	A 193 Gr B7		G41400	10269	42 Cr Mo 4	1.7225	G 4107, Class 2, SNB7
	Nuts (general)	683-1-C35e	A 194 Gr 2H		K04002	10269	C 35 E	1.1181	G 4051, CI S45C
	Plate	9328-4, P 355 TN/PL 355 TN	A 516 Gr 65/70		K02403/ K02700	10028-3 10028-2	P 355 N P 355 NL1 P 295 GH P 355 GH	1.0562 1.0566 1.0481 1.0473	G 3106, Gr. SM400B

Table F.1 (continued)

Material class	Applications	International Standard ISO	USA		EN <sup>b</sup>	Europe		Japan JIS
			ASTM	UNS <sup>a</sup>		Designation	Number	
Carbon steel (cont.)	Pipe	9329-2, PH26-PH35	A 106 GrB	K03006	10208-1	L 245 GA	1.0459	G 3456, Gr. STPT 370/410
	Fittings	—	A 105	K03504	—	—	—	G 4051, CI S25C G 3202, CI SFVC 2A, SFVC2B
AISI 4140 Chromium steel	Bar stock	—	A 434 Class BB A 434 Class BC	G41400 <sup>c</sup>	10083-1	42 Cr Mo 4	1.7225	G 4105, CI SCM 440
	Bolts and studs	—	A 193 Gr B7	G41400	10269	42 Cr Mo 4	1.7225	G 4107, Class 2, SNB7
	Nuts	9327-2-F31	A 194 Gr 2H	K04002	10269	C 45 E	1.1191	G 4051, CI S45C
					10269	C 35 E	1.1181	
12% Chromium steel	Pressure castings	—	A 217 Gr CA 15	J91150	10213-2	GX 8 Cr Ni 12	1.4107	G 5121, CI SCS 1
			A 487 Gr CA6NM	J91540	10213-2	GX 4 Cr Ni 13-4	1.4317	G 5121, CI SCS 6, CI SCS 6X
	General castings	—	A 743 Gr CA 15	J91150	10283	GX 12 Cr 12	1.4011	G 5121, CI SCS1, CI SCS1X
			A 743 Gr CA6NM	J91540	10283	GX 4 Cr Ni 13-4	1.4317	G 5121, CI SCS6, CI SCS6X
	Wrought/forgings: pressure	—	A 182 Gr F6a CI 1 A 182 Gr F 6 NM	S41000 S41500	10250-4 10222-5	X12 Cr 13 X 3 Cr NiMo 13-4-1	1.4006 1.4313	G 3214, Gr. SUS 410-A G 3214, CI SUS F6 NM
			A 473 Type 410	S41000	10088-3	X 12 Cr 13	1.4006	G 3214, Gr. SUS 410-A
	Wrought/forgings: general	—						
	Bar stock: pressure	—	A 479 Type 410	S41000	10272	X12 Cr 13	1.4006	G 4303, Gr. SUS 410 or 403
	Bar stock: general	—	A 276 Type 410	S41400	10088-3	X 12 Cr 13	1.4006	G 4303, Gr. SUS 410 or 403
			A 276 Type 420 A 473 Type 416 A 582 Type 416	S42000 S41600 S41600	10088-3	X 20 Cr 13 X 20 Cr S 13 X 20 Cr S 13	1.4021 1.4005 1.4005	G 4303, Gr. SUS 420J1 or 420J2

Table F.1 (continued)

Material class	Applications	International Standard ISO	USA		EN <sup>b</sup>	Europe		Japan JIS
			ASTM	UNS <sup>a</sup>		Designation	Number	
12% Chromium steel (cont.)	Bolts and studs <sup>d</sup>	3506-1, C4-70	A 193 Gr B6	S41000	10269	X22CrMoV 12-1	1.4923	G 4303, Gr. SUS 410 or 403
	Nuts <sup>d</sup>	3506-2, C4-70	A 194 Gr 6	S41000	10269	X22CrMoV 12-1	1.4923	G 4303, Gr. SUS 410 or 403
	Plate	—	A 240 Type 410	S41000	10088-2	X 12 Cr 13	1.4006	G 4304/4305 Gr. SUS 410 or 403
Austenitic stainless steel	Pressure castings	11972, GX2CrNi18-10	A 351 Gr CF3	J92500	10213-4	GX2 Cr Ni 19-11	1.4309	G 5121, CI SCS 19A
		11972, GX2CrNiMo19-11-2	A 351 Gr CF3M	J92800	10213-4	GX2 Cr Ni Mo 19-11-2	1.4409	G 5121, CI SCS 16A G 5121, CI SCS16AX
	General castings	11972, GX2CrNi18-10	A 743 Gr CF3	J92500	10283	GX2 Cr Ni 19-11	1.4309	G 5121, CI SCS 19A
		11972, GX2CrNiMo19-11-2	A 743 Gr CF3M	J92800	10283	GX2 Cr Ni Mo 19-11-2	1.4409	G 5121, CI SCS 16A G 5121, CI SCS16AX
	Wrought/ forgings	9327-5, XCrNi18-10	A 182 Gr F 304L	S30403	10222-5	X2 Cr Ni 19-11	1.4306	G 3214, Gr. SUS F 304 L
		9327-5, XCrNiMo17-12	A 182 Gr F 316L	S31603	10222-5 10250-4	X2 Cr Ni Mo 17-12-2	1.4404	G 3214, Gr. SUS F 316 L
	Bar stock <sup>e</sup>	9327-5, X2CrNi18-10	A 479 Type 304L	S30403	10088-3	X2 Cr Ni 19-11	1.4306	G 4303, Gr. SUS 304 L
		9327-5, X2CrNiMo17-12	A 479 Type 316L	S31603	10088-3	X2 Cr Ni Mo 17-12-2	1.4404	G 4303, Gr. SUS 316 L
			A 479 Type 317	S31700	10088-3	X2 Cr Ni Mo 18-15-4	1.4361	
			A 479 Type XM19	S20910	—	—	—	
	Plate	—	A 240 Type XM19	S20910	—	—	—	—
	Pipe	9329-4, X2CrNi18-10, 9329-4, X2CrNiMo17-13,	A 240 Gr 304L / 316L	S30403 S31603	10028-7 10028-7	X2 Cr Ni 19-11 X2 Cr Ni Mo 17-12-2	1.4306 1.4404	G 4304/4305, Gr. SUS 304L/316L
			A 312 Type 304L 316L	S30403 S31603	—	—	—	G 3459, Gr. SUS 304LTP/316LTP

Table F.1 (continued)

Material class	Applications	International Standard ISO	USA		EN <sup>b</sup>	Europe		Japan JIS
			ASTM	UNS <sup>a</sup>		Designation	Number	
Austenitic stainless steel	Fittings	9327-5, X2CrNi18-10 9327-5, X2CrNiMo17-12	A 182 Gr F304L, Gr 316L	S30403 S31603	10222-5	X2 Cr Ni 19-11 X2 Cr Ni Mo 17-12-2	1.4306 1.4404	G 3214, Gr. SUS F304L/F316L
	Bolts and studs	3506-1, A4-70	A 193 Gr B8M	S31600	10250-4	X6 Cr Ni Mo Ti 17-12-2	1.4571	G 4303, Gr. SUS 316
	Nuts	3506-2, A4-70	A 194 Gr B8M	S31600	10250-4	X6 Cr Ni Mo Ti 17-12-2	1.4571	G 4303, Gr. SUS 316
Precipitation hardened stainless steel	Pressure forgings	—	A 705 ("15-5 PH") A 705 ("17-4 PH")	S 5500 S 17400	—	—	—	—
Duplex stainless steel	Pressure castings	11972, GX2CrNiCuMoN 26 5 3 3	A 351 Gr CD4 MCu A 890 Gr 1 B	S93370 S93372	10213-4	GX2 CrNiMoCuN 25-6-3-3	1.4517	
		11972, GX2CrNiMoN 26 5 3	A 890 Gr 3A <sup>c</sup>	S93371	—	—	—	G 5121, Gr. SCS 11
		—	A 890 Gr 4A <sup>c</sup>	S92205	10213-4	GX2 CrNiMoN 22-5-3	1.4470	G 5121, Gr. SCS 10
Wrought/forgings		9327-5, X2CrNiMoN22-5-3	A 182 Gr F 51	S31803	10250-4 10222-5	X2 Cr Ni Mo N 22-5-3	1.4462	
		—	A 479	S32550	10088-3	X2 Cr Ni Mo Cu N 25-6-3	1.4507	
	Bar stock	9327-5, X2CrNiMoN22-5-3	A 276-S31803	S31803	10088-3	X2 Cr Ni Mo N 22-5-3	1.4462	G 4303, Gr. SUS 329J3L
Plate		—	A 240-S31803	S31803	10028-7	X2 Cr Ni Mo N 22-5-3	1.4462	G 4304/G 4305, Gr. SUS 329J3L
Pipe		—	A 790-S31803	S31803	—	—	—	G 3459, Gr. SUS 329J3L TP
Fittings		9327-5, X2CrNiMoN22-5-3	A 182 Gr F 51	S31803	10250-4 10222-5	X2 Cr Ni Mo N 22-5-3	1.4462	B 2312/B 2316 Gr. SUS329J3L
Duplex stainless steel	Bolts and studs	9327-5, X2CrNiMoN22-5-3	A 276-S31803	S31803	10088-3	X2 Cr Ni Mo N 22-5-3	1.4462	G 4303, Gr. SUS 329J3L
	Nuts	9327-5, X2CrNiMoN22-5-3	A 276-S31803	S31803	10088-3	X2 Cr Ni Mo N 22-5-3	1.4462	G 4303, Gr. SUS 329J3L