INTERNATIONAL STANDARD



First edition 2009-10-15

Thermal insulation products for building applications — Determination of the mechanical properties of glass fibre meshes

Produits isolants thermiques destinés aux applications du bâtiment — Détermination des caractéristiques mécaniques des treillis de fibres de **iTeh STyere DARD PREVIEW**

(standards.iteh.ai)

<u>ISO 29805:2009</u> https://standards.iteh.ai/catalog/standards/sist/1e847fcb-0781-492b-949be46d364d173d/iso-29805-2009



Reference number ISO 29805:2009(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 29805:2009</u> https://standards.iteh.ai/catalog/standards/sist/1e847fcb-0781-492b-949be46d364d173d/iso-29805-2009



COPYRIGHT PROTECTED DOCUMENT

© ISO 2009

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org Published in Switzerland

Contents

Forev	word	iv
1	Scope	1
2	Normative references	1
3 3.1 3.2	Terms, definitions, symbols and units Terms and definitions Symbols and units	1 1 2
4	Principle	2
5	Apparatus	2
6 6.1 6.2 6.3 6.4	Test specimens Number of test specimens Dimensions of the test specimens Preparation of the test specimens Conditioning of the test specimens	2 2 3 3
7 7.1 7.2 7.3	Procedure Test conditions Ten Str.A.N.D.A.R.D.D.P.R.V.L. Attachment of the test specimens in the tensile testing machine Test procedure	4 4 4 4
8	Calculation and expression of results	4
9 10	Accuracy of measurement. https://standards.iteh.ai/catalog/standards/sist/1e847fcb-0781-492b-949b- Test report	5 5

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 29805 was prepared by Technical Committee ISO/TC 163, *Thermal performance and energy use in the built environment*, Subcommittee SC 1, *Test and measurement methods*.

ISO 29805 is based on EN 13496:2002, prepared by Technical Committee CEN/TC 88 Thermal insulating materials and products. However (standards.iteh.ai)

- 6.4 conditioning of the test specimens and storage under ambient conditions,
- 7.1 test conditions, and https://standards.iteh.ai/catalog/standards/sist/1e847fcb-0781-492b-949be46d364d173d/iso-29805-2009
- Clause 10 test report,

have been modified to reflect the conditions for tropical countries. Other modifications were made in 3.1.1, 5.3, 6.4.2 and Clause 8.

This International Standard is based on EN 13496:2002 prepared by Technical Committee CEN/TC 88 *Thermal insulating materials and products*, which has been amended by ISO/TC 163/SC 1 with reference to conditioning and testing conditions in tropical countries.

This International Standard is one of a series of documents specifying test methods, based on existing European Standards, that are being adopted by ISO. This "package" of standards includes the following group of interrelated documents.

International Standard	Title	Respective EN standard
12968	Thermal insulation products for building applications — Determination of the pull-off resistance of external thermal insulation composite systems (ETICS) (foam block test)	EN 13495
29465	Thermal insulating products for building applications — Determination of length and width	EN 822
29466	Thermal insulating products for building applications — Determination of thickness	EN 823
29467	Thermal insulating products for building applications — Determination of squareness	EN 824
29468	Thermal insulating products for building applications — Determination of flatness	EN 825
29469	Thermal insulating products for building applications — Determination of compression behaviour	EN 826
29470	Thermal insulating products for building applications — Determination of the apparent density	EN 1602
29471	Thermal insulating products for building applications — Determination of dimensional stability under constant normal laboratory conditions (23°C/50 % relative humidity) ISO 29805:2009	EN 1603
29472	Thermal insulating products for building applications — Determination of dimensional stability under specified temperature and humidity conditions	EN 1604
29764	Thermal insulating products for building applications — Determination of deformation under specified compressive load and temperature conditions	EN 1605
29765	Thermal insulating products for building applications — Determination of tensile strength perpendicular to faces	EN 1607
29766	Thermal insulating products for building applications — Determination of tensile strength parallel to faces	EN 1608
29767	Thermal insulating products for building applications — Determination of short-term water absorption by partial immersion	EN 1609
29768	Thermal insulating products for building applications — Determination of linear dimensions of test specimens	EN 12085
29769	Thermal insulating products for building applications — Determination of behaviour under point load	EN 12430
29770	Thermal insulating products for building applications — Determination of thickness for floating floor insulating products	EN 12431
29771	Thermal insulating materials for building applications — Determination of organic content	EN 13820
29803	Thermal insulation products for building applications — Determination of the resistance to impact of external thermal insulation composite systems (ETICS)	EN 13497
29804	Thermal insulation products for building applications — Determination of the tensile bond strength of the adhesive and of the base coat to the thermal insulation material	EN 13494
29805	Thermal insulation products for building applications — Determination of the mechanical properties of glass fibre meshes	EN 13496

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 29805:2009</u> https://standards.iteh.ai/catalog/standards/sist/1e847fcb-0781-492b-949be46d364d173d/iso-29805-2009

Thermal insulation products for building applications — Determination of the mechanical properties of glass fibre meshes

1 Scope

This International Standard specifies equipment and procedures for determining the tensile strength and elongation of glass fibre meshes, which are used for the reinforcement of the base coat in External Thermal Insulation Composite Systems (ETICS).

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 29765, Thermal insulating products for building applications E Determination of tensile strength perpendicular to faces (standards.iteh.ai)

EN 13499, Thermal insulation products for buildings — External thermal insulation composite systems (ETICS) based on expanded polystyrene — <u>Specification</u>9

https://standards.iteh.ai/catalog/standards/sist/1e847fcb-0781-492b-949b-ISO 9229, *Thermal insulation — Vocabulary*4d173d/iso-29805-2009

ISO 1887, Textile glass — Determination of combustible-matter content

3 Terms, definitions, symbols and units

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 9229 and EN 13499 and the following apply.

3.1.1

elongation of glass fibre mesh

\mathcal{E}_{F}

quotient of the change in length, $l_{\rm F} - l_0$, and the initial length, before failure, of the test specimen between the clamps at the failure, l_0

3.1.2

tensile strength of glass fibre mesh

strength of the test specimen at failure relative to the width of the test specimen

3.2 Symbols and units

- F_{F} is the force at failure, in N;
- l_0 is the distance between the clamps, in mm;
- $l_{\rm F}$ is the distance between the clamps at failure, in mm;
- *w* is the width of the test specimen, in mm;
- $\beta_{\rm F}$ is the tensile strength of the test specimen in relation to the width of the test specimen, in N/mm;

 $\varepsilon_{\rm F}$ is the elongation at failure, in mm/mm.

4 Principle

The tensile strength and the elongation of glass fibre meshes are determined at failure using a tensile testing machine.

5 Apparatus

5.1 Tensile testing machine, appropriate for the range of force and displacement involved, capable of having a constant crosshead speed adjusted to (50 ± 5) mm/min. It shall be capable of measuring the force and elongation to an error limit of at least 1 % (in accordance with ISO 29765).

standards.iteh.ai)

5.2 Clamps, of the tensile testing machine, coated with a material to ensure attachment without slippage of the test specimen, such as rubber, and shall fasten the test specimen across its whole width. The clamps shall be sufficiently rigid to resist deformation during the test.

5.3 Container, wide and deep enough so that the test specimens can be immersed completely in an alkaline test solution. This can be a cylindrical container, of volume $(2,5 \pm 0,5)$ l, of height (48 ± 1) cm, of internal diameter $(8 \pm 0,5)$ cm, in which $(2 \pm 0,1)$ l of the alkaline test solution is introduced. The container shall be covered. The material of the container shall be resistant to the alkaline test solution (e.g. plastics or stainless steel).

6 Test specimens

6.1 Number of test specimens

Seven test specimens shall be used in warp direction, stored under ambient conditions.

Seven test specimens shall be used in warp direction, stored in aggressive medium.

Seven test specimens shall be used in weft direction, stored under ambient conditions.

Seven test specimens shall be used in weft direction, stored in aggressive medium.

6.2 Dimensions of the test specimens

The tensile strength of the meshes are tested in both the warp and the weft directions. The test specimen shall contain a minimum number of five threads within the width. The ratio of the length between the clamps to the width of the test specimen shall be 4:1. The dimensions of the test specimens shall be a minimum of $300 \text{ mm} \times 50 \text{ mm}$.

6.3 Preparation of the test specimens

The test specimens shall be cut from the original packed product after removal of the first 5 m of the roll and at a distance of at least 100 mm from the edges. The test specimen shall be cut between the single warp or weft threads. The number of threads in the warp or in the weft direction shall be the same for the seven test specimens. The number of threads shall be indicated in the test report. Test specimens shall not be bent or folded and shall be handled carefully during the whole test procedure.

6.4 Conditioning of the test specimens

6.4.1 Storage under ambient conditions

The test specimens shall be stored at (23 \pm 2) °C and (50 \pm 5) % relative humidity for at least 24 h.

In tropical countries, different conditioning and testing conditions might be relevant. In this case, the conditions shall be (27 ± 2) °C and (65 ± 5) % relative humidity and be stated clearly in the test report.

6.4.2 Storage in aggressive medium

The test specimens shall be stored in the following alkaline test solution for 28 days for a 3-ions test at (23 ± 2) °C.

Concentrations in g/l distilled water:

Ca(OH) ₂	0,5 g	at 96 %1	1 STANDARD PREVIEW	
NaOH	1 g	at 97 %	(standards.iteh.ai)	
КОН	4 g	at 85 % https://standard	ISO 29805:2009 ls.iteh.ai/catalog/standards/sist/1e847fcb-0781-492b-949b-	

For the preparation of the alkaline test solution, the reagents shall be dissolved in distilled water in the given order above. For the storage of 30 g to 35 g glass fibre mesh, 1 l of the alkaline test solution is necessary.

After 28 days of storage, the samples are rinsed by immersion for 5 min in acid solution [5 ml HCl (35 % diluted) to 4 litres water] and then placed successively in 3 baths of water (4 litres each). The samples are left for 5 min in each bath. They are subsequently dried at $(23 \pm 2)^{\circ}$ C and (50 ± 5) % relative humidity for 48 h.

Users who do not have reagents in the indicated concentration shall correct for the difference in mass.

For FPC, the storage of 24 h at $(60 \pm 2)^{\circ}$ C may be used instead of the 28 days at $(23 \pm 2)^{\circ}$ C.

If the glass mesh to be tested is only used in a specified base coat, an aggressive medium consisting of a 20 % suspension of base coat in water at (60 \pm 2) °C may be used.

6.4.3 Wash and drying procedure

After storage in the aggressive medium, the test specimens shall be gently rinsed in running tap water at (20 ± 5) °C until the pH value at the surface of the specimens is less than 9, as measured with pH indicator paper. The test specimens shall be stored for 1 h in 0,5 % hydrochloric acid. After this storage, the test specimens shall be gently rinsed in running tap water at (20 ± 5) °C, without significant mechanical movement, until a pH value of 7 is measured carefully with pH indicator paper. The test specimens shall be dried for 60 min at (60 ± 2) °C and afterwards stored for at least 24 h at (23 ± 2) °C and (50 ± 5) % relative humidity before testing.