
**Self adhesive tapes — Measurement of
static shear adhesion**

Rubans auto-adhésifs — Mesurage du pouvoir adhésif tangentiel

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 29863:2007](https://standards.iteh.ai/catalog/standards/sist/bd747258-0342-4c4e-8509-90dd5e19cb6a/iso-29863-2007)

<https://standards.iteh.ai/catalog/standards/sist/bd747258-0342-4c4e-8509-90dd5e19cb6a/iso-29863-2007>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 29863:2007](https://standards.iteh.ai/catalog/standards/sist/bd747258-0342-4c4e-8509-90dd5e19cb6a/iso-29863-2007)

<https://standards.iteh.ai/catalog/standards/sist/bd747258-0342-4c4e-8509-90dd5e19cb6a/iso-29863-2007>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 29863 was prepared by the European Committee for Standardization (CEN) (as EN 1943) and was adopted, under a special "fast-track procedure", by the ISO Technical Management Board (TMB), in parallel with its approval by the ISO member bodies.

ITEH STANDARD PREVIEW
(standards.iteh.ai)

[ISO 29863:2007](https://standards.iteh.ai/catalog/standards/sist/bd747258-0342-4c4e-8509-90dd5e19cb6a/iso-29863-2007)

<https://standards.iteh.ai/catalog/standards/sist/bd747258-0342-4c4e-8509-90dd5e19cb6a/iso-29863-2007>

Contents

	page
Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions.....	5
4 Significance and use	5
5 Method A: Measurement of shear adhesion to a vertical standard steel panel	6
5.1 Principle	6
5.2 Materials.....	6
5.3 Apparatus	6
5.4 Test samples and test piece	7
5.5 Procedure	8
5.6 Expression of results	9
5.7 Test report	9
6 Method B: Measurement of shear adhesion to a vertical panel covered with NIST SRM 1810A standard fibreboard	9
6.1 Principle	9
6.2 Materials.....	9
6.3 Apparatus	10
6.4 Test samples and test piece	10
6.5 Procedure	10
6.6 Expression of results	10
6.7 Test report	10
7 Method C: Measurement of shear adhesion to a vertical panel covered with a fibreboard agreed upon by the buyer and the seller.....	11
7.1 Principle	11
7.2 Procedure	11
8 Method D: Measurement of shear adhesion of filament reinforced tape applied to a horizontal standard steel panel	11
8.1 Principle	11
8.2 Materials.....	11
8.3 Apparatus	11
8.4 Test samples and test piece	12
8.5 Procedure	12
8.6 Expression of results	13
8.7 Test report	13
9 Method E: Measurement of shear adhesion of filament reinforced tape applied to a horizontal panel covered with NIST SRM 1810A standard fibreboard	13
9.1 Principle	13
9.2 Procedure	13
10 Method F: Measurement of shear adhesion of filament reinforced tape applied to a horizontal panel covered with a fibreboard agreed upon by the buyer and the seller	14
10.1 Principle	14
10.2 Procedure	14
11 Method G: Measurement of shear adhesion to a vertical standard steel panel at an elevated temperature after 10 min dwell time.....	14
11.1 Principle	14
11.2 Procedure	14

Foreword

This document EN 1943:2002 has been prepared by Technical Committee CEN/TC 253 "Self adhesive tapes", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2003, and conflicting national standards shall be withdrawn at the latest by April 2003.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 29863:2007](https://standards.iteh.ai/catalog/standards/sist/bd747258-0342-4c4e-8509-90dd5e19cb6a/iso-29863-2007)

<https://standards.iteh.ai/catalog/standards/sist/bd747258-0342-4c4e-8509-90dd5e19cb6a/iso-29863-2007>

Introduction

This European Standard has been revised in conjunction with AFERA (European Association for the Self Adhesive Tape Industry) in Europe and PSTC (Pressure Sensitive Tape Council) in USA with the purpose to produce a standard which will be acceptable in due course by ISO.

Key changes from EN 1943:1996

- the principle of shear adhesion measurement changes to time to failure under constant load from a measurement of the load to induce failure within four hours;
- scope of the test is expanded to include horizontal shear measurement of filament reinforced tape and to include fibreboard substrate;
- steel plates are revised to readily available, industry standard steel with a smoother surface finish “in line with EN 1939 Rev.”;
- test piece preparation procedure is revised in line with EN 1939 Rev.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 29863:2007](https://standards.iteh.ai/catalog/standards/sist/bd747258-0342-4c4e-8509-90dd5e19cb6a/iso-29863-2007)

<https://standards.iteh.ai/catalog/standards/sist/bd747258-0342-4c4e-8509-90dd5e19cb6a/iso-29863-2007>

1 Scope

This European Standard specifies a series of methods for the determination of the ability of a pressure sensitive tape to remain adhered under a constant load applied parallel to the surfaces of the tape and substrate.

The European Standard contains:

- method A : Self adhesive tapes – Measurement of shear adhesion to a vertical standard steel panel;
- method B : Self adhesive tapes – Measurement of shear adhesion to a vertical panel covered with NIST SRM 1810A ¹⁾ standard fibreboard;
- method C : Self adhesive tapes – Measurement of shear adhesion to a vertical panel covered with a fibreboard agreed upon by the buyer and seller;
- method D : Self adhesive tapes – Measurement of shear adhesion of filament reinforced tape applied to a horizontal standard steel panel;
- method E : Self adhesive tapes – Measurement of shear adhesion of filament reinforced tape applied to a horizontal panel covered with NIST SRM 1810A ¹⁾ standard fibreboard;
- method F : Self adhesive tapes – Measurement of shear adhesion of filament reinforced tape applied to a horizontal panel covered with a fibreboard agreed upon by the buyer and seller;
- method G : Self adhesive tapes – Measurement of shear adhesion to a vertical standard steel panel at elevated temperature after a 10 min dwell time.

[ISO 29863:2007](https://standards.iteh.ai/catalog/standards/sist/bd747258-0342-4c4e-8509-90dd5e19cb6a/iso-29863-2007)

2 Normative references

standards.iteh.ai/catalog/standards/sist/bd747258-0342-4c4e-8509-90dd5e19cb6a/iso-29863-2007

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 10088-2:1995, *Stainless steels – Part 2: Technical delivery conditions for sheet/plate and strip for general purposes*.

EN 12481:2000, *Self adhesive tapes – Terminology*.

3 Terms and definitions

For the purposes of this European Standard, the terms and definitions given in EN 12481:2000 and the following term and definition apply.

3.1

shear adhesion

resistance of the pressure sensitive adhesive against shear when forces are exerted parallel to the bonding surface

4 Significance and use

These test methods are tools for quality control use. Given specific self adhesive tape and a requirement in terms of the minimum or maximum value expected for this tape, the data from the test can be used in conjunction with acceptance criteria.

These methods provide a means of assessing the uniformity of the adhesive of a given type of pressure-sensitive tape (an example are tapes used for packaging applications). The assessment may be within a roll of tape, between rolls or production lots.

Variations in the tape backing and adhesive affect the results, therefore, these methods cannot be used to pinpoint the specific cause(s) of non-uniformity.

These test methods may not provide design information as there is usually no direct relationship between shear adhesion and any functional requirement.

5 Method A: Measurement of shear adhesion to a vertical standard steel panel

5.1 Principle

Method A of this standard measures the shear adhesion of a self adhesive tape to a standard steel panel by its time to failure at 23 °C and 50 % relative humidity (RH) under constant load.

Shear adhesion to standard steel panel – A strip of tape is applied to a standard steel panel under controlled roll down. The panel is mounted vertically, a standard mass is attached to the free end of the tape and the time to failure is determined.

5.2 Materials

5.2.1 Absorbent cleaning material : surgical gauze, cotton wool or tissue. To be suitable, materials shall be lint free during use, absorbent, contain no additives that are soluble in the solvents listed in 5.2.2 and made exclusively from virgin materials.

5.2.2 One or more of the following solvents: [ISO 29863:2007](https://standards.iteh.ai/catalog/standards/sist/bd747258-0342-4c4e-8509-90d15e19eb6a/iso-29863-2007)
<https://standards.iteh.ai/catalog/standards/sist/bd747258-0342-4c4e-8509-90d15e19eb6a/iso-29863-2007>

- diacetone alcohol (4-Hydroxy-4-methyl-2-pentanone) non-residual grade;
- methanol;
- methyl ethyl ketone;
- acetone;
- n-heptane.
- a mixture of n-heptane and a fluorinated hydrocarbon such as refrigerant (suitable when toxicity or flammability restrictions apply).

Solvents shall be of general purpose chemical grade and held in a suitable dispensing system.

5.3 Apparatus

5.3.1 Test piece cutter

A test piece cutter shall hold two single edge razor blades in parallel planes a precise distance apart, to form a cutter of exact specimen width; two cutters, 12 mm and 24 mm cutting width, shall be available or appropriate alternatives which will not cause edge damage. The precision of the razor blade separation shall be the nominal width $\pm 0,1$ mm.

5.3.2 Stainless steel panels

These shall be perfectly flat, at least 125 mm long and 50 mm wide and at least 1,1 mm thick, stainless steel type 1.4301 in accordance with the 2 R quality defined in EN 10088-2:1995, having a bright annealed finish with a surface roughness of $50 \text{ nm} \pm 25 \text{ nm}$. Panels showing stains, discoloration or many scratches are not acceptable. New panels shall be cleaned prior to use as described in 5.5.2.1 except with ten washes of the final solvent. Between uses the panel test surface shall be protected from scratches and contamination and the panels shall be stored in the conditions described in 5.5.2.1.

5.3.3 Roller mechanically or hand operated

5.3.3.1 A steel roller $85 \text{ mm} \pm 2,5 \text{ mm}$ in diameter and $45 \text{ mm} \pm 1,5 \text{ mm}$ in width, covered with rubber approximately 6 mm in thickness, having a Shore A durometer hardness of 80 ± 5 . The surface shall be a true cylinder, void of any convex or concave deviations. The mass of the roller shall be $2 \text{ kg} \pm 0,1 \text{ kg}$.

5.3.3.2 No part of the apparatus shall increase the mass of the roller during use. The roller shall move either mechanically or by hand at the rate of $10 \text{ mm/s} \pm 0,5 \text{ mm/s}$.

5.3.4 Test stands and ancillary apparatus

5.3.4.1 Test stand

A test stand that shall hold the test panel, with tape applied, at an angle between 0° and 2° from the vertical, so that when the mass is acting on the test specimen, no peel force will be exerted on the tape.

5.3.4.2 Clamps

Clamps that will allow the attachment of the mass to the specimen, distributing the load equally across the tape specimen width.

<https://standards.iteh.ai/catalog/standards/sist/bd747258-0342-4c4e-8509-90dd5e19cb6a/iso-29863-2007>

5.3.4.3 Test masses

The test mass shall be $1\ 000 \text{ g} \pm 5 \text{ g}$ or other mass as specified. The mass of the clamp described in 5.3.4.2 shall be included as part of the total mass.

5.3.4.4 Timing system

A timing system to measure the interval between the application of the load to the specimen and its separation from the panel.

5.4 Test samples and test piece

5.4.1 Conditioning

Condition the sample rolls of tape in the standard conditions of $23 \text{ }^\circ\text{C} \pm 1 \text{ }^\circ\text{C}$ and $50 \% \pm 5 \% \text{ RH}$. Test at these conditions unless otherwise specified (see 5.7.h).

If these tolerances cannot be maintained, the closest possible tolerances shall be used and these revised tolerances quoted in the report.

5.4.2 The test requires 3 test pieces, each shall be $12 \text{ mm} \pm 0,5 \text{ mm}$ wide by approximately 150 mm long. Alternatively test pieces of $24 \text{ mm} \pm 0,5 \text{ mm}$ or other widths may be used specifying the contact area used with the results.

5.4.3 Discard at least three but no more than six outer wraps of tape from the sample roll before taking the test pieces for testing.

5.4.4 Remove 3 test pieces for each test to be performed. Remove each test piece from a freely rotating roll at the rate of 500 mm/s to 750 mm/s. Where high unwind force makes it impossible to remove the test piece at the prescribed rate, remove it at a rate as close to 500 mm/s as possible.

5.4.5 When the tape is wider than 12 mm, test pieces of the specified width are to be cut with an apparatus as described in 5.3.1 from the centre of a strip removed from the roll in accordance with 5.4.4.

5.4.6 Apply the test pieces within 5 minutes after unwinding.

5.5 Procedure

5.5.1 Standard test conditions

Standard test conditions shall be the same as 5.4.1 for test pieces and test samples conditioning.

5.5.2 Preparation of the panel

5.5.2.1 Dispense one of the solvents listed in 5.2.2 on to the panel, wiping it to dryness with fresh absorbent cleaning material. Repeat for a total of three washes with this solvent.

Final wipe shall be with methyl ethyl ketone or acetone. The panel should be allowed to dry for at least 10 min. Panels not used within 10 h should be recleaned.

In order to obtain consistent results a new panel shall be wiped at least ten times with final solvent before use.

NOTE Discard plates showing stains, discoloration, or many scratches. Avoid contacting panel surface with fingers. During storage panel should, be protected from damage or contamination.

5.5.3 Shear adhesion

[ISO 29863:2007](https://standards.iteh.ai/catalog/standards/sist/bd747258-0342-4c4e-8509-90dd5e19cb6a/iso-29863-2007)

<https://standards.iteh.ai/catalog/standards/sist/bd747258-0342-4c4e-8509-90dd5e19cb6a/iso-29863-2007>

5.5.3.1 Test piece preparation

Centre the test piece at one end of the test panel and apply without added pressure to cover an area of 12 mm ± 0,5 mm by 12 mm ± 0,5 mm, unless other dimensions are specified. The exposed adhesive of the free area of the test piece may be masked.

To prevent damaging the test piece by the end of the panel during roll down, place another panel of the same or slightly lesser thickness under the free masked end of the test piece, and in contact with the end of the panel prior to roll down. Roll down the applied test area twice, once in each lengthwise direction.

Individually prepare each specimen and begin test within 1 min. For tapes other than packaging tapes, other dwell times may be used but shall be reported.

NOTE The tester should know that by prolonged handling, heat is transmitted to the stainless steel test panel. Therefore during and after application of the adhesive tape to the test panel, the panel should be handled as little as possible.

5.5.3.2 Shear adhesion test

The following action shall be completed within one minute of rolling the sample in 5.5.3.1.

Place the clamp on the free end of the test piece, ensuring that the clamp extends completely across the width of the test piece and is aligned to uniformly distribute the load.

Place the test assembly in the test stand so that the free end of the test piece is vertical, ensuring that no peel force acts on the test piece.

Apply the mass to the clamp gently so as to cause no shear impact force on the test piece. Record the time elapsed until the test piece has completely separated from the test panel.

5.6 Expression of results

To determine the test result, convert each of the test piece results (times to failure) to its common or natural logarithm. Obtain the arithmetic mean of all logarithms and then convert back to time by obtaining the appropriate antilogarithm.

5.7 Test report

The test report shall include the following information:

- a) a reference to this European Standard;
- b) statement that this test method was used and indicating any deviations from the method as written;
- c) identification of each roll of tape tested;
- d) the time to separate completely from the panel as calculated in 5.6;
- e) the dwell time, if other than 1 min;
- f) test contact area if other than 12 mm \pm 0,5 mm by 12 mm \pm 0,5 mm;
- g) mode of failure, cohesive or adhesive failure or other observation:
 - cohesive failure : failure of an adhesive bond such that the separation is within the adhesive;
 - adhesive failure : failure of an adhesive bond such that the separation is at the interface of adhesive and substrate leaving negligible residue.
- h) conditions of test if other than 23 °C \pm 1 °C and 50 % \pm 5 % RH.

6 Method B: Measurement of shear adhesion to a vertical panel covered with NIST SRM 1810A standard fibreboard

6.1 Principle

Method B of this standard measures the shear adhesion of a self adhesive tape to a standard fibreboard surface by its time to failure at 23 °C and 50 % relative humidity (RH) under constant load.

Shear Adhesion to fibreboard – A strip of tape is applied to a suitable panel covered with fibreboard under controlled roll down. The panel is mounted vertically, a standard mass is attached to the free end of the tape and the time to failure is determined.

6.2 Materials

6.2.1 Standard fibreboard : NIST SRM 1810A ¹⁾ standard fibreboard as available from the National Institute of Standards and Technology in Gaithersburg, Maryland, MD 20899, USA.

6.2.2 Double sided tape

Shall be of a width suitable to adhere the fibreboard to the panel.

¹⁾ NIST SRM 1810A is National Institute of Standards and Technology Standard Reference Material 1810A and is available from the Institute at Gaithersburg, Maryland MD 20899, USA.