NOTICE: This standard has either been superseded and replaced by a new version or withdrawn. Contact ASTM International (www.astm.org) for the latest information



Designation: D 3280 – 85 (Reapproved 1999)

Standard Test Methods for Analysis of White Zinc Pigments¹

This standard is issued under the fixed designation D 3280; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 These test methods cover procedures for the analysis of white zinc pigments.

1.2 The analytical procedures appear in the following order:

	Section
Preparation of Sample	6
Zinc Oxide	
Total Zinc, Using Diphenylamine as Internal Indicator	7
Total Zinc, Using Uranyl Acetate as External Indicator	8
Total Impurities	9
Total Sulfur	10
Moisture and Other Volatile Matter	11
Leaded Zinc Oxide	
Total Lead	12
Total Zinc	13
Total Sulfur	
Total Impurities	15
Moisture and Other Volatile Matter	16
Water-Soluble Salts	17
Zinc Sulfide	
Zinc Oxide	18
Zinc Sulfide	19
Water-Soluble Salts	20
Moisture and Other Volatile Matter	21
Barium Sulfate	22
Titanium Dioxide	AS 23 / D3

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

- 2.1 ASTM Standards:
- D 280 Test Methods for Hygroscopic Moisture (and Other Matter Volatile Under the Test Conditions) in Pigments² D 1193 Specification for Reagent Water³

- D 1394 Test Methods for Chemical Analysis of White Titanium Pigments²
- E 11 Specification for Wire-Cloth Sieves for Testing Purposes⁴

3. Summary of Test Methods

3.1 Zinc Oxide:

3.1.1 *Total Zinc*—Determined using diphenylamine as an internal indicator and also using uranyl acetate as an external indicator. Total impurities are calculated.

3.1.2 *Total Sulfur*—Determined as BaSO $_4$ and calculated to sulfur.

3.1.3 *Moisture and Volatile Matter*—Determined in accordance with Method A of Test Methods D 280.

3.2 Leaded Zinc Oxide:

3.2.1 *Total Lead*—Determined as PbSO $_4$ and calculated to percent PbO.

3.2.2 *Total Zinc*—Determined on the filtrate from procedure in 13.1.1 in accordance with methods in Sections 8 or 9.

3.2.3 *Total Sulfur*—Determined as BaSO $_4$ and calculated to percent SO₃.

address all of the 3.2.4 Total Impurities—Calculated from compositional data.

3.2.5 *Moisture and Other Volatile Matter*— Determined in accordance with Method A of Test Methods D 280.

3.2.6 Water Soluble Salts—Determined gravimetrically.

3.3 Zinc Sulfide:

3.3.1 *Total Zinc*—Determined using uranyl acetate external indicator in accordance with Section 9.

3.3.2 Zinc Sulfide—Determined in accordance with Sections 8 or 9 and calculating ZnO to ZnS.

3.3.3 *Water Soluble Salts*—Determined in accordance with Section 18.

3.3.4 *Moisture*—Determined in accordance with Method A of Test Methods D 280.

3.3.5 *Barium Sulfate*—The sample is treated with N_2SO_4 and Na_2CO_3 and the residue of $BaCO_3$ is dissolved in NCl and $(NH_4)_2SO_4$ added to precipitate $BaSO_4$, which is weighed.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

¹ These test methods are under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications and are the direct responsibility of Subcommittee D01.31 on Pigment Specifications.

Current edition approved Oct. 25, 1985. Published December 1985. Originally published as D 3280 - 73. Last previous edition D 3280 - 73 (1979) ^{e2}.

² Annual Book of ASTM Standards, Vol 06.03.

³ Annual Book of ASTM Standards, Vol 11.01.

⁴ Annual Book of ASTM Standards, Vol 14.02.

3.3.6 *Titanium Dioxide*—Determined in accordance with Test Methods D 1394.

4. Significance and Use

4.1 White zinc pigments find considerable use in white paints, and as such it is useful to formulators and users to be able to monitor the amounts of these pigments in whole paints. It is also of interest to raw material suppliers and paint producers to check the specifications of each pigment.

5. Reagents

5.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.⁵ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

5.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean Type II reagent grade water conforming to Specification D 1193.

5.3 Concentration of Reagents:

5.3.1 *Concentrated Acids and Ammonium Hydroxide*— When acids and ammonium hydroxide are specified by name or chemical formula only it should be understood that concentrated reagents of the following specific gravities or concentrations are intended:

99.5 %
sp gr 1.19
48 %
sp gr 1.42
sp gr 1.84
sp gr 0.90

The desired specific gravities or concentrations of all other concentrated acids are stated whenever they are specified.

5.3.2 Diluted Acids and Ammonium Hydroxide— Concentrations of diluted acids and ammonium hydroxide, except when standardized, are specified as a ratio stating the number of volumes of the concentrated reagents to be diluted with a given number of volumes of water, as in the following example: HCl (1+99) means 1 volume of concentrated HCl (sp gr 1.19) diluted with 99 volumes of water.

6. Preparation of Sample

6.1 Grind dry pigments, if lumpy or not finely ground, to a fine powder for analysis. Large samples may be thoroughly mixed and a representative portion taken and powdered if lumpy or not finely ground. Mix the sample in all cases thoroughly before taking specimens for analysis.

6.2 Separate pigments from paints or pastes, grind to a fine powder, pass through a 180- μ m (No. 80) sieve (Note 1) to remove any skins, thoroughly mix, and oven dry at 105°C.

Moisten such pigments after weighing with a little alcohol before adding reagents for analysis.

Note 1—Detailed requirements for this sieve are given in Specification E 11.

6.3 Preserve all samples in stoppered bottles or containers.

ZINC OXIDE

7. Total Zinc, Using Diphenylamine as Internal Indicator

7.1 Reagents:

7.1.1 *Diphenylamine Indicator Solution* (10 g/L)—Dissolve 1 g of diphenylamine in 100 mL of H $_2$ SO₄.

7.1.2 Potassium Ferrocyanide (1 mL = 0.008 g Zn)— Dissolve 35 g of $K_4Fe(CN)_6 \cdot 3H_2O$ in water and dilute to 1 L and add 0.3 g of potassium ferricyanide ($K_3Fe(CN)_6$). Standardize the solution by titrating against zinc (320 to 340 mg), following the procedure described in 6.2. Calculate the grams of zinc equivalent to 1.00 mL of the solution.

7.2 *Procedure*—Weigh to 0.1 mg about 0.4 g of the sample into a tall form 400-mL beaker. Moisten with about 20 mL of water, and dissolve in 15 mL of HCl. Neutralize with NH₄OH, using litmus as the indicator. Add an excess of 15 mL of H₂SO 4 (1+2) and dilute to 200 mL. Heat to approximately 60°C, add 2 drops of diphenylamine indicator solution and while stirring vigorously, titrate with K₄Fe(CN)₆ solution to the color change from purple to a persistent yellowish green.

Note 2—The true end point is a sharp, persistent change from a purple to a yellowish green. At the beginning of the titration, a deep blue color is developed after addition of a few millilitres of $K_4Fe(CN)_6$ solution. About 0.5 to 1.0 mL before the true end point is reached, the solution changes from a blue to a purple color. After the purple color is developed, the titration should be continued dropwise to the persistent yellowish green end point.

7.3 *Calculation*—Calculate the percent total zinc as ZnO, *A*, as follows:

$$A = \left[\frac{V_2 Z \times 1.245}{S_1}\right] \times 100 \tag{1}$$

where:

 $V_2 = K_4 Fe(CN)_6$ solution required for titration of the specimen, mL,

Z = zinc equivalent of the K_4 Fe(CN)₆ solution, g/mL,

 S_1 = specimen weight, and

1.245 = molecular weight ZnO (81.38)/molecular weight Zn (65.38).

8. Total Zinc, Using Uranyl Acetate as External Indicator

8.1 Reagents:

8.1.1 Uranyl Acetate Indicator Solution (50 g/L)—Dissolve 5 g of $UO_2(C_2H_3O_2)_2$ ·2H₂O in 100 mL of water and make slightly acid with acetic acid.

8.1.2 Potassium Ferrocyanide, Standard Solution (1 mL = 0.008 g Zn)—Prepare and standardize as in 7.1.2. Run a blank titration with the same amounts of reagents and water. Calculate the zinc equivalent of the solution as follows:

$$Z = W(V - B) \tag{2}$$

where:

⁵ Reagent Chemicals, American Chemical Society Specifications, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see Analar Standards for Laboratory Chemicals, BDH Ltd., Poole, Dorset, U.K., and the United States Pharmacopeia and National Formulary, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.