

---

---

**Rubber latex, synthetic — Determination  
of mechanical stability —**

Part 1:  
**High-speed method**

*Latex de caoutchouc synthétique — Détermination de la stabilité  
mécanique —*

**iTeh STANDARD PREVIEW**  
*Partie 1: Méthode à vitesse élevée*  
**(standards.iteh.ai)**

ISO 2006-1:2009

<https://standards.iteh.ai/catalog/standards/sist/9ae48807-7859-4df6-877b-b16922082614/iso-2006-1-2009>



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 2006-1:2009

<https://standards.iteh.ai/catalog/standards/sist/9ae48807-7859-4df6-877b-b16922082614/iso-2006-1-2009>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2009

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

**Contents**

Page

<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>2</b>
<b>5 Reagents</b> .....	<b>2</b>
<b>6 Apparatus</b> .....	<b>2</b>
<b>7 Sampling</b> .....	<b>2</b>
<b>8 Procedure</b> .....	<b>2</b>
<b>9 Expression of results</b> .....	<b>3</b>
<b>10 Test report</b> .....	<b>4</b>
<b>Annex A (informative) Precision</b> .....	<b>5</b>
<b>Bibliography</b> .....	<b>7</b>

iTech STANDARD PREVIEW  
(standards.iteh.ai)

ISO 2006-1:2009  
<https://standards.iteh.ai/catalog/standards/sist/9ae48807-7859-4df6-877b-b16922082614/iso-2006-1-2009>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2006-1 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

It cancels and replaces ISO 2006:1985, which has been technically revised.

ISO 2006 consists of the following parts, under the general title *Rubber latex, synthetic — Determination of mechanical stability*:

- *Part 1: High-speed method*
- *Part 2: Moderate-speed method under load*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 2006-1:2009

<https://standards.iteh.ai/catalog/standards/sist/9ae48807-7859-4df6-877b-b16922082614/iso-2006-1-2009>

## Introduction

The mechanical stability of synthetic latices is important in a variety of manufacturing processes, and a number of empirical methods are used for testing. This part of ISO 2006 provides a method of determining the mechanical stability by stirring a test portion of latex at a high speed without applying pressure.

This part of ISO 2006 is a revision of ISO 2006:1985 which has been rewritten to bring it into line with ISO 2006-2, which provides an alternative method of measuring mechanical stability.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 2006-1:2009

<https://standards.iteh.ai/catalog/standards/sist/9ae48807-7859-4df6-877b-b16922082614/iso-2006-1-2009>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 2006-1:2009

<https://standards.iteh.ai/catalog/standards/sist/9ae48807-7859-4df6-877b-b16922082614/iso-2006-1-2009>

# Rubber latex, synthetic — Determination of mechanical stability —

## Part 1: High-speed method

**WARNING** — Persons using this part of ISO 2006 should be familiar with normal laboratory practice. This part of ISO 2006 does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

### 1 Scope

This International Standard specifies a method for the determination of the high-speed mechanical stability of synthetic rubber latex. The method is not applicable to compounded synthetic rubber latices.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 123, *Rubber latex — Sampling*

ISO 124, *Latex, rubber — Determination of total solids content*

ISO 1652, *Rubber latex — Determination of apparent viscosity by the Brookfield test method*

ISO 3310-1, *Test sieves — Technical requirements and testing — Part 1: Test sieves of metal wire cloth*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

#### 3.1

##### **mechanical stability**

resistance to coagulation of latex when subjected to mechanical shear under specified conditions

**NOTE** The greater the percentage of coagulum formed [ $w_c(A)$  and  $w_c(B)$  as defined in 9.2 and 9.3], the poorer the mechanical stability.

## 4 Principle

A test portion of latex is stirred at a high speed for a given time, and the coagulum formed is separated and weighed. The mass of coagulum formed is inversely proportional to the mechanical stability. Latices with a viscosity of over 200 mPa·s require dilution.

## 5 Reagents

During the analysis, use only carbonate-free distilled water or water of equivalent purity.

**5.1 Surfactant solution:** 5 % (by mass) solution of potassium oleate of pH value  $10 \pm 0,5$  or, for use with a latex which is coagulated by potassium oleate solution, a 5 % (by mass) solution of a synthetic anionic or non-ionic surfactant.

## 6 Apparatus

Ordinary laboratory apparatus, plus the following:

**6.1 Mechanical stability measuring apparatus**, consisting of the items specified in 6.1.1 to 6.1.2.

**6.1.1 Latex container**, flat-bottomed, cylindrical, at least 100 mm high, with an internal diameter of  $58 \text{ mm} \pm 2 \text{ mm}$  and a wall thickness of about 2,5 mm. The inner surface shall be smooth, and a glass container is preferred.

**6.1.2 Stirring apparatus**, consisting of a vertical stainless-steel shaft of sufficient length to reach the bottom of the latex container (6.1.1) and tapering to approximately 6,3 mm diameter at its lower end. A horizontal, smooth, stainless-steel disc  $36,12 \text{ mm} \pm 0,03 \text{ mm}$  in diameter and  $1,57 \text{ mm} \pm 0,05 \text{ mm}$  thick is attached to the shaft by means of a threaded stud at the exact centre of the disc. The apparatus shall maintain a stirring speed of  $14\,000 \text{ min}^{-1} \pm 200 \text{ min}^{-1}$  throughout a test, at which frequency the shaft shall not run out of true by more than 0,25 mm.

NOTE The stirring disc which is specified has a diameter greater than that specified for natural rubber latex concentrate in ISO 35.

**6.1.3 Holder**, for the latex container (6.1.1). The holding arrangement shall ensure that the axis of the rotating shaft is concentric with the axis of the latex container and that the bottom of the stirring disc is at  $13 \text{ mm} \pm 1 \text{ mm}$  from the inner surface of the bottom of the latex container.

**6.2 Preliminary filter**, of stainless-steel wire cloth with an average aperture width of  $180 \mu\text{m} \pm 10 \mu\text{m}$ , complying with ISO 3310-1.

**6.3 Test filter**, consisting of a disc of stainless-steel wire cloth with an average aperture width of  $180 \mu\text{m} \pm 10 \mu\text{m}$ , complying with ISO 3310-1, dried to constant mass and weighed to the nearest 1 mg, firmly clamped between two stainless-steel rings of equal internal diameter between 25 mm and 50 mm.

## 7 Sampling

Carry out sampling in accordance with one of the methods specified in ISO 123.

## 8 Procedure

**8.1** If the total solids content of the latex is not known, determine it in accordance with ISO 124.



**8.2** If the viscosity of the latex, determined with the L instrument as specified in ISO 1652, exceeds 200 mPa·s (200 cP), dilute it to this or a lower value with an amount of water (see Clause 5) which reduces the concentration of the latex by no more than 10 % (by mass) total solids content.

NOTE Dilution of the latex may decrease its stability since the balance of free and absorbed soap is changed.

**8.3** Adjust the temperature of the latex to  $25\text{ °C} \pm 3\text{ °C}$  by means of a suitable heating device, then pass it through the preliminary filter (6.2) into a beaker and accurately transfer  $50\text{ g} \pm 0,5\text{ g}$  to the latex container (6.1.1), recording the mass  $m$ .

**8.4** Secure the latex container in the holder (6.1.3) of the apparatus and start the stirrer, ensuring that the stirring speed (see 6.1.2) is  $14\ 000\text{ min}^{-1} \pm 200\text{ min}^{-1}$ . Stir the latex for a time between 1 min and 30 min, as agreed between the interested parties, but of duration such that the latex does not increase in temperature to more than  $60\text{ °C}$  and does not rise to a height exceeding 100 mm in the container. In the case of a latex which contains ammonia, the duration of stirring shall be limited since loss of ammonia by evaporation during the test may cause additional destabilization. If it is necessary to control foaming, a paste of a silicone defoamer shall be smeared around the upper part of the inner surface of the container.

**8.5** Immediately after the termination of stirring, remove the latex container and wash the stirrer shaft and disc free from latex deposits with surfactant solution (5.1) or water (see Clause 5). Collect the washings in a beaker.

**8.6** Wet the test filter (6.3) with surfactant solution or water and pour the latex and washings onto the test filter. Use surfactant solution or water to ensure quantitative transfer of all latex and deposits of coagulum, including skin.

**8.7** Wash the residue on the test filter with surfactant solution or water until it is free from latex and no longer cloudy, then with water until the washings are clear.

**8.8** Carefully remove the test filter containing the wet solid matter and blot the underside with filter paper. Place the filter on a watch glass.

**8.9** Dry the watch glass with the test filter containing the coagulum at  $100\text{ °C} \pm 5\text{ °C}$ . After 15 min of drying, transfer to a desiccator and allow to cool to ambient temperature. Then carefully remove the filter from the watch glass and weigh. Repeat the drying procedure for periods of 15 min until the loss in mass between two successive weighings is less than 1 mg.

**8.10** Carry out the procedure described in 8.3 to 8.9 in duplicate.

## 9 Expression of results

### 9.1 General

There are two methods of expressing the test result, as described in 9.2 and 9.3.

### 9.2 Method A

The mechanical stability of the latex is expressed as the percentage by mass of coagulum formed,  $w_c(A)$ , relative to the mass of the test portion of latex, calculated using the following equation:

$$w_c(A) = \frac{m_c \times 100}{m}$$

where

$m_c$  is the mass of coagulum formed, in grams;

$m$  is the mass of the test portion, in grams.

NOTE The greater the percentage of coagulum formed, the poorer the mechanical stability.