
**Resilient floor coverings —
Heterogeneous poly(vinyl chloride) floor
coverings — Specification**

*Revêtements de sol résilients — Revêtements de sol hétérogènes en
poly(chlorure de vinyle) — Spécifications*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 10582:2010](https://standards.iteh.ai/catalog/standards/sist/1164af12-33e8-4ed8-b818-96323ace5974/iso-10582-2010)

[https://standards.iteh.ai/catalog/standards/sist/1164af12-33e8-4ed8-b818-
96323ace5974/iso-10582-2010](https://standards.iteh.ai/catalog/standards/sist/1164af12-33e8-4ed8-b818-96323ace5974/iso-10582-2010)



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 10582:2010

<https://standards.iteh.ai/catalog/standards/sist/1164af12-33e8-4ed8-b818-96323ace5974/iso-10582-2010>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Requirements	2
5 Classification	3
6 Marking, labelling and packaging	5
Annex A (informative) Optional properties	6
Bibliography	7

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 10582:2010](https://standards.iteh.ai/catalog/standards/sist/1164af12-33e8-4ed8-b818-96323ace5974/iso-10582-2010)

<https://standards.iteh.ai/catalog/standards/sist/1164af12-33e8-4ed8-b818-96323ace5974/iso-10582-2010>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 10582 was prepared by Technical Committee ISO/TC 219, *Floor coverings*.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 10582:2010](https://standards.iteh.ai/catalog/standards/sist/1164af12-33e8-4ed8-b818-96323ace5974/iso-10582-2010)

<https://standards.iteh.ai/catalog/standards/sist/1164af12-33e8-4ed8-b818-96323ace5974/iso-10582-2010>

Resilient floor coverings — Heterogeneous poly(vinyl chloride) floor coverings — Specification

1 Scope

This International Standard specifies the characteristics of non-cushioned, heterogeneous floor coverings, based on poly(vinyl chloride) (PVC), supplied in either tile or roll form. Products may contain a transparent, non-PVC factory finish.

To encourage the consumer to make an informed choice, this International Standard includes a classification system (see ISO 10874) based on the intensity of use, which shows where these floor coverings give satisfactory service. It also specifies requirements for marking.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-B02:1994, *Textiles — Tests for colour fastness — Part B02: Colour fastness to artificial light: Xenon arc fading lamp test* <https://standards.iteh.ai/catalog/standards/sist/1164af12-33e8-4ed8-b818-96323ae5974/iso-10582-2010>

ISO 105-B02:1994, *Textiles — Tests for colour fastness — Part B02: Colour fastness to artificial light: Xenon arc fading lamp test*. Amendment 1:1998

ISO/TR 4918, *Textile floor coverings — Determination of wear — Castor chair test*

ISO 10874, *Resilient, textile and laminate floor coverings — Classification*

ISO 23996, *Resilient floor coverings — Determination of density*

ISO 23997, *Resilient floor coverings — Determination of mass per unit area*

ISO 23999, *Resilient floor coverings — Determination of dimensional stability and curling after exposure to heat*

ISO 24340, *Resilient floor coverings — Determination of thickness of layers*

ISO 24341, *Resilient and textile floor coverings — Determination of length, width and straightness of sheet*

ISO 24342, *Resilient and textile floor-coverings — Determination of side length, edge straightness and squareness of tiles*

ISO 24343-1, *Resilient and laminate floor coverings — Determination of indentation and residual indentation — Part 1: Residual indentation*

ISO 24344:2008, *Resilient floor coverings — Determination of flexibility and deflection*

ISO 24346, *Resilient floor coverings — Determination of overall thickness*

ASTM F1515, *Standard test method for measuring light stability of resilient flooring by color change*

EN 684, *Resilient floor coverings — Determination of seam strength*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 heterogeneous floor covering
floor covering consisting of a wear layer and other layer(s) which differ in composition and/or design and can contain a reinforcement

3.2 poly(vinyl chloride) floor covering
floor covering with surface layer(s) which are produced using poly(vinyl chloride) as the binder

3.3 wear layer
layer of the floor covering directly exposed to wear

3.4 factory finish
transparent coating applied during the manufacture, usually not thicker than 0,03 mm

3.5 binder content
that portion of the flooring composition, consisting of poly(vinyl chloride) (PVC) resin, plasticizers and stabilizers

ITeH STANDARD PREVIEW
(standards.iteh.ai)
ISO 10582:2010
<https://standards.iteh.ai/catalog/standards/sist/1164af12-33e8-4ed8-b818-7039acc97486/iso-10582-2010>

NOTE Binder content is expressed as a percentage mass fraction of the total composition.

4 Requirements

4.1 Identification requirements

Products described in this International Standard shall be identified by wear-layer binder content by mass as shown in Table 1.

Table 1 — Identification requirements

Type	Wear-layer binder content
I	Minimum 80 %
II	Minimum 30 %

4.2 General requirements

Floor coverings described in this International Standard shall conform to the appropriate general requirements specified in Table 2, when tested in accordance with the methods given therein.

Table 2 — General requirements












Characteristic	Requirement	Test method
Roll form: length: m width: mm	Not less than the nominal values	ISO 24341
Tiles: side length mm Does not apply to planks squareness and straightness for side length: mm ≤ 400 mm > 400 mm > 400 mm (intended for heat welding)	Deviation ≤ 0,15 % of nominal length up to 0,5 mm maximum Deviation allowed at any point ≤ 0,25 ≤ 0,35 ≤ 0,50	ISO 24342
Overall thickness: mm Average Individual results	Nominal value $\begin{matrix} +0,13 \\ -0,10 \end{matrix}$ Average value ±0,15	ISO 24346
Total mass per unit area (average) g/m ²	Nominal value $\begin{matrix} +13 \\ -10 \end{matrix}$ %	ISO 23997
Dimensional stability after exposure to heat: % Sheets and tiles (intended for welding) Tiles (intended for dry-joint laying)	≤ 0,4 ≤ 0,25	ISO 23999
Curling after exposure to heat: mm Sheets and tiles (intended for heat welding) Tiles (intended for dry-joint laying)	≤ 8 ≤ 2	ISO 23999
Flexibility	Test using a 20 mm mandrel. For products which show signs of cracking, perform a further test using a 50 mm mandrel. If results show no further cracking, record the use of a 50 mm mandrel	ISO 24344:2008, Method A
Residual indentation (average) mm	≤ 0,1	ISO 24343-1
Effect of castor chair	After 25 000 cycles, no delamination shall occur. No disturbance to the surface other than a slight change in appearance	ISO 4918
Colour fastness to artificial light	6 minimum or $\Delta E \leq 8$ after 300 h, where E is the irradiance, expressed in watts per square metre	ISO 105-B02:1994, Method 3 ^a ASTM F1515
^a Expose a full size test specimen. Store a further test specimen in the dark, which will constitute the reference standard for assessment of colour change.		

5 Classification

The classification scheme for resilient floor coverings is described in ISO 10874. The requirements for the use of heterogeneous poly(vinyl chloride) floor covering in accordance with this scheme are specified in Table 3.

Table 3 — Classification requirement for level of use (minimal)

Dimensions in millimetres

Class	Symbol	Level of use	Thickness of wear layer, nominal value		Nominal overall thickness	Seam strength N/50 mm
			Type I	Type II		
		Domestic	Type I	Type II	All types	
21		Moderate/light	0,15	0,40	1,0	No requirement
22		General/medium	0,20	0,50	1,5	
22+		General	0,20	0,50	1,5	
23		Heavy	0,30	0,65	1,5	
		Commercial				
31		Moderate	0,30	0,65	2,0	When welded in accordance with the manufacturer's instructions: Average value ≥ 240 Individual values ≥ 180
32		General	0,40	0,80	2,0	
33		Heavy	0,55	1,00	2,0	
34		Very heavy	0,70	1,50	2,0	
		Light industrial				
41		Moderate	0,40	0,80	2,0	
42		General	0,55	1,00	2,0	
43		Heavy	0,70	1,50	2,0	
Test method			ISO 24340		ISO 24346	EN 684

6 Marking, labelling and packaging

Floor coverings covered by this International Standard and/or their packaging shall bear the following marking:

- a) number and date of this International Standard, i.e. ISO 10582:2010;
- b) manufacturer's or supplier's identification;
- c) product name;
- d) colour/pattern, batch number and, if applicable, roll number;
- e) classes/symbols appropriate for the product;
- f) for rolls: the length, width and thickness;
- g) for tiles: the dimensions of a tile and the area, in square metres, contained in the package.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 10582:2010](https://standards.iteh.ai/catalog/standards/sist/1164af12-33e8-4ed8-b818-96323ace5974/iso-10582-2010)

<https://standards.iteh.ai/catalog/standards/sist/1164af12-33e8-4ed8-b818-96323ace5974/iso-10582-2010>