
**Paper and board — Determination of
grease resistance —**

Part 3:

**Turpentine test for voids in glassine and
greaseproof papers**

iTeh STANDARD PREVIEW
(standards.iteh.ai)
*Papier et carton — Détermination de l'imperméabilité aux graisses —
Partie 3: Essai à la térébenthine pour papiers glassine et papiers
ingraissables*

ISO 16532-3:2010

<https://standards.iteh.ai/catalog/standards/sist/11a835ab-e683-4ed2-972a-c48d1f377de0/iso-16532-3-2010>



Reference number
ISO 16532-3:2010(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 16532-3:2010

<https://standards.iteh.ai/catalog/standards/sist/11a835ab-e683-4ed2-972a-c48d1f377de0/iso-16532-3-2010>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle.....	1
5 Reagents.....	2
6 Apparatus	2
7 Sampling.....	2
8 Conditioning	3
9 Preparation of test pieces.....	3
10 Procedure	3
11 Observation intervals	3
12 Expression of results	4
13 Test report	4
Annex A (informative) Precision.....	5
Bibliography.....	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 16532-3 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 2, *Test methods and quality specifications for paper and board*.

ISO 16532 consists of the following parts, under the general title *Paper and board — Determination of grease resistance*:

— *Part 1: Permeability test*

— *Part 2: Surface repellency test*

— *Part 3: Turpentine test for voids in glassine and greaseproof papers*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 16532-3:2010](https://standards.iteh.ai/catalog/standards/sist/11a835ab-e683-4ed2-972a-c48d1f377de0/iso-16532-3-2010)

<https://standards.iteh.ai/catalog/standards/sist/11a835ab-e683-4ed2-972a-c48d1f377de0/iso-16532-3-2010>

Introduction

The resistance of paper and board to penetration by fats, greases and oils in paper and board is of particular importance for certain purposes, for example the packaging of food. The packaging should not only provide an effective grease barrier, but should also prevent the formation of aesthetically unacceptable grease spots on the packaging surfaces.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 16532-3:2010

<https://standards.iteh.ai/catalog/standards/sist/11a835ab-e683-4ed2-972a-c48d1f377de0/iso-16532-3-2010>

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

ISO 16532-3:2010

<https://standards.iteh.ai/catalog/standards/sist/11a835ab-e683-4ed2-972a-c48d1f377de0/iso-16532-3-2010>

Paper and board — Determination of grease resistance —

Part 3:

Turpentine test for voids in glassine and greaseproof papers

1 Scope

This part of ISO 16532 specifies a method for the determination of the grease resistance of paper and board. It provides an accelerated comparison of the relative rates at which oils or greases, such as those commonly found in foodstuffs, can be expected to penetrate voids in papers such as greaseproof or glassine, where the grease or oil resistance is provided by mechanical means only. It is not applicable to grades of paper or board that are given grease or oil resistance by means of a coating or internal treatment for which ISO 16532-1 or ISO 16532-2 apply.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 16532-3:2010
<https://standards.iso.org/standards/catalog/standards/sist/11a835ab-c683-4ed2-972a-c48d1f377de0/iso-16532-3-2010>
ISO 186, *Paper and board — Sampling to determine average quality*

ISO 187, *Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning the samples*

ISO 536, *Paper and board — Determination of grammage*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

grease resistance

ability of the paper or board to resist the formation of surface spots or stains, or the permeation of grease through the sheet

3.2

voids

places in the paper where the arrangement of the fibres is such that oil or grease can penetrate the sheet

4 Principle

The test piece is placed on a sheet of coated paper on a flat surface and a small mound of sand is placed on the test piece. The sand is then saturated with coloured turpentine. The time taken for a stain to appear on the coated paper beneath the sand is noted.

5 Reagents

5.1 Pure gum spirits of turpentine, with a density of 860 kg/m³ to 875 kg/m³ at 20 °C.

5.2 Anhydrous calcium chloride.

5.3 Oil-soluble dye (for example Sudan red).

5.4 Sand, Ottawa cement-testing sand, screened to pass an 800 µm screen but retained on a 630 µm screen.

NOTE Ottawa cement-testing sand is available commercially from some laboratory suppliers.

5.5 Test solution: to 100 ml of turpentine (5.1), add 5 g of anhydrous calcium chloride (5.2) and 1,0 g of oil-soluble dye (5.3) and store in a stoppered bottle (6.7). Shake well, and let the solution stand for at least 10 h, shaking occasionally. Then filter through a dry filter paper at a temperature of 23 °C ± 1 °C, and store in the stoppered bottle (6.7). Ensure that the bottle is airtight.

6 Apparatus

6.1 Tube of any rigid material, 25 mm internal diameter and at least 25 mm in height, the ends of which have been smoothed.

6.2 Automatic pipette, of appropriate maximum volume, calibrated to deliver 1,1 ml of test solution.

6.3 Printing paper, flat, white, coated and calendered sheet or sheets of a convenient size to support at least 10 test pieces.

A grammage of 100 g/m² to 120 g/m² is recommended (see ISO 536).

6.4 Stopwatch or timer, accuracy ± 0,5 s.

6.5 Watch glass, diameter 76 mm.

6.6 Scoop, of capacity 5 g. Verify the capacity of the scoop by weighing 2 charges of sand (5.4) on an analytical balance (6.8): each charge should weigh (5,0 ± 0,1) g. The design of the scoop should preferably facilitate the pouring of the sand (5.4) into the tube (6.1).

6.7 Stoppered glass bottle, of capacity 100 ml.

6.8 Analytical balance, of minimum capacity 10 g and with a scale interval of 0,01 g; accuracy class ordinary (III)¹⁾.

7 Sampling

If the test is being made on a lot of paper or board, the sample shall be selected in accordance to ISO 186. If the test is being made on another type of sample, report the source of the sample and, if possible, the sampling procedure used. Make sure that the test pieces taken are representative of the paper or board sample.

1) Accuracy classes for non-automatic weighing instruments are described in OIML R 76-1^[5].

8 Conditioning

Condition the sample in accordance with ISO 187. The alternative conditions specified in ISO 187 shall not be used, as it has been determined that the temperature has a strong influence on the test results. Thus only $23\text{ }^{\circ}\text{C} \pm 1\text{ }^{\circ}\text{C}$ shall be used. Place the bottle of test solution (5.5) in the conditioned atmosphere and allow its temperature to come into equilibrium.

9 Preparation of test pieces

Prepare from the conditioned sample, in the same conditioned atmosphere (see Clause 8), ten test pieces of $100\text{ mm} \times 100\text{ mm}$, identifying, if possible, five pieces as the top side and five pieces as the wire side. Mark the first side of each test piece as side 1.

10 Procedure

10.1 Place a coated paper sheet or sheets (6.3), on a smooth, flat horizontal surface. Then, alternatively place the first marked side (top side if known or side 1 if unknown) of a test piece, followed by the other side, such that no test piece extends beyond the edge of the coated paper.

10.2 Rest one end of the tube (6.1) squarely on a test piece and with the scoop (6.6) put $5,0\text{ g} \pm 0,1\text{ g}$ of the sand (5.4) in the tube. Remove the tube immediately after addition of the sand by carefully lifting it vertically.

NOTE The purpose of the tube is solely to ensure that a uniform sand pile is applied to the test piece.

10.3 Add $1,1\text{ ml} \pm 0,05\text{ ml}$ of the test solution (5.5) to the sand pile, using an automatic pipette (6.2). Start the timing device (6.4) as the last drop of test solution leaves the pipette.

10.4 At specific intervals (see Clause 11), gently slide the test piece to a new unexposed position of the coated paper and examine the previously exposed position for signs of staining. The first sign of staining, which indicates that the test solution (5.5) has penetrated the test piece, is the end-point of the test.

10.5 Record the time elapsed from the addition of the test solution (5.5) to the sand until the first sign of staining of the coated paper. If staining has not occurred after 30 min (1 800 s), terminate the test.

If it takes longer than 120 s for the test solution (5.5) to penetrate the test piece, cover the sand pile with the watch glass (6.5).

10.6 Repeat 10.2 to 10.4 for the remaining test pieces.

NOTE If the first pair of tests show that the end-point times exceed 900 s, the test may be expedited by placing the remaining 8 test pieces on the coated paper, adding sand (5.4) and then test solution (5.5), followed by starting the timer (6.4) as in 10.3 at 10 s intervals.

11 Observation intervals

Make observations at least at the following intervals:

- every 15 s between 0 and 1 min;
- every 1 min between 1 min and 5 min;
- every 5 min between 5 min and 30 min.

If the end-point times for the first two test pieces exceed 15 min, make observations every 5 min, starting at 15 min.