



Designation: A 1014/A 1014M – 06

# Standard Specification for Precipitation-Hardening Bolting Material (UNS N07718) for High Temperature Service<sup>1</sup>

This standard is issued under the fixed designation A 1014/A 1014M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ε) indicates an editorial change since the last revision or reappraisal.

## 1. Scope\*

1.1 This specification covers a precipitation hardening bolting material (UNS N07718) for high temperature service.

1.2 This specification is expressed in both inch-pound and in SI units. However, unless the order specifies the applicable “M” designation (SI units), the material shall be furnished to inch-pound units.

1.3 The values stated in either inch-pounds or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**A 370** Test Methods and Definitions for Mechanical Testing of Steel Products

**A 962/A 962M** Specification for Common Requirements for Steel Fasteners or Fastener Materials, or Both, Intended for Use at Any Temperature from Cryogenic to the Creep Range

**B 637** Specification for Precipitation-Hardening Nickel Alloy Bars, Forgings, and Forging Stock for High-Temperature Service

**B 880** Specification for General Requirements for Chemical Check Analysis Limits for Nickel, Nickel Alloys and Cobalt Alloys

**E 112** Test Methods for Determining Average Grain Size

**E 292** Test Methods for Conducting Time-for-Rupture Notch Tension Tests of Materials

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.22 on Steel Forgings and Wrought Fittings for Piping Applications and Bolting Materials for Piping and Special Purpose Applications.

Current edition approved March 1, 2006. Published April 2006. Originally approved in 2000. Last previous edition approved in 2003 as A 1014 – 03.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

2.2 *ANSI Standards:*

**B1.1** Screw Threads<sup>3</sup>

2.3 *SAE Standards:*

**AS 7467** Bolts And Screws, Nickel Alloy, UNS N07718 Tensile Strength 185 KSI [1275 MPa] Stress Rupture Rated Procurement Specification<sup>4</sup>

## 3. Ordering Information

3.1 *Ordering*—It shall be the responsibility of the purchaser to specify all requirements that are necessary for product under this specification including any supplementary ones and those included in the ordering information required by Specification **A 962/A 962M**.

## 4. Common Requirements

4.1 *Common Requirements*—Product furnished to this specification shall conform to Specification **A 962/A 962M**, including any supplementary requirements indicated on the purchase order. Failure to comply with Specification **A 962/A 962M** constitutes non-conformance with this specification. If the requirements of this specification conflict with those of Specification **A 962/A 962M**, then the requirements of this specification shall prevail.

## 5. Manufacture

5.1 *Melting Process*—Alloy shall be multiple melted using consumable electrode practice in the remelt cycle or shall be induction melted under vacuum. If consumable electrode remelting is not performed in vacuum, electrodes produced by vacuum induction melting shall be used.

5.2 *Heat Treatment:*

5.2.1 *Solution Treatment*—Material shall be solution heat treated at a temperature within the range of 1725 to 1850 °F [940 to 1010 °C], held at the selected temperature for a time commensurate with cross-sectional thickness, and cooled at a rate equivalent to an air cool or faster.

<sup>3</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

<sup>4</sup> Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001.

\*A Summary of Changes section appears at the end of this standard.