



## Standard Specification for Nonrigid Vinyl Chloride Polymer Tubing<sup>1</sup>

This standard is issued under the fixed designation D 922; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This specification covers nonrigid tubing of vinyl chloride polymer or its copolymers with other materials for use in electrical insulation in three grades, as follows:

- 1.1.1 *Grade A*—General-purpose.
- 1.1.2 *Grade B*—Low-temperature.
- 1.1.3 *Grade C*—High-temperature.

NOTE 1—This standard is similar but not identical to IEC-60684-3-100 to -105.

### 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

- D 876 [Test Methods for Nonrigid Vinyl Chloride Polymer Tubing Used for Electrical Insulation](#)
- D 1711 [Terminology Relating to Electrical Insulation](#)
- D 3636 [Practice for Sampling and Judging Quality of Solid Electrical Insulating Materials](#)
- E 176 [Terminology of Fire Standards](#)

2.2 *IEC Standards*:

- IEC-60684-3-100 to -105 Flexible insulating sleeving, Part 3, Sheets 100 to 105: Extruded PVC sleeving<sup>3</sup>

### 3. Terminology

3.1 *Definitions*:

- 3.1.1 For definitions pertaining to electrical insulation, refer to Terminology D 1711.
- 3.1.2 For definitions pertaining to fire standards, refer to Terminology E 176.

### 4. Ordering Information

4.1 Orders for material covered by this specification shall include the following:

- 4.1.1 Grade of tubing,
- 4.1.2 Size and color,
- 4.1.3 Total length in feet (or metres); [or metres],
- 4.1.4 Length of cut pieces in inches (or centimetres); [or centimetres], if any, and
- 4.1.5 Amount of tubing on each spool or in each coil, if not standard packaging with the supplier.

### 5. Color

5.1 Clear transparent, black, white, yellow, green, blue, and red shall be considered standard colors. Other colors shall be considered special. The color desired shall be specified in the purchase order.

### 6. Dimensional Requirements

6.1 *Inside Diameter*—The inside diameter of the tubing shall conform to the requirements prescribed in Table 1 or Table 2.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.07 on Flexible and Rigid Insulating Materials.

Current edition approved Sept. 10, 2000. Published November 2000. Originally published as D922-47F. Last previous edition D922-00.

Current edition approved April 1, 2006. Published April 2006. Originally approved in 1947. Last previous edition approved in 2000 as D 922 – 00a.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* Vol 10.01, volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 10.02.

<sup>3</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

**TABLE 1 Dimensional Tolerances of Tubing<sup>A,B</sup>**

Specified Size	Inside Diameter, in.		Wall Thickness	
	max	min	Wall Thick- ness, in.	Tolerances, plus or minus, in.
No. 24 (0.022 in.)	0.027	0.020	0.012	0.002
No. 24 [0.022 in.]	0.027	0.020	0.012	0.002
No. 22 (0.027 in.)	0.032	0.025	0.012	0.002
No. 22 [0.027 in.]	0.032	0.025	0.012	0.002
No. 20 (0.034 in.)	0.039	0.032	0.016	0.003
No. 20 [0.034 in.]	0.039	0.032	0.016	0.003
No. 18 (0.042 in.)	0.049	0.040	0.016	0.003
No. 18 [0.042 in.]	0.049	0.040	0.016	0.003
No. 16 (0.053 in.)	0.061	0.051	0.016	0.003
No. 16 [0.053 in.]	0.061	0.051	0.016	0.003
No. 14 (0.066 in.)	0.074	0.064	0.016	0.003
No. 14 [0.066 in.]	0.074	0.064	0.016	0.003
No. 12 (0.085 in.)	0.091	0.081	0.016	0.003
No. 12 [0.085 in.]	0.091	0.081	0.016	0.003
No. 11 (0.095 in.)	0.101	0.091	0.016	0.003
No. 11 [0.095 in.]	0.101	0.091	0.016	0.003
No. 10 (0.106 in.)	0.112	0.102	0.016	0.003
No. 10 [0.106 in.]	0.112	0.102	0.016	0.003
No. 9 (0.118 in.)	0.124	0.114	0.020	0.003
No. 9 [0.118 in.]	0.124	0.114	0.020	0.003
No. 8 (0.133 in.)	0.141	0.129	0.020	0.003
No. 8 [0.133 in.]	0.141	0.129	0.020	0.003
No. 7 (0.148 in.)	0.158	0.144	0.020	0.003
No. 7 [0.148 in.]	0.158	0.144	0.020	0.003
No. 6 (0.166 in.)	0.178	0.162	0.020	0.003
No. 6 [0.166 in.]	0.178	0.162	0.020	0.003
No. 5 (0.186 in.)	0.198	0.182	0.020	0.003
No. 5 [0.186 in.]	0.198	0.182	0.020	0.003
No. 4 (0.208 in.)	0.224	0.204	0.020	0.003
No. 4 [0.208 in.]	0.224	0.204	0.020	0.003
No. 3 (0.234 in.)	0.249	0.229	0.020	0.003
No. 3 [0.234 in.]	0.249	0.229	0.020	0.003
No. 2 (0.263 in.)	0.278	0.258	0.020	0.003
No. 2 [0.263 in.]	0.278	0.258	0.020	0.003
No. 1 (0.294 in.)	0.311	0.289	0.020	0.003
No. 1 [0.294 in.]	0.311	0.289	0.020	0.003
No. 0 (0.330 in.)	0.347	0.325	0.020	0.003
No. 0 [0.330 in.]	0.347	0.325	0.020	0.003
5/16 in.	0.334	0.312	0.025	0.003
3/8 in.	0.399	0.375	0.025	0.003
7/16 in.	0.462	0.438	0.025	0.003
1/2 in.	0.524	0.500	0.025	0.003
5/8 in.	0.655	0.625	0.030	0.003
3/4 in.	0.786	0.750	0.035	0.005
7/8 in.	0.911	0.875	0.035	0.005
1 in.	1.036	1.000	0.035	0.005
1 1/4 in.	1.290	1.250	0.040	0.005
1 1/2 in.	1.550	1.500	0.045	0.006
1 3/4 in.	1.812	1.750	0.055	0.008
2 in.	2.070	2.000	0.060	0.010

<sup>A</sup> Multiply inches by 25.4 to get millimetres.

<sup>B</sup> For tubing sizes not listed in this table, the wall thickness of the nearest larger diameter shall apply.

6.2 *Wall Thickness*—The wall thickness of the tubing shall conform to the requirements prescribed in Table 1 or Table 2.

6.3 *Commercial Lengths*—The tubing shall be supplied in continuous lengths.

## 7. Workmanship, Finish, and Appearance

7.1 The surface shall be smooth, free of blisters, cracks, or any other defects that may detrimentally affect its suitability for the service intended. It shall not be subject to peeling, scaling, or flaking.

## 8. Physical and Electrical Requirements

8.1 Tubing shall conform to the following requirements for physical and electrical properties: