



SLOVENSKI STANDARD

SIST ISO 2834-3:2010

01-maj-2010

Nadomešča:
SIST ISO 2834:2002

**Grafična tehnologija - Laboratorijska izdelava preskusnih odtisov - 3. del:
Tiskarske barve za sitotisk**

Graphic technology - Laboratory preparation of test prints - Part 3: Screen printing inks

iTeh STANDARD PREVIEW

(standards.itech.ai)
Technologie graphique - Préparation en laboratoire des impressions d'essai - Partie 3:
Encres de sérigraphie

[SIST ISO 2834-3:2010](https://standards.itech.ai/catalog/standards/sist/c794bdc4-cc23-4725-bea2-6c99b9/sist-iso-2834-3:2010)

<https://standards.itech.ai/catalog/standards/sist/c794bdc4-cc23-4725-bea2-6c99b9/sist-iso-2834-3:2010>

Ta slovenski standard je istoveten z: ISO 2834-3:2008

ICS:

87.080 Barvila. Tiskarske barve Inks. Printing inks

SIST ISO 2834-3:2010

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 2834-3:2010

<https://standards.iteh.ai/catalog/standards/sist/c794bdc4-cc23-4725-bea2-b871a63e99b9/sist-iso-2834-3-2010>

INTERNATIONAL
STANDARD

ISO
2834-3

First edition
2008-12-15

Graphic technology — Laboratory
preparation of test prints —

Part 3:
Screen printing inks

*Technologie graphique — Préparation en laboratoire des impressions
d'essai —*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Partie 3: Encres de sérigraphie

SIST ISO 2834-3:2010

<https://standards.iteh.ai/catalog/standards/sist/c794bdc4-cc23-4725-bea2-b871a63e99b9/sist-iso-2834-3-2010>



Reference number
ISO 2834-3:2008(E)

© ISO 2008

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST ISO 2834-3:2010

<https://standards.iteh.ai/catalog/standards/sist/c794bdc4-cc23-4725-bea2-b871a63e99b9/sist-iso-2834-3-2010>

**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2834-3 was prepared by Technical Committee ISO/TC 130, *Graphic technology*.

ISO 2834 consists of the following parts, under the general title *Graphic technology — Laboratory preparation of test prints*:

— Part 1: *Paste inks*

— Part 2: *Liquid printing inks*

— Part 3: *Screen printing inks*

ITC STANDARD PREVIEW
(standards.iteh.ai)
SIST ISO 2834-3:2010
<https://standards.iteh.ai/catalog/standards/sist/c794bdc4-cc23-4725-bea2-b871a63e99b9/sist-iso-2834-3-2010>

Introduction

This part of ISO 2834 describes the procedure for the preparation of test prints using screen inks. Test prints need to have a uniform distribution of ink on the substrate to be used for testing. Where such test prints are to be used for optical tests, the level of ink coverage needs to be controlled and reproducible to allow the relationship between reflectance data and ink coverage to be determined. If test prints are intended to only be used for evaluation of mechanical and/or chemical resistance, less accurate preparation methods can be used.

Test prints, as well as production prints, can have an ink film thicknesses that range between 10 µm and more than 100 µm. The viscosity range is from about 300 Pa·s to 2 000 Pa·s. The inks' varnish systems used can be oil-based, solvent-based, water-based, plastisol or energy curing. Print substrates include paper, board, glass, textiles, plastics and metals.

The test print preparation methods described in this document support, and are referenced by, ISO 2846-4 and ISO 2836. The preparation of test prints using paste inks (lithography) is defined in ISO 2834-1 and the preparation of test prints using liquid inks is defined in ISO 2834-2.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 2834-3:2010](https://standards.iteh.ai/catalog/standards/sist/c794bdc4-cc23-4725-bea2-b871a63e99b9/sist-iso-2834-3-2010)

<https://standards.iteh.ai/catalog/standards/sist/c794bdc4-cc23-4725-bea2-b871a63e99b9/sist-iso-2834-3-2010>

Graphic technology — Laboratory preparation of test prints —

Part 3: Screen printing inks

1 Scope

This part of ISO 2834 specifies a test method for preparation of test prints produced with screen printing inks. These test prints are intended primarily for optical tests, such as colorimetry, transparency and reflection density as described in ISO 2846-4. They can also be used for testing gloss, light fastness and the chemical, physical and mechanical resistance to mechanical and chemical attack regarding either printing ink or substrate, or both.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 187, *Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples*

ISO 2846-4, *Graphic technology — Colour and transparency of printing ink sets for four-colour-printing — Part 4: Screen printing*

ISO 14981, *Graphic technology — Process control — Optical, geometrical and metrological requirements for reflection densitometers for graphic arts use*

3 Terms and definitions

For the purpose of this document, the following terms and definitions apply.

3.1

extender

transparent material (varnish or polymer solution) to reduce the colorant concentration and to adapt ink concentration to print substrates

3.2

flooding

procedure of filling the openings of the screen printing forme with printing ink before the printing process

3.3

flooding device

device not in contact with the mesh used to fill the openings of the screen printing forme with printing ink before the printing process

ISO 2834-3:2008(E)

- 3.4**
ink rest
area on the surface of the screen-printing forme outside the ink trail
- 3.5**
mesh
uniformly spaced arrangement of interlaced or interlocked stands of thread; screen material
- 3.6**
mesh count
number of threads per unit length in a screen mesh
- 3.7**
mesh volume
open space between the threads of a woven screen printing fabric or effective openings of otherwise manufactured screen
- 3.8**
off contact distance
adjustable distance between printing forme and substrate
- 3.9**
printing forme
device consisting of a frame, a mesh and a stencil carrying the image to print
- 3.10**
printability tester
device for uniformly inking a printing forme and transferring a reproducible amount of ink onto a substrate under specified conditions
- 3.11**
retarder
additive to reduce the evaporation speed of the solvent in an ink to prevent drying during the application of ink to the substrate
- 3.12**
squeegee
device for simultaneously pressing the mesh against the substrate, forcing the printing ink through the openings of the forme on the substrate, and scraping the excess ink from the forme, consisting, for example of a holder and a blade or a roll coater (revolving squeegee)
- 3.13**
squeegee angle
angle between the blade and the forme before pressure has been applied
- 3.14**
stencil
blocking layer on or in the mesh, making the mesh impermeable to printing ink at the places which are not to print
- 3.15**
test-ready ink
printing ink of the appropriate composition and viscosity for the purpose of the test

iTeh STANDARD PREVIEW

(standards.iteh.ai)

SIST ISO 2834-3:2010

<https://standards.iteh.ai/catalog/standards/sist/c794bdc4-cc23-4725-bea2->

[b871a63e99b9/sist-iso-2834-3-2010](https://standards.iteh.ai/catalog/standards/sist/c794bdc4-cc23-4725-bea2-b871a63e99b9/sist-iso-2834-3-2010)

4 Test method

4.1 Principle

Using a printability tester, an amount of screen printing ink is applied uniformly on the chosen substrate. The procedures described in this part of ISO 2834 are used to prepare test prints for optical tests and can be used to prepare test prints for any other testing of printed ink.

4.2 Apparatus

Any printability tester, printing ink, substrate and drying apparatus may be used as long as the requirements of 4.2.1 to 4.2.4, 4.3 and 4.4 are met. Test conditions and variables associated with such equipment and materials shall be agreed upon between parties since variations have a strong influence on the results and comparability of the properties of the test sample.

4.2.1 Printability tester

The printability tester may use flatbed or rotational principals. To ensure repeatable operation, the printability tester shall provide motorized control of the ink transfer function. The printing speed, the squeegee angle, the pressure of the squeegee and the off contact distance shall be adjustable. These shall be constant and uniform during the printing process. The used settings shall be recorded. The squeegee should be easily replaceable. A flooding device shall be provided.

4.2.2 Printing forme

The printing forme shall be designed for solid tones of an area not smaller than 50 mm × 75 mm. The stencil shall be produced using a capillary film of an agreed-upon thickness to ensure a sufficient surface smoothness. The mesh shall be produced from polyester. The mesh count and the diameter of the wires determine the mesh volume and therefore shall be agreed upon between parties. For flatbed equipment and printed areas smaller than 150 mm × 200 mm, the ink rest area on each side of the printing area of the mesh shall be at least as large as the corresponding size of the printing area. The mesh tension shall be appropriate with respect to the type of mesh and the dimension of the frame.

During cleaning processes and printing, the printing forme is subjected to abrasion. Therefore, reference test prints using a black ink shall be performed at regular intervals, in accordance with the intensity of use of the printing forme. This black ink shall be test ready and shall be stored during the lifetime of the particular printing forme but not for longer than 6 months. Each reference print shall be made five consecutive times, where the first two prints will be discarded. Density measurements shall be performed in accordance with ISO 14981 and the average density of at least 10 measurements of each of the last three prints shall be calculated. If this density differs by more than 5 % from the reference density determined with the printing forme in first use, the forme shall be replaced.

4.2.3 Squeegee and flooding device

The squeegee may be produced from any suitable material, but there shall be prior agreement regarding the hardness of the material, and the shape, profile and smoothness of the doctoring edge.

There shall be prior agreement regarding the type of and settings for the flooding device and its use.

4.2.4 Quality requirements for printability testers

Before use, a screen ink printability tester shall be tested to insure uniformity of printing. Sample prints shall be prepared using a black ink and shall be performed in a way that an optical density of $1,5 \pm 0,3$ is achieved. Print density shall be measured in accordance to ISO 14981. Measurements shall be made in an equally spaced pattern adapted to the geometric form of the print area (minimum 25 measurements). If the standard deviation of density measurements exceeds 0,03, the performance of the screen ink printability tester shall be considered unacceptable.