



Designation: C715 – 90 (Reapproved 2006)

# Standard Test Method for Nickel on Steel for Porcelain Enameling by Photometric Analysis<sup>1</sup>

This standard is issued under the fixed designation C715; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers the determination of the amount of nickel deposited on sheet steel during its preparation for porcelain enameling. It is a photometric method commonly used on production parts and is suitable for determining the heavier nickel deposits that may be obtained during the processing of steel for one-coat enameling.

NOTE 1—An alternative X-ray emission spectrometry method is Test Method C810.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

C810 Test Method for Nickel on Steel for Porcelain Enameling by X-Ray Emission Spectrometry

E30 Test Methods for Chemical Analysis of Steel, Cast Iron, Open-Hearth Iron, and Wrought Iron<sup>3</sup>

E60 Practice for Analysis of Metals, Ores, and Related Materials by Molecular Absorption Spectrometry

## 3. Significance and Use

3.1 This test method is primarily used to control the nickel dipping operation to ensure that the desired level of nickel deposition is attained. It is also used to prepare test plates used for calibration in Test Method C810.

## 4. Apparatus

4.1 *Photoelectric Photometer*, conforming to Practice E60.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee B08 on Metallic and Inorganic Coatings and is the direct responsibility of Subcommittee B08.12 on Materials for Porcelain Enamel and Ceramic-Metal Systems.

Current edition approved April 1, 2006. Published April 2006. Originally approved in 1977. Last previous edition approved in 2000 as C715 – 90 (2000). DOI: 10.1520/C0715-90R06.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Withdrawn.

4.2 *Weighted Rubber Ring Assembly*, required to confine stripping agents to a definite area, consisting of a molded rubber ring and a metal outer ring. The rubber ring shall have an inside diameter of 1.35 in. (34.3 mm) in order to encircle an area of 0.01 ft<sup>2</sup> (0.000929 m<sup>2</sup>), a wall configuration as shown in Fig. 1, and the lower portion beveled at a 45° angle (0.78 rad) to reduce the contact area and ensure a better seal. The metal outer ring shall weigh about 3.5 lb (1.5 kg), suitably machined to fit over the top of the rubber ring as shown in Fig. 1.

4.2.1 The exact area covered by the rubber ring will gradually increase as the rubber ring itself is consumed by the acid reagent used. In the most accurate analysis, the area etched by the rubber ring shall be calculated occasionally, factored against the prescribed area, and that number applied to the reading obtained from the graph.

4.3 *Aspirator*, consisting of a calibrated 500-mL flask, equipped with a two-hole stopper, an aspirator bulb, and a suction tube formed from 0.079-in. (2-mm) inside diameter capillary glass tubing.

## 5. Reagents and Materials

5.1 Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee of Analytical Reagents of the American Chemical Society.<sup>4</sup> Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

5.2 *Purity of Water*—Use distilled or deionized water.

5.3 *Ammonium Hydroxide* (*sp gr 0.90*)—Concentrated ammonium hydroxide (NH<sub>4</sub>OH).

5.4 *Ammonium Persulfate*—(NH<sub>4</sub>)<sub>2</sub>S<sub>2</sub>O<sub>8</sub>.

5.5 *Dimethylglyoxime*—Prepare a 1 % solution of dimethylglyoxime in methyl alcohol or a 2.62 % solution of sodium dimethylglyoximate in water (store in a polyethylene bottle).

<sup>4</sup> *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.