



Designation: D 3351 – 93

AMERICAN SOCIETY FOR TESTING AND MATERIALS
100 Barr Harbor Dr., West Conshohocken, PA 19428
Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

Standard Test Method for Gel Count of Plastic Film¹

This standard is issued under the fixed designation D 3351; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the number of gels present in plastic film when observing the images formed on a screen when light is projected through the film.

1.2 The thickness of the films covered by this specification is 100 μm (0.004 in.) or less.

1.3 *This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no similar or equivalent ISO standard.

2. Terminology

2.1 Definitions:

2.1.1 *gel*—a nodule of plastic material which is present in the matrix of film and is of such a composition that it is not readily blended with the matrix. Gels are believed to be composed of oxidized or high molecular weight materials, or both. A gel is to be distinguished from contamination such as particles of dirt, carbon, or lint.

3. Summary of Test Method

3.1 This test method was developed because the counting of gels in plastic film with the unaided eye is difficult and fatiguing to the operator. The test method calls for magnifying the specimen by about 8 to 1, thus making the gels easier to see. At the same time, standard-size images are projected on the screen at the same magnification.

4. Significance and Use

4.1 The presence of gels in plastic film is often objectionable due to appearance and to the problems associated with printing the film. This test method is designed to allow gels to be counted that would normally be difficult to observe with the unaided eye.

5. Apparatus

5.1 *Overhead Projector*, with a viewing plate at least 200 by 200 mm (8 by 8 in.) in size.

5.1.1 A rectangle 190 by 200 mm (7½ by 8 in.) shall be drawn on the viewing plate of the projector.

5.2 *Projection Screen*, at least 2 by 2 m (6 by 6 ft) in size.

5.3 *Acrylic Plate*, approximately 230 by 230 mm (9 by 9 in.) by 3.2 mm (0.125 in.) thick containing two standard holes, one of which is 0.80 mm (⅛ in.) in diameter and the other is 0.40 mm (¼ in.) in diameter. The holes shall be approximately 1 mm deep and shall have smooth edges. They shall be approximately 12 mm apart, and roughly centered on the acrylic plate.

6. Test Specimens

6.1 A test specimen consists of four layers of film which are at least 200 mm (8 in.) square. A convenient size is 254 mm (10 in.) square. It is also convenient to staple the four layers together at one corner.

6.2 Three test specimens shall be prepared for testing.

6.3 An area 190 by 200 mm (7½ by 8 in.) is viewed through four layers of film, which gives a total film test area of 1520 cm^2 (240 in.^2).

7. Preparation of Apparatus

7.1 Set up the projector and screen so that a magnification of between 8 to 1 and 10 to 1 is obtained. Care should be taken in projection not to distort the image on the screen. To prevent distortion, the line of projection from the mirror to the screen should be perpendicular to the screen.

8. Conditioning

8.1 No specific conditioning period is required.

9. Procedure

9.1 Place two blown tubing specimens or four flat film specimens, four layers of film in each case, on top of each other on the viewing plate of the projector, so that the lines on the viewing plate include the center portion of each specimen.

9.2 Place the transparent plastic plate with standard holes in contact with the film on the stack of specimens and press firmly to remove wrinkles as far as possible. Do not allow the staple holding film layers together to come between plates.

9.3 Focus the projector so that the gel images and the image of the gel size standards are clearly projected on the screen.

9.4 Count the gels within the rectangle that are as large or are larger than the 0.80 mm (larger) standard, and also the gels that are smaller than the 0.80-mm standard, but as large as or larger than the 0.40-mm (smaller) standard.

¹ This test method is under the jurisdiction of ASTM Committee D-20 on Plastics and is the direct responsibility of Subcommittee D20.19 on Film and Sheeting.

Current edition approved July 15, 1993. Published September 1993. Originally published as D 3351-74. Last previous edition D 3351-74 (1988)¹.

NOTE 2—The rectangle may be subdivided into smaller increments and gels counted in each small rectangle and then totaled for the report.

9.5 Record the number of gels equal to or larger than the 0.80-mm standard as 0.80-mm gels and those smaller than the 0.80-mm standard but as large or larger than the 0.40-mm standard as 0.40-mm gels.

9.6 Repeat with a second and third stack of specimens.

10. Calculation

10.1 Determine average and range of each size gel for each set of three specimens.

11. Report

11.1 Report the following information:

11.1.1 The average and range of 0.80-mm gels per 1520 cm² (240 in.²),

11.1.2 The average and range of 0.40-mm gels per 1520 cm² (240 in.²),

11.1.3 Complete identification of the materials tested,

11.1.4 Date of test,

11.1.5 Number of specimens, and

11.1.6 Nominal film thickness.

12. Precision and Bias ²

12.1 *Precision*—In round-robin work with two film samples and three operators in each of six laboratories, it was found that the square root function, when applied to counts of 0.80-mm and 0.40-mm gels per 1520 cm², resulted in a standard deviation of measurement that was independent of the gel level. If the average (of three specimens) count is denoted by C , standard deviations for the measurement of $C^{1/2}$ within-laboratory or between-laboratory, or both, were estimated to be 0.40 for 0.80-mm gels and 0.80 for 0.40-mm gels. Based on these estimates, illustrations of 90 % confidence intervals for four levels of C are as follows:

Observed Count	90 % CI	
	0.80-mm Gels	0.40-mm Gels
4	1.8–7.1	0.5–11.0
9	5.5–13.4	2.8–18.6
16	11.2–21.7	7.2–28.2
25	18.9–32.0	13.6–39.8

13. Keywords

13.1 film; gel count; plastics

² Research report available from ASTM Headquarters. Request RR: D20-1044.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.

ASTM D3351-93

/catalog/standards/astm/bfi04212-7969-488e-b53f-56d92f9f738e/astm-d3351-93