



SLOVENSKI STANDARD
SIST EN 12503-3:2002
01-september-2002

Športne blazine - 3. del: Blazine za judo, varnostne zahteve

Sports mats - Part 3: Judo mats, safety requirements

Sportmatten - Teil 3: Judomatten, sicherheitstechnische Anforderungen

Tapis de sport - Partie 3: Tapis de judo, exigences de sécurité

Ta slovenski standard je istoveten z: EN 12503-3:2001

[SIST EN 12503-3:2002](https://standards.iteh.ai/catalog/standards/sist/dfc37da1-60e8-489b-9f72-09f301fda64f/sist-en-12503-3-2002)

<https://standards.iteh.ai/catalog/standards/sist/dfc37da1-60e8-489b-9f72-09f301fda64f/sist-en-12503-3-2002>

ICS:

97.220.30 Oprema za dvoranske športe Indoor sports equipment

SIST EN 12503-3:2002

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 12503-3:2002

<https://standards.iteh.ai/catalog/standards/sist/df37da1-60e8-489b-9f72-09f301fda64f/sist-en-12503-3-2002>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 12503-3

April 2001

ICS 97.220.30

English version

Sports mats - Part 3: Judo mats, safety requirements

Tapis de sport - Partie 3: Tapis de judo, exigences de
sécurité

Sportmatten - Teil 3: Judomatten, sicherheitstechnische
Anforderungen

This European Standard was approved by CEN on 21 January 2001.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 12503-3:2002

<https://standards.iteh.ai/catalog/standards/sist/df37da1-60e8-489b-9f72-09f301fda64f/sist-en-12503-3-2002>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

| | Page |
|---|------|
| Foreword | 2 |
| 1 Scope | 3 |
| 2 Normative references | 3 |
| 3 Terms and definitions | 3 |
| 4 Classification | 4 |
| 5 Performance and safety requirements | 4 |
| 6 Marking | 4 |
| Annex A (informative) Dimensions and tolerances | 5 |
| Annex B (informative) Flame retardancy | 6 |

Foreword

This European Standard has been prepared by Technical Committee CEN/TC 136 "Sports, playground and other recreational equipment", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2001, and conflicting national standards shall be withdrawn at the latest by October 2001.

This standard EN 12503 "Sports mats" consists of:

- Part 1: **iTeh STANDARD PREVIEW**
Gymnastic mats, safety requirements
(standards.iteh.ai)
- Part 2: Pole vault and high jump mats, safety requirements
SIST EN 12503-3:2002
- Part 3: <https://standards.iteh.ai/catalog/standards/sist/dfc37da1-60e8-489b-9f72-09f301fda64f/sist-en-12503-3-2002>
Judo mats, safety requirements
- Part 4: Determination of shock absorption
- Part 5: Determination of the base friction
- Part 6: Determination of the top friction
- Part 7: Determination of static stiffness

The annexes A and B are informative.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This standard specifies performance and safety requirements for judo mats used in schools, training and competition.

The performance and safety values concern shock absorption, stiffness, anti-slip characteristics of the base and top friction characteristics of the surface. They refer to test methods defined in specific standards indicated in clause 2.

Dimensions and tolerances are given in an informative annex.

NOTE For the specific requirements of international official competitions, see appropriate international regulations.

2 Normative references

This European Standard incorporates, by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references, the latest edition of the publication referred to applies (including amendments).

EN 12503-1:2001

Sports mats – Part 1: Gymnastic mats, safety requirements

EN 12503-2:2001

Sports mats – Part 2: Pole vault and high jump mats, safety requirements

EN 12503-4:2001

Sports mats – Part 4: Determination of shock absorption

EN 12503-5:2001

Sports mats – Part 5: Determination of the base friction

EN 12503-6:2001

Sports mats – Part 6: Determination of the top friction

EN 12503-7:2001

Sports mats – Part 7: Determination of static stiffness

3 Terms and definitions

For the purposes of this standard the following terms and definitions apply.

3.1

shock absorption

ability of the mat to reduce impact forces on the athlete, expressed as a maximum deceleration under defined test conditions [EN 12503-1:2001]

3.2

static stiffness

ability of the mat to deform under a force expressed as a maximum deflection under test conditions

3.3

resilience

ability of the mat to return energy after an impact, expressed as resilience in percent under defined test conditions [EN 12503-1:2001]

**3.4
surface**

upper side of the mat on which the athlete moves [EN 12503-1:2001]

**3.5
base**

under side of the mat designed to be in contact with the floor during use [EN 12503-1:2001]

4 Classification

Judo mats shall be classified as type 12.

NOTE For types 1 to 8 see EN 12503-1:2001 and for types 9 to 11 see EN 12503-2:2001.

5 Performance and safety requirements**5.1 Shock absorption****5.1.1 Homogeneity test**

When tested in accordance with 7.2 of EN 12503-4:2001, the maximum allowable difference between any of the 8 individual points (average reading between 3 to 5) and the overall mean shall be $\pm 3 g$.

5.1.2 Peak g and resilience

When tested in accordance with 7.2 of EN 12503-4:2001, the values shall be in accordance with table 1.

Table 1 - Required values
(standards.iteh.ai)

| Parameters | Indenter diameter mm | | | |
|---------------------------|-------------------------|----|-----|----|
| | 43 | | 116 | |
| | Fall height cm | | | |
| | 20 | 60 | 20 | 60 |
| Peak deceleration ... g | 30 | 90 | 40 | 85 |
| Resilience % | 30 | 28 | 32 | 28 |

5.2 Static stiffness

When tested in accordance with EN 12503-7:2001, the maximum static stiffness value shall not be greater than 9 mm.

5.3 Base friction characteristics of the base

If the manufacturer describes a mat as having an anti-slip system, it shall be tested in accordance with the test method defined in EN 12503-5:2001.

When tested in accordance with EN 12503-5:2001, the frictional value shall be equal to or greater than 6,5.

5.4 Top friction characteristics

When tested in accordance with the test method defined in EN 12503-6:2001, the coefficient of rotational friction shall be equal to or greater than 1,0.

6 Marking

Mats shall be marked legibly and indelibly with the following information:

- a) the number of this European Standard EN 12503-3 and the type number;
- b) the name and trademark of the manufacturer, retailer or importer and the year of manufacture;
- c) which is the top surface of the mat (if not clearly recognizable).

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 12503-3:2002](https://standards.iteh.ai/catalog/standards/sist/dfc37da1-60e8-489b-9f72-09f301fda64f/sist-en-12503-3-2002)

<https://standards.iteh.ai/catalog/standards/sist/dfc37da1-60e8-489b-9f72-09f301fda64f/sist-en-12503-3-2002>

Annex A (informative)**Dimensions and tolerances**

The dimensions and tolerances of judo mats are measured in normal use conditions (temperature, humidity).

The dimensions of judo mats are given in table A.1, and the tolerances in table A.2

Table A.1- Dimensions of judo mats

| | |
|----------------|-----------------|
| Length (mm) | multiple of 1 m |
| Width (mm) | multiple of 1 m |
| Thickness (mm) | 40 or 50 |

Table A.2 - Tolerances of dimensions

| | |
|------------------------|------------|
| Tolerance on length | ± 5 mm |
| Tolerance on width | ± 5 mm |
| Tolerance on thickness | ± 3 % |

ITeH STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 12503-3:2002

<https://standards.iteh.ai/catalog/standards/sist/dfc37da1-60e8-489b-9f72-09f301fda64f/sist-en-12503-3-2002>