



Designation: F434 – 93 (Reapproved 2003)<sup>ε1</sup>

## Standard Test Method for Blow-Out Testing of Preformed Gaskets<sup>1</sup>

This standard is issued under the fixed designation F434; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

<sup>ε1</sup> NOTE—Section 2 was included editorially in April 2006.

### 1. Scope

1.1 This test method covers the determination of the resistance against blow-out of preformed gaskets. The test is conducted under ambient conditions and should be used for comparison purposes only to select suitable designs and constructions for specific applications.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Adjuncts:*

Detailed Drawings of Test Unit<sup>2</sup>

### 3. Significance and Use

3.1 This test method is designed to compare all types of preformed gaskets under controlled conditions with respect to blow-out resistance. This test method may be used as a routine test when agreed upon between the purchaser and the seller.

### 4. Apparatus

4.1 *Pressure Supply*, capable of 7 MPa (1000 psi), preferably hydraulic, and with proper safety precautions, in the event of a rapid-gasket failure.

4.2 *Test Unit*,<sup>3</sup> capable of withstanding 7 MPa (1000 psi) internal pressure under ambient conditions. Provisions should be made for valve and pressure gage mountings, as shown in Fig. 1. The gage shall read from 0 to 7 MPa (0 to 1000 psi) and be mounted so as to be visible at some distance.

4.3 *Booster Pump*—An air-operated hydraulic (water) pressure pump, capable of delivering  $1.1 \times 10^{-5} \text{ m}^3/\text{s}$  (40 in.<sup>3</sup>/min) against a back pressure of 35 MPa (5000 psi).

4.4 *Temperature Indicating Device*—A thermometer capable of reading 1°C (2°F) in the ambient temperature range.

### 5. Test Specimen

5.1 The specimen shall be a 102 mm (4-in.) nominal-size gasket 114 mm (4.5 in.) in inside diameter by 165 mm (6.5 in.) in outside diameter. The thickness of the test gasket will depend upon its expected usage and must be specified in the report, as results will vary accordingly.

### 6. Procedure

6.1 Assemble the specimen in the test unit.

6.2 The bolt threads should be well lubricated using molybdisulfide dry film or grease. Sanding the bottom of the bolt heads and the washers will reduce torque variable and ensure duplication of results.

6.3 Tighten the bolts, using the sequence shown in Fig. 2, increasing the torque loading in 25 % increments to the targeted torque, but do not exceed the rating on the bolts.

6.4 Fill the test unit with water, and bleed out all excess air by tilting until no further air bubbles are forthcoming.

6.5 Fill the oil reservoir (thermowell) three-quarters full of light oil. Allow 15 min for the temperature to stabilize, and insert the temperature sensor.

6.6 Before applying hydrostatic pressure, cover the entire test receptacle with a metal shield, leaving the gage exposed for the recording of data.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee F03 on Gaskets and is the direct responsibility of Subcommittee F03.20 on Mechanical Test Methods.

Current edition approved Oct. 1, 2003. Published October 2003. Originally approved in 1975. Last previous edition approved in 1997 as F434 – 93(1997). DOI: 10.1520/F0434-93R03E01.

<sup>2</sup> Available from ASTM International Headquarters. Order Adjunct No. ADJF0434.

<sup>3</sup> The sole source of supply of the apparatus known to the committee at this time is the Pfaudler Co., PO Box 1600, Rochester, NY 14603. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend.