



Designation: D1879 – 06

Standard Practice for Exposure of Adhesive Specimens to Ionizing Radiation¹

This standard is issued under the fixed designation D1879; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 The purpose of this practice is to define conditions for the exposure of polymeric adhesives in bonded specimens to ionizing radiation prior to determination of radiation-induced changes in physical or chemical properties. This recommended practice specifically covers the following kinds of radiation: gamma or X-ray radiation, electron or beta radiation, neutrons, and mixtures of these such as reactor radiation.

1.2 This practice specifies only the conditions of irradiation but does not cover the preparation of test specimens, testing conditions, or the evaluation of test. These are covered in the various ASTM methods or specifications for specific materials.

1.3 This practice covers procedures for the following five types of exposure:

Procedure A—Exposure at ambient conditions.

Procedure B—Exposure at controlled temperature.

Procedure C—Exposure in a medium other than air.

Procedure D—Exposure under load.

Procedure E—Exposure combining two or more of the variables listed in Procedures A to D.

NOTE 1—The problems of measuring the properties of materials during irradiation involve shielding and remote control facilities and are, therefore, not considered in this practice.

1.4 The values stated in SI units are to be regarded as the standard. The values given in parentheses are provided for information purposes only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.5.1 **Electrical Hazard: Warning**—The users of this practice must be aware that there are inherent dangers associated with the use of electrical instrumentation and that this practice

cannot and will not substitute for a practical knowledge of the instrument used for a particular procedure.

1.5.2 **Radio Frequency: Warning**—Persons with pacemakers may be affected by the radio frequency.

2. Referenced Documents

2.1 ASTM Standards:²

D618 Practice for Conditioning Plastics for Testing

D907 Terminology of Adhesives

D1672 Practice for Exposure of Polymeric Materials to High-Energy Radiation (Withdrawn 1984)³

D2953 Classification System for Polymeric Materials for Service in Ionizing Radiation (Withdrawn 1984)³

E170 Terminology Relating to Radiation Measurements and Dosimetry

E261 Practice for Determining Neutron Fluence, Fluence Rate, and Spectra by Radioactivation Techniques

E666 Practice for Calculating Absorbed Dose From Gamma or X Radiation

E720 Guide for Selection and Use of Neutron Sensors for Determining Neutron Spectra Employed in Radiation-Hardness Testing of Electronics

E2005 Guide for Benchmark Testing of Reactor Dosimetry in Standard and Reference Neutron Fields

2.2 ISO/ASTM Standards:²

ISO/ASTM 51261 Guide for Selection and Calibration of Dosimetry Systems for Radiation Processing

ISO/ASTM 51649 Practice for Dosimetry in an Electron Beam Facility for Radiation Processing at Energies Between 300 keV and 25 MeV

ISO/ASTM 51702 Practice for Dosimetry in Gamma Irradiation Facilities for Radiation Processing

ISO/ASTM 51818 Practice for Dosimetry in an Electron Beam Facility for Radiation Processing at Energies Between 80 and 300 keV

¹ This practice is under the jurisdiction of ASTM Committee D14 on Adhesives and is the direct responsibility of Subcommittee D14.80 on Metal Bonding Adhesives.

Current edition approved March 1, 2006. Published May 2006. Originally approved in 1961. Last previous edition approved in 1999 as D1879 – 99. DOI: 10.1520/D1879-06.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

2.3 *ANSI Document:*

N1.1 Glossary of Terms in Nuclear Science and Technology⁴

2.3 *IEEE Documents:*⁵

278 Classifying Electrical Insulating Materials Exposed to Neutron and Gamma Radiation

323 Qualifying Class 1E Equipment for Nuclear Power Generating Stations

3. Terminology

3.1 Many terms in this practice are defined in Terminology **D907** and in Terminology **E170**.

3.2 *gray, n*—the unit of absorbed dose when the energy per unit mass imparted to matter by radiation is one joule per kilogram.

3.3 *rad, n*—the unit of absorbed dose when the energy per unit mass imparted to matter by radiation is 100 ergs per gram.

NOTE 2—To convert from rad to gray (Gy), multiply by 1.00×10^{-2} . 1 rad = 0.01 gray and 1 megarad (MR) = 10 kilograys (kGy).

4. Significance and Use

4.1 The procedures outlined in this practice are designed to standardize the exposure of adhesive-bonded specimens for the purpose of studying the effects of ionizing radiation, but have been made flexible enough so that a large variety of conditions may be met within the scope of this one irradiation method. Because of this flexibility in the procedures, it is important that the experimenter have some idea of the kind of changes that will occur, and of the conditions that will affect these changes.

5. Effects of Irradiation

5.1 Exposure to radiation can result in changes in monomers, oligomers and high polymers, which owe some of their properties to chemical links formed within molecular structures. These structures may be cross-linked by radiation into insoluble, three-dimensional networks, may be cleaved into smaller molecules, or unaffected by radiation exposure. Cross-linking and cleavage or scission may occur at the same time.

5.2 One effect of the reaction of ionizing radiation with polymers is the formation of free radicals, atoms containing unpaired electrons. In some instances, the rate at which free radicals are formed may be much greater than their rate of extinction. In a few instances, this can lead to trapped reactive species within the irradiated material and to the possibility of continuing reactions for days or weeks after the specimen has been removed from the radiation field. Because of these limited post-irradiation reactions it has been found necessary to standardize the times and conditions of storage between irradiation and testing of specimens.

5.3 The resultant changes in the morphology of polymeric materials caused by exposure to radiation can be dependent on the respective rates of recombination, crosslinking, or cleavage of the material segments. These rates are affected by the

mobility of the excited atoms (free radicals or ionized) which in turn is influenced by temperature and by the concentration of the excited or ionized atoms.

5.4 The concentration of reactive species will vary with the rate of absorption of radiation. Both radiation exposure or dose and dose-rate should be specified in reporting the results of tests. The effect of dose, dose-rate and specimen thickness can sometimes be observed when irradiations are carried out in air, that is in the presence of oxygen, wherein oxygen reacts with radicals produced in the irradiated material. This oxygen reaction is diffusion controlled. The reactivity of some irradiated specimens toward oxygen makes it necessary to specify whether irradiations are carried out in air or in an inert atmosphere. The accessibility to an air supply undepleted in oxygen should be assured if possible.

5.5 The localized concentration of reactive species during irradiation will vary, depending on the type of radiation employed. The proton and carbon recoils from neutron bombardment produce densely ionized tracks in the specimen compared to the diffuse ionization in the wake of protons or electrons. The effect of different types of radiation may therefore be different. It is required that the type of radiation to which the specimen has been exposed be reported as well as the irradiation dose in terms of energy absorbed units, that is, grays or kiloGrays (kGy).

5.6 Various chemical structures respond differently on exposure to radiation. The exposure levels for testing should be based upon the end-use of the bonded assembly and upon consideration of the chemical structure of the adhesive material. Aromatic materials, such as polystyrene (PS), polycarbonates (PC) and polyethylene terephthalate (PET), tend to be unaffected, in terms of physical properties, by modest radiation exposure. Materials with an abstractable hydrogen, such as polyethylene (PE), will crosslink, with the radiation response being very dependent on the specific morphology of a given grade and its additives. Materials with tetra-substituted carbon atoms, such as polymethylmethacrylate (PMMA), polytetrafluoroethylene (PTFE) and polyvinylidene chloride (PVdC), will exhibit scissioning and generally a weakening of physical properties. The exposure levels or cumulative dose should be those which will produce measurable changes in a stipulated property rather than a specified fixed irradiation dose. Such changes in property may progress at different rates, with some materials changing rapidly once a change has been initiated, while others may change quite slowly. It is necessary therefore to irradiate to several fixed levels of property change in order to establish the rate of change (see 13.2).

5.7 Some materials that have been exposed to reactor radiation in terms of neutron flux may become radioactive. These can be metallic and other inorganic adherends and fillers. For exact work, where the reactor spectrum is being studied, exposure in a reactor would give the only accurate results.

6. Test Specimens

6.1 Wherever possible, use the type of specimens in accordance with the ASTM test methods for the specific properties to be measured.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁵ Available from Institute of Electrical and Electronics Engineers, Inc. (IEEE), 445 Hoes Ln., P.O. Box 1331, Piscataway, NJ 08854-1331, <http://www.ieee.org>.