



Designation: ~~A 671-04~~ Designation: A671 - 06

Standard Specification for Electric-Fusion-Welded Steel Pipe for Atmospheric and Lower Temperatures¹

This standard is issued under the fixed designation A671; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification² covers electric-fusion-welded steel pipe with filler metal added, fabricated from pressure vessel quality plate of several analyses and strength levels and suitable for high-pressure service at atmospheric and lower temperatures. Heat treatment may or may not be required to attain the desired properties or to comply with applicable code requirements. Supplementary requirements are provided for use when additional testing or examination is desired.

1.2 The specification nominally covers pipe 16 in. (405 mm) in outside diameter or larger and of 1/4 in. (6.4 mm) wall thickness or greater. Pipe having other dimensions may be furnished provided it complies with all other requirements of this specification.

1.3 Several grades and classes of pipe are provided.

1.3.1 Grade designates the type of plate used as listed in 5.1.

1.3.2 Class designates the type of heat treatment performed during manufacture of the pipe, whether the weld is radiographically examined, and whether the pipe has been pressure tested as listed in 1.3.3.

1.3.3 Class designations are as follows (Note 1):

Class	Heat Treatment on Pipe	Radiography, see Section	Pressure Test, see:
10	none	none	none
11	none	9	none
12	none	9	8.3
13	none	none	8.3
20	stress relieved, see 5.3.1	none	none
21	stress relieved, see 5.3.1	9	none
22	stress relieved, see 5.3.1	9	8.3
23	stress relieved, see 5.3.1	none	8.3
30	normalized, see 5.3.2	none	none
31	normalized, see 5.3.2	9	none
32	normalized, see 5.3.2	9	8.3
33	normalized, see 5.3.2	none	8.3
40	normalized and tempered, see 5.3.3	none	none
41	normalized and tempered, see 5.3.3	9	none
42	normalized and tempered, see 5.3.3	9	8.3
43	normalized and tempered, see 5.3.3	none	8.3
50	quenched and tempered, see 5.3.4	none	none
51	quenched and tempered, see 5.3.4	9	none
52	quenched and tempered, see 5.3.4	9	8.3
53	quenched and tempered, see 5.3.4	none	8.3
60	normalized and precipitation heat treated	none	none
61	normalized and precipitation heat treated	9	none
62	normalized and precipitation heat treated	9	8.3
63	normalized and precipitation heat treated	none	8.3
70	quenched and precipitation heat treated	none	none
71	quenched and precipitation heat treated	9	none

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.09 on Carbon Steel Tubular Products.

Current edition approved May 1, 2004; 2006. Published May 2004; 2006. Originally approved in 1972. Last previous edition approved in 2004 as A 671-96(2001); A671 - 04. DOI: 10.1520/A0671-06.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SA-671 in Section II of that Code.

*A Summary of Changes section appears at the end of this standard.

72	quenched and precipitation heat treated	9	8.3
73	quenched and precipitation heat treated	none	8.3

NOTE 1—Selection of materials should be made with attention to temperature of service. For such guidance, Specification ~~A 20/A 20M~~A20/A20M may be consulted.

1.4 The values stated in inch-pound units are to be regarded as the standard.

2. Referenced Documents

2.1 ASTM Standards:³

A20/A20M [Specification for General Requirements for Steel Plates for Pressure Vessels](#)

A370 [Test Methods and Definitions for Mechanical Testing of Steel Products](#)

A435/A435M [Specification for Straight-Beam Ultrasonic Examination of Steel Plates](#)

A530/A530M [Specification for General Requirements for Specialized Carbon and Alloy Steel Pipe](#)

A577/A577M [Specification for Ultrasonic Angle-Beam Examination of Steel Plates](#)

A578/A578M [Specification for Straight-Beam Ultrasonic Examination of ~~Plain and Clad~~Rolled Steel Plates for Special Applications](#)

E110 [Test Method for Indentation Hardness of Metallic Materials by Portable Hardness Testers](#)

E165 [Test Method for Liquid Penetrant Examination](#) ~~Practice for Liquid Penetrant Examination for General Industry~~

E709 [Guide for Magnetic Particle Examination](#) ~~Testing~~

2.2 Plate Steels:

~~A 203/A 203M Specification for Pressure Vessel Plates, Alloy Steel, Nickel~~ [A203/A203M Specification for Pressure Vessel Plates, Alloy Steel, Nickel](#)

~~A 285/A 285M~~ [A285/A285M Specification for Pressure Vessel Plates, Carbon Steel, Low- and Intermediate-Tensile Strength](#)

~~A 299/A 299M~~ [A299/A299M Specification for Pressure Vessel Plates, Carbon Steel, Manganese-Silicon](#)

~~A 353/A 353M~~ [A353/A353M Specification for Pressure Vessel Plates, Alloy Steel, 9 Percent Nickel, Double-Normalized and Tempered](#)

~~A 442/A 442M Specification for Pressure Vessel Plates, Carbon Steel, Improved Transition Properties~~ [A353/A353M Specification for Pressure Vessel Plates, Alloy Steel, Double-Normalized and Tempered 9 % Nickel](#)

~~A 515/A 515M~~ [A515/A515M Specification for Pressure Vessel Plates, Carbon Steel, for Intermediate- and Higher-Temperature Service](#)

~~A 516/A 516M~~ [A516/A516M Specification for Pressure Vessel Plates, Carbon Steel, for Moderate- and Lower-Temperature Service](#)

~~A 517/A 517M~~ [A517/A517M Specification for Pressure Vessel Plates, Alloy Steel, High-Strength, Quenched and Tempered](#)

~~A 537/A 537M Specification for Pressure Vessel Plates, Heat-Treated, Carbon-Manganese-Silicon Steel~~ [A537/A537M Specification for Pressure Vessel Plates, Heat-Treated, Carbon-Manganese-Silicon Steel](#)

~~A 553/A 553M~~ [A553/A553M Specification for Pressure Vessel Plates, Alloy Steel, Quenched and Tempered 8 and 9 Percent Nickel](#)

~~A 736/A 736M Specification for Pressure Vessel Plates, Low-Carbon Age-Hardening, Nickel-Copper-Chromium-Molybdenum-Columbium and Nickel-Copper-Manganese-Molybdenum-Columbium Alloy Steel~~ [A736/A736M Specification for Pressure Vessel Plates, Low-Carbon Age-Hardening Nickel-Copper-Chromium-Molybdenum-Columbium Alloy Steel](#)

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.3 ASME Boiler and Pressure Vessel Code:⁴

Section II, Material Specifications

Section III, Nuclear Vessels

Section VIII, Unfired Pressure Vessels

Section IX, Welding Qualifications

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *lot*—a lot shall consist of 200 ft (61 m) or fraction thereof of pipe from the same heat of steel.

3.1.2 The description of a lot may be further restricted by the use of Supplementary Requirement S14.

4. Ordering Information

4.1 The inquiry and order for material under this specification should include the following information:

4.1.1 Quantity (feet, metres, or number of lengths),

4.1.2 Name of material (steel pipe, electric-fusionwelded),

4.1.3 Specification number,

4.1.4 Grade and class designations (see 1.3),

4.1.5 Size (inside or outside diameter, nominal or minimum wall thickness),

4.1.6 Length (specific or random),

4.1.7 End finish (11.4),

4.1.8 Purchase options, if any (see 5.2.3 and 11.3 of this specification. See also Specification A-530/A-530M/A530/A530M),

4.1.9 Supplementary requirements, if any.

5. Materials and Manufacture

5.1 *Materials*—The steel plate material shall conform to the requirement of the applicable plate specification for the pipe grade ordered as listed in Table 1.

5.2 Welding:

5.2.1 The joints shall be double-welded, full-penetration welds made in accordance with procedures and by welders or welding operators qualified in accordance with the ASME Boiler and Pressure Vessel Code, Section IX.

5.2.2 The welds shall be made either manually or automatically by an electric process involving the deposition of filler metal.

5.2.3 As welded, the welded joint shall have positive reinforcement at the center of each side of the weld, but no more than 1/8 in. (3.2 mm). This reinforcement may be removed at the manufacturer's option or by agreement between the manufacturer and purchaser. The contour of the reinforcement shall be smooth and the deposited metal shall be fused smoothly and uniformly into the plate surface.

5.2.4 When radiographic examination in accordance with 9.1 is to be used, the weld reinforcements shall be governed by the more restrictive provision UW-51 of Section VIII of the ASME Boiler and Pressure Vessel Code instead of 5.2.3 of this specification.

5.3 *Heat Treatment*—All classes other than 10, 11, 12, and 13 shall be heat treated in furnace controlled to ± 25 °F (± 14 °C) and equipped with a recording pyrometer so that heating records are available. Heat treating after forming and welding shall be to one of the following:

5.3.1 Classes 20, 21, 22, and 23 pipe shall be uniformly heated within the post-weld heat-treatment temperature range indicated in Table 2 for a minimum of 1 h/in. of thickness or for 1 h, whichever is greater.

5.3.2 Classes 30, 31, 32, and 33, pipe shall be uniformly heated to a temperature in the austenitizing range and not exceeding the maximum normalizing temperature indicated in Table 2 and subsequently cooled in air at room temperature.

5.3.3 Classes 40, 41, 42, and 43 pipe shall be normalized in accordance with 5.3.2. After normalizing, the pipe shall be reheated to the tempering temperature indicated in Table 2 as a minimum and held at temperature for a minimum of 1/2 h/in. of thickness or for 1/2 h, whichever is greater, and air cooled.

5.3.4 Classes 50, 51, 52, and 53 pipe shall be uniformly heated to a temperature in the austenitizing range, and not exceeding the maximum quenching temperature indicated in Table 2 and subsequently quenched in water or oil. After quenching, the pipe shall be reheated to the tempering temperature indicated in Table 2 as a minimum and held at that temperature for a minimum of 1/2 h/in. of thickness or for 1/2 h, whichever is greater, and air cooled.

5.3.5 Classes 60, 61, 62, and 63 pipe shall be normalized in accordance with 5.3.2. After normalizing, the pipe shall be precipitation heat treated in the range shown in Table 2 for a time to be determined by the manufacturer.

5.3.6 Classes 70, 71, 72, and 73 pipe shall be uniformly heated to a temperature in the austenitizing range, not exceeding the maximum quenching temperature indicated in Table 2, and subsequently quenched in water or oil. After quenching the pipe shall be reheated into the precipitation heat treating range indicated in Table 2 for a time to be determined by the manufacturer.

⁴Withdrawn.

⁴ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5990.

TABLE 1 Plate Specifications

Pipe Grade	Type of Steel	ASTM Specification	
		No.	Grade
GA-55	plain carbon	A-285/A-285M	C
CA 55	plain carbon	A285/A285M	C
GB-60	plain carbon, killed	A-515/A-515M	60
CB 60	plain carbon, killed	A515/A515M	60
GB-65	plain carbon, killed	A-515/A-515M	65
CB 65	plain carbon, killed	A515/A515M	65
GB-70	plain carbon, killed	A-515/A-515M	70
CB 70	plain carbon, killed	A515/A515M	70
GC-60	plain carbon, killed, fine grain	A-516/A-516M	60
CC 60	plain carbon, killed, fine grain	A516/A516M	60
GC-65	plain carbon, killed, fine grain	A-516/A-516M	65
CC 65	plain carbon, killed, fine grain	A516/A516M	65
GC-70	plain carbon, killed, fine grain	A-516/A-516M	70
CC 70	plain carbon, killed, fine grain	A516/A516M	70
GD-70	manganese-silicon, normalized	A-537/A-537M	1
CD 70	manganese-silicon, normalized	A537/A537M	1
GD-80	manganese-silicon, quenched and tempered	A-537/A-537M	2
CD 80	manganese-silicon, quenched and tempered	A537/A537M	2
GE-55	plain carbon	A-442/A-442M	55
CE-60	plain carbon	A-442/A-442M	60
GF-65	nickel steel	A-203/A-203M	A
CF 65	nickel steel	A203/A203M	A
GF-70	nickel steel	A-203/A-203M	B
CF 70	nickel steel	A203/A203M	B
GF-66	nickel steel	A-203/A-203M	D
CF 66	nickel steel	A203/A203M	D
GF-71	nickel steel	A-203/A-203M	E
CF 71	nickel steel	A203/A203M	E
GG-100	9% nickel	A-353/A-353M	
CG 100	9% nickel	A353/A353M	
GH-100	9% nickel	A-553/A-553M	1
CH 100	9% nickel	A553/A553M	1
GJ-101	alloy steel, quenched and tempered	A-517/A-517M	A
CJ 101	alloy steel, quenched and tempered	A517/A517M	A
GJ-102	alloy steel, quenched and tempered	A-517/A-517M	B
CJ 102	alloy steel, quenched and tempered	A517/A517M	B
GJ-103	alloy steel, quenched and tempered	A-517/A-517M	C
CJ 103	alloy steel, quenched and tempered	A517/A517M	C
GJ-104	alloy steel, quenched and tempered	A-517/A-517M	D
CJ 104	alloy steel, quenched and tempered	A517/A517M	D
GJ-105	alloy steel, quenched and tempered	A-517/A-517M	E
CJ 105	alloy steel, quenched and tempered	A517/A517M	E
GJ-106	alloy steel, quenched and tempered	A-517/A-517M	F
CJ 106	alloy steel, quenched and tempered	A517/A517M	F
GJ-107	alloy steel, quenched and tempered	A-517/A-517M	G
CJ 107	alloy steel, quenched and tempered	A517/A517M	G
GJ-108	alloy steel, quenched and tempered	A-517/A-517M	H
CJ 108	alloy steel, quenched and tempered	A517/A517M	H
GJ-109	alloy steel, quenched and tempered	A-517/A-517M	J
CJ 109	alloy steel, quenched and tempered	A517/A517M	J
GJ-110	alloy steel, quenched and tempered	A-517/A-517M	K
CJ 110	alloy steel, quenched and tempered	A517/A517M	K
GJ-111	alloy steel, quenched and tempered	A-517/A-517M	L
CJ 111	alloy steel, quenched and tempered	A517/A517M	L
GJ-112	alloy steel, quenched and tempered	A-517/A-517M	M
CJ 112	alloy steel, quenched and tempered	A517/A517M	M
GJ-113	alloy steel, quenched and tempered	A-517/A-517M	P
CJ 113	alloy steel, quenched and tempered	A517/A517M	P
GK-75	carbon-manganese-silicon	A-299/A-299M	
CK 75	carbon-manganese-silicon	A299/A299M	
GP65	alloy steel, age hardening, normalized — and precipitation heat treated	A-736/A-736M	2
CP65	alloy steel, age hardening, normalized — and precipitation heat treated	A736/A736M	2
GP75	alloy steel, age hardening, quenched — and precipitation heat treated	A-736/A-736M	3
CP75	alloy steel, age hardening, quenched — and precipitation heat treated	A736/A736M	3