

Designation: B417 – 00 (Reapproved 2006) $^{\epsilon 1}$

Standard Test Method for Apparent Density of Non-Free-Flowing Metal Powders Using the Carney Funnel¹

This standard is issued under the fixed designation B417; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

 ε^1 Note—Footnote 3 was editorially updated in May 2006.

1. Scope

- 1.1 This test method covers a procedure for determining the apparent density of non-free-flowing metal powders. It is designed for those metal powders that do not freely flow through the Hall flowmeter funnel.
- 1.2 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:²

B215 Practices for Sampling Metal Powders

B243 Terminology of Powder Metallurgy

B873 Test Method for Measuring Volume of Apparent Density Cup Used in Test Methods B 212, B 329, and B 417

3. Terminology

3.1 *Definitions*—Terms in Terminology B243 are applicable to this test method.

4. Summary of Test Method

4.1 A container of definite volume is filled with non-free-flowing powder under controlled conditions. The mass of powder per unit volume is determined and reported as apparent density, Carney.

5. Significance and Use

5.1 This test method provides a guide for evaluation of the apparent density physical characteristic of powders. The den-

sity measured bears a relationship to the mass of powder that will fill a fixed volume die cavity when parts are being made. The degree of correlation between the results of this test method and the quality of powders in use will vary with each particular application.

6. Apparatus

- 6.1 Powder Funnel³—A Carney funnel (Fig. 1).
- 6.2 *Density Cup*³—A cylindrical brass cup (Fig. 2) having a capacity of 25 cm³. The actual cup volume shall be determined according to Test Method B873.
- 6.3 Stand—A stand (Fig. 1) to support the powder funnel concentric with the density cup so that the bottom of the powder funnel is approximately 25 mm (1 in.) above the top of the density cup when the apparatus is assembled as shown in Fig. 1.
- 6.4 Base—A level, vibration-free base to support the powder flowmeter.
- 6.5 *Balance*, having a capacity of at least 200 g and a sensitivity of 0.01 g.
- 6.6 Wire, approximately 2.5 mm (0.10 in.) in diameter by 150 mm (6 in.) in length.

7. Test Specimen

- 7.1 The test specimen shall consist of a volume of approximately 30 to 40 cm of metal powder obtained in accordance with Practices B215.
- 7.2 The test specimen shall be tested as sampled. Note, however, that temperature, moisture, oils, stearic acid, stearates, waxes, and so forth may alter the characteristics of the powder.

8. Procedure

8.1 Weigh the empty density cup to the nearest 0.1 g or, alternatively, place the empty density cup on the balance and tare the balance to zero.

¹ This test method is under the jurisdiction of ASTM Committee B09 on Metal Powders and Metal Powder Products and is the direct responsibility of Subcommittee B09.02 on Base Metal Powders.

Current edition approved April 1, 2006. Published May 2006. Originally approved in 1964. Last previous edition approved in 2000 as B417-00. DOI: 10.1520/B0417-00R06E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The sole source of supply of the flowmeter funnel, density cup, and stand known to the committee at this time is Acu Powder International, LLC. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, ¹ which you may attend.