



Designation: B 381 – 06

Standard Specification for Titanium and Titanium Alloy Forgings¹

This standard is issued under the fixed designation B 381; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification² covers 35 grades of annealed titanium and titanium alloy forgings as follows:

- 1.1.1 *Grade F-1*—Unalloyed titanium,
- 1.1.2 *Grade F-2*—Unalloyed titanium,
- 1.1.3 *Grade F-3*—Unalloyed titanium,
- 1.1.4 *Grade F-4*—Unalloyed titanium,
- 1.1.5 *Grade F-5*—Titanium alloy (6 % aluminum, 4 % vanadium),
- 1.1.6 *Grade F-6*—Titanium alloy (5 % aluminum, 2.5 % tin),
- 1.1.7 *Grade F-7*—Unalloyed titanium plus 0.12 to 0.25 % palladium,
- 1.1.8 *Grade F-9*—Titanium alloy (3 % aluminum, 2.5 % vanadium),
- 1.1.9 *Grade F-11*—Unalloyed titanium plus 0.12 to 0.25 % palladium,
- 1.1.10 *Grade F-12*—Titanium alloy (0.3 % molybdenum, 0.8 % nickel),
- 1.1.11 *Grade F-13*—Titanium alloy (0.5 % nickel, 0.05 % ruthenium),
- 1.1.12 *Grade F-14*—Titanium alloy (0.5 % nickel, 0.05 % ruthenium),
- 1.1.13 *Grade F-15*—Titanium alloy (0.5 % nickel, 0.05 % ruthenium),
- 1.1.14 *Grade F-16*—Unalloyed titanium plus 0.04 % to 0.08 % palladium,
- 1.1.15 *Grade F-17*—Unalloyed titanium plus 0.04 % to 0.08 % palladium,
- 1.1.16 *Grade F-18*—Titanium alloy (3 % aluminum, 2.5 % vanadium) plus 0.04 % to 0.08 % palladium,

- 1.1.17 *Grade F-19*—Titanium alloy (3 % aluminum, 8 % vanadium, 6 % chromium, 4 % zirconium, 4 % molybdenum),
- 1.1.18 *Grade F-20*—Titanium alloy (3 % aluminum, 8 % vanadium, 6 % chromium, 4 % zirconium, 4 % molybdenum) plus 0.04 % to 0.08 % palladium,
- 1.1.19 *Grade F-21*—Titanium alloy (3 % aluminum, 2.7 % niobium, 15 % molybdenum, 0.25 % silicon),
- 1.1.20 *Grade F-23*—Titanium alloy (6 % aluminum, 4 % vanadium, extra low interstitials, ELI),
- 1.1.21 *Grade F-24*—Titanium alloy (6 % aluminum, 4 % vanadium) plus 0.04 % to 0.08 % palladium,
- 1.1.22 *Grade F-25*—Titanium alloy (6 % aluminum, 4 % vanadium) plus 0.3 % to 0.8 % nickel and 0.04 % to 0.08 % palladium,
- 1.1.23 *Grade F-26*—Unalloyed titanium plus 0.08 to 0.14 % ruthenium,
- 1.1.24 *Grade F-27*—Unalloyed titanium plus 0.08 to 0.14 % ruthenium,
- 1.1.25 *Grade F-28*—Titanium alloy (3% aluminum, 2.5% vanadium plus 0.08–0.14% ruthenium),
- 1.1.26 *Grade F-29*—Titanium alloy (6% aluminum, 4% vanadium, extra low interstitial, ELI plus 0.08–0.14% ruthenium),
- 1.1.27 *Grade F-30*—Titanium alloy (0.3 % cobalt, 0.05 % palladium),
- 1.1.28 *Grade F-31*—Titanium alloy (0.3 % cobalt, 0.05 % palladium),
- 1.1.29 *Grade F-32*—Titanium alloy (5 % aluminum, 1 % vanadium, 1 % tin, 1 % zirconium, 0.8 % molybdenum),
- 1.1.30 *Grade F-33*—Titanium alloy (0.4 % nickel, 0.015 % palladium, 0.025 % ruthenium, 0.15 % chromium),
- 1.1.31 *Grade F-34*—Titanium alloy (0.4 % nickel, 0.015 % palladium, 0.025 % ruthenium, 0.15 % chromium),
- 1.1.32 *Grade F-35*—Titanium alloy (4.5 % aluminum, 2 % molybdenum, 1.6 % vanadium, 0.5 % iron, 0.3 % silicon),
- 1.1.33 *Grade F-36*—Titanium alloy (45 % niobium),
- 1.1.34 *Grade F-37*—Titanium alloy (1.5 % aluminum), and
- 1.1.35 *Grade F-38*—Titanium alloy (4 % aluminum, 2.5 % vanadium, 1.5 % iron).

¹ This specification is under the jurisdiction of ASTM Committee B10 on Reactive and Refractory Metals and Alloys and is the direct responsibility of Subcommittee B10.01 on Titanium.

Current edition approved April 1, 2006. Published May 2006. Originally approved in 1961. Last previous edition approved in 2005 as B 381 – 05^{ε1}.

² For ASME Boiler and Pressure Vessel Code applications, see related Specification SB-381 in Section II of that Code.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

2. Referenced Documents

2.1 ASTM Standards:³

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- B 348** Specification for Titanium and Titanium Alloy Bars and Billets
- E 8** Test Methods for Tension Testing of Metallic Materials
- E 29** Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- E 120** Test Methods for Chemical Analysis of Titanium and Titanium Alloys⁴
- E 1409** Test Method for Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Technique

⁴ Withdrawn.

TABLE 1 Tensile Requirements^A

Grade	Tensile Strength, min		Yield Strength (0.2 % Offset), min or Range		Elongation in 4D, min, %	Reduction of Area, min, %
	ksi	(MPa)	ksi	(MPa)		
F-1	35	(240)	20	(138)	24	30
F-2	50	(345)	40	(275)	20	30
F-3	65†	(450)†	55	(380)	18	30
F-4	80†	(550)†	70	(483)	15	25
F-5	130	(895)	120	(828)	10	25
F-6	120	(828)	115	(795)	10	25
F-7	50	(345)	40	(275)	20	30
F-9	120	(828)	110	(759)	10	25
F-9 ^B	90	(620)	70	(483)	15	25
F-11	35	(240)	20	(138)	24	30
F-12	70	(483)	50	(345)	18	25
F-13	40	(275)	25	(170)	24	30
F-14	60	(410)	40	(275)	20	30
F-15	70	(483)	55	(380)	18	25
F-16	50	(345)	40	(275)	20	30
F-17	35	(240)	20	(138)	24	30
F-18	90	(620)	70	(483)	15	25
F-18 ^B	90	(620)	70	(483)	12	20
F-19 ^C	115	(793)	110	(759)	15	25
F-19 ^D	135	(930)	130 to 159	(897) to (1096)	10	20
F-19 ^E	165	(1138)	160 to 185	(1104) to (1276)	5	20
F-20 ^C	115	(793)	110	(759)	15	25
F-20 ^D	135	(930)	130 to 159	(897) to (1096)	10	20
F-20 ^E	165	(1138)	160 to 185	(1104) to (1276)	5	20
F-21 ^C	115	(793)	110	(759)	15	35
F-21 ^D	140	(966)	130 to 159	(897) to (1096)	10	30
F-21 ^E	170	(1172)	160 to 185	(1104) to (1276)	8	20
F-23	120	(828)	110	(759)	10	25
F-23 ^B	120	(828)	110	(759)	7.5 ^F , 6.0 ^G	25
F-24	130	(895)	120	(828)	10	25
F-25	130	(895)	120	(828)	10	25
F-26	50	(345)	40	(275)	20	30
F-27	35	(240)	20	(138)	24	30
F-28	90	(620)	70	(483)	15	25
F-28 ^B	90	(620)	70	(483)	12	20
F-29	120	(828)	110	(759)	10	25
F-29 ^B	120	(828)	110	(759)	7.5 ^F , 6.0 ^G	15
F-30	50	(345)	40	(275)	20	30
F-31	65	(450)	55	(380)	18	30
F-32	100	(689)	85	(586)	10	25
F-33	50	(345)	40	(275)	20	30
F-34	65	(450)	55	(380)	18	30
F-35	130	(895)	120	(828)	5	20
F-36	65	(450)	60 to 95	(410 to 655)	10	...
F-37	50	(345)	31	(215)	20	30
F-38	130	(895)	115	(794)	10	25

^A These properties apply to forgings having a cross section no greater than 3 in.²(1935 mm²). Mechanical properties of forgings having greater cross sections shall be negotiated between the manufacturer and the purchaser.

^B Properties for material in transformed-beta condition.

^C Properties for material in the solution treated condition.

^D Properties for solution treated and aged condition-Moderate strength (determined by aging temperature).

^E Properties for solution treated and aged condition-High Strength (determined by aging temperature).

^F For product section or wall thickness values <1.0 in.

^G For product section or wall thickness values ≤1.0 in.

† Tensile strength for Grade F-3 and F-4 was corrected editorially.

E 1447 Test Method for Determination of Hydrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Thermal Conductivity/Infrared Detection Method

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *bar, n*—a hot rolled, forged or cold worked semifinished solid section product whose cross sectional area is less than 16 in.²(10 323 mm²).

3.1.2 *billet, n*—a solid semifinished section, hot rolled or forged from an ingot, with a cross sectional area greater than 16 in.²(10 323 mm²).

3.1.3 *forging, n*—any product of work on metal formed to a desired shape by impact or pressure in hammers, forging machines, upsetters presses or related forming equipment.

4. Ordering Information

4.1 Orders for forgings under this specification shall include the following information, as applicable:

- 4.1.1 Grade number (Section 1),
- 4.1.2 Tensile properties (Table 1),
- 4.1.3 Dimensions and tolerances (Section 9),
- 4.1.4 Sampling, mechanical properties (Section 7),
- 4.1.5 Methods for chemical analysis (Section 6),
- 4.1.6 Marking (Section 16),
- 4.1.7 Packaging (Section 16),
- 4.1.8 Certification (Section 15),
- 4.1.9 Disposition of rejected material (Section 13), and
- 4.1.10 Supplementary requirements (S1).

TABLE 2 Chemical Requirements^A

Element	Composition, %									
	F-1	F-2	F-3	F-4	F-5	F-6	F-7	F-9	F-11	F-12
Nitrogen, max	0.03	0.03	0.05	0.05	0.05	0.03	0.03	0.03	0.03	0.03
Carbon, max	0.08	0.08	0.08	0.08	0.08	0.08	0.08	0.08	0.08	0.08
Hydrogen, ^{B,C} max	0.015	0.015	0.015	0.015	0.015	0.015	0.015	0.015	0.015	0.015
Iron, max	0.20	0.30	0.30	0.50	0.40	0.50	0.30	0.25	0.20	0.30
Oxygen, max	0.18	0.25	0.35	0.40	0.20	0.20	0.25	0.15	0.18	0.25
Aluminum	5.5–6.75	4.0–6.0	...	2.5–3.5
Vanadium	3.5–4.5	2.0–3.0
Tin	2.0–3.0
Ruthenium
Palladium	0.12–0.25	...	0.12–0.25	...
Cobalt
Molybdenum	0.2–0.4
Chromium
Nickel	0.6–0.9
Niobium
Zirconium
Silicon
Residuals, ^{D,E,F} max each	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Residuals, ^{D,E,F} max total	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4
Titanium ^G	balance	balance	balance	balance	balance	balance	balance	balance	balance	balance

Element	Composition, %									
	F-13	F-14	F-15	F-16	F-17	F-18	F-19	F-20	F-21	F-23
Nitrogen, max	0.03	0.03	0.05	0.03	0.03	0.03	0.03	0.03	0.03	0.03
Carbon, max	0.08	0.08	0.08	0.08	0.08	0.08	0.05	0.05	0.05	0.08
Hydrogen, ^{B,C} max	0.015	0.015	0.015	0.015	0.015	0.015	0.02	0.02	0.015	0.0125
Iron, max	0.20	0.30	0.30	0.30	0.20	0.25	0.30	0.30	0.40	0.25
Oxygen, max	0.10	0.15	0.25	0.25	0.18	0.15	0.12	0.12	0.17	0.13
Aluminum	2.5–3.5	3.0–4.0	3.0–4.0	2.5–3.5	5.5–6.5
Vanadium	2.0–3.0	7.5–8.5	7.5–8.5	...	3.5–4.5
Tin
Ruthenium	0.04–0.06	0.04–0.06	0.04–0.06
Palladium	0.04–0.08	0.04–0.08	0.04–0.08	...	0.04–0.08
Cobalt
Molybdenum	3.5–4.5	3.5–4.5	14.0–16.0	...
Chromium	5.5–6.5	5.5–6.5
Nickel	0.4–0.6	0.4–0.6	0.4–0.6
Niobium	2.2–3.2	...
Zirconium	3.5–4.5	3.5–4.5
Silicon	0.15–0.25	...
Residuals, ^{D,E,F} max each	0.1	0.1	0.1	0.1	0.1	0.1	0.15	0.15	0.1	0.1
Residuals, ^{D,E,F} max total	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4
Titanium ^G	balance	balance	balance	balance	balance	balance	balance	balance	balance	balance