



Designation: B430 – 97 (Reapproved 2006)^{ε1}

Standard Test Method for Particle Size Distribution of Refractory Metal Powders and Related Compounds by Turbidimetry¹

This standard is issued under the fixed designation B430; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

^{ε1} NOTE—Multiple source footnotes were removed editorially in May 2006.

1. Scope

1.1 This test method covers the determination of particle size distribution of refractory metal powders with a turbidimeter (1).² Experience has shown that this test method is satisfactory for the analysis of elemental tungsten, molybdenum, rhenium, tantalum metal powders, and tungsten carbide powders. Other refractory metal powders, for example, elemental metals, carbides, and nitrides, may be analyzed using this test method with caution as to significance until actual satisfactory experience is developed. The procedure covers the determination of particle size distribution of the powder in two conditions:

1.1.1 As the powder is supplied (as-supplied), and

1.1.2 After the powder has been de-agglomerated by rod milling (laboratory milled) according to Practice B859.

1.2 Where dual units are given, inch-pound units are to be regarded as standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*³

B330 Test Method for Fisher Number of Metal Powders and Related Compounds

B821 Guide for Liquid Dispersion of Metal Powders and Related Compounds for Particle Size Analysis

¹ This test method is under the jurisdiction of ASTM Committee B09 on Metal Powders and Metal Powder Products and is the direct responsibility of Subcommittee B09.03 on Refractory Metal Powders.

Current edition approved April 1, 2006. Published May 2006. Originally approved in 1965. Last previous edition approved in 2001 as B430 – 97 (2001)^{ε1}. DOI: 10.1520/B0430-97R06E01.

² The boldface numbers in parenthesis refer to the references listed at the end of this test method.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

B859 Practice for De-Agglomeration of Refractory Metal Powders and Their Compounds Prior to Particle Size Analysis

E456 Terminology Relating to Quality and Statistics

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

2.2 *ASTM Adjunct:*⁴

Turbidimeter (6 dwgs)

3. Summary of Test Method

3.1 A uniform dispersion of the powder in a liquid medium is allowed to settle in a glass cell. A beam of light is passed through the cell at a level having a known vertical distance from the liquid level. The intensity of the light beam is determined using a photo cell. This intensity increases with time as sedimentation of the dispersion takes place.

3.2 The times at which all particles of a given size have settled below the level of the transmitted light beam are calculated from Stokes' law for the series of sizes chosen for the particle size analysis.

3.3 The intensity of the light beam at these times is measured as percent of the light transmitted through the cell with the clear liquid medium. The size distribution in the powder can be calculated from these relative intensities using the Lambert-Beer law in the modified form (also see Refs 2, 3, 4).

$$\Delta W_{1-2} = d_m (\log I_{d1} - \log I_{d2}) \quad (1)$$

where I_{d1} and I_{d2} are the intensities measured at the times when all particles having diameters larger than d_1 and d_2 respectively have settled below the level of the light beam, d_m is the arithmetic mean of particle sizes d_1 and d_2 , and ΔW_{1-2} refers to the relative weight for the particle size range between d_1 and d_2 . Values of ΔW are determined for each of the particle size ranges chosen. The sum of these values is $\Sigma \Delta W$. The weight percent of particles in the size range from d_1 to d_2 can then be calculated as:

⁴ Copies of detailed drawings of an acceptable instrument are available from ASTM International Headquarters. Order Adjunct No. ADJB0430. Original adjunct produced in 1966.

$$\text{Weight, \%} = (\Delta W_{1-2} / \Sigma \Delta W) \times 100 \quad (2)$$

4. Significance and Use

4.1 Knowledge of the particle size distribution of refractory metal powders is useful in predicting powder-processing behavior, and ultimate performance of powder metallurgy parts. Particle size distribution is closely related to the flowability, compressibility, and die-filling characteristics of a powder, as well as to the final structure and properties of the finished parts. However, the degree of correlation between the results of this test method and the quality of powders in use has not been fully determined quantitatively.

4.2 This test method is suitable for manufacturing control and research and development in the production and use of refractory metal-type powders, as indicated in 1.1.

4.3 Reported particle size measurement is a function of both the actual particle dimension and shape factor, as well as the particular physical or chemical properties being measured. Caution is required when comparing data from instruments operating on different physical or chemical parameters or with different particle size measurement ranges. Sample acquisition, handling, and preparation also can affect reported particle size results.

5. Apparatus

5.1 *Turbidimeter (5)*—The recommended instrument is one⁴ using a cell rectangular in cross section, approximately 50 mm high, 40 mm wide, and 10-mm sedimentation medium thickness, and having optically parallel faces.

5.2 *Millivolt Recorder*, 0 to 10-mV range, 10-in. (254-mm) wide strip chart, 0 to 100 graduations, 120 in./h (50 mm/min) chart speed, or microammeter with 0 to 100 graduations, 15- μ A full scale, 4.5-mV full scale.

NOTE 1—While a 120-in./h (50-mm/min) chart speed is recommended, other speeds may be satisfactory.

5.3 *Ultrasonic Cleaning Tank*, with tank dimensions approximately 5 by 5 by 3 in. (127 by 127 by 76 mm) deep and an output of 50 W, or approximately 3½ by 3½ by 2½ in. (89 by 89 by 67 mm) deep and an output of 25 W.

5.4 *Glass Vial*, nominal 2-dram, flat-bottom, with a tight-fitting cap. The vial shall be approximately 2 in. (51 mm) in height with a 5/8-in. (16-mm) outside diameter and approximately a 1/32-in. (0.8-mm) wall.

6. Reagents

6.1 *Sedimentation Medium:*

6.1.1 *Base Medium*, distilled or deionized water (see Note 4).

6.1.2 Use either one of the following as recommended in Guide B821:

6.1.2.1 *Daxad (No. 11)*—Dissolve 25 mg in 1 L of base medium.

6.1.2.2 *Sodium Hexametaphosphate*—Dissolve 0.1 g in 1 L of base medium.

NOTE 2—Use water that is pure. Do not store the sedimentation medium longer than a week, and do not use rubber tubing in any storage container. Clean thoroughly all sedimentation medium containers every week.

7. Preparation of Apparatus

7.1 Warm up equipment by turning on the light source and recorder for a minimum of 1 h prior to use.

7.2 Fill the cell with sedimentation medium to a height sufficient to cover the light beam path by at least 10 mm and place the cell in the turbidimeter (Note 3). If a microammeter is used to measure light intensity, adjust the light transmission to 100 % using the diaphragm. If a millivolt recorder is used, adjust the potentiometer so that the photovoltaic cell output is 10 mV or 100 %. In this case, the diaphragm is not adjusted and is completely open.

NOTE 3—For convenience in filling the cell to the proper height, inscribe a line on each face of the cell at the desired liquid-level height. The height of fall is usually 25 mm. To determine the location of the line, the center of the light beam path must be established and 25 mm added to this value.

7.3 After the instrument is adjusted to 100 % light transmission through the sedimentation cell and medium, move the cell carriage until light is passing through a reference glass held in another slot of the cell carriage. Read and record the percent of reference light transmission. Having been selected to have approximately 70 to 95 % of the transmission of the sedimentation cell and medium, the reference glass will indicate 100 % light transmission through the sedimentation cell when the recorder reads this value through the reference cell.

8. Calculation of Times at Which Light Intensity is Measured

8.1 The times at which the light transmission values should be read are calculated from Stokes' law. A uniform 1- μ m interval should be used in making measurements through the 10- μ m size and, depending upon the particular powder, either 1- μ m or 5- μ m intervals thereafter. The form of Stokes' law used is as follows:

$$t = (18 \times 10^8 Nh) / d^2 (\rho_x - \rho_m) g \quad (3)$$

where:

- t = time, s,
- N = viscosity of settling medium at ambient temperature, P (Note 4),
- h = height of fall, cm (distance from liquid level height to midpoint of light beam),
- d = diameter of particle, μ m (d_1 , d_2 , et al),
- ρ_x = theoretical density of the powder being tested (for tungsten, use 19.3 g/cm³),
- ρ_m = density of settling medium at ambient temperature (Note 4), and
- g = gravitational constant (980 cm/s²).

NOTE 4—The viscosity and density values at different temperatures that are used for the sedimentation medium in this procedure are the same as for pure water. Some viscosity (from the *Handbook of Chemistry and Physics*, 65th Edition, CRC Press, 1984) and density (from *Metrological Handbook 145*, NIST, 1990) values are given as follows:

Temperature, °C	Temperature, °F	Viscosity, cP	Density, g/cm ³
18	64.4	1.0530	0.9986
19	66.2	1.0270	0.9984
20	68.0	1.0020	0.9982
21	69.8	0.9779	0.9980