



Designation: C1384 – 06a

## Standard Specification for Admixtures for Masonry Mortars<sup>1</sup>

This standard is issued under the fixed designation C1384; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

### 1. Scope\*

1.1 This specification pertains to admixtures for masonry mortars. Admixtures are substances other than Specification C270 prescribed materials of water, aggregate, and cementitious materials that are used to improve one or more of the recognized desirable properties of conventional masonry mortar.

1.2 This specification does not cover coloring pigments.

NOTE 1—Information on coloring pigments can be found in Specification C979.

1.3 This specification does not cover additives that are added to the cementitious materials during the manufacture of the cementitious materials.

1.4 Acceptance of an admixture is based on its performance in an admixed mortar. Acceptance of the admixed masonry mortar is based on attainment of performance either equivalent to that required for conventional mortar or improved performance of one or more indicated properties, while maintaining required performance levels for other properties.

1.5 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

NOTE 2—The testing laboratory performing the test methods referenced in this specification should be evaluated in accordance with Practice C1093.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

C91 Specification for Masonry Cement

C144 Specification for Aggregate for Masonry Mortar

C150 Specification for Portland Cement

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C12 on Mortars and Grouts for Unit Masonry and is the direct responsibility of Subcommittee C12.03 on Specifications for Mortars.

Current edition approved May 1, 2006. Published May 2006. Originally approved in 1998. Last previous approved in 2006 as edition C1384 – 06. DOI: 10.1520/C1384-06A.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

C207 Specification for Hydrated Lime for Masonry Purposes

C270 Specification for Mortar for Unit Masonry

C305 Practice for Mechanical Mixing of Hydraulic Cement Pastes and Mortars of Plastic Consistency

C403/C403M Test Method for Time of Setting of Concrete Mixtures by Penetration Resistance

C595 Specification for Blended Hydraulic Cements

C723 Practice for Chemical-Resistant Resin Grouts for Brick or Tile

C778 Specification for Sand

C780 Test Method for Preconstruction and Construction Evaluation of Mortars for Plain and Reinforced Unit Masonry

C979 Specification for Pigments for Integrally Colored Concrete

C1093 Practice for Accreditation of Testing Agencies for Masonry

C1152/C1152M Test Method for Acid-Soluble Chloride in Mortar and Concrete

C1157 Performance Specification for Hydraulic Cement

C1218/C1218M Test Method for Water-Soluble Chloride in Mortar and Concrete

C1329 Specification for Mortar Cement

C1357 Test Methods for Evaluating Masonry Bond Strength

C1403 Test Method for Rate of Water Absorption of Masonry Mortars

C1437 Test Method for Flow of Hydraulic Cement Mortar

### 3. Terminology

#### 3.1 Definitions of Terms Specific to This Standard:

3.1.1 *admixed mortar, n*—masonry mortar that deviates from those combinations of materials recognized by Specification C270 in that it also contains an admixture.

3.1.2 *admixture, n*—substance other than the Specification C270 prescribed materials of water, aggregate, and cementitious materials that is added to a masonry mortar to modify one or more properties of the conventional masonry mortar.

3.1.3 *bond enhancer, n*—admixture used to increase the bond strength between the masonry mortar and the masonry unit.

\*A Summary of Changes section appears at the end of this standard

3.1.4 *reference mortar, n*—mortar of the same composition as an admixed mortar except that the reference mortar does not include the admixture and may contain a different amount of water to obtain an equivalent flow or penetration as the admixed mortar.

3.1.5 *set accelerator, n*—admixture used to shorten the time of setting of a masonry mortar.

3.1.6 *set retarder, n*—admixture used to lengthen the time of setting of a masonry mortar.

3.1.7 *water repellent, n*—admixture used to decrease the rate of water absorption of the hardened masonry mortar.

3.1.8 *workability enhancer, n*—admixture used in a masonry mortar to increase the ease of being worked and used.

3.1.8.1 *Discussion*—Workability is a combination of several properties, including: plasticity, consistency, cohesion, adhesion, water retentivity, setting characteristics, and its capacity to remain satisfactory under the influence of masonry unit suction and ambient environmental conditions. Many of these properties have defied exact laboratory measurement. The mason can best assess workability by observing the response of the mortar to the trowel and the masonry unit. For further discussion on workability, see the Appendix of Specification C270.

#### 4. Classification

4.1 Admixtures are classified by their effect on the performance characteristics of conventional masonry mortars. Admixed mortars are classified by their modified properties, as compared to a reference mortar. The following classifications are recognized:

- 4.1.1 Bond Enhancer.
- 4.1.2 Workability Enhancer.
- 4.1.3 Set Accelerator.
- 4.1.4 Set Retarder.
- 4.1.5 Water Repellent.

#### 5. Materials

5.1 *Cements*—The cement used in the evaluation of the admixture shall conform to applicable requirements specified in 5.1.1-5.1.5.

5.1.1 *Cement, Portland*—When the admixture is evaluated in a mortar containing portland cement, the portland cement shall conform to the requirements for Type I, IA, II, IIA, III, or IIIA of Specification C150.

5.1.2 *Cement, Blended Hydraulic*—When the admixture is evaluated in a mortar containing blended hydraulic cement, the blended hydraulic cement shall conform to the requirements for Type IS, IS-A, IP, IP-A, I(PM) or I(PM)-A of Specification C595.

5.1.3 *Cement, Hydraulic*—When the admixture is evaluated in a mortar containing a hydraulic cement, the hydraulic cement shall conform to the requirements for Type GU, HE, MS, HS, MH, or LH of Specification C1157.

5.1.4 *Cement, Masonry*—When the admixture is evaluated in a mortar containing a masonry cement, the masonry cement shall conform to the requirements of Specification C91.

5.1.5 *Cement, Mortar*—When the admixture is evaluated in a mortar containing a mortar cement, the mortar cement shall conform to the requirements of Specification C1329.

5.2 *Lime*—When the admixture is evaluated in a cement-lime mortar, the hydrated lime shall conform to Specification C207.

5.3 *Sand*—The fine aggregate used in the tests will vary dependent on the test procedure.

5.3.1 Sands used for soluble chloride, flexural bond strength and rate of water absorption tests shall be a blend of equal parts by weight of graded standard sand and standard 20-30 sand conforming with Specification C778.

5.3.2 Sands used for compressive strength, water retention, determination of air content of plastic mortar, board life, and time of setting tests shall conform to the requirements of Specification C144.

#### 6. Chemical Composition

6.1 The admixture shall not react adversely with embedded or attached materials common to masonry.

NOTE 3—Currently, there is no standard test method for determining the corrosion potential of masonry mortars toward embedded and attached materials. Nonetheless, the admixture shall not be offered for sale if the manufacturer has evidence that the admixture does react adversely with embedded or attached materials common to masonry.

6.2 At the maximum recommended dosage, the mortar admixture shall add not more than 65 ppm (0.0065 %) water-soluble chloride, or 90 ppm (0.0090 %) acid-soluble chloride to the mortar's overall chloride content as determined by testing of the reference and admixed mortars in accordance with 9.1.1.

#### 7. Physical Properties

7.1 All modified masonry mortars shall comply with the property specification requirements of Specification C270. In addition, the admixed mortars shall conform to all of the specific classification requirements in Table 1 for which the admixture is obtaining qualification. Unless more specimens are required by a specific test method, a minimum of three specimens shall be tested and the results averaged. These result averages shall meet the requirements of this section.

7.2 Admixture compliance tests shall be the responsibility of the manufacturer of the admixture. These compliance tests shall be completed within the past five (5) years and prior to any admixture composition change.

#### 8. Mortar Types and Proportions

8.1 Design the reference mortar to be a specific type of cement/lime, mortar cement, or masonry cement mortar in conformance with the proportion specification of Specification C270 except that the aggregate ratio shall be fixed at three times the sum of the separate volumes of cementitious materials. In addition, the aggregate shall meet the requirements in 5.3.

8.2 The corresponding admixed mortars shall have the same composition as the reference mortars but also shall include the admixture, and the water content shall be adjusted to yield the