

SLOVENSKI STANDARD SIST EN 60249-2-3:1997

01-avgust-1997

Base materials for printed circuits - Part 2: Specifications - Specification No.3: Epoxide cellulose paper copper-clad laminated sheet of defined flammability (vertical burning test) (IEC 249-2-3:1987 + A1:1989)

Base materials for printed circuits -- Part 2: Specifications -- Specification No. 3: Epoxide cellulose paper copper-clad laminated sheet of defined flammability (vertical burning test)

Basismaterialien für gedruckte Schaltungen -- Teil 2: Einzelbestimmungen -- Einzelbestimmung Nr. 3: Kupferkaschierte Epoxidharz-Hartpapiertafeln definierter Brennbarkeit (Brennprüfung mit vertikaler Probenlage). 21

Matériaux de base pour circuits imprimés : Partie 2: Spécifications 58 Spécification n° 3: Feuille de papier cellulose phénolique époxyde recouverte de cuivre, d'inflammabilité définie (essai de combustion verticale)

Ta slovenski standard je istoveten z: EN 60249-2-3:1994

ICS:

13.220.40 Sposobnost vžiga in Ignitability and burning

obnašanje materialov in behaviour of materials and

proizvodov pri gorenju products

31.180 Tiskana vezja (TIV) in tiskane Printed circuits and boards

plošče

SIST EN 60249-2-3:1997 en

SIST EN 60249-2-3:1997

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 60249-2-3:1997 https://standards.iteh.ai/catalog/standards/sist/3e59b15c-9bc1-408a-bb82-5439362cef10/sist-en-60249-2-3-1997 EUROPEAN STANDARD

EN 60249-2-3

NORME EUROPEENNE

EUROPÄISCHE NORM

February 1994

UDC 621.3.049.75-035.4

Supersedes HD 313.2.3 S2:1990

Descriptors: Printed circuit, composite materials, paper, copper, flammability

ENGLISH VERSION

Base materials for printed circuits
Part 2: Specifications
Specification No. 3: Epoxide cellulose paper
copper-clad laminated sheet of defined
flammability (vertical burning test)
(IEC 249-2-3:1987 + A1:1989)

Matériaux de base pour circuits imprimés
Partie 2: Spécifications
Spécification n° 3: Feuille de papier cellulose époxyde recouverte de cuivre, d'inflammabilité définie (essai de combustion verticale)

Basismaterialien für gedruckte Schaltungen Teil 2: Einzelbestimmungen Einzelbestimmung Nr. 3: Kupferkaschierte Epoxidharz-Hartpapiertafeln definierter Brennbarkeit (Brennprüfung mit vertikaler Probenlage)

(CEI 249-2-3:1987 + A1:1989)

(IEC 249-2-3:1987 + A1:1989)

indards.iteh.ai

This European Standard was approved by CENEUEC on 1993-12-08. CENEUEC members are bound to comply with the CENEUEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization Comité Européen de Normalisation Electrotechnique Europaisches Komitee für Elektrotechnische Normung

Central Secretariat: rue de Stassart 35, 8-1050 Brussels

Page 2 EN 60249-2-3:1994

FOREWORD

At the request of CENELEC 74th Technical Board, HD 313.2.3 S2:1990 (IEC 249-2-3:1987 + A1:1989) was submitted to the CENELEC voting procedure for conversion into a European Standard.

The text of the International Standard was approved by CENELEC as EN 60249-2-3 on 8 December 1993.

The following dates were fixed:

- latest date of publication of an identical national standard
- (dop) 1995-03-15
- latest date of withdrawal of conflicting national standards

(dow)

Annexes designated "normative" are part of the body of the standard. In this standard, annex ZA is normative.

iTeh STANDARD PREVIEW

ENDORSEMENT NOTICE (standards.iten.ai)

The text of the International Standard TEC 249-2-3:1987 and its amendment 1:1989 was approved by a CENELEC 9 as a beuropean 2 Standard without any modification 362 cefl 0/sist-en-60249-2-3-1997



ANNEX ZA (normative)

OTHER INTERNATIONAL PUBLICATIONS QUOTED IN THIS STANDARD WITH THE REFERENCES OF THE RELEVANT EUROPEAN PUBLICATIONS

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

NOTE: When the international publication has been modified by CENELEC common modifications, indicated by (mod), the relevant EN/HD applies.

IEC Publication	Date	Title	EN/HD	Date
249-1	1982	Base materials for printed circuits Part 1: Test methods	EN 60249-1*	1993
249-3A	1976	Part 3: Special materials used in connection with printed circuits First supplement: Specification No. 2: Specification for copper foil for use in the manufacture of copper-clad base materials Standards. Item.	-	-

<u>SIST EN 60249-2-3:1997</u> https://standards.iteh.ai/catalog/standards/sist/3e59b15c-9bc1-408a-bb82-5439362cef10/sist-en-60249-2-3-1997


^{*} EN 60249-1 includes A1:1984 + A2:1989 + A3:1991 to IEC 249-1

SIST EN 60249-2-3:1997

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 60249-2-3:1997 https://standards.iteh.ai/catalog/standards/sist/3e59b15c-9bc1-408a-bb82-5439362cef10/sist-en-60249-2-3-1997

NORME INTERNATIONALE INTERNATIONAL STANDARD



Matériaux de base pour circuits imprimés

Deuxième partie: Spécifications

Spécification n° 3: Feuille de papier cellulose époxyde recouverte de cuivre,

d'inflammabilité définie (essai de combustion verticale) **iTeh STANDARD**

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST EN 60249-2-3:1997</u> https://standards.iteh.ai/catalog/standards/sist/3e59b15c-9bc1-408a-bb82-5439362cef10/sist-en-60249-2-3-1997

Base materials for printed circuits

Part 2: Specifications
Specification No. 3: Epoxide cellulose paper copper-clad laminated sheet of defined flammability (vertical burning test)

CEI IEC 249-2-3

Deuxième édition Second edition 1987

CONTENTS

Fo	DEWORD	Page
	DREWORD	4
PR	REFACE	-
٥.		5
	1456	
1.	Scope	
2.	Scope	7
4.	Internal marking Electrical properties Non-electrical properties of the copper all 1.1.	7
5.	Non-electrical properties of the copper-clad sheet.	9
5.	Non-electrical properties of the topped-clad sneet	9
	Non-electrical properties of the base material after complete removal of the copper foil.	19
7.	Packaging and marking	
3.	Packaging and marking	21
	Acceptance testing	23

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST EN 60249-2-3:1997</u> https://standards.iteh.ai/catalog/standards/sist/3e59b15c-9bc1-408a-bb82-5439362cef10/sist-en-60249-2-3-1997

INTERNATIONAL ELECTROTECHNICAL COMMISSION

BASE MATERIALS FOR PRINTED CIRCUITS

Part 2: Specifications Specification No. 3: Epoxide cellulose paper copper-clad laminated sheet of defined flammability (vertical burning test)

FOREWORD

- 1) The formal decisions or agreements of the IEC on technical matters, prepared by Technical Committees on which all the National Committees having a special interest therein are represented, express, as nearly as possible, an international consensus of opinion on the subjects dealt with.
- 2) They have the form of recommendations for international use and they are accepted by the National Committees in that
- 3) In order to promote international unification, the IEC expresses the wish that all National Committees should adopt the text of the IEC recommendation for their national rules in so far as national conditions will permit. Any divergence between the IEC recommendation and the corresponding national rules should, as far as possible, be clearly indicated in
- 4) The IEC has not laid down any procedure concerning marking as an indication of approval and has no responsibility when an item of equipment is declared to comply with one of its recommendations.

PREFACE 1997

tps://standards.iteh.ai/catalog/standards/sist/3e59b15c-9bc1-408a-bb82-

This standard has been prepared by IEC Technical Committee No. 52: Printed Circuits.

This second edition replaces the first edition of Specification No. 3 which was included in IEC Publication 249-2.

This standard forms Specification No. 3 of a publication series which will replace the specifications originally included in IEC Publication 249-2 and will also include new specifications.

The text of this standard is based on the following documents:

Six Months' Rule Report on Voting		Two Months' Procedure Report on Voting		
52(CO)238	52(CO)267	52(CO)253	52(CO)281	

Further information can be found in the relevant Reports on Voting indicated in the table above.

The following IEC publications are quoted in this standard:

Publications Nos. 249-1 (1982): Base Materials for Printed Circuits, Part 1: Test Methods.

249-3A (1976): Part 3: Special Materials Used in Connection with Printed Circuits. First supplement: Specification No. 2: Specification for Copper Foil for Use in the Manufacture of Copper-clad Base Materials.

BASE MATERIALS FOR PRINTED CIRCUITS

Part 2: Specifications
Specification No. 3: Epoxide cellulose paper copper-clad laminated sheet
of defined flammability
(vertical burning test)

1. Scope

This specification gives requirements for properties of epoxide cellulose paper copper-clad laminated sheet, of defined flammability, in thicknesses of 0.5 mm up to 6.4 mm.

Note. — To designate this material, the reference: 249-2-3-FV*-IEC-EP-CP-Cu may be used; if there is no risk of confusion, the type designation may be abbreviated to read IEC-249-2-3-FV*.

2. Materials and construction

The sheet consists of an insulating base with metal foil bonded to one or both sides.

2.1 Insulating base

Epoxide resin bonded cellulose paper laminate. Its flame resistance is defined in terms of the flammability requirements of Sub-clause 6.3.

2.2 Metal foil

(standards.iteh.ai)

Copper as specified in IEC Publication 249-3A: First Supplement to Publication 249-3: Base Materials for Printed Circuits Part 3: Special Materials Used in Connection with Printed Circuits Specification to 2. Specification for Copper Foil for Use in the Manufacture of Copper-clad Base Materials.

The preferred foils are Type A (electro-deposited copper) of standard ductility.

3. Internal marking

Each sheet should bear a manufacturer's identification mark that is:

- a) in red, to indicate that the material is of defined flammability;
- b) repeated at intervals so that no part of the sheet is further than 75 mm (3 in) from the furthest point of the nearest mark;
- c) printed so as to indicate the machine direction of the filling material; if letters or numbers are used, these shall be upright in the machine direction.

Examples:

A	Α	Α	Α	Α
Α	Α	Α	Α	Α
A	Α	Α	Α	Α
Α	Α	Α	Α	Α
Α	Α	Α	Α	Α
<u></u>				

fachine direction	/
Ma	1

_						
	12	12	12	12	12	
	12	12	12	12	12	
	12	12	12	12	12	
	12	12	12	12	12	
	12	12	12	12	12	

^{* 0} or 1, see Sub-clause 6.3.

4. Electrical properties

TABLE I

Property	Test method (Sub-clause of IEC Publication 249-1)*	Requirement
Resistance of foil	2.1	As specified in IEC Publication 249-3A
Surface resistance while in the humidity chamber (optional)	2.2	2 000 MΩ min.
Surface resistance after recovery	2.2	20 000 MΩ min.
Volume resistivity while in the humidity chamber (optional)	2.3	800 MΩm min.
Volume resistivity after recovery	2.3	2 000 MΩm min.
Surface corrosion	2.4	No visible corrosion products in the gap
Corrosion at the edge	2.5	Positive pole: not worse than A/B Negative pole: not worse than 1.6
Relative permittivity after damp heat and recovery	NDARD PRE	The average value shall not exceed 5.0
Dielectric dissipation factor after dampleat and recovery	ndard&iteh.ai)	The average value shall not exceed 0.05
Surface resistance at 100°C	IST EN 60249 ₉ 2-3:1997 talog/standards/sist/3e59b15c-9	1 000 MΩ min.
Volume and in 10000	2cef10/sist-er 2.9 0249-2-3-1997	100 MΩm min.

^{*} Base Materials for Printed Circuits, Part 1: Test Methods.

5. Non-electrical properties of the copper-clad sheet

5.1 Appearance of the copper-clad face

5.1.1 Normal surface finish

The copper-clad face shall be substantially free from blisters, wrinkles, pinholes, deep scratches, pits and resin. Any discoloration or contamination shall be readily removable with a hydrochloric acid solution of density 1.02 g/cm³ or with a suitable organic solvent.

5.1.2 High-quality surface finish (optional)

If a surface of high quality is essential for precious metal plating or fine line etching and is ordered by the purchaser, the following requirements shall apply in addition to those of Subclause 5.1.1 when inspected in accordance with Sub-clause 3.9 of IEC Publication 249-1.

The surface finish of the copper-clad face shall be such as not to conceal imperfections.

The surface of the copper foil shall be free from scratches of depth greater than 0.010 mm (0.0004 in), or $\frac{1}{5}$ of the nominal thickness of the copper foil, whichever is the lower.