



Designation: D3644 – 06

Standard Test Method for Acid Number of Styrene-Maleic Anhydride Resins¹

This standard is issued under the fixed designation D3644; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the measurement of the free acidity present in styrene-maleic anhydride resins.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D329 Specification for Acetone

D1193 Specification for Reagent Water

3. Terminology

3.1 *Definitions:*

3.1.1 *acid number*—the number of milligrams of potassium hydroxide (KOH) required to neutralize the alkali-reactive groups in 1 g of material under the conditions of test.

4. Significance and Use

4.1 This test method is used to determine the property of styrene-maleic anhydride resins functionality. Acid functionality determines the utility of resin as well as being a significant quality control test.

5. Reagents and Materials

5.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society,

where such specifications are available.³ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

5.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water conforming to Specification D1193.

5.3 *Acetone*, conforming to the requirements described in Specification D329.

5.4 *Phenolphthalein Indicator Solution (20 g/L)*—Dissolve 10 g of phenolphthalein in 100 mL of acetone.

5.5 *Sodium Hydroxide, Standard Solution (0.1 N)*—Dissolve 7 g of sodium hydroxide (NaOH) in 7 mL of water, and filter the resulting solution through a glass mat in a Gooch crucible with the aid of suction. Do not wash the residue. Dilute two thirds of the clear filtrate to 1 L with freshly boiled water. Standardize against National Institute of Standards and Technology standard sample of acid potassium phthalate No. 84, using phenolphthalein as the indicator. Do not adjust the concentration of the solution, but calculate the normality.

5.6 *Sulfuric Acid, Standard Solution (0.1 N)*—Measure out 3 mL of concentrated sulfuric acid (H_2SO_4) ($d = 1.84$) and pour it slowly, and with constant stirring, into about 100 mL of water. Cool to room temperature, mix thoroughly, and dilute to 1 L. Standardize against 0.1 N NaOH solution, as prepared in 4.5, using phenolphthalein as the indicator. Do not adjust the concentration of the solution, but calculate the normality.

6. Procedure

6.1 Weigh 0.1 g of the sample to the nearest 0.0001 g into a 250-mL Erlenmeyer flask.

6.2 Add 150 ± 2 mL of acetone to the flask, stopper it, and swirl it until the sample is dissolved. Add 0.2 mL of phenolphthalein indicator solution and titrate with NaOH solution to the end point, a faint pink color which persists for 30 s. Then

¹ This test method is under the jurisdiction of ASTM Committee D21 on Polishes and is the direct responsibility of Subcommittee D21.02 on Raw Materials.

Current edition approved June 1, 2006. Published June 2006. Originally approved in 1983. Last previous edition approved in 2004 as D3644 – 98(2004). DOI: 10.1520/D3644-06.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.