

INTERNATIONAL STANDARD

NORME INTERNATIONALE



**Plastic films for electrical purposes –
Part 3: Specifications for individual materials – Sheet 1: Biaxially oriented
polypropylene (PP) films for capacitors**

**Films plastiques à usages électriques –
Partie 3: Spécifications pour matériaux particuliers – Feuille 1: Films de
polypropylène biorienté (PP) pour condensateurs**

<https://standards.iteh.ai/catalog/standards/iec/5881e7a5-13a6-471b-b763-16ca03df2ec0/iec-60674-3-1-1998>



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2011 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland
Email: inmail@iec.ch
Web: www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: www.iec.ch/searchpub

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

- IEC Just Published: www.iec.ch/online_news/justpub

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

- Electropedia: www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

- Customer Service Centre: www.iec.ch/webstore/custserv

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: csc@iec.ch

Tel.: +41 22 919 02 11

Fax: +41 22 919 03 00

A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

- Catalogue des publications de la CEI: www.iec.ch/searchpub/cur_fut-f.htm

Le Catalogue en-ligne de la CEI vous permet d'effectuer des recherches en utilisant différents critères (numéro de référence, texte, comité d'études,...). Il donne aussi des informations sur les projets et les publications retirées ou remplacées.

- Just Published CEI: www.iec.ch/online_news/justpub

Restez informé sur les nouvelles publications de la CEI. Just Published détaille deux fois par mois les nouvelles publications parues. Disponible en-ligne et aussi par email.

- Electropedia: www.electropedia.org

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 20 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International en ligne.

- Service Clients: www.iec.ch/webstore/custserv/custserv_entry-f.htm

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions, visitez le FAQ du Service clients ou contactez-nous:

Email: csc@iec.ch

Tél.: +41 22 919 02 11

Fax: +41 22 919 03 00

INTERNATIONAL STANDARD

NORME INTERNATIONALE



**Plastic films for electrical purposes –
Part 3: Specifications for individual materials – Sheet 1: Biaxially oriented
polypropylene (PP) films for capacitors**

**Films plastiques à usages électriques –
Partie 3: Spécifications pour matériaux particuliers – Feuille 1: Films de
polypropylène biorienté (PP) pour condensateurs**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 General.....	6
1.1 Scope.....	6
1.2 Normative references.....	6
1.3 Classification.....	6
2 Designation.....	7
3 General requirements.....	7
4 Dimensions.....	7
4.1 Thickness.....	7
4.2 Width.....	8
4.3 Length/diameter.....	8
5 Properties.....	8
5.1 Physical properties.....	8
5.2 Electric strength (d.c. test).....	10
5.3 Electrical weak spots.....	10
5.4 Thermal endurance.....	11
5.5 Wetting tension (types 1b + 1c, 2b + 2c and 3b + 3c only).....	11
5.6 Liquid absorption.....	11
5.7 Compatibility with impregnants.....	12
5.8 Dissipation factor under impregnated conditions.....	12
5.9 Space factor.....	12
6 Roll characteristics.....	12
6.1 Windability.....	12
6.2 Joins.....	13
6.3 Roll width (overall width).....	13
6.4 Core.....	13
6.5 Labelling.....	13
Table 1 – Physical properties.....	9
Table 2 – Electric strength (d.c. test) for types 1, 2 and 3.....	10
Table 3 – Electrical weak spots for types 1, 2 and 3.....	11
Table 4 – Maximum number of joins within a roll (types 1, 2 and 3).....	13

INTERNATIONAL ELECTROTECHNICAL COMMISSION

PLASTIC FILMS FOR ELECTRICAL PURPOSES –

**Part 3: Specifications for individual materials –
Sheet 1: Biaxially oriented polypropylene (PP) films for capacitors**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This consolidated version of IEC 60674-3-1 consists of the first edition (1998) [documents 15C/862/FDIS and 15C/952/RVD] and its amendment 1 (2011) [documents 15/596/CDV and 15/609/RVC]. It bears the edition number 1.1.

The technical content is therefore identical to the base edition and its amendment and has been prepared for user convenience. A vertical line in the margin shows where the base publication has been modified by amendment 1. Additions and deletions are displayed in red, with deletions being struck through.

International Standard IEC 60674-3-1 has been prepared by subcommittee 15C: Specifications, of IEC technical committee 15: Insulating materials.

The committee has decided that the contents of the base publication and its amendments will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The “colour inside” logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this publication using a colour printer.

iTech Standards
(<https://standards.itih.ai>)
Document Preview

[IEC 60674-3-1:1998](https://standards.itih.ai/standards/iec/5881e7a5-13a6-471b-b763-16ca03df2ec0/iec-60674-3-1-1998)

<https://standards.itih.ai/standards/iec/5881e7a5-13a6-471b-b763-16ca03df2ec0/iec-60674-3-1-1998>

WITHDRAWN

INTRODUCTION

This International Standard is one of a series which deals with plastic films for electrical purposes.

The series consists of three parts.

- Part 1: Definitions and general requirements (IEC 60674-1).
- Part 2: Methods of test (IEC 60674-2).
- Part 3: Specifications for individual materials (IEC 60674-3).

This standard contains one of the sheets comprising part 3, as follows:

Sheet 1: Biaxially oriented (PP) polypropylene films for capacitors.

Withheld

iTech Standards
(<https://standards.itih.ai>)
Document Preview

<https://standards.itih.ai/standards/iec/5881e7a5-13a6-471b-b763-16ca03df2ec0/iec-60674-3-1-1998>

PLASTIC FILMS FOR ELECTRICAL PURPOSES –

Part 3: Specifications for individual materials – Sheet 1: Biaxially oriented polypropylene (PP) films for capacitors

1 General

1.1 Scope

This sheet of IEC 60674-3 gives the requirements for biaxially oriented polypropylene film having a smooth or rough surface, corona treated when required for vacuum metallization. The films are for use as dielectric in capacitors.

Materials which conform to this specification meet established levels of performance. However, the selection of a material by a user for a specific application should be based on the actual requirements necessary for adequate performance in that application and not based on this specification alone.

Safety warning: It is the responsibility of the user of the methods contained or referred to in this document to ensure that they are used in a safe manner.

1.2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this sheet of IEC 60674-3. At the time of publication, the editions indicated were valid. All normative documents are subject to revision, and parties to agreement based on this sheet of IEC 60674-3 are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below ¹⁾. Members of IEC and ISO maintain registers of currently valid International Standards.

IEC 60674-1:1980, *Specification for plastic films for electrical purposes – Part 1: Definitions and general requirements*

IEC 60674-2:1988, *Specification for plastic films for electrical purposes – Part 2: Methods of test*

IEC 61074:1991, *Determination of heats and temperatures of melting and crystallization of electrically insulating materials by differential scanning calorimetry*

ISO 534:1988, *Paper and board – Determination of thickness and apparent bulk density or apparent sheet density*

ISO 11357-3, *Plastics – Differential scanning calorimetry (DSC) – Part 3: Determination of temperature and enthalpy of melting and crystallization*

1.3 Classification

The polypropylene film shall be of the following types:

Type 1: having smooth surfaces (space factor <5 %, see 5.9);

Type 1a: not corona treated;

¹⁾ In case of dispute, the referenced edition is applicable.

- Type 1b: one side pre-treated to facilitate the vacuum deposition of metal;
Type 1c: both sides pre-treated;
Type 2: having at least one rough surface (space factor $\geq 5\%$, voir 5.9);
Type 2a: not corona treated;
Type 2b: one side pre-treated to facilitate the vacuum deposition of metal;
Type 2c: both sides pre-treated.
Type 3: having high electric strength for thin film (film thickness $\leq 3,5\ \mu\text{m}$);
Type 3a: not corona treated;
Type 3b: one side pre-treated to facilitate the vacuum deposition of metal;
Type 3c: both sides pre-treated.

2 Designation

The plastic film shall be identified by the following designation:

Designation of the film - IEC 60674-3-1 - PP - type - thickness in micrometres - width in millimetres - length in metres.

EXAMPLE

Polypropylene film - IEC 60674-3-1 - PP - 1a - 6 - 100 - 3000.

3 General requirements

The materials shall be made essentially from isotactic type polypropylene homopolymer and shall conform to the requirements laid down in IEC 60674-1.

4 Dimensions

4.1 Thickness

The film thickness shall be measured in accordance with the requirements of 3.3 of IEC 60674-2. This is in general the gravimetric thickness, but for type 2 distinction shall be made between thickness determined by weighing (t_g = gravimetric thickness) and thickness measured by micrometer method (t_b = bulking thickness).

Gravimetric thickness shall be measured in accordance with the requirements of 3.3 of IEC 60674-2.

Bulking (micrometric) thickness shall be measured in accordance with ISO 534, except that the four test pieces are initially made up of 12 film layers, the layers being cut together using a suitable template (preferably 250 mm \times 200 mm, the 200 mm dimension being in the machine direction) from a blanket of film about 0,5 mm thick taken from the outer surface of the roll being sampled. Discard the first and last layer of each pack or test piece just prior to imposing the pack between the open pressure faces of the micrometer.

There are no requirements for thickness in this standard but preferred gravimetric thicknesses are as follows:

Type 1: 4,0; 5,0; 6,0; 7,0; 8,0; 10,0; 12,0; 15,0; 18,0; 20,0 and 25 μm .

Type 2: 7,4; 9,0; 10,1; 11,0; 12,0; 12,7; 13,6; 14,4; 15,2; 16,2 and 17,8 μm .

Type 3: 2,5; 2,8; 3,0 and 3,5 μm .

The thickness tolerance shall comply with the requirements of IEC 60674-1 unless otherwise specified.

4.2 Width

The film width shall be measured in accordance with the requirements of clause 5 of IEC 60674-2.

Preferred widths cannot be given on account of the great variety of applications and different requirements throughout the capacitor industry.

The tolerance on the width shall comply with the requirements of 4.2 of IEC 60674-1.

4.3 Length/diameter

There are no requirements in this standard for length or diameters of rolls. These should be subject to purchase contract.

5 Properties

5.1 Physical properties

See table 1.

IEC 60674-3-1:1998

<https://standards.iteh.ai/standards/iec/5881e7a5-13a6-471b-b763-16ca03df2ec0/iec-60674-3-1-1998>

Table 1 – Physical properties

Property	Test method	Unit	Requirement	Remarks
Density	IEC 60674-2, clause 4, method D	Mg/m ³	0,91 ± 0,01	This method is only suitable for film thickness >12 µm. The recommended mixture is methanol/ethylene glycol
Melting point	IEC 61074 ISO 11357-3	°C	165 to 175	DSC method
Tensile strength (either direction)	IEC 60674-2, clause 10	MPa	Minimum Type 1: 120 Type 2: 90	Specimen width (15 ± 3) mm, rate of extension (100 ± 2) mm/min, reference lines with the initial grip separation (100 ± 2) mm apart
Elongation at break (either direction)		%	Minimum Type 1: 40 Type 2: 30 Type 3: 30	
Surface resistivity	IEC 60674-2, clause 14 ¹⁾	Ω	≥10 ¹⁴	
Volume resistivity	IEC 60674-2, clause 15 ¹⁾	Ωm	>10 ¹⁵	The test voltages are (100 ± 10) V for thicknesses >10 µm and (10 ± 1) V for thicknesses ≤10 µm
Dissipation factor at 23 °C and 48 Hz – 62 Hz: 1 kHz:	IEC 60674-2, subclause 16.1 or 16.2		≤3 × 10 ⁻⁴ ≤3 × 10 ⁻⁴	Use non-contacting electrodes or evaporated metal electrodes (subclause 16.1)
Permittivity	IEC 60674-2, subclause 16.1		2,2 ± 0,1	Use non-contacting electrodes or evaporated metal electrodes (subclause 16.1)
Dimensional change for shrinkage: – Machine direction – Transverse direction	IEC 60674-2, clause 23	% %		Shrinkage shall be agreed between buyer and seller
NOTE Although the potential effects of certain properties such as crystallinity, orientation and isotactic/ atactic content on the performance of the film are recognized, no recommendations regarding the determination of these parameters have been made, particularly as no suitable test methods are available in IEC 60674-2.				
¹⁾ Measurement conditions: (23 ± 2) °C and (50 ± 5) % relative humidity after at least 24 h exposure.				