



Designation: D 1073 – 06

Standard Specification for Fine Aggregate for Bituminous Paving Mixtures¹

This standard is issued under the fixed designation D 1073; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers fine aggregate for use in bituminous paving mixtures.

1.2 This specification is intended to describe material from a single source. When material from two or more sources is to be blended to produce a grading to meet requirements as described in Specification D 3515 or other specifications for bituminous paving mixtures, the grading requirements of Table 1 of this specification are not applicable.

NOTE 1—When obtaining materials from two or more sources that are to be blended to produce the final mix, it is recommended that the specifying or the ordering agency specify the alternative gradings and blend ratios to be supplied.

1.3 The values stated in SI units are to be regarded as standard. Inch-pound units, shown in parentheses, are for information only.

1.4 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

2. Referenced Documents

2.1 *ASTM Standards:*²

C 88 Test Method for Soundness of Aggregates by Use of Sodium Sulfate or Magnesium Sulfate

C 117 Test Method for Materials Finer than 75- μ m (No. 200) Sieve in Mineral Aggregates by Washing

C 125 Terminology Relating to Concrete and Concrete Aggregates

C 136 Test Method for Sieve Analysis of Fine and Coarse Aggregates

C 294 Descriptive Nomenclature for Constituents of Concrete Aggregates

D 8 Terminology Relating to Materials for Roads and Pavements

D 75 Practice for Sampling Aggregates

D 3515 Specification for Hot-Mixed, Hot-Laid Bituminous Paving Mixtures

D 3665 Practice for Random Sampling of Construction Materials

D 4318 Test Methods for Liquid Limit, Plastic Limit, and Plasticity Index of Soils

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

3. Terminology

3.1 *Definitions:*

3.1.1 For defining aggregate types, see Descriptive Nomenclature C 294, and Terminology D 8 and C 125.

3.1.2 *expanded shale, n; expanded clay, n; expanded slate, n;* the product resulting from the expanding of selected materials (shale, clay, or slate) in a rotary kiln at temperatures over 1000°C.

4. Ordering Information

4.1 Orders for material under this specification shall include the following:

4.1.1 This specification designation including year,

4.1.2 Grading (6.2 and Table 1), or alternative grading designated by the purchaser,

4.1.3 Supplementary requirement for sulfate soundness, if required, including salt to be used (See S1), and

4.1.4 Any exceptions or additions to this specification.

5. General Characteristics

5.1 Fine aggregate is aggregate passing the 9.5-mm ($\frac{3}{8}$ -in.) sieve and almost entirely passing the 4.75-mm (No. 4) sieve. It shall consist of natural sand; or of manufactured fine aggregate

¹ This specification is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.50 on Aggregate Specifications.

Current edition approved June 1, 2006. Published June 2006. Originally approved in 1949. Last previous edition approved in 2001 as D 1073 – 01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.