



Standard Specification for Track-Resistant Black Crosslinked Polyethylene Insulation for Wire and Cable, 90°C Operation¹

This standard is issued under the fixed designation D 3555; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope *

1.1 This specification covers a track-resistant black crosslinked polyethylene insulation, the base polymer which consists substantially of polyethylene or its copolymers. This insulation shall be carbon black pigmented.

1.2 This type of insulation is considered suitable for use on wire or cable that will be used for continuous operation at conductor temperatures up to 90°C.

1.3 This insulation is suitable for use on wire or in cable used for power transmission in overhead spaced-line service, installed at temperatures above -25° and exposed to sunlight and other atmospheric environments between -55 and $+90^{\circ}\text{C}$.

1.4 In many instances, the insulation cannot be tested unless it has been formed around a conductor. Therefore, tests are done on insulated wire in this standard solely to determine the relevant property of the insulation and not to test the conductor or completed cable.

1.5 Whenever two sets of values are presented, in different units, the values in the first set are the standard, while those in parentheses are for information only.

2. Referenced Documents

2.1 ASTM Standards:

D 470 Test Methods for Crosslinked Insulations and Jackets for Wire and Cable²

D 1711 Terminology Relating to Electrical Insulation²

D 2132 Test Method for Dust-and-Fog Tracking and Erosion Resistance of Electrical Insulating Materials²

D 2765 Test Methods for Determination of Gel Content and Swell Ratio of Crosslinked Ethylene Plastics³

2.2 ICEA Standard:

ICEA T-28-562 Test Method for Measurement of Hot Creep of Polymeric Insulations⁴

3. Terminology

3.1 *Definitions:* For definitions of terms used in this specification refer to Terminology D 1711.

3.2 Definition of Term Specific to This Standard:

3.2.1 *aging, (act of), n*—exposure of materials to air at a temperature of 121°C for 168 h.

4. Physical Properties

4.1 When tested for physical and aging requirements, heat distortion, cold bend, U-bend discharge, surface resistivity, and track resistance in accordance with Test Methods D 470, the track-resistant black crosslinked polyethylene insulation shall meet the requirements specified in Table 1. The insulation is to meet the requirements for percent hot creep and hot set specified in Table 1. The test is to be performed in accordance with ICEA T-28-562. Only in case of dispute, the solvent extraction (gel content and swell ratio) test in Test Methods D 2765 is to be the referee method. The extractables, after a drying time of 20 h, shall be no more than 30 %.

5. Electrical Requirements

5.1 Subject cable specimens to a 5 min ac or dc voltage withstand test at voltages which are based on the nominal thickness of the insulation. Conduct tests in accordance with Methods D 470 using 125 V/mil (5 kV/mm) for ac tests or 375 V/mil (15 kv/mm) for dc tests.

6. Sampling

6.1 Sample the insulation in accordance with Test Methods D 470, D 2765, and ICEA T-28-562.

7. Test Methods

7.1 Test the insulation in accordance with Test Methods D 470, D 2132, and D 2765, modified as noted in Table 1, and ICEA T-28-562.

¹ This specification is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.18 on Solid Insulations, Nonmetallic Shieldings, and Coverings for Electrical and Telecommunications Wires and Cables.

Current edition approved March 10, 2001. Published May 2001. Originally published as D 3555 – 77. Last previous edition D 3555 – 98.

² *Annual Book of ASTM Standards*, Vol 10.01.

³ *Annual Book of ASTM Standards*, Vol 08.03.

⁴ Available from Insulated Cable Engineers Association, P.O. Box 440, South Yarmouth, MA 02664, or Global Engineering Documents, 15 Inverness Way East, Englewood, CO 80112.

*A Summary of Changes section appears at the end of this standard.