



SLOVENSKI STANDARD

SIST EN 14584:2005

01-november-2005

BYdcfi ý]h Ybc`dfY]g_i ýUb`Y`E`5_i gh] bUYa]g]U`E`DfY[`YX`_cj]bg_] `hU b] bUdfUj `a YX`dfYg_i ýUb`Ya `E`FUj b]bg_]UbUa Ygh]hYj `j]fcj `U_i gh] bY`Ya]g]Y

Non-destructive testing - Acoustic emission - Examination of metallic pressure equipment during proof testing - Planar location of AE sources

Zerstörungsfreie Prüfung - Schallemissionsprüfung - Prüfung von metallischen Druckgeräten während der Abnahmeprüfung - Planare Ortung von Schallemissionsquellen

Essais non destructifs - Emission acoustique - Vérification des équipements métalliques sous pression pendant l'épreuve - Localisation planaire des sources d'EA

Ta slovenski standard je istoveten z: EN 14584:2005

ICS:

17.140.20	Emisija hrupa naprav in opreme	Noise emitted by machines and equipment
19.100	Neporušitveno preskušanje	Non-destructive testing

SIST EN 14584:2005

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 14584:2005](#)

<https://standards.iteh.ai/catalog/standards/sist/09014320-fe9c-4c15-8954-c97bf99e9d50/sist-en-14584-2005>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 14584

August 2005

ICS 17.140.20; 77.040.20

English Version

**Non-destructive testing - Acoustic emission - Examination of
metallic pressure equipment during proof testing - Planar
location of AE sources**

Essais non destructifs - Emission acoustique - Vérification
des équipements métalliques sous pression pendant
l'épreuve - Localisation planaire des sources d'EA

Zerstörungsfreie Prüfung - Schallemissionsprüfung -
Prüfung von metallischen Druckgeräten während der
Abnahmeprüfung - Planare Ortung von
Schallemissionsquellen

This European Standard was approved by CEN on 8 July 2005.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	Page
Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Personnel qualification	4
5 Test method.....	4
5.1 General.....	4
5.2 Application of load.....	5
5.3 Sensors	5
5.4 Location	5
5.5 Preliminary information	5
5.6 Written instruction requirements	6
6 Instrumentation.....	6
7 Testing	7
7.1 Pre-test measurements	7
7.2 Test steps	9
8 Interpretation of results	10
8.1 Grading criteria	10
8.2 Real time control	10
8.3 AE source severity grading	11
9 Documentation.....	12
Annex A (normative) Distance peak amplitude correction procedures.....	13
Bibliography.....	15

Foreword

This European Standard (EN 14584:2005) has been prepared by Technical Committee CEN/TC 138 “Non-destructive testing”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2006, and conflicting national standards shall be withdrawn at the latest by February 2006.

This European Standard has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 14584:2005](https://standards.iteh.ai/catalog/standards/sist/09014320-fe9c-4c15-8954-c97bf99e9d50/sist-en-14584-2005)

<https://standards.iteh.ai/catalog/standards/sist/09014320-fe9c-4c15-8954-c97bf99e9d50/sist-en-14584-2005>

EN 14584:2005 (E)**1 Scope**

This European Standard specifies the method for conducting acoustic emission (AE) + testing of metallic pressure equipment during acceptance pressure testing using a planar location method. General principles of acoustic emissions are described in EN 13554.

The objectives of the AE testing are to provide 100 % volumetric testing to define regions of the structure, which are acoustically active with burst type AE e.g. as a result of sub-critical flaw evolution; thus increasing the reliability of the acceptance test. The test provides a reference map for comparison with results of future tests.

2 Normative references

The following referenced documents are indispensable for the application of this European Standard. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 473, *Non-destructive testing – Qualification and certification of NDT personnel – General principles*

EN 1330-1:1998, *Non-destructive testing – Terminology – Part 1: List of general terms*

EN 1330-2:1998, *Non-destructive testing – Terminology – Part 2: Terms common to the non-destructive testing methods*

EN 1330-9:2000, *Non-destructive testing – Terminology – Part 9: Terms used in acoustic emission testing*

EN 13477-1, *Non-destructive testing – Acoustic emission – Equipment characterisation – Part 1: Equipment description*

EN 13477-2, *Non-destructive testing – Acoustic emission – Equipment characterisation – Part 2: Verification of operating characteristic*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 14584:2005](https://standards.iteh.ai/catalog/standards/sist/09014320-69c-4c15-8954-c97bf99e9d50/sist-en-14584-2005)

<https://standards.iteh.ai/catalog/standards/sist/09014320-69c-4c15-8954-c97bf99e9d50/sist-en-14584-2005>

3 Terms and definitions

For the purpose of this European Standard, the terms and definitions given in EN 1330-1:1998, EN 1330-2:1998 and EN 1330-9:2000 apply.

4 Personnel qualification

It is assumed that acoustic emission testing is performed by qualified and capable personnel. In order to prove this qualification, it is recommended to certify the personnel in accordance with EN 473.

NOTE For pressure equipment see directive 97/23/EC, Annex 3.1.3: "For pressure equipment in categories III and IV, the personnel must be approved by a third party organization recognized by a Member State".

5 Test method**5.1 General**

The main target of the AE test is to locate and monitor acoustic emission sources caused by phenomena e.g. crack growth and yielding generated by the applied load to the equipment.

The properties and structural state of the material, the type and magnitude of the applied stress and stress rate are significant factors affecting the emission.

All the relevant located AE sources shall be evaluated by other NDT methods.

5.2 Application of load

The application of the stress to the equipment shall be made using internal pressure following the procedure specified in the relevant product standard. The rate of the application of pressure shall be established so as to avoid burst signal overlap. The pressurising system shall permit pressurisation at a steady controllable rate and shall allow the pressure to be held constant at the hold points. The pressurisation rate would not normally exceed 1 % for pneumatic and 5 % for hydraulic test pressure per minute. The intermediate hold periods, if necessary according to the AE activity or the pre-defined pressure schedule, will normally be 5 min to 10 min. The final hold period at the test pressure shall have a minimum duration of 15 min.

NOTE Intermediate hold periods are strongly recommended, especially if pressurisation rates exceed 0,5 %/min for pneumatic or 2 %/min for hydraulic tests.

Prior to starting the test, all the necessary actions shall be taken to identify and to reduce potential sources of extraneous noise.

Dependent upon the results of the initial loading, a reduction of the load to working pressure or lower, followed by re-pressurisation, may be required.

5.3 Sensors

The most commonly used frequency range is 100 kHz to 300 kHz. Lower frequency monitoring allows detection at greater distances and high frequency monitoring provides improved rejection of external noise. Selection of frequency range may optimise location accuracy by avoiding the detection of multiple wave modes.

The equipment surface below the sensors shall be cleaned to ensure the maximum coupling efficiency. The sensor couplant shall be as specified in the written test instruction. The sensors may be directly attached to the structure using magnetic devices or an adhesive.

<https://standards.iteh.ai/catalog/standards/sist/09014320-fe9c-4c15-8954-077d1e04501e/en-14584-2005>

The effectiveness and reliability of the acoustic couplant shall be verified. The characteristics of the type of the acoustic couplant used shall not affect the structure adversely.

5.4 Location

The location of AE sources is performed using delta t measurement.

The accuracy is normally within ± 5 % of the sensor spacing and shall be measured and verified using an artificial source. If the accuracy is not within ± 5 %, appropriate action shall be taken.

For difficult geometry e.g. nozzles, manholes, reference measurements shall be made.

5.5 Preliminary information

Prior to the test, the AE Test Organisation shall collect the following information, as relevant:

- a) relevant product standard;
- b) type of equipment or structure and material characteristics and specifications;
- c) assembly and/or layout drawings with sufficient details of the structure;
- d) material specifications, including heat treatment, if applicable;
- e) proposed pressure/stress application sequence;
- f) potential acoustic noise interference sources and the isolating mechanism applied;

EN 14584:2005 (E)

g) where possible, locations of known discontinuities and the general results of prior NDT.

5.6 Written instruction requirements

The AE test organisation shall provide a written test procedure, which shall include but not necessarily be restricted to the following:

- a) explicit indication of the purpose of the test and limitations if any;
- b) sensor type, frequency and manufacturer;
- c) method of sensor attachment;
- d) type of acoustic couplant used;
- e) type of surface preparation;
- f) type of AE equipment used with the main characteristics;
- g) energy measurement method to be used;
- h) value of K from relevant product standard, if available;
- i) sensor location maps representing the structure or part of it;
- j) description of equipment verification procedure;
- k) description of the in-situ verification (see 7.2.2);
- l) sequence of pressurisation; [SIST EN 14584:2005](https://standards.iteh.ai/catalog/standards/sist/09014320-fe9c-4c15-8954-c97bf99e9d50/sist-en-14584-2005)
- m) recorded data and recording method; <https://standards.iteh.ai/catalog/standards/sist/09014320-fe9c-4c15-8954-c97bf99e9d50/sist-en-14584-2005>
- n) available on-line presentation of data;
- o) real time evaluation criteria;
- p) post analysis procedure with adopted filtering technique if used;
- q) final report requirements;
- r) qualification/certification of the personnel.

The test instruction shall be prepared in accordance with EN 473.

6 Instrumentation

An AE system consists of sensors and equipment for signal conditioning and processing and for displaying and recording data according to EN 13447-1.

The AE instrument shall be capable of measuring at least the following parameters on the first hit channel:

- a) AE burst count;
- b) burst signal peak amplitude;
- c) burst signal duration;

- d) burst signal rise time;
- e) burst signal energy;
- f) arrival time (leading edge and/or peak);
- g) pressure and/or other stress parameters.

The test instrumentation shall:

- store all the acquired AE data and the external parameter(s);
- provide an on-line location display; and
- provide an on-line display of AE data and pressure;

to allow a real time control of the pressure equipment under test. To assist the on-line evaluation it is recommended that the instrumentation provides real time distance peak amplitude correction and applies grading.

The AE system performance check (including sensors) shall be performed according to EN 13477-2.

7 Testing

7.1 Pre-test measurements

7.1.1 Wave propagation

Attenuation measurements shall be performed on the structure in order to determine the maximum sensor spacing. The measurements shall be performed with the test fluid in the equipment using the Hsu-Nielsen source. In the case that the Hsu-Nielsen source saturates the measurement chain, a lower energy artificial source shall be used up to the 20e distance (see Annex A). The obtained curve shall be shifted-up to correspond with the original Hsu-Nielsen source.

The burst signal peak amplitude versus distance and wave velocity to be used in the location algorithm shall be measured using two sensors mounted in a region of the pressure equipment away from nozzles, manways etc.

The shadowing effect of nozzles and ancillary attachments shall be quantified and transmission through the test fluid shall be taken into consideration.

7.1.2 Determination of maximum allowed sensor spacing

The sensors shall be positioned on the structure such that a source K dB less than those of the Hsu-Nielsen source at any position on the equipment can be detected by at least three sensors and can be located to the specified accuracy for the test.

The value of K shall be obtained from the relevant product standard and given in the written test instruction.

With reference to Figure 1:

- a) set the detection threshold X dB above the peak background noise;
- b) set the evaluation threshold for determining the sensor spacing K dB above the detection threshold;
- c) maximum distance (d_{max}) is given by the intersection of the attenuation curve with the evaluation threshold (A_e).

The sensor spacing shall not be greater than d_{max} .