



Designation: C642 – 06

## Standard Test Method for Density, Absorption, and Voids in Hardened Concrete<sup>1</sup>

This standard is issued under the fixed designation C642; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

### 1. Scope\*

1.1 This test method covers the determinations of density, percent absorption, and percent voids in hardened concrete.

1.2 The text of this test method references notes and footnotes which provide explanatory information. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of this standard.

1.3 The values stated in SI units are to be regarded as the standard.

### 2. Significance and Use

2.1 This test method is useful in developing the data required for conversions between mass and volume for concrete. It can be used to determine conformance with specifications for concrete and to show differences from place to place within a mass of concrete.

### 3. Apparatus

3.1 *Balance*, sensitive to 0.025 % of the mass of the specimen.

3.2 *Container*, suitable for immersing the specimen and suitable wire for suspending the specimen in water.

### 4. Test Specimen

4.1 Whenever possible, the sample shall consist of several individual portions of concrete, each to be tested separately. The individual portions may be pieces of cylinders, cores, or beams of any desired shape or size, except that the volume of each portion shall be not less than 350 cm<sup>3</sup> (or for normal weight concrete, approximately 800 g); and each portion shall be free from observable cracks, fissures, or shattered edges.

### 5. Procedure

5.1 *Oven-Dry Mass*—Determine the mass of the portions, and dry in an oven at a temperature of 100 to 110 °C for not less than 24 h. After removing each specimen from the oven,

allow it to cool in dry air (preferably in a desiccator) to a temperature of 20 to 25 °C and determine the mass. If the specimen was comparatively dry when its mass was first determined, and the second mass closely agrees with the first, consider it dry. If the specimen was wet when its mass was first determined, place it in the oven for a second drying treatment of 24 h and again determine the mass. If the third value checks the second, consider the specimen dry. In case of any doubt, redry the specimen for 24-h periods until check values of mass are obtained. If the difference between values obtained from two successive values of mass exceeds 0.5 % of the lesser value, return the specimens to the oven for an additional 24-h drying period, and repeat the procedure until the difference between any two successive values is less than 0.5 % of the lowest value obtained. Designate this last value *A*.

5.2 *Saturated Mass After Immersion*—Immerse the specimen, after final drying, cooling, and determination of mass, in water at approximately 21 °C for not less than 48 h and until two successive values of mass of the surface-dried sample at intervals of 24 h show an increase in mass of less than 0.5 % of the larger value. Surface-dry the specimen by removing surface moisture with a towel, and determine the mass. Designate the final surface-dry mass after immersion *B*.

5.3 *Saturated Mass After Boiling*—Place the specimen, processed as described in 5.2, in a suitable receptacle, covered with tap water, and boil for 5 h. Allow it to cool by natural loss of heat for not less than 14 h to a final temperature of 20 to 25 °C. Remove the surface moisture with a towel and determine the mass of the specimen. Designate the soaked, boiled, surface-dried mass *C*.

5.4 *Immersed Apparent Mass*—Suspend the specimen, after immersion and boiling, by a wire and determine the apparent mass in water. Designate this apparent mass *D*.

### 6. Calculation

6.1 By using the values for mass determined in accordance with the procedures described in Section 5, make the following calculations:

$$\text{Absorption after immersion, \%} = [(B - A)/A] \times 100 \quad (1)$$

$$\text{Absorption after immersion and boiling, \%} = [(C - A)/A] \times 100 \quad (2)$$

$$\text{Bulk density, dry} = [A/(C - D)] \cdot \rho = g_1 \quad (3)$$

$$\text{Bulk density after immersion} = [B/(C - D)] \cdot \rho \quad (4)$$

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.66 on Concrete's Resistance to Fluid Penetration.

Current edition approved July 1, 2006. Published August 2006. Originally approved in 1969. Last previous edition approved in 1997 as C642 – 97. DOI: 10.1520/C0642-06.

\*A Summary of Changes section appears at the end of this standard