# INTERNATIONAL STANDARD



Second edition 1992-08-15

# Heat-treatable steels, alloy steels and free-cutting steels $-\!\!-$

## Part 15:

iTeh Valve steels for internal combustion engines

## (standards.iteh.ai)

Aciers pour traitement thermique, aciers alliés et aciers pour décolletage <u>683-15:1992</u> https://standards.ieh.ai/catalog/standards/sist/fl2dcff4-189a-4hd8-812d Partie, 15: Aciers pour soupapes de moteurs à combustion interne



#### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75% of the member bodies casting a vote.

International Standard ISO 683-15 was prepared by **Technical Committee** ISO/TC 17, Steel, Sub-Committee SC 4, Heat treatable and alloy steels.

This second edition cancels and replaces SQ he3-1frist92 edition (ISO 683-15:1976), of which it constitutes attechnical revision/sist/fl2dcff4-189a-4bd8-812dc92510f5f286/iso-683-15-1992

ISO 683 consists of the following parts, under the general title *Heat-treatable steels*, *alloy steels and free-cutting steels*:

- Part 1: Direct-hardening unalloyed and low-alloyed wrought steel in form of different black products
- Part 9: Wrought free-cutting steels
- Part 10: Wrought nitriding steels
- Part 11: Wrought case-hardening steels
- Part 13: Wrought stainless steels
- Part 14: Hot-rolled steels for quenched and tempered springs
- Part 15: Valve steels for internal combustion engines
- Part 16: Precipitation hardening stainless steels
- Part 17: Ball and roller bearing steels

© ISO 1992

Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization

Part 18: Bright products of unalloyed and low alloy steels
Annex A of this part of ISO 683 is for information only.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 683-15:1992</u> https://standards.iteh.ai/catalog/standards/sist/f12dcff4-189a-4bd8-812dc92510f5f286/iso-683-15-1992

## iTeh STANDARD PREVIEW (standards iteh ai) This page intentionally left blank

<u>ISO 683-15:1992</u> https://standards.iteh.ai/catalog/standards/sist/f12dcff4-189a-4bd8-812dc92510f5f286/iso-683-15-1992

## Heat-treatable steels, alloy steels and free-cutting steels —

## Part 15:

Valve steels for internal combustion engines

#### 1 Scope

1.1 This part of ISO 683 applies to the grades of wrought high-alloy materials listed in table 1. These valve materials are used for intake and exhaust valves in reciprocating internal combustion engines.

ISO 643:1983, Steels — Micrographic determination It is applicable to bars, wire, wire rod and forgings CS. 16 the ferritic or austenitic grain size. and for the surface finishes listed in note 3 of 6.2.

> JSO 783:1989, Metallic materials – Tensile testing at ISO 683-15:19 elevated temperature

technical delivery requirements.

VIC

KĽ

1.2 This part of ISO 683 does not apply to alloys resistant to wear and corrosion which are used to protect valve seat surfaces. mensions of round bars.

**1.3** In addition to this part of ISO 683, the general technical delivery requirements of ISO 404 are applicable.

#### Normative references 2

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 683. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 683 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards

ISO 286-1:1988, ISO system of limits and fits -Part 1: Bases of tolerances, deviations and fits.

ISO 377-1:1989, Selection and preparation of samples and test pieces of wrought steels – Part 1: Samples and test pieces for mechanical test.

1SO 1035-1:1980, Hot-rolled steel bars - Part 1; Di-

ISO 377-2:1989, Selection and preparation of samples

and test pieces of wrought steels - Part 2: Samples for the determination of the chemical composition.

ISO 404:1992, Steel and steel products - General

ISO 1035-4:1982, Hot-rolled steel bars - Part 4: Tolerances.

ISO 6506:1981, Metallic materials -- Hardness test --Brinell test.

ISO 6508:1986, Metallic materials – Hardness test – Rockwell test (scales A - B - C - D - E - F - G - H -K).

ISO 6892:1984, Metallic materials – Tensile testing.

ISO 8457-1:1989, Steel wire rod – Part 1: Dimensions and tolerances.

ISO 9443:1991, Heat-treatable and alloy steels -Surface quality classes for hot-rolled round bars and wire rods - Technical delivery conditions.

ISO/TR 9769:1991, Steel and iron - Review of available methods of analysis.

ISO 10474:1991, Steel and steel products - Inspection documents.

#### 3 Definition

For the purposes of this part of ISO 683, the following definition applies.

3.1 valve materials: Steels and non-ferrous metal alloys which exhibit, to varying degrees, resistance to:

heat.

- thermal cycling,
- corrosion.
- oxidation.
- fatigue loading,
- impact.
- adhesive and abrasive wear.

Valve materials are therefore used for the manufacture of intake and exhaust valves in reciprocating internal combustion engines.

## iTeh STANDARD PREVIEW

6.1.2 The non-ferrous metal alloys NiCr 15 Fe 7 Grade classification and categorization arc TiAI, NiFe 25 Cr 20 NbTi and NiCr 20 TiAI are usually 4

#### ISO 683-15:1992

4.1 The materials listed in this part of ISO 683 are standards in this part of ISO 683 are standards in this part of ISO 683 are standards in the standard standard standard standards are standards in the standard standard standard standards in the standard standard standard standards are standards in the standard standard standard standard standard standards are standard standar classified according to their chemical composition <sup>286/iso</sup>finish<sup>5</sup>at<sup>9</sup>the time of delivery (see table 1).

**4.2** Valve materials are divided into two categories based upon structure, which is itself determined by the general chemical composition:

- martensitic steels which are primarily used for intake valves and the stem portion of exhaust valves;
- austenitic alloys, which are primarily used for exhaust valves.

#### 5 Ordering

The purchaser shall state in his enquiry and order

- a) the quantity to be delivered;
- b) the designation of the product form (e.g. "bar", see 1.1);
- c) the number of the product standard, the dimensions and, where these are not specified in the standard, the surface finish (see 6.2, note 3) and the tolerances (see 6.6);

- d) the designation "valve material";
- e) the number of this part of ISO 683;
- f) the alloy grade (see table 1);
- g) the heat-treatment condition on delivery (see 6.2);
- h) all other necessary details including the intended method of processing (hot extrusion or upsetting with electric resistance heating);
- i) the required type of document (see 7.1).

#### Requirements 6

#### 6.1 Manufacturing process

6.1.1 Unless otherwise agreed in the order, the type of melting process (see 6.1.2) and the type of process used in making the product are left to the discretion of the manufacturer.

produced by remelting processes.

The heat-treatment condition and surface finish of the products at the time of delivery shall be agreed when ordering.

NOTES

1 Valve materials intended for subsequent processing by metal forming are normally ordered in one of the heat-treatment conditions indicated in table 3.

2 When they have become finished components, the materials are used, depending on their chemical compoquenched and tempered or in the the sition. precipitation-hardened condition (see tables A.1 and A.5).

3 Valve materials are mainly supplied in bar form, with one of the following surface finishes:

- peeled and polished;
- peeled and ground;
- ground;
- ground and polished;
- peeled and ground, then polished;
- as rolled.

#### 6.3 Chemical composition

**6.3.1** The chemical composition of the materials, as given by the cast analysis, shall conform to the specifications in table 1.

**6.3.2** Slight deviations from the specified limits may be permitted by the purchaser, if the characteristics in use are only affected to a negligible extent.

**6.3.3** At the time of ordering, it may be agreed that the result of the product analysis, with the permissible deviations given in table 2, shall serve as proof that the limiting values for the cast analysis in table 1 have been complied with.

#### 6.4 Mechanical properties

Table 3 specifies values of the mechanical properties at room temperature for the soft annealed and quenched and tempered conditions of martensitic steels and for the controlled cooled and/or quenched conditions of austenitic materials (see also tables A.1 to A.4).

#### 6.6 Dimensions and tolerances

The dimensions and tolerances of the product shall comply with the requirements agreed upon at the time of enquiry and order. The agreements shall, as far as possible, be based on corresponding International Standards or otherwise on suitable national Standards.

NOTE 5 The following International Standards cover dimensions and/or tolerances for products included in this part of ISO 683:

- for as-rolled bars: ISO 1035-1 and ISO 1035-4,

- for as-rolled wire rod: ISO 8457-1.

### 7 Testing

#### 7.1 Agreement between tests and documents

**7.1.1** For each delivery, the issue of one of the documents listed in 7.6 may be agreed upon at the time of enquiry and order.

6.5 Internal and external condition TANDART.1.2 Df, in accordance with the agreements at the time of enquiry and order, a test report is to be pro6.5.1 Any limitations on non-metallic inclusions for ds. vided, this shall cover the results of the cast analysis for all elements specified for the steel type supplied.

enquiry and order. ISO 683-15:1924.3 If, in accordance with the agreements at the NOTE 4 In connection with agreements of the type described in this subclause, it should be borne in mind that/iso-68 of an inspection report is to be provided, the speciin the case of open melting, the percentage of nonfications in 7.2 to 7.5 are to be observed.

In the case of open melting, the percentage of nonmetallic inclusions will be high because of the high alloy contents of the materials complying with this part of ISO 683 and also that an irregular distribution of the nonmetallic inclusions is to be expected.

**6.5.2** The valve materials shall not have internal bursts, open centreline, or any other kind of internal void apparent on a polished cross-section at  $100 \times \text{magnification}$ .

**6.5.3** The NiCr 20 TiAl alloy shall have a grain size of 4 and/or finer when tested in accordance with ISO 643, but occasional coarser grains shall be tolerated.

**6.5.4** In the case of bars which were peeled or ground during finishing (see 6.2, note 3), the depth of surface defects shall not exceed the tolerance class h11 of ISO 286-1.

**6.5.5** In all other cases, the requirements governing surface quality shall be agreed upon at the time of enquiry and order.

For round bars and wire rods to be delivered in the hot-rolled surface condition, these requirements should where appropriate be based on ISO 9443.

#### 7.2 Number of tests

#### 7.2.1 Mechanical tests

**7.2.1.1** The test unit shall consist of products from the same cast, the same type of manufacturing process and the same heat-treatment batch; all products of the test unit shall have cross-sections of the same form and nominal dimensions.

**7.2.1.2** For the purpose of verifying the mechanical properties given in table 3, unless otherwise agreed at the time of ordering, one sample per 10 t shall be taken from the test units as described in 7.2.1.1. As far as possible, the hardness shall be determined, otherwise the tensile test shall be carried out.

#### 7.2.2 Other tests

Where, in addition to the tests in 7.2.1, other tests are to be carried out and certified in an inspection certificate or inspection report, this shall be agreed upon at the time of enquiry and order together with the necessary details on the test unit and the number of tests.

#### 7.3 Selection and preparation of samples and test pieces

#### 7.3.1 Product analysis

For product analysis, the selection and preparation of samples shall be carried out in accordance with the requirements of ISO 377-2.

If the spectrographic analysis method is used, testing may be carried out on the surface of the product. However, in cases of doubt, it will be necessary to carry out several analyses evenly distributed over the cross-section of the product and to average their results.

#### 7.3.2 Tensile and hardness tests

7.3.2.1 The test pieces for the tensile test shall be taken in the longitudinal direction of the products (in accordance with figure 1) and be prepared in accordance with ISO 377-1 and ISO 6892.

7.3.2.2 The hardness test shall be made in the cross-sectional area from which the tensile test pieces are to be taken, in accordance with figure 1. The test pieces for the hardness test shall be pre-DA-Ratest report, VIEW pared in accordance with ISO 6506 or ISO 6508.

#### 7.4.4 Grain size

The austenitic grain size shall be determined in accordance with ISO 643.

Unless otherwise agreed, the choice between the various methods specified in ISO 643 is left to the discretion of the manufacturer.

#### 7.4.5 Surface defects

In cases of dispute, the depth of surface defects shall, in accordance with ISO 9443, be determined by metallography on a transverse microsection. If this is not possible, the defective spot shall be filed until the defect disappears, in order to determine the depth of the defect by suitable means.

#### 7.5 Retests

(standare San inspection certificate, or

ISO 404 shall apply for retests.

#### 7.6 Certification of the tests

ISO 10474 is valid, acceptable documents being:

#### 7.3.3 Grain size

The instructions given in ISO 643 shall apply to the SO 683-15:1992 sampling and preparation of test/pieces/sforhdeten/og/standards/sist/f12dcff4-189a-4bd8-812dmining the austenitic grain size. c92510f5f286/i8-68Marking

#### 7.3.4 Surface testing

In accordance with ISO 9443, in cases of dispute, transverse microsections shall be prepared for the microscopic examination of the surface quality (see also 7.4.5).

#### 7.4 Test methods

#### 7.4.1 Chemical analysis

The chemical composition shall be determined in accordance with the appropriate International Standards listed in ISO/TR 9769 or prepared since the publication of ISO/TR 9769.

#### 7.4.2 Tensile test

The tensile test shall be performed in accordance with ISO 6892.

#### 7.4.3 Hardness test

The Rockwell C hardness test shall be performed in accordance with ISO 6508, the Brinell hardness test shall be performed in accordance with ISO 6506.

8.1 Each coil of wire or bundle of bars shall be identified by means of a securely affixed label, featurina

- the manufacturer's mark or name.
- the grade of material.
- the cast number.
- the nominal size.

Marking which identifies the surface finish and/or indicates the coil or bundle weight may be agreed upon.

8.2 The marking on the label shall remain clearly legible even after prolonged outdoor exposure of the coil or bundle.

8.3 In the case of bars with diameters not smaller than 30 mm or with a cross-section of equivalent area, the manufacturer shall also ensure that one bar per bundle is marked as a guide bar. This requires painting its front end white and affixing the manufacturer's mark, the material grade and the cast number on the front end, either by engraving (die-stamping), or by printing (rubber stamping), or by means of adhesive tape.

In the case of diameters smaller than 30 mm, or cross-sections of equivalent area, a second label

giving information about the manufacturer, the material grade and the cast number shall be provided.

#### 9 Complaints

The conditions for dealing with complaints specified in ISC 404 shall apply.

Dimensions in millimetres



Figure 1 – Location of tensile test pieces

## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 683-15:1992 https://standards.iteh.ai/catalog/standards/sist/f12dcff4-189a-4bd8-812dc92510f5f286/iso-683-15-1992

	ible SO 976	Chemical composition [% (m/m)]								
Material designation	para in l -15:1	с	Si	Mn	Р	s	Cr	Мо	Ni	Others
	Con type 683				max.	max.				
Martensitic steels										
X 50 CrSi 8 2 X 45 CrSi 9 3	1	0,45 to 0,55 0,40 to 0,50	1,0 to 2,0 2,7 to 3,3	max. 0,60	0,030	0,030	7,5 to 9,5		max. 0,60	
X 85 CrMoV 18 2	3	0,80 to 0,90	max. 1,0	max. 1,5	0,040	0,030	16,5 to 18,5	2,0 to 2,5		0,30 to 0,60 ∨
Austenitic materials										
X 55 CrMnNiN 20 8 X 53 CrMnNiN 21 9 X 50 CrMnNiNbN 21 9	8,9 	0,50 to 0,60 0,48 to 0,58 0,45 to 0,55	max. 0,25 max. 0,25 max. 0,45	7,0 to 10,0 8,0 to 10,0 8,0 to 10,0	0,050 0,050 0,050	0,030 0,030 0,030	19,5 to 21,5 20,0 to 22,0 20,0 to 22,0		1,5 to 2,75 3,25 to 4,5 3,5 to 5,5	0,20 to 0,40 N 0,35 to 0,50 N 0,80 to 1,50 W 1,80 to 2,50 Nb + Ta 0,40 to 0,60 N
X 53 CrMnNiNbN 219	80.59	0,48 to 0,58	max. 0,45	8,0 to 10,0	0,050	0,030	20,0 to 22,0		3,25 to 4,5	0,38 to 0,50 N C + N > 0,90 2,00 to 3,00 Nb + Ta
X 33 CrNiMnN 23 8		0,28 to 0,38	0,50 to 1,00	1,5 to 3,5	0,050	0,030	22,0 to 24,0	max. 0,50	7,0 to 9,0	max. 0,50 W 0,25 to 0,35 N
NiCr 15 Fe 7 TiAl		0,03 to 0, 10	max. 0,50	max. 0,50	0,015	0,015	14,0 to 17,0	max. 0,50	Remainder	1,10 to 1,35 Al 5,0 to 9,0 Fe 0,70 to 1,20 Nb + Ta 2,0 to 2,6 Ti
NiFe 25 Cr 20 NbTi		max. 0, 10	max: 1,0 <b>Feh S</b>	max. 1,0 FANI stand	o,oso DAI ard	0,015 RD s.it	18,0 to 21,0 PRE eh.ai)	<b>/IEW</b>	Remainder	0,30 to 1,00 AI 23,0 to 28,0 Fe 1,0 to 2,0 Nb + Ta 1,0 to 2,0 Ti max. 0,008 B
NiCr 20 TiAl	11	0,04 to 0, 10	max. 1,0	max. 1,0 <u>IS(</u> th.ai/catalog c92510f51	0,020 <u>) 683-</u> [standa 286/isc	0,015 15:199 rds/sist -683-1	18,0 to 21,0 2 f12dcff4-18 5-1992	9a-4bd8-81	min. 65 2d-	max. 3,0 Fe max. 0,2 Cu max. 2,0 Co max. 0,008 B 1,0 to 1,8 Al 1,8 to 2,7 Ti

### Table 1 — Types of valve materials and specified chemical composition (applicable to cast analysis)

Element	Cast analysis (specified limits) % (m/m)	Permissible deviations <sup>1) 2)</sup> from the specified composition % (m/m)				
с		$\begin{array}{c} \pm \ 0,01 \\ \pm \ 0.02 \\ \pm \ 0.03 \end{array}$				
Si	≤ 1,0 > 1,0 ≤ 3,3	$\begin{array}{c} \pm \ 0.05 \\ \pm \ 0.10 \end{array}$				
Mn	< 1,0 $\ge 1,0 \le 2,0$ $> 2,0 \le 10,0$	$\begin{array}{c} \pm \ 0,03 \\ \pm \ 0,04 \\ \pm \ 0,06 \end{array}$				
Р	$\leq 0,040$ > 0,040 $\leq 0,050$	+ 0,005 + 0,010				
S	≤ 0,030	+ 0,005				
N	≤ 0,60	± 0,02				
Cr	$\begin{array}{rrrrrrrrrrrrrrrrrrrrrrrrrrrrrrrrrrrr$	$\begin{array}{c} \pm \ 0,10 \\ \pm \ 0,15 \\ \pm \ 0,20 \\ \pm \ 0,25 \end{array}$				
Мо	iTeh S€T7ANDARD	$\begin{array}{c} \mathbf{PREVIEW} \pm 0.05 \\ \pm 0.10 \end{array}$				
Ni	≥ 5,0 ≤ 9,0	$\pm 0,07$ $\pm 0,10$				
Nb (+ Ta)	https://standards.iteh.ai/catalog/standards/sist/1	12dcff4-189a-4bd8-812d- ± 0,05				
V	≥ 0,30 ≤ 0,66,510151286/iso-683-1	5-1992 <u>± 0,03</u>				
W	≤ 1,50	$\pm$ 0,05				

## Table 2 — Product analysis — Permissible deviations from the specified cast analysis (see table 1)

1) The permissible deviations for the NiCr 20 TiAl, NiFe 25 Cr 20 NbTi and NiCr 15 Fe 7 TiAl alloys shall be agreed upon at the time of ordering, if required.

2) " $\pm$ " means that in one cast, and in more than one product analysis, the deviation may occur over the upper value or under the lower value of the specified range in table 1, but not both at the same time.