SLOVENSKI STANDARD
SIST EN 60249-2-10:1997/A3:1997

01-avgust-1997

Base materials for printed circuits - Part 2: Specifications - Specification No.10: Epoxide non-woven/woven reinforced glass copper-clad laminated sheet of defined flammability (vertical burning test) (IEC 249-2-10:1987/A3:1993) - Amendment 3

Base materials for printed circuits -- Part 2: Specifications -- Specification No. 10: Epoxide non-woven/woven glass reinforced copper-clad laminated sheet of defined flammability (vertical burning test)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Basismaterialien für gedruckte Schaltungen -- Teil 2: Einzelbestimmungen -- Einzelbestimmung Nr. 10: Kupferkaschierte glaswirrfaser/glasgewebeverstärkte Epoxidharz-Schichtpreßstofftafeln definierter Brennbarkeit (Brennprüfung mit vertikaler Probenlage)

SIST EN 60249-2-10:1997/A3:1997
https://standards.iteh.ai/catalog/standards/sist/183a8092-549f-4e48-a27a-556e771c2e06/sist-en-60249-2-10-1997-a3-1997

Matériaux de base pour circuits imprimés -- Partie 2: Spécifications -- Spécification n° 10: Feuille de stratifié époxyde recouverte de cuivre avec renforcement non tissé/tissu de verre, d'inflammabilité définie (essai de combustion verticale)

Ta slovenski standard je istoveten z: **EN 60249-2-10:1994/A3:1994**

ICS:

13.220.40	Sposobnost vžiga in obnašanje materialov in proizvodov pri gorenju	Ignitability and burning behaviour of materials and products
31.180	Tiskana vezja (TIV) in tiskane plošče	Printed circuits and boards

SIST EN 60249-2-10:1997/A3:1997 **en**

2003-01.Slovenski inštitut za standardizacijo. Razmnoževanje celote ali delov tega standarda ni dovoljeno.

SIST EN 60249-2-10:1997/A3:1997

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 60249-2-10:1997/A3:1997
https://standards.iteh.ai/catalog/standards/sist/183a8092-549f-4e48-a27a-556e771c2e06/sist-en-60249-2-10-1997-a3-1997

SIST EN 60249-2-10:1997/A3:1997

EUROPEAN STANDARD

NORME EUROPEENNE

EUROPÄISCHE NORM

EN 60249-2-10/A3

February 1994

UDC 621.3.049.77-033.5-41

Descriptors: Printed circuit, composite materials, glass, copper, flammability

Amendment A3 to the English version of EN 60249-2-10

Base materials for printed circuits
Part 2: Specifications
Specification No. 10: Epoxide non-woven/woven glass reinforced copper-clad laminated sheet of defined flammability (vertical burning test)
(IEC 249-2-10:1987/A3:1993)

Matériaux de base pour circuits imprimés
Partie 2: Spécifications
Spécification n° 10: Feuille de stratifié époxyde recouverte de cuivre avec renforcement non tissé/tissu de verre, d'inflammabilité définie (essai de combustion verticale)
(CEI 249-2-10:1987/A3:1993)

Basismaterialien für gedruckte Schaltungen
Teil 2: Einzelbestimmungen
Einzelbestimmung Nr. 10: Kupferkaschierte glaswirrfaser/glasgewebeverstärkte Epoxidharz-Schichtpreßstoff-tafeln definierter Brennbarkeit (Brennprüfung mit vertikaler Probenlage)
(IEC 249-2-10:1987/A3:1993)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

This amendment A3 modifies the European Standard EN 60249-2-10:1994. It was approved by CENELEC on 1993-12-08. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this amendment the status of a national standard without any alteration.

SIST EN 60249-2-10:1997/A3:1997
https://standards.iteh.ai/catalog/standards/sist/183a8002-5406-4e48-a27a-556e771c2e06/sist-en-60249-2-10-1997-a3-1997

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member.

This amendment exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

Central Secretariat: rue de Stassart 35, B-1050 Brussels

© 1994 Copyright reserved to CENELEC members

SIST EN 60249-2-10:1997/A3:1997

FOREWORD

At the request of the 76th Technical Board of CENELEC, amendment 3:1993 to the International Standard IEC 249-2-10:1987 was submitted to the CENELEC members for formal vote.

The text of the International Standard was approved by CENELEC as amendment A3 to EN 60249-2-10 on 8 December 1993.

The following dates were fixed:

- latest date of publication of an identical national standard (dop) 1995-03-15

- latest date of withdrawal of conflicting national standards (dow) 1995-03-15

ENDORSEMENT NOTICE

The text of amendment 3:1993 to the International Standard IEC 249-2-10:1987 was approved by CENELEC as an amendment to the European Standard without any modification.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
SIST EN 60249-2-10:1997/A3:1997
https://standards.iteh.ai/catalog/standards/sist/183a8092-549f-4e48-a27a-556e771c2e06/sist-en-60249-2-10-1997-a3-1997

SIST EN 60249-2-10:1997/A3:1997

NORME INTERNATIONALE
INTERNATIONAL STANDARD

CEI
IEC
249-2-10

1987

AMENDEMENT 3
AMENDMENT 3

1993-05

Comprenant les amendements 1 (1989) et 2 (1990)
Incorporating Amendments 1 (1989) and 2 (1990)

Amendement 3

Matériaux de base pour circuits imprimés

Partie 2: Spécifications
Spécification n° 10: Feuille de stratifié époxide recouverte de cuivre avec renforcement non tissé/tissu de verre, d'inflammabilité définie (essai de combustion verticale)

iTeh STANDARD PREVIEW
(standards.iteh.ai)
SIST EN 60249-2-10:1997/A3:1997
https://standards.iteh.ai/catalog/standards/sist/183a8092-549f-4e48-a27a-556e771c2e06/sist-en-60249-2-10-1997-a3-1997

Amendment 3

Base materials for printed circuits

Part 2: Specifications
Specification No. 10: Epoxide non-woven/woven glass reinforced copper-clad laminated sheet of defined flammability (vertical burning test)

© CEI 1993 Droits de reproduction réservés — Copyright – all rights reserved

Bureau Central de la Commission Electrotechnique Internationale 3, rue de Varembé Genève, Suisse

Commission Electrotechnique Internationale
International Electrotechnical Commission
Международная Электротехническая Комиссия

CODE PRIX
PRICE CODE E

Pour prix, voir catalogue en vigueur
For price, see current catalogue

SIST EN 60249-2-10:1997/A3:1997

FOREWORD

This amendment has been prepared by IEC technical committee 52: Printed circuits.

The text of this amendment is based on the following documents:

Amendments	Six Months' Rule/DIS	Reports on Voting
3	52(CO)378 52(CO)379 52(CO)380 52(CO)391	52(CO)387 52(CO)388 52(CO)389 52(CO)395
2	52(CO)322	52(CO)337
1	52(CO)319	52(CO)330

Full information on the voting for the approval of this amendment can be found in the reports on voting indicated in the above table.

The text of amendment 3 is indicated by a vertical line in the margin.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Page 9

SIST EN 60249-2-10:1997/A3:1997
https://standards.iteh.ai/catalog/standards/sist/183a8092-549f-4e48-a27a-556e771c2e06/sist-en-60249-2-10-1997-a3-1997

4 Electrical properties

Replace, in table I, the present property designation by:

Surface resistance after damp heat while in the humidity chamber (optional)

Surface resistance after damp heat and recovery

Volume resistivity after damp heat while in the humidity chamber (optional)

Volume resistivity after damp heat and recovery

SIST EN 60249-2-10:1997/A3:1997

Page 15, table VI

Replace table VI as follows:

Property	Test method (subclause of IEC 249-1)	Requirement		
Pull-off strength	3.5	Not less than 60 N (13,4 lbf)		
		Thickness of the copper foil		
		18 µm*	35 µm*	70 µm* and 105 µm*
Peel strength after heat shock of 20 s	3.6.2.1 or 3.6.2.2 or 3.6.2.3	Not less than 1,1 N/mm (6,3 lbf/in)	Not less than 1,4 N/mm (8,0 lbf/in)	Not less than 1,8 N/mm (10,3 lbf/in)
		No blistering nor delamination		
Peel strength after dry heat at 125 °C	3.6.3	Not less than 1,1 N/mm (6,3 lbf/in)	Not less than 1,4 N/mm (8,0 lbf/in)	Not less than 1,8 N/mm (10,3 lbf/in)
		No blistering nor delamination		
Peel strength after exposure to solvent vapour. Solvents as agreed upon between purchaser and supplier	3.6.4	Not less than 1,1 N/mm (6,3 lbf/in)	Not less than 1,4 N/mm (8,0 lbf/in)	Not less than 1,8 N/mm (10,3 lbf/in)
		No blistering nor delamination		
Peel strength after simulated plating	3.6.5	Not less than 0,8 N/mm (4,6 lbf/in)	Not less than 1,0 N/mm (5,7 lbf/in)	Not less than 1,3 N/mm (7,4 lbf/in)
Blistering after 20 s heat shock	3.7.2.1 or 3.7.2.2 or 3.7.2.3	No blistering nor delamination		
* 18 µm (152 g/m^2, 0,5 oz/ft^2); 35 µm (305 g/m^2, 1 oz/ft^2); 70 µm (610 g/m^2, 2 oz/ft^2); 105 µm (915 g/m^2, 3 oz/ft^2)				

iTeh STANDARD PREVIEW
(standards.iteh.ai)
SIST EN 60249-2-10:1997/A3:1997
https://standards.iteh.ai/catalog/standards/sist/183a8092-549f-4e48-a27a-556e771c2e07/sist-en-60249-2-10-1997-a3-1997

5.6 *Solderability*

Delete the title and text of this subclause.

SIST EN 60249-2-10:1997/A3:1997

Page 17

5.7 *Dimensional stability*

Replace the present table VIII by the following new table VIII:

Table VIII

Property	Test method (subclause of IEC 249-1)	Requirement
Dimensional stability	3.11 T = (150 ± 2) °C	0,8 mm/m max.

Add the following subclauses:

5.8 *Size tolerances*

5.8.1 *Size tolerances for sheets*

The size of the sheets as delivered by the supplier shall not deviate from the nominal size by more than $^{+10}_{0}$ mm.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

5.8.2 *Size tolerances for cut panels*

For panels cut to size according to the purchaser's specification, the following tolerances for length and width shall apply.

SIST EN 60249-2-10:1997/A3:1997
https://standards.iteh.ai/catalog/standards/sist/183a8092-549f-4e48-a27a-556e771c2e06/sist-en-60249-2-10-1997-a3-1997

Panel size (mm)	Tolerance ± (mm)	
	Normal	Close
Up to 300	2	0,5
Over 300 to 600		0,8
Over 600		1,6
NOTE - The specified tolerances include all deviations caused by cutting the panels.		

5.9 *Rectangularity of cut panels*

Property	Test method (subclause of IEC 249-1)	Requirements	
		Coarse (mm/m)	Normal (mm/m)
Rectangularity of cut panels	3.15 .	3	2

SIST EN 60249-2-10:1997/A3:1997

Page 17

6.2 *Flexural strength*

Replace the existing table IX by the following:

Table IX

Property	Test method (subclause of IEC 249-1)	Requirements
Flexural strength Nominal thickness: 1,0 mm (0,039 in) 1,2 mm (0,047 in) 1,5 mm (0,059 in) and 1,6 mm (0,063 in) 2,0 mm (0,079 in) 2,4 mm (0,094 in) 3,2 mm (0,125 in)	4.1	Not less than: 240 N/mm² (34 800 lbf/in²) 230 N/mm² (33 400 lbf/in²) 220 N/mm² (31 900 lbf/in²) 200 N/mm² (29 000 lbf/in²) 185 N/mm² (26 800 lbf/in²) 160 N/mm² (23 200 lbf/in²)

Page 19

iTeh STANDARD PREVIEW
(standards.iteh.ai)

6.3 *Flammability*

Amend table X as follows (editorial):

SIST EN 60249-2-10:1997/A3:1997
https://standards.iteh.ai/catalog/standards/sist/183a8092-549f-4e48-a27a-556e771c2e06/sist-en-60249-2-10-1997-a3-1997

Property	Test method (subclause of IEC 249-1)	Requirements
Flammability (vertical burning test)	4.3.4	Designation
		FV0
Flaming combustion time after each application of the test flame for each test specimen		≤ 10 s
Total flaming combustion time for the 10 flame applications for each set of live specimens		≤ 50 s
Glowing combustion time after the second removal of the test flame		≤ 30 s
Flaming or glowing combustion up to the holding clamp		None
Dripping flaming particles that ignite the tissue paper		None