



Designation: A1049/A1049M – 06

# Standard Specification for Stainless Steel Forgings, Ferritic/Austenitic (Duplex), for Pressure Vessels and Related Components<sup>1</sup>

This standard is issued under the fixed designation A1049/A1049M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers ferritic/austenitic (duplex) stainless steel forgings for boilers, pressure vessels, and associated equipment in grades that are also found in Specification [A182/A182M](#).

1.2 The purchaser may specify in the order or contract any appropriate supplementary requirements that are provided in Specification [A788/A788M](#).

1.3 Unless the order specifies the applicable “M” specification designation the material shall be furnished to the inch-pound units.

1.4 The values stated in either inch-pound or SI (metric) units are to be regarded separately as standard. Within the text and tables, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[A182/A182M](#) Specification for Forged or Rolled Alloy and Stainless Steel Pipe Flanges, Forged Fittings, and Valves and Parts for High-Temperature Service

[A370](#) Test Methods and Definitions for Mechanical Testing of Steel Products

[A388/A388M](#) Practice for Ultrasonic Examination of Steel Forgings

[A745/A745M](#) Practice for Ultrasonic Examination of Austenitic Steel Forgings

[A788/A788M](#) Specification for Steel Forgings, General Requirements

[A923](#) Test Methods for Detecting Detrimental Intermetallic Phase in Duplex Austenitic/Ferritic Stainless Steels

[E165](#) Practice for Liquid Penetrant Examination for General Industry

[G48](#) Test Methods for Pitting and Crevice Corrosion Resistance of Stainless Steels and Related Alloys by Use of Ferric Chloride Solution

2.2 *Other Standards:*

[ASME](#) Boiler and Pressure Vessel Code<sup>3</sup>

[NACE MR0175/ISO15156](#) Petroleum and Natural Gas Industries—Materials for Use in H<sub>2</sub>S—Containing Environments in Oil and Gas Production<sup>4</sup>

## 3. Ordering Information and General Requirements

3.1 Material supplied to this specification shall conform to the requirements of Specification [A788/A788M](#), which outlines additional ordering information, manufacturing requirements, testing and retesting methods and procedures, marking, certification, product analysis variations, and additional supplementary requirements.

3.1.1 If the requirements of this specification are in conflict with the requirements of Specification [A788/A788M](#), the requirements of this specification shall prevail.

3.1.2 The purchaser may require that the forging be machined to an approved heat treatment drawing indicating the proposed configuration of the forging at the time of the specified solution heat treatment.

3.1.3 The purchaser may approve the use of an alternate liquid quenching medium for cooling from the solution treatment temperature.

3.2 The purchaser shall specify the acceptance criteria for either Methods B or C of Test Methods [A923](#), if supplementary requirement S1 is selected.

3.3 The purchaser shall specify the required minimum pitting resistance equivalent number (PREN) value determined according to the applicable equation in [Table 1](#).

3.4 When Practice [A745/A745M](#) is the basis for ultrasonic examination in accordance with [7.1](#), the purchaser shall specify whether Quality levels 1 or 2 form the basis for acceptance. Supplementary requirement S4 permits the purchaser to

<sup>3</sup> Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5990.

<sup>4</sup> Available from National Association of Corrosion Engineers (NACE), 1440 South Creek Dr., Houston, TX 77084-4906.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.06 on Steel Forgings and Billets.

Current edition approved Sept. 1, 2006. Published September 2006. DOI: 10.1520/A1049\_A1049M-06.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

**TABLE 1 Chemical Requirements**

Grade UNS No.	F50 <sup>A</sup> S31200 <sup>A</sup>	F51 <sup>A</sup> S31803 <sup>A</sup>	F52 <sup>A</sup> S32950 <sup>A</sup>	F53 <sup>A</sup> S32750 <sup>A</sup>	F54 <sup>B</sup> S39274 <sup>B</sup>	F55 <sup>B</sup> S32760 <sup>B</sup>	F57 <sup>B</sup> S39277 <sup>B</sup>	F59 <sup>A</sup> S32520 <sup>A</sup>	F60 <sup>A</sup> S32205 <sup>A</sup>	F61 <sup>A</sup> S32550 <sup>A</sup>
Carbon, max	0.030	0.030	0.030	0.030	0.030	0.030	0.025	0.030	0.030	0.04
Manganese, max	2.00	2.00	2.00	1.20	1.00	1.00	0.80	1.50	2.00	1.50
Phosphorous, max	0.045	0.030	0.035	0.035	0.030	0.030	0.025	0.035	0.030	0.040
Sulfur, max	0.030	0.020	0.010	0.020	0.020	0.010	0.002	0.020	0.020	0.030
Silicon, max	1.00	1.00	0.60	0.80	0.80	1.00	0.80	0.80	1.00	1.00
Nickel	5.5-6.5	4.5-6.5	3.5-5.2	6.0-8.0	6.0-8.0	6.0-8.0	6.5-8.0	5.5-8.0	4.5-6.5	4.5-6.5
Chromium	24.0-26.0	21.0-23.0	26.0-29.0	24.0-26.0	24.0-26.0	24.0-26.0	24.0-26.0	24.0-26.0	22.0-23.0	24.0-27.0
Molybdenum	1.20-2.00	2.5-3.5	1.00-2.50	3.0-5.0	2.5-3.5	3.0-4.0	3.0-4.0	3.0-5.0	3.0-3.5	2.9-3.9
Nitrogen	0.14-0.20	0.08-0.20	0.15-0.35	0.240.32	0.24-0.32	0.20-0.30	0.23-0.33	0.20-0.35	0.14-0.20	0.10-0.25
Copper	...	...	...	0.50 max	0.20-0.80	0.50-1.00	1.20-2.00	0.50-3.00	...	1.50-2.50
Tungsten	...	...	...	...	1.50-2.50	0.50-1.00	0.80-1.20	...	...	...

<sup>A</sup> PREN = Cr + 3.3(Mo) + 16(N)

<sup>B</sup> PREN = Cr + 3.3(Mo + ½ W) + 16(N)

NOTE—The required PREN value for both the tungsten bearing forging Grades with the superscript *B* and the non-tungsten bearing Grades with the superscript *A* frequently lies between 33 and 40 depending on service experience, so that the Purchaser shall specify the required minimum PREN value (see 3.3).

specify Practice **A388/A388M** in lieu of Practice **A745/A745M**, in which case the purchaser must also specify the acceptance criteria.

3.5 When Supplementary requirement S3, for pitting corrosion testing, of Test Methods **G48** is specified, the purchaser shall identify the method and test temperature to be used.

3.6 When Supplementary requirement S5 for the liquid penetrant examination of forgings in the final machined configuration is specified, the purchaser shall specify the necessary acceptance criteria, if the requirements of S19 in Specification **A788/A788M** are not sufficient.

#### 4. Materials and Manufacture

4.1 Steel melting and forging shall be in accordance with Specification **A788/A788M**.

##### 4.2 Heat Treatment:

4.2.1 Forgings may be machined before solution annealing at the manufacturer's option, unless the purchaser requires that machining to a prescribed configuration be done before heat treatment (see 3.2).

4.2.2 All forgings shall be reheated to the required temperature for solution treatment followed, unless otherwise agreed with the purchaser, by water quenching. With the purchaser's consent (see 3.1.3) some other liquid quenching medium may be used to rapidly cool the forging.

4.2.3 The solution treatment temperature is dependant on the ordered Grade or composition (UNS number) and shall be as listed in **Table 2**.

4.2.4 The forgings shall be held at the specified solution treatment temperature for a minimum of 30 min per inch of maximum heat-treated section thickness.

#### 5. Chemical Requirements

5.1 The heat analysis taken in accordance with Specification **A788/A788M** shall comply with **Table 1** for the ordered Grade.

5.2 A PREN value is included as a requirement in **Table 1** depending on the specified Grade and this will further restrict the chemical requirements.

5.3 The manufacturer shall use the product analysis provisions of Specification **A788/A788M** to obtain a product analysis from a forging representing each heat or multiple heat.

**TABLE 2 Solution Heat Treatment**

UNS Designation	Grade	Solution Temperature °F [°C]	Water Quench <sup>A</sup> to Below °F [°C]
S31200	F 50	1925 [1050] min	200 [95]
S31803	F 51	1870 [1020] min	200 [95]
S32950	F 52	1825-1875 [1000-1025]	200 [95]
S32750	F 53	1880 [1025] min	200 [95]
S39274	F 54	1920-2060 [1050-1125]	200 [95]
S32760	F 55	2010-2085 [1100-1140]	200 [95]
S39277	F 57	1940 [1060] min	200 [95]
S32520	F 59	1975-2050 [1080-1120]	200 [95]
S32205	F 60	1870 [1020] min	200 [95]
S32550	F 61	1920-2060 [1050-1125]	200 [95]

<sup>A</sup> Water quenching is required unless the use of another liquid quenching medium is approved by the purchaser (see 3.1.3).

5.4 Dual marking is permitted when the actual values of the listed elements match two or more of the Grades in **Table 1**; however, grade substitution such as combining a tungsten bearing Grade with one that has no requirement for tungsten is not permitted.

#### 6. Mechanical Properties

6.1 *Requirements*—The material shall conform to the requirements for mechanical properties prescribed in **Table 3**. The mechanical testing requirements of Test Methods **A370** and Specification **A788/A788M** apply.

6.2 *Number of Tension Tests*—The number and location of tension tests are based on the solution-treated weight of the forging(s) from the same heat and solution treated in the same furnace charge.

6.2.1 For forgings weighing less than 5000 lb [2250 kg] as heat treated one tension test shall be required. This may be taken from an integral prolongation from one forging or from a forged test bar. Separate forged test bars shall have been forged in the same manner, and with equivalent forging reduction as the forgings they represent, and shall not be less than the represented forgings in heat-treated section thickness.

6.2.1.1 When solution treatment is performed in a continuous-type furnace, equipped with recording pyrometers, such that complete heating records are available, a solution annealing charge may be considered as any continuous run for forgings from the same heat not exceeding 8 h.