



Designation: A 488/A 488M – 06

Standard Practice for Steel Castings, Welding, Qualifications of Procedures and Personnel¹

This standard is issued under the fixed designation A 488/A 488M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This practice covers the qualification of procedures, welders, and operators for the fabrication and repair of steel castings by electric arc welding.

1.1.1 Qualifications of a procedure and either or both the operator or welder under Section IX of the **ASME Boiler and Pressure Vessel Code** shall automatically qualify the procedure and either or both the operator or welder under this practice. P-number designations in the ASME grouping of base metals for qualification may be different than the category numbers listed in **Table 1**. Refer to **Appendix X1** for a comparison of ASTM category numbers with the corresponding ASME P-Number designations.

1.2 Each manufacturer or contractor is responsible for the welding done by his organization and shall conduct the tests required to qualify his welding procedures, welders, and operators.

1.3 Each manufacturer or contractor shall maintain a record of welding procedure qualification tests (**Fig. 1**), welder or operator performance qualification tests (**Fig. 2**), and welding procedure specification (**Fig. 3**), which shall be made available to the purchaser's representative on request.

1.4 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with this practice.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

A 27/A 27M Specification for Steel Castings, Carbon, for General Application

A 128/A 128M Specification for Steel Castings, Austenitic Manganese

A 148/A 148M Specification for Steel Castings, High Strength, for Structural Purposes

A 216/A 216M Specification for Steel Castings, Carbon, Suitable for Fusion Welding, for High-Temperature Service

A 217/A 217M Specification for Steel Castings, Martensitic Stainless and Alloy, for Pressure-Containing Parts, Suitable for High-Temperature Service

A 351/A 351M Specification for Castings, Austenitic, for Pressure-Containing Parts

A 352/A 352M Specification for Steel Castings, Ferritic and Martensitic, for Pressure-Containing Parts, Suitable for Low-Temperature Service

A 356/A 356M Specification for Steel Castings, Carbon, Low Alloy, and Stainless Steel, Heavy-Walled for Steam Turbines

A 370 Test Methods and Definitions for Mechanical Testing of Steel Products

A 389/A 389M Specification for Steel Castings, Alloy, Specially Heat-Treated, for Pressure-Containing Parts, Suitable for High-Temperature Service

A 447/A 447M Specification for Steel Castings, Chromium-Nickel-Iron Alloy (25-12 Class), for High-Temperature Service

A 487/A 487M Specification for Steel Castings Suitable for Pressure Service

A 494/A 494M Specification for Castings, Nickel and Nickel Alloy

¹ This practice is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved Sept. 1, 2006. Published September 2006. Originally approved in 1963. Last previous edition approved in 2004 as A 488/A 488M – 04.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

TABLE 1 Categories of Base Materials

Category Number	Material Description	ASTM Specification	Grades
1	Carbon steel (carbon less than 0.35 %, tensile strength less than or equal to 70 ksi [480 MPa]).	A 27/A 27M A 216/A 216M A 352/A 352M A 356/A 356M A 732/A 732M A 757/A 757M	all grades WCA, WCB LCB, LCA 1 1A, 2A A1Q
2	Carbon steel (tensile strength greater than 70 ksi [480 MPa]). Carbon-manganese steel (tensile strength equal to or greater than 70 ksi but less than 90 ksi [620 MPa]).	A 148/A 148M A 216/A 216M A 352/A 352M A 732/A 732M A 757/A 757M	80-40 WCC LCC 2Q, 3A A2Q
3	Carbon and carbon-manganese steel (tensile strength equal to or greater than 90 ksi [620 MPa]).	A 732/A 732M	3Q, 4A, 4Q, 5N
4	Low-alloy steel (annealed, normalized, or normalized and tempered. Tensile strength less than 85 ksi [585 MPa]).	A 148/A 148M A 217/A 217M A 352/A 352M A 356/A 356M A 389/A 389M A 487/A 487M A 757/A 757M	80-50 WC1, WC4, WC5, WC6, WC9 LC1, LC2, LC3, LC4 2, 5, 6, 8 C23, C24 11A, 12A, 16A B2N, B3N, B4N
5	Low-alloy steel (annealed, normalized, or normalized and tempered. Tensile strength equal to or greater than 85 ksi [585 MPa]).	A 148/A 148M A 217/A 217M A 356/A 356M A 487/A 487M A 732/A 732M A 757/A 757M	90-60, 105-85 C5, C12, C12A, WC11 9, 10, 12 1A, 1C, 2A, 2C, 4A, 4C, 6A, 8A, 9A, 9C, 10A, 13A 6N, 15A D1N1, D1N2, D1N3, E2N1, E2N2, E2N3
6	Low-alloy steel (quenched and tempered)	A 148/A 148M A 352/A 352M A 487/A 487M A 732/A 732M A 757/A 757M	90-60, 105-85, 115-95, 130-115, 135-125, 150-135, 160-145, 165-150, 165-150L, 210-180, 210-180L, 260-210, 260-210L LC2-1, LC1, LC2, LC3, LC4, LC9 1B, 1C, 2B, 2C, 4B, 4C, 4D, 4E, 6B, 7A, 8B, 8C, 9A, 9B, 9C, 9D, 9E, 10B, 11B, 12B, 13B, 14A 7Q, 8Q, 9Q, 10Q, 11Q, 12Q, 13Q, 14Q B2Q, B3Q, B4Q, C1Q, D1Q1, D1Q2, D1Q3, E1Q, E2Q1, E2Q2, E2Q3
7	Ferritic stainless steel	A 743/A 743M	CB-30, CC-50
8	Martensitic stainless steel	A 217/A 217M A 352/A 352M A 356/A 356M A 487/A 487M A 743/A 743M A 757/A 757M	CA-15 CA6NM CA6NM CA15-A, CA15-B, CA15-C, CA15-D, CA15M-A, CA6NM-A, CA6NM-B CA-15, CA-15M, CA6NM, CA-40, CA6N, CB6 E3N
9	Low-carbon austenitic stainless steel (carbon equal to or less than 0.03 %)	A 351/A 351M A 743/A 743M A 744/A 744M	CF-3, CF-3A, CF-3M, CF-3MA, CF-3MN, CK-3MCUN, CG3M, CN3MN CF-3, CF-3M, CF-3MN, CK-3MCUN, CN-3M, CG3M, CN3MN CF-3, CF-3M, CK-3MCUN, CG3M , CN3MN
10	Unstabilized austenitic stainless steel (carbon greater than 0.03 %)	A 351/A 351M A 447/A 447M A 743/A 743M A 744/A 744M	CE-8MN, CF-8, CF-8A, CF-8M, CF-10, CF-10M, CG-8M, CH-8, CH-10, CH-20, CG6MMN, CF10S1MNN, CE20N Type I CF-8, CG-12, CF-20, CF-8M, CF-16F, CF10SMNN, CH-20, CG-8M, CE-30, CG6MMN, CH10, CF16Fa CF-8, CF-8M, CG-8M
11	Stabilized austenitic stainless steel	A 351/A 351M A 447/A 447M A 743/A 743M	CF-8C, CF-10MC, CK-20, HK-30, HK-40, HT-30, CN-7M, CT-15C Type II CF-8C, CN-7M, CN-7MS, CK-20

Category Number	Material Description	ASTM Specification	Grades
		A 744/A 744M	CF-8C, CN-7M, CN-7MS
12	Duplex (austenitic-ferritic) stainless steel	A 351/A 351M A 872/A 872M A 890/A 890M A 995/A 995M	CD3MWCuN, CD-4MCU J93183, J93550 1A, 1B, 2A, 3A, 4A, 5A, 6A 1B, 2A, 3A, 4A, 5A, 6A
13	Precipitation-hardened austenitic stainless steel	A 747/A 747M	CB7CU-1, CB7CU-2
14	Nickel-base alloys	A 494/A 494M	CW-12MW, CY-40 Class 1, CY-40 Class 2, CZ-100, M-35-1, M-35-2, M-30C, N-12MV, N-7M, CW-6M, CW-2M, CW-6MC, CX-2MW, CU5MCUC
		A 990 A 128/A 128M	CW2M A, B-1, B-2, B-3, B-4, C, D, E-1, E-2, F
15	Steel Castings, Austenitic Manganese		

A 732/A 732M Specification for Castings, Investment, Carbon and Low Alloy Steel for General Application, and Cobalt Alloy for High Strength at Elevated Temperatures
A 743/A 743M Specification for Castings, Iron-Chromium, Iron-Chromium-Nickel, Corrosion Resistant, for General Application

A 744/A 744M Specification for Castings, Iron-Chromium-Nickel, Corrosion Resistant, for Severe Service

A 747/A 747M Specification for Steel Castings, Stainless, Precipitation Hardening

A 757/A 757M Specification for Steel Castings, Ferritic and Martensitic, for Pressure-Containing and Other Applications, for Low-Temperature Service

A 872/A 872M Specification for Centrifugally Cast Ferritic/Austenitic Stainless Steel Pipe for Corrosive Environments

A 890/A 890M Specification for Castings, Iron-Chromium-Nickel-Molybdenum Corrosion-Resistant, Duplex (Austenitic/Ferritic) for General Application

A 990 Specification for Castings, Iron-Nickel-Chromium and Nickel Alloys, Specially Controlled for Pressure Retaining Parts for Corrosive Service

A 995/A 995M Specification for Castings, Austenitic-Ferritic (Duplex) Stainless Steel, for Pressure-Containing Parts

2.2 *American Society of Mechanical Engineers:*³

ASME Boiler and Pressure Vessel Code, Section IX

2.3 *American Welding Society:*⁴

ANSI/AWS 3.0 Definitions for Welding and Cutting

3. Terminology

3.1 *Definitions*—Definitions of terms relating to welding shall be in agreement with the definitions of the American Welding Society, ANSI/AWS A3.0.

4. Weld Orientation

4.1 *Orientation*—The orientation of welds with respect to horizontal and vertical planes of reference are classified into

four positions, namely, flat, horizontal, vertical, and overhead as shown in Fig. 4. Test material shall be oriented as shown in Fig. 4; however, an angular deviation of $\pm 15^\circ$ from the specified horizontal and vertical planes is permitted during welding.

4.2 *Flat Position* (Fig. 4(a))—This position covers plate in a horizontal plane with the weld metal deposited from above, or pipe or a cylindrical casting with its axis horizontal and rolled during welding so that the weld metal is deposited from above.

4.3 *Horizontal Position* (Fig. 4(b))—This position covers plate in a vertical plane with the axis of the weld horizontal, or pipe or a cylindrical casting with its axis vertical and the axis of the weld horizontal.

4.4 *Vertical Position* (Fig. 4(c))—In this position, the plate is in a vertical plane with the axis of the weld vertical.

4.5 *Overhead Position* (Fig. 4(d))—In this position, the plate is in a horizontal plane with the weld metal deposited from underneath.

4.6 *Horizontal Fixed Position* (Fig. 4(e))—In this position, the pipe or cylindrical casting has its axis horizontal and the welding groove in a vertical plane. Welding shall be done without rotating the pipe or casting so that the weld metal is deposited from the flat, vertical, and overhead position.

4.7 *Qualification*—Qualification in the horizontal, vertical, or overhead position shall qualify also for the flat position. Qualification in the horizontal fixed position, or in the horizontal and vertical and overhead positions, shall qualify for all positions (Fig. 4(f)).

5. Preparation of Test Plate

5.1 Procedure qualification testing shall be performed on cast or wrought material having the same category number as the casting being welded. Test material shall be subjected to the same heat treatment before and after welding as will be applied to the casting. If the castings are not to be postweld heat treated, then the test material is not to be postweld heat treated. Test plate material for performance qualification testing is covered in 12.2.

5.2 The dimensions of the test plate shall be such as to provide the required number of test specimens.

³ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

⁴ Available from American Welding Society (AWS), 550 NW LeJeune Rd., Miami, FL 33126, <http://www.aws.org>.



A 488/A 488M – 06

RECOMMENDED FORM FOR MANUFACTURER'S RECORD OF WELDING PROCEDURE QUALIFICATION TESTS

Procedure No. _____ Date: _____ Welding Process: _____
 Material Specification: _____ to _____ of category No. _____ to category No. _____
 Plate Thickness: _____ Thickness Range Qualified _____
 Filler Metal F Group No. _____ Weld Deposit A-Group No.: _____
 Flux Designation: _____ Gas Composition: _____
 Gas Flow Rate: _____ Backing Strip, if any: _____
 Preheat Temperature Range: _____ Single or Multiple Pass: _____
 Position of Groove: _____ Filler Wire Diameter: _____
 Trade Name: _____ Type of Backing: _____
 Forehand or Backhand: _____ Amps: _____ Volts _____ Inches/min: _____
 Postheat Temperature _____ Time at Temperature _____

TENSION TEST RESULTS

Specimen No.	Width	Dimensions Thickness	Area	Ultimate Total Load, lb	Ultimate Unit Stress, psi	Nature of Failure and Location

GUIDED BEND TEST RESULTS

Specimen No.	Results	Specimen No.	Results

Welder's Name: _____ Clock No. _____ Stamp No. _____

Who by virtue of these tests meets the welder performance qualification.

Test Conducted By: _____ Test No. _____
per _____

We certify that the statements in this record are correct and that the test welds were prepared, welded, and tested in accordance with the requirements of ASTM Standard _____

Signed: _____
Manufacturer or Contractor

Date: _____

FIG. 1 Report Form 1

ASTM A488/A488M-06

<https://standards.iteh.ai/catalog/standards/sist/a08f92fb-9596-45eb-93c7-df3152ef65a8/astm-a488-a488m-06>

RECOMMENDED FORM FOR MANUFACTURER'S OR CONTRACTOR'S RECORD OF WELDER OR OPERATOR
PERFORMANCE QUALIFICATION TESTS

Welder or Operator's Name: Stamp No. _____
 Clock No. _____ Welding Process: _____
 Position: _____
 In accordance with Procedure No. _____
 Material Specification: _____ to _____ of category No. _____ to category No. _____
 Plate Thickness: _____ Range of Thickness Qualified: _____
 Filler Metal Specification No. _____ Group No. F. _____
 Filler Metal A-Group No. _____ Filler Metal Diameter _____
 Trade Name: _____ Flux Designation or Gas Analysis: _____
 Was Backing Strip Used? _____

GUIDED BEND TEST RESULTS

Specimen No.	Results	Specimen No.	Results

Test Conducted By: _____ Laboratory Test No. _____
 per _____

We certify that the statements in this record are correct and that the test welds were prepared, welded, and tested in accordance with ASTM Standard _____.

Signed: _____

Manufacturer or Contractor

Date: _____

FIG. 2 Report Form 2

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

[ASTM A488/A488M-06](#)

<https://standards.itih.ai/catalog/standards/sist/a08f92fb-9596-45eb-93c7-df3152ef65a8/astm-a488-a488m-06>



REPORT FORM 3

RECOMMENDED FORM FOR WELDING PROCEDURE SPECIFICATION

1. Title

Welding of^A steel castings.
^A Indicate general material description, such as carbon, Cr-Mo, 12 Cr, etc.

2. Specification No. _____ Rev. _____
Date _____

3. Scope

3.1 Procedure Specification No. _____ covers the welding of^A steel castings using the^B welding process.
^A Indicate general material description in the Title.
^B Indicate specific welding process, such as shielded metal arc, etc.

4. Base Material

4.1 The base material shall conform to the specification for^A which is found in materials category number^B.
^A Insert reference to ASTM designation or indicate chemical analysis and physical properties.
^B Indicate category number from Table 1.
4.2 Base material shall be in the^A heat treated condition before welding.
^A Indicate heat treatment before welding.

5. Filler Metal

5.1 The filler metal shall conform to ANSI/AWS Specification^A which is found in weld metal analysis group A^B.
^A Indicate appropriate American Welding Society specification number and filler metal classification (e.g., A5.1 E7018).
^B Indicate A Number from Table 4.
5.2 Flux for submerged arc welding shall conform to the following nominal composition:^A
^A Indicate chemical composition or trade designation.
5.3 Shielding gas for gas shielded arc welding shall conform to the following nominal composition:^A
^A Indicate the single gas or proportional parts of mixed gases and flow rates.

6. Preparation of Base Material

6.1 Metal removal shall be performed by^A.
^A Indicate method of metal removal, such as chipping, grinding, carbon arc cutting, frame cutting, etc. Also indicate whether preheat is required during metal removal.
6.2 Configuration of the weld preparation for partial penetration welds shall conform to the following geometry:^A
^A Indicate minimum root radius and minimum side wall angle.
6.3 Configuration of the weld preparation for full penetration welds shall conform to the following geometry:^A
^A Indicate minimum side wall angle.
6.4 Backing plates shall be used for welding full penetration welds. Backing plates shall be made from^A steel and shall fit the back of the cavity with a minimum gap of^B.
^A Indicate material of backing plate.
^B Indicate dimension of maximum gap.
6.5 Surfaces of the weld preparation shall be cleaned of all oil, grease, dirt, scale, slag, shot blasting grit, or any foreign material which may be harmful to the quality of the weld. Surfaces of backing plates when used shall also meet the same cleanliness requirements.
6.6 All surfaces of the weld preparation shall be inspected as follows:^A
^A Indicate type of inspection.

7. Preheat

7.1 Preheat and interpass temperature shall be maintained in the range from^A to^B during^C.
^A Indicate minimum temperature.
^B Indicate maximum temperature.
^C Indicate if preheat maintenance is during welding or until postweld heat treatment is performed.
7.2 Preheat for tack welding of backing plates is the same as required for welding.
7.3 Minimum temperature before applying heat shall be^A.
^A Indicate temperature.
7.4 Local preheating to the temperatures indicated may be performed so that the heated area completely surrounds the weld preparation for a minimum distance of^A in any direction.
^A Indicate minimum distance for local preheating.

8. Welding Position

8.1 Welds shall be made in the^A position.
^A Indicate position or positions in which the welding will be performed. See Fig. 4.

9. Electrical Characteristics

9.1 The current used shall be^A. The base material shall be attached to the^B welding electrode lead.
^A Indicate whether direct or alternating current. If direct, state whether non-pulsed or pulsed. If pulsed, state frequency.
^B Indicate whether electrode positive (EP) or electrode negative (EN) output terminal of power supply is used.

Electrode Wire	Diameter ^A	Amperage ^A	Range ^A	Voltage ^A
	_____	_____	_____	_____
	_____	_____	_____	_____
	_____	_____	_____	_____

^A Indicate for each diameter of electrode, the amperage, the range of amperage permitted, and the voltage requirements. For welding processes using wire, indicate wire diameter, wire feed speed, and current requirements.

9.2 Electrodes subject to moisture absorption must be stored and handled to maintain dryness according to the following:^A
^A Where applicable, indicate electrode care instructions.

10. Welding Details

10.1 The width of any pass of welding shall not exceed^A times the size of the filler metal used.
^A Indicate the number for controlling the maximum width.
10.2 Craters shall be properly filled before each interruption of the arc.
10.3 Slag or flux shall be removed on any bead before depositing the next successive bead.
10.4 Interpass inspection shall be performed according to the following:^A
^A Indicate degree of interpass inspection required.
10.5 Peening shall be performed according to the following:^A
^A Indicate the degree of peening required. Indicate any limits on peening first and last layers.

11. Post-Weld Heat Treatment

11.1 Post-weld heat treatment shall consist of the following:^A
^A Indicate the heating and cooking rates, holding temperatures and times.

12. Inspection

12.1 Inspection of the completed weld shall be performed according to the following:^A
^A Indicate degree of inspection.

FIG. 3 Report Form 3