



Designation: A683 – 05^{ε1}

Standard Specification for Nonoriented Electrical Steel, Semiprocessed Types¹

This standard is issued under the fixed designation A683; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—The values statement (1.4) was corrected editorially in September 2006.

1. Scope

1.1 This specification covers the detailed requirements to which flat-rolled, nonoriented semiprocessed electrical steel shall conform.

1.2 This steel is produced to specified maximum core-loss values and is intended primarily for commercial power frequency (50- and 60-Hz) applications in magnetic devices. Desirable core-loss and permeability characteristics are developed through heat treatment by the user.

1.3 These nonoriented, semiprocessed electrical steels are low carbon, silicon-iron or silicon-aluminum-iron alloys containing up to about 2.5 % silicon and less than 1 % aluminum.

1.4 The values stated in customary (cgs-emu and inch-pound) units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units which are provided for information only and are not considered standard.

2. Referenced Documents

2.1 *ASTM Standards*:²

[A34/A34M Practice for Sampling and Procurement Testing of Magnetic Materials](#)

[A340 Terminology of Symbols and Definitions Relating to Magnetic Testing](#)

[A343/A343M Test Method for Alternating-Current Magnetic Properties of Materials at Power Frequencies Using Wattmeter-Ammeter-Voltmeter Method and 25-cm Epstein Test Frame](#)

[A664 Practice for Identification of Standard Electrical Steel Grades in ASTM Specifications](#)

¹ This specification is under the jurisdiction of ASTM Committee A06 on Magnetic Properties and is the direct responsibility of Subcommittee A06.02 on Material Specifications.

Current edition approved Aug. 15, 2005. Published August 2005. Originally approved in 1974. Last previous edition approved in 1999 as A683/A683M – 99. DOI: 10.1520/A0683-05E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[A700 Practices for Packaging, Marking, and Loading Methods for Steel Products for Shipment](#)

[A719/A719M Test Method for Lamination Factor of Magnetic Materials](#)

[A720/A720M Test Method for Ductility of Nonoriented Electrical Steel](#)

[A971 Test Method for Measuring Edge Taper and Crown of Flat-Rolled Electrical Steel Coils](#)

[A976 Classification of Insulating Coatings for Electrical Steels by Composition, Relative Insulating Ability and Application](#)

3. Terminology

3.1 The terms and symbols used in this specification are defined in Terminology [A340](#).

4. Classification

4.1 The nonoriented electrical steel types described by this specification are shown in [Table 1](#).

5. Ordering Information

5.1 Orders for material under this specification shall include as much of the following information as necessary to describe the desired material adequately:

5.1.1 ASTM specification number.

5.1.2 Core-loss type number.

5.1.3 Surface coating type.

5.1.4 Thickness, width, and length (if in cut lengths instead of coils).

5.1.5 Total weight of ordered item.

5.1.6 Limitations in coil size or lift weights.

5.1.7 *End Use*—The user shall disclose as much pertinent information as possible about the intended application to enable the producer to provide material characteristics most suitable for specific fabricating practices.

5.1.8 Special requirements or exceptions to the provisions of this specification.

6. Materials and Manufacture

6.1 *Typical Melting and Casting:*

TABLE 1 Core-Loss Types^A and Maximum Core Losses^B at a Magnetic Flux Density of 15 kG (1.5 T) and 60 Hz^C of Quality Evaluation Annealed Epstein Specimens^D

0.0185-in. (0.47-mm) Thickness			0.025-in. (0.64-mm) Thickness		
Core-Loss Type	Maximum Core Loss		Core-Loss Type	Maximum Core Loss	
	W/lb	W/kg		W/lb	W/kg
47S155	1.55	3.42	64S200	2.00	4.41
47S165	1.65	3.64	64S210	2.10	4.63
47S175	1.75	3.86	64S220	2.20	4.85
47S190	1.90	4.19	64S230	2.30	5.07

^A See Practice A664.

^B The test density shall be the correct ASTM assumed density (in accordance with 14.2) for the chemistry used by the producer to meet the property requirements of this specification.

^C Maximum core losses at a magnetic flux density of 15 kG (1.5 T) and 50 Hz are 0.79 times maximum core losses at 60 Hz.

^D One half of strips cut parallel to the steel rolling direction and one half of strips cut perpendicular to the steel rolling direction.

6.1.1 These semiprocessed electrical steels may be made by basic-oxygen, electric furnace, or other steelmaking practice(s).

6.1.2 These electrical steels are characterized by low carbon, usually less than 0.030 %. The principal alloying element is commonly silicon, but aluminum up to about 0.8 % is sometimes used instead of, or in addition to, silicon, depending on mill processing practice for the desired magnetic grade. Individual producers will often have different silicon or aluminum contents for a particular grade as a result of intrinsic mill processing procedures.

6.1.3 Sulfur content is typically less than 0.025 % and is usually lowest in the numbered types representing lowest core loss. Manganese is typically present in amounts between 0.10 and 0.70 %. Phosphorus, copper, nickel, chromium, molybdenum, antimony, and tin are usually present only in residual amounts except in the higher numbered core-loss types where phosphorus, tin, or antimony up to 0.15 % may be present.

6.1.4 The producer is not required to report chemical composition of each lot except where a clear need for such information has been shown. In such cases, the analyses to be reported shall be negotiated between the producer and user.

6.2 *Typical Processing*—The processing sequence for semiprocessed nonoriented electrical steel comprises hot rolling, pickling, cold rolling, and annealing. An additional annealing operation may precede or follow the pickling operation.

6.3 When changes in the manufacture of the material are believed to exert possible significant effects upon the user's fabricating practices and upon the magnetic performance to be obtained in the specified end use, the producer shall notify the user before shipment is made so the user has an opportunity to evaluate the effects.

7. Magnetic Property Requirements Magnetic Property Requirements

7.1 *Specific Core Loss*—Each core-loss type of electrical steel is identified by maximum core-loss limits as shown in Table 1.

7.2 *Permeability*—The permeability at all inductions shall be as high as possible consistent with the required core-loss limits that govern the grade. Typical relative peak permeability (μ_p) values are given in Appendix X1.

7.3 *Specific Exciting Power*—The rms exciting power required for the excitation of a particular type of electrical steel is frequently useful to the user. Typical values of specific exciting power are given in Appendix X1.

8. Surface Insulation Characteristics

8.1 Unless otherwise specified, semiprocessed electrical steels are supplied with a thin, tightly adherent surface oxide (coating Type C-0 in Classification A976) which has sufficient insulating ability for most small cores. The insulating ability of coating Type C-0 can be enhanced during the user's heat treatment by using a slightly oxidizing atmosphere.

8.2 Applied Coatings:

8.2.1 Semiprocessed electrical steels may also be supplied with a thin applied coating (coating Types C-4-AS and C-5-AS in Classification A976) which has sufficient insulating ability for most small cores. A major purpose for using coating Types C-4-AS and C-5-AS is to reduce surface-to-surface sticking during the user's heat treatment.

8.2.2 When essential, higher levels of insulating ability may be obtained by coating semiprocessed electrical steels with thicker applied coatings (coating Types C-4 and C-5 in Classification A976). Usage of such coatings should be approached with great caution since the coatings may have an inhibiting effect on decarburization and thereby limit the attainment of the lowest core losses in the user's heat treatment.

9. Mechanical Requirements

9.1 *Lamination Factor*—The lamination factor shall be determined using Test Method A719/A719M and shall be as high as practicable. It is normally greater for 0.025-in. (0.64-mm) thick steel than for 0.0185-in. (0.47-mm) thick steel and when the surfaces are smooth and have no applied coating.

9.2 *Ductility*—The material shall be as ductile as possible, consistent with meeting magnetic requirements. When required the ductility shall be determined by the bend test for ductility described in Test Method A720/A720M. Ductility is a function of microstructure and may differ between producers. The user's anneal may also affect ductility.

10. Dimensions and Permissible Variations

10.1 *Thickness*—Specified thickness should be one of the common thicknesses as follows:

Thickness, in. (mm)
0.025 (0.64)
0.0185 (0.47)

10.2 *Thickness Variations*—The average thickness of the material supplied shall be as close as possible to the ordered thickness. Measurements made with a contacting micrometer at points no closer than 3/8 in. (10 mm) from the edge of a sheet or coil of specified width shall not differ from the specified thickness by more than the values (which include taper) shown in Table 2.

10.3 *Edge Taper*—The rolling of flat-rolled strip inherently produces an edge that is thinner than the rest of the strip. This characteristic is termed "edge taper," "feather," or "gamma."