

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 3682:1998](#)

<https://standards.iteh.ai/catalog/standards/sist/c0df144f-dc3f-4a71-bc4e-7c897af55ace/sist-en-iso-3682-1998>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 3682

April 1998

ICS 87.060.20

Descriptors: see ISO document

English version

**Binders for paints and varnishes - Determination of acid value -
Titrimetric method (ISO 3682:1996)**

Liants pour peintures et vernis - Détermination de l'indice
d'acide - Méthode titrimétrique (ISO 3682:1996)

Bindemittel für Beschichtungsstoffe - Bestimmung der
Säurezahl - Titrimetrisches Verfahren (ISO 3682:1996)

This European Standard was approved by CEN on 9 March 1998.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN ISO 3682:1998](https://standards.iteh.ai/catalog/standards/sist/c0df144f-dc3f-4a71-bc4e-7c897af55ace/sist-en-iso-3682-1998)

<https://standards.iteh.ai/catalog/standards/sist/c0df144f-dc3f-4a71-bc4e-7c897af55ace/sist-en-iso-3682-1998>



REPUBLIKA SLOVENIJA
MINISTRSTVO ZA ZNANOST IN TEHNOLOGIJO
Urad RS za standardizacijo in meroslovje
LJUBLJANA

SIST..... **EN ISO 3682**

PREVZET PO METODI RAZGLASITVE

-08- 1998



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Page 2
EN ISO 3682:1998

Foreword

The text of the International Standard from Technical Committee ISO/TC 35 "Paints and varnishes" of the International Organization for Standardization (ISO) has been taken over as an European Standard by Technical Committee CEN/TC 139 "Paints and varnishes", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by month of October 1998, and conflicting national standards shall be withdrawn at the latest by October 1998.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 3682:1996 has been approved by CEN as a European Standard without any modification.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 3682:1998

<https://standards.iteh.ai/catalog/standards/sist/c0df144f-dc3f-4a71-bc4e-7c897af55ace/sist-en-iso-3682-1998>



INTERNATIONAL
STANDARD

ISO
3682

Third edition
1996-06-01

**Binders for paints and varnishes —
Determination of acid value —
Titrimetric method**

iTeh STANDARD PREVIEW

(standards.iteh.ai)

*Liants pour peintures et vernis — Détermination de l'indice d'acide —
Méthode titrimétrique*

[SIST EN ISO 3682:1998](https://standards.iteh.ai/catalog/standards/sist/c0df144f-dc3f-4a71-bc4e-7c897af55ace/sist-en-iso-3682-1998)

<https://standards.iteh.ai/catalog/standards/sist/c0df144f-dc3f-4a71-bc4e-7c897af55ace/sist-en-iso-3682-1998>



Reference number
ISO 3682:1996(E)

ISO 3682:1996(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 3682 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 10, *Test methods for binders for paints and varnishes*.

This third edition cancels and replaces the second edition (ISO 3682:1983), which has been technically and editorially revised. The main change is that the acid value is no longer related to 1 g of non-volatile matter of the product but to 1 g of the product itself.

© ISO 1996

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Binders for paints and varnishes — Determination of acid value — Titrimetric method

1 Scope

This International Standard specifies a titrimetric method for determining the acid value of binders for paints and varnishes.

It is not applicable to phenolic resins.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 385-1:1984, *Laboratory glassware — Burettes — Part 1: General requirements*.

ISO 842:1984, *Raw materials for paints and varnishes — Sampling*.

3 Definition

For the purposes of this International Standard, the following definition applies:

3.1 acid value: The number of milligrams of potassium hydroxide (KOH) required to neutralize the free acids in 1 g of the product tested.

4 Principle

The free acids contained in a test portion are titrated with potassium hydroxide solution, either in the presence of a colour indicator or potentiometrically.

5 Reagents

During the analysis, use only reagents of recognized analytical grade.

5.1 Solvent mixture, consisting of 2 parts by volume of toluene and 1 part by volume of at least 95 % (V/V) ethanol (see note 4 to 8.2), unless otherwise agreed or specified. If denaturated alcohol, or alcohol of another quality, is used, its suitability for the test shall be checked. Neutralize, using phenolphthalein as indicator, the solvent mixture with potassium hydroxide solution (5.2) prior to use.

5.2 Potassium hydroxide, standard volumetric solution, $c(\text{KOH}) = 0,1 \text{ mol/l}$, in 95 % (V/V) ethanol (see 5.1) or in methanol, free from carbonates, standardized against potassium hydrogen phthalate.

NOTE 1 A 0,5 mol/l standard volumetric solution of potassium hydroxide may also be used in cases when more than 50 ml of titrant would be required with a 0,1 mol/l solution, thus avoiding the additional errors involved in refilling the 50 ml burette.

Check the concentration of this solution on the day of use.

5.3 Phenolphthalein, 10 g/l solution in 95 % (V/V) ethanol, in methanol or in isopropanol.

NOTE 2 Other suitable indicators may be used, for example a 10 g/l solution of bromothymol blue in 95 % (V/V) ethanol, in methanol or in isopropanol.

6 Apparatus

Ordinary laboratory apparatus and glassware, together with the following:

6.1 Conical flask, capacity 250 ml.

6.2 Burette, capacity 50 ml, complying with the requirements of ISO 385-1.

6.3 Potentiometric titration apparatus, fitted with a glass electrode and a reference electrode. The use of this apparatus is an optional alternative (see note 3 to 8.2).

6.4 Magnetic stirrer.

7 Sampling

Take a representative sample of the product to be tested, as described in ISO 842.

8 Procedure

Carry out the determination in duplicate.

8.1 Test portion

By reference to table 1, select the appropriate mass of test portion to be taken. This mass shall be chosen so that the volume of potassium hydroxide solution (5.2) used is in the range 10 ml to 30 ml.

Table 1 — Mass of test portion

Expected acid value mg KOH/g	Approximate mass of test portion
up to 10	10
above 10 to 25	5
above 25 to 50	2,5
above 50 to 150	1
above 150	0,5

Weigh, to the nearest 1 mg, the test portion into the conical flask (6.1).

8.2 Determination

Dissolve the test portion (8.1), with stirring, in 50 ml of the solvent mixture (5.1).

If free acid anhydrides are present in the binder, as in the case of certain polyester resins, the alcoholic potassium hydroxide solution reacts only partially with the anhydrides. This, however, is generally of little importance with most binders because of the small amount of free anhydrides present. If it is suspected that significant amounts of free anhydrides are present, an aqueous potassium hydroxide solution shall be used.

Warm, if necessary, but cool the solution to room temperature before carrying out the titration.

CAUTION — If the solution is warmed, this shall be carried out in a fume cupboard or well ventilated atmosphere. Avoid overheating.

Add 2 or 3 drops of phenolphthalein solution (5.3) and titrate rapidly with potassium hydroxide solution (5.2) until a red coloration just appears and is stable for at least 10 s while the solution is being stirred.

NOTE 3 With some substances, for example certain polyester resins, no very definite colour change will be obtained with phenolphthalein. In such cases, another indicator, for example bromothymol blue (see note 2 to 5.3) may be used. In all cases of doubt, and especially when the solutions are coloured, a potentiometric titration to pH 7 is to be preferred, using glass electrodes with a suitable response time.

In the case of polybasic acids, there may also be points of inflection above pH 7. In such cases, the point of inflection in the most basic range shall be taken as the end point.

If a precipitate is formed during the titration which interferes with the determination of the end point, add additional solvent as indicated in note 4. When a suitable solvent mixture has been found, repeat the titration using the same solvent mixture.

NOTE 4 The type and volume of solvent mixture to be used depend on whether precipitation occurs during the titration. The volume of solvent mixture may be increased up to 150 ml, or 25 ml of acetone may be added. The purpose of the solvent is to prevent precipitation during titration and not to dissolve the resin initially.

Use the same solvent mixture for the blank test (8.3) and record the type and volume of the solvent mixture in the test report (clause 10).

8.3 Blank test

Carry out a blank test following the same procedure, but omitting the test portion.

NOTE 5 Theoretically, if the neutralization of the solvent mixture (5.1) has been carried out correctly, the result of the blank test will be zero.

9 Expression of results

9.1 Calculation

Calculate the acid value AV, in milligrams of KOH per gram of product, using the equation

$$AV = \frac{(V_1 - V_0) \times c \times 56,1}{m}$$