



Designation: C 315 – 06

## Standard Specification for Clay Flue Liners<sup>1</sup>

This standard is issued under the fixed designation C 315; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This specification establishes the criteria for acceptance, prior to installation, of clay flue liners used for conveying hot gases in masonry chimneys.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 For installation of clay flue liners, see Practice C 1283.

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

C 67 Test Methods for Sampling and Testing Brick and Structural Clay Tile

C 301 Test Methods for Vitrified Clay Pipe

C 896 Terminology Relating to Clay Products

C 1283 Practice for Installing Clay Flue Lining

### 3. Terminology

3.1 *Definitions*—Clay, fire clay, shale, and surface clay are as defined in Terminology C 896.

### 4. Classification

4.1 *Types*—Flue liners acceptable under this specification shall be designated as rectangular nonmodular, rectangular modular, round or oval.

### 5. Materials and Manufacture

5.1 Flue liners shall be manufactured from fire clay, shale, surface clay, or a combination of these materials that when formed and fired to suitable temperatures, shall yield a product that is strong, durable, serviceable, and conforms to this specification.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C04 on Vitrified Clay Pipe and is the direct responsibility of Subcommittee C04.20 on Methods of Test and Specifications.

Current edition approved Sept. 1, 2006. Published September 2006. Originally approved in 1953. Last previous edition approved in 2002 as C 315 – 02.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

### 6. Physical and Chemical Requirements Physical and Chemical Requirements

#### 6.1 Absorption:

6.1.1 The absorption of clay flue liners shall not exceed 8.0 % when tested in accordance with Test Methods C 301.

6.1.2 *Test Specimens*— Five dry test specimens shall be obtained from the five flue liners to be tested and shall measure as closely as possible to 4 by 4 in. (100 by 100 mm) per side. All rough edges shall be ground off and loose particles removed.

6.1.3 If any of the test specimens fail to meet the requirements, the manufacturer shall be allowed to retest on two additional specimens for each one that failed. The flues will be acceptable if all the subsequent specimens for retest meet the requirements.

#### 6.2 Acid Resistance:

6.2.1 This is a test used to determine the resistance of clay flue liners to the action of acids encountered in chimneys. This test shall be performed only when specified.

6.2.2 The flue liner shall be acceptable if the acid soluble material does not exceed 0.25 % when tested in accordance with Test Methods C 301.

6.2.3 *Test Specimens*— Select one test specimen from each size of flue liner. The specimens shall measure about 2 by 2 in. (51 by 51 mm) per side and weigh not more than 200 g. They shall be sound pieces with all edges freshly broken, free of cracks or shattered edges, and shall be thoroughly cleaned.

#### 6.3 Freeze-Thaw Cycle Test:

6.3.1 When flue liners are tested in accordance with Test Methods C 67, Section 8 on structural clay tile, there shall be no breakage and the percentage of weight loss shall not exceed 0.5 %.

6.3.2 *Test Specimens*— Five dry test specimens shall be obtained from the five flue liners to be tested and shall measure as closely as possible to 4 by 4 in. (100 by 100 mm) per side. All rough edges shall be ground off and loose particles removed.