
**Priprava jeklenih podlag pred nanašanjem barvnih in sorodnih premazov -
Preskusne metode za kovinske granulate za peskanje - 1. del: Vzorčenje (ISO
11125-1:1993)**

Preparation of steel substrates before application of paints and related products - Test
methods for metallic blast-cleaning abrasives - Part 1: Sampling (ISO 11125-1:1993)

Vorbereitung von Stahlflächen vor dem Auftragen von Beschichtungsstoffen -
Prüfverfahren für metallische Strahlmittel - Teil 1: Probenahme (ISO 11125-1:1993)
(standards.iteh.ai)

Préparation des subjectiles d'acier avant application de peintures et de produits
assimilés - Méthodes d'essai pour abrasifs métalliques destinés à la préparation par
projection - Partie 1: Echantillonnage (ISO 11125-1:1993)

Ta slovenski standard je istoveten z: EN ISO 11125-1:1997

ICS:

25.220.10 Priprava površine Surface preparation

SIST EN ISO 11125-1:1997 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 11125-1:1997](#)

<https://standards.iteh.ai/catalog/standards/sist/19cae432-6042-4721-ba60-d2c217acf728/sist-en-iso-11125-1-1997>

EUROPEAN STANDARD

EN ISO 11125-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 1997

ICS 87.020

Descriptors: see ISO document

English version

**Preparation of steel substrates before application
of paints and related products - Test methods for
metallic blast-cleaning abrasives - Part 1:
Sampling (ISO 11125-1:1993)**

Préparation des subjectiles d'acier avant
application de peintures et de produits
assimilés - Méthodes d'essai pour abrasifs
métalliques destinés à la préparation par
projection - Partie 1: Echantillonnage
(ISO 11125-1:1993)

Vorbereitung von Stahloberflächen vor dem
Auftragen von Beschichtungsstoffen -
Prüfverfahren für metallische Strahlmittel -
Teil 1: Probenahme (ISO 11125-1:1993)

[SIST EN ISO 11125-1:1997](https://standards.iteh.ai/catalog/standards/sist/19cae432-6042-4721-ba60-d2c217acf728/sist-en-iso-11125-1-1997)

<https://standards.iteh.ai/catalog/standards/sist/19cae432-6042-4721-ba60-d2c217acf728/sist-en-iso-11125-1-1997>

This European Standard was approved by CEN on 1997-05-28. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart,36 B-1050 Brussels

Page 2
EN ISO 11125-1:1997

Foreword

The text of the International Standard from Technical Committee ISO/TC 35 "Paints and varnishes" of the International Organization for Standardization (ISO) has been taken over as an European Standard by Technical Committee CEN/TC 139 "Paints and varnishes", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 1997, and conflicting national standards shall be withdrawn at the latest by December 1997.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW
Endorsement notice
(standards.iteh.ai)

The text of the International Standard ISO 11125-1:1993 has been approved by CEN as a European Standard without any modification.

<https://standards.iteh.ai/catalog/standards/sist/19cae432-6042-4721-ba60-d2c217acf728/sist-en-iso-11125-1-1997>

INTERNATIONAL
STANDARD

ISO
11125-1

First edition
1993-12-15

**Preparation of steel substrates before
application of paints and related
products — Test methods for metallic
blast-cleaning abrasives —**

iTeh STANDARD PREVIEW

Part 1:
Sampling

[SIST EN ISO 11125-1:1997](https://standards.iteh.ai/catalog/standards/sist/19cae432-6042-4721-ba60-d2c217acf728/sist-en-iso-11125-1-1997)

[https://standards.iteh.ai/catalog/standards/sist/19cae432-6042-4721-ba60-](https://standards.iteh.ai/catalog/standards/sist/19cae432-6042-4721-ba60-d2c217acf728/sist-en-iso-11125-1-1997)

[d2c217acf728/sist-en-iso-11125-1-1997](https://standards.iteh.ai/catalog/standards/sist/19cae432-6042-4721-ba60-d2c217acf728/sist-en-iso-11125-1-1997)

*Préparation des subjectiles d'acier avant application de peintures et de
produits assimilés — Méthodes d'essai pour abrasifs métalliques destinés
à la préparation par projection —*

Partie 1: Échantillonnage



Reference number
ISO 11125-1:1993(E)

ISO 11125-1:1993(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 11125-1 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 12, *Preparation of steel substrates before application of paints and related products*.

ISO 11125 consists of the following parts, under the general title *Preparation of steel substrates before application of paints and related products* — *Test methods for metallic blast-cleaning abrasives*:

- Part 1: *Sampling*
- Part 2: *Determination of particle size distribution*
- Part 3: *Determination of hardness*
- Part 4: *Determination of apparent density*
- Part 5: *Determination of percentage defective particles and of microstructure*
- Part 6: *Determination of foreign matter*
- Part 7: *Determination of moisture*
- Part 8: *Determination of abrasive mechanical properties*

© ISO 1993

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

At the time of publication of this part of ISO 11125, part 8 was in course of preparation.

Annex A of this part of ISO 11125 is for information only.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 11125-1:1997](https://standards.iteh.ai/catalog/standards/sist/19cae432-6042-4721-ba60-d2c217acf728/sist-en-iso-11125-1-1997)

<https://standards.iteh.ai/catalog/standards/sist/19cae432-6042-4721-ba60-d2c217acf728/sist-en-iso-11125-1-1997>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

This page intentionally left blank

SIST EN ISO 11125-1:1997

<https://standards.iteh.ai/catalog/standards/sist/19cae432-6042-4721-ba60-d2c217acf728/sist-en-iso-11125-1-1997>

Preparation of steel substrates before application of paints and related products — Test methods for metallic blast-cleaning abrasives —

Part 1: Sampling

1 Scope

This is one of a number of parts of ISO 11125 dealing with the sampling and testing of metallic abrasives for blast-cleaning.

The types of metallic abrasive and requirements on each are contained in the various parts of ISO 11124.

The ISO 11124 and ISO 11125 series have been drafted as a coherent set of International Standards on metallic blast-cleaning abrasives. Information on all parts of both series is given in annex A.

This part of ISO 11125 specifies a method for the sampling of metallic blast-cleaning abrasives from consignments and for the subdivision of the sample into quantities suitable for undertaking the appropriate test methods specified in other parts of ISO 11125.

2 Definitions

For the purposes of this part of ISO 11125, the following definitions apply.

2.1 total quantity: The overall quantity of the abrasive to be tested (for example the quantity of a consignment) for which the sampling procedure is to be considered as representative.

2.2 sample unit: The packaged unit of sale, e.g. pallet, drum, bulk sack, from which single samples (see 2.3) are taken.

2.3 single sample: A sample obtained from the total quantity by a single sampling operation. This sample is not immediately used for testing.

2.4 mixed sample: A sample obtained by mixing a number of single samples.

2.5 reduced sample: A sample obtained by reduction of a mixed sample.

NOTE 1 In order to obtain a sample quantity which is suitable for testing, all reduced samples but one are discarded after each reduction; the reduction procedure is then repeated if necessary on the sample retained.

2.6 test sample: A sample that comprises a mass or volume sufficient for testing, portions of which are immediately used for testing.

3 Apparatus

3.1 Sample thief, made from seamless steel tubing of inside diameter approximately 25 mm and length approximately 800 mm. The tube shall be pointed at one end and have a "T" handle at the other end. Holes shall be bored in a straight line, lengthways along the tube, and spaced at 50 mm intervals. The diameter of the holes shall be determined by the size of the particles to be sampled and shall be approximately three times the size of the largest particle.

NOTE 2 It is usually sufficient to use holes 10 mm in diameter for metallic abrasives.