



Designation: D4463 – 96 (Reapproved 2006)

Standard Guide for Metals Free Steam Deactivation of Fresh Fluid Cracking Catalysts¹

This standard is issued under the fixed designation D4463; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This guide covers the deactivation of fresh fluid catalytic cracking (FCC) catalyst by hydrothermal treatment prior to the determination of the catalytic cracking activity in the microactivity test (MAT).

1.2 The hydrothermal treatment of fresh FCC catalyst, prior to the MAT, is important because the catalytic activity of the catalyst in its fresh state is an inadequate measure of its true commercial performance. During operation in a commercial cracking unit, the catalyst is deactivated by thermal, hydrothermal and chemical degradation. Therefore, to maintain catalytic activity, fresh catalyst is added (semi) continuously to the cracking unit, to replace catalyst lost through the stack or by withdrawal, or both. Under steady state conditions, the catalyst inventory of the unit is called equilibrium catalyst. This catalyst has an activity level substantially below that of fresh catalyst. Therefore, artificially deactivating a fresh catalyst prior to determination of its cracking activity should provide more meaningful catalyst performance data.

1.3 Due to the large variations in properties among fresh FCC catalyst types as well as between commercial cracking unit designs or operating conditions, or both, no single set of steam deactivation conditions is adequate to artificially simulate the equilibrium catalyst for all purposes.

1.3.1 In addition, there are many other factors that will influence the properties and performance of the equilibrium catalyst. These include, but are not limited to: deposition of heavy metals such as Ni, V, Cu; deposition of light metals such as Na; contamination from attrited refractory linings of vessel walls. Furthermore, commercially derived equilibrium catalyst represents a distribution of catalysts of different ages (from fresh to >300 days). Despite these apparent problems, it is possible to obtain reasonably close agreement between the performances of steam deactivated and equilibrium catalysts. It is also recognized that it is possible to steam deactivate a catalyst so that its properties and performance poorly represent the equilibrium. It is therefore recommended that when assess-

ing the performance of different catalyst types, a common steaming condition be used. Catalyst deactivation by metals deposition is not addressed in this guide.

1.4 This guide offers two approaches to steam deactivate fresh catalysts. The first part provides specific sets of conditions (time, temperature and steam pressure) that can be used as general pre-treatments prior to comparison of fresh FCC catalyst MAT activities (Test Method [D3907](#)) or activities plus selectivities (Test Method [D5154](#)).

1.4.1 The second part provides guidance on how to pretreat catalysts to simulate their deactivation in a specific FCCU and suggests catalyst properties which can be used to judge adequacy of the simulation. This technique is especially useful when examining how different types of catalyst may perform in a specific FCCU, provided no other changes (catalyst addition rate, regenerator temperature, contaminant metals levels, etc.) occur. This approach covers catalyst physical properties that can be used as monitors to indicate the closeness to equilibrium catalyst properties.

1.5 The values stated in SI units are to be regarded as standard. The values given in parentheses are for information only.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

[D3663 Test Method for Surface Area of Catalysts and Catalyst Carriers](#)

[D3907 Test Method for Testing Fluid Catalytic Cracking \(FCC\) Catalysts by Microactivity Test](#)

[D3942 Test Method for Determination of the Unit Cell Dimension of a Faujasite-Type Zeolite](#)

[D4365 Test Method for Determining Micropore Volume and Zeolite Area of a Catalyst](#)

¹ This guide is under the jurisdiction of ASTM Committee [D32](#) on Catalysts and is the direct responsibility of Subcommittee [D32.04](#) on Catalytic Properties.

Current edition approved Oct. 1, 2006. Published November 2006. Originally approved in 1985. Last previous edition approved in 2001 as D4463–96(2001). DOI: 10.1520/D4463-96R06.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.