



# SLOVENSKI STANDARD

## SIST ISO 16000-28:2013

01-december-2013

---

**Notranji zrak - 28. del: Določevanje emisij vonjav iz gradbenih proizvodov s preskusno komoro**

Indoor air - Part 28: Determination of odour emissions from building products using test chambers

### iTeh STANDARD PREVIEW

Air intérieur - Partie 28: Détermination des émissions d'odeurs des produits de construction au moyen de chambres d'essai

[SIST ISO 16000-28:2013](https://standards.iteh.ai/catalog/standards/sist/2a0e0fd8-d7cf-4fcc-8baf-8cc169920530/sist-iso-16000-28-2013)

Ta slovenski standard je istoveten z: **ISO 16000-28:2012**

---

**ICS:**

13.040.20      Kakovost okoljskega zraka      Ambient atmospheres

**SIST ISO 16000-28:2013**

**en,fr**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST ISO 16000-28:2013](#)

<https://standards.iteh.ai/catalog/standards/sist/2a0e0fd8-d7cf-4fcc-8baf-8ce169920530/sist-iso-16000-28-2013>

# INTERNATIONAL STANDARD

**ISO**  
**16000-28**

First edition  
2012-03-15

---

---

## Indoor air —

### Part 28: Determination of odour emissions from building products using test chambers

*Air intérieur —*

*Partie 28: Détermination des émissions d'odeurs des produits de  
construction au moyen de chambres d'essai*

**(standards.iteh.ai)**

[SIST ISO 16000-28:2013](https://standards.iteh.ai/catalog/standards/sist/2a0e0fd8-d7cf-4fcc-8baf-8ce169920530/sist-iso-16000-28-2013)

<https://standards.iteh.ai/catalog/standards/sist/2a0e0fd8-d7cf-4fcc-8baf-8ce169920530/sist-iso-16000-28-2013>



Reference number  
ISO 16000-28:2012(E)

© ISO 2012

## iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST ISO 16000-28:2013

<https://standards.iteh.ai/catalog/standards/sist/2a0e0fd8-d7cf-4fcc-8baf-8ce169920530/sist-iso-16000-28-2013>



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

Foreword .....	v
Introduction .....	vii
<b>1 Scope .....</b>	<b>1</b>
<b>2 Normative references .....</b>	<b>1</b>
<b>3 Terms, definitions, symbols, units and abbreviated terms .....</b>	<b>1</b>
<b>3.1 Terms and definitions .....</b>	<b>1</b>
<b>3.2 Symbols and units .....</b>	<b>4</b>
<b>3.3 Abbreviated terms .....</b>	<b>4</b>
<b>4 Principle .....</b>	<b>5</b>
<b>5 Test facilities .....</b>	<b>5</b>
<b>5.1 General .....</b>	<b>5</b>
<b>5.2 Apparatus .....</b>	<b>5</b>
<b>5.3 Test chamber and equipment materials .....</b>	<b>6</b>
<b>5.4 Air supply and mixing facilities .....</b>	<b>6</b>
<b>5.5 Airtightness .....</b>	<b>6</b>
<b>5.6 Odour sampling and assessment devices .....</b>	<b>6</b>
<b>6 Test conditions .....</b>	<b>7</b>
<b>6.1 General .....</b>	<b>7</b>
<b>6.2 Temperature and relative humidity in the test chamber .....</b>	<b>8</b>
<b>6.3 Supply air quality and background concentration in the test chamber .....</b>	<b>8</b>
<b>6.4 Air velocity in the test chamber .....</b>	<b>8</b>
<b>6.5 Area-specific air flow rate and air exchange rate in the test chamber .....</b>	<b>8</b>
<b>6.6 Test chamber airtightness .....</b>	<b>9</b>
<b>6.7 Efficiency of the internal test chamber air mixing .....</b>	<b>9</b>
<b>6.8 Test chamber and test room background odour .....</b>	<b>9</b>
<b>7 Test specimens .....</b>	<b>10</b>
<b>8 Odour testing from emission chamber .....</b>	<b>11</b>
<b>8.1 Test chamber preparation .....</b>	<b>11</b>
<b>8.2 Test specimen location in the test chamber .....</b>	<b>11</b>
<b>8.3 Time of odour measurements .....</b>	<b>11</b>
<b>9 Odour panels .....</b>	<b>11</b>
<b>9.1 Panel leader .....</b>	<b>11</b>
<b>9.2 Panel selection .....</b>	<b>12</b>
<b>9.3 Code of behaviour of the panel members .....</b>	<b>12</b>
<b>9.4 Panel size and accuracy of the evaluation .....</b>	<b>12</b>
<b>10 Odour assessment .....</b>	<b>13</b>
<b>10.1 General .....</b>	<b>13</b>
<b>10.2 Acceptability using an untrained panel .....</b>	<b>13</b>
<b>10.3 Perceived odour intensity .....</b>	<b>14</b>
<b>10.4 Complementary method — Hedonic tone using an untrained panel .....</b>	<b>15</b>
<b>11 Test report .....</b>	<b>15</b>
<b>Annex A (normative) System for quality assurance/quality control .....</b>	<b>17</b>
<b>Annex B (informative) Statistical background .....</b>	<b>18</b>
<b>Annex C (informative) Examples of diffuser and mask used for odour evaluation .....</b>	<b>20</b>
<b>Annex D (informative) Description of a possible sampling and presentation device for air samples collected at the emission chamber outlet .....</b>	<b>21</b>
<b>Annex E (informative) Panel selection using the stick method .....</b>	<b>26</b>

**ISO 16000-28:2012(E)**

<b>Annex F (informative) Panel selection using five standard odorants .....</b>	<b>28</b>
<b>Annex G (informative) Training procedure for the comparative scale .....</b>	<b>30</b>
<b>Annex H (informative) Examples of area-specific air flow rates in a model room .....</b>	<b>33</b>
<b>Annex I (normative) Acceptability scale for an untrained panel.....</b>	<b>34</b>
<b>Annex J (normative) Hedonic scale for an untrained panel.....</b>	<b>35</b>
<b>Bibliography .....</b>	<b>36</b>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST ISO 16000-28:2013](https://standards.iteh.ai/catalog/standards/sist/2a0e0fd8-d7cf-4fcc-8baf-8ce169920530/sist-iso-16000-28-2013)

<https://standards.iteh.ai/catalog/standards/sist/2a0e0fd8-d7cf-4fcc-8baf-8ce169920530/sist-iso-16000-28-2013>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 16000-28 was prepared by Technical Committee ISO/TC 146, *Air quality*, Subcommittee SC 6, *Indoor air*.

ISO 16000 consists of the following parts, under the general title *Indoor air*:

- Part 1: *General aspects of sampling strategy*
- Part 2: *Sampling strategy for formaldehyde*
- Part 3: *Determination of formaldehyde and other carbonyl compounds in indoor air and test chamber air — Active sampling method*
- Part 4: *Determination of formaldehyde — Diffusive sampling method*
- Part 5: *Sampling strategy for volatile organic compounds (VOCs)*
- Part 6: *Determination of volatile organic compounds in indoor and test chamber air by active sampling on Tenax TA® sorbent, thermal desorption and gas chromatography using MS or MS-FID*
- Part 7: *Sampling strategy for determination of airborne asbestos fibre concentrations*
- Part 8: *Determination of local mean ages of air in buildings for characterizing ventilation conditions*
- Part 9: *Determination of the emission of volatile organic compounds from building products and furnishing — Emission test chamber method*
- Part 10: *Determination of the emission of volatile organic compounds from building products and furnishing — Emission test cell method*
- Part 11: *Determination of the emission of volatile organic compounds from building products and furnishing — Sampling, storage of samples and preparation of test specimens*
- Part 12: *Sampling strategy for polychlorinated biphenyls (PCBs), polychlorinated dibenzo-p-dioxins (PCDDs), polychlorinated dibenzofurans (PCDFs) and polycyclic aromatic hydrocarbons (PAHs)*
- Part 13: *Determination of total (gas and particle-phase) polychlorinated dioxin-like biphenyls (PCBs) and polychlorinated dibenzo-p-dioxins/dibenzofurans (PCDDs/PCDFs) — Collection on sorbent-backed filters*
- Part 14: *Determination of total (gas and particle-phase) polychlorinated dioxin-like biphenyls (PCBs) and polychlorinated dibenzo-p-dioxins/dibenzofurans (PCDDs/PCDFs) — Extraction, clean-up and analysis by high-resolution gas chromatography and mass spectrometry*
- Part 15: *Sampling strategy for nitrogen dioxide (NO<sub>2</sub>)*
- Part 16: *Detection and enumeration of moulds — Sampling by filtration*

## ISO 16000-28:2012(E)

- Part 17: Detection and enumeration of moulds — Culture-based method
- Part 18: Detection and enumeration of moulds — Sampling by impaction
- Part 19: Sampling strategy for moulds
- Part 23: Performance test for evaluating the reduction of formaldehyde concentrations by sorptive building materials
- Part 24: Performance test for evaluating the reduction of volatile organic compound (except formaldehyde) concentrations by sorptive building materials
- Part 25: Determination of the emission of semi-volatile organic compounds by building products — Micro-chamber method
- Part 26: Sampling strategy for carbon dioxide (CO<sub>2</sub>)
- Part 28: Determination of odour emissions from building products using test chambers

The following parts are under preparation:

- Part 21: Detection and enumeration of moulds — Sampling from materials
- Part 27: Determination of settled fibrous dust on surfaces by SEM (scanning electron microscopy) (direct method)
- Part 29: Test methods for VOC detectors
- Part 30: Sensory testing of indoor air
- Part 31: Measurement of flame retardants and plasticizers based on organophosphorus compounds — Phosphoric acid ester
- Part 32: Investigation of constructions on pollutants and other injurious factors — Inspections

iteh STANDARD PREVIEW  
(standards.iteh.ai)

SIST ISO 16000-28:2013

<https://standards.iteh.ai/standards/sist/2012-08-15/iso-8846-8ce169920530/sist-iso-16000-28-2013>

## Introduction

Odour evaluation is a complementary method to the chemical testing of emissions from building products.

The determination of odour acceptability, intensity and hedonic tone, and intensity of emissions from building products using test chambers has objectives such as:

- to provide manufacturers, builders, and end users with data useful for the evaluation of the odour impact of building products on the indoor air quality;
- to promote the development of improved products.

The method can also be used for building furnishings.

ISO 16017<sup>[31]</sup> [32] and ISO 12219<sup>[26]</sup>–<sup>[30]</sup> focus on volatile organic compound (VOC) measurements.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 16000-28:2013](https://standards.iteh.ai/catalog/standards/sist/2a0e0fd8-d7cf-4fcc-8baf-8ce169920530/sist-iso-16000-28-2013)

<https://standards.iteh.ai/catalog/standards/sist/2a0e0fd8-d7cf-4fcc-8baf-8ce169920530/sist-iso-16000-28-2013>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST ISO 16000-28:2013](#)

<https://standards.iteh.ai/catalog/standards/sist/2a0e0fd8-d7cf-4fcc-8baf-8ce169920530/sist-iso-16000-28-2013>

## Indoor air —

### Part 28:

## Determination of odour emissions from building products using test chambers

### 1 Scope

This part of ISO 16000 specifies a laboratory test method using test chambers defined in ISO 16000-9 and evaluation procedures for the determination of odours emitted from newly produced building products under defined climate conditions. The method can also, in principle, be applied to aged products. This part of ISO 16000 is applicable to various test chambers used for the determination of emissions from building products.

NOTE This part of ISO 16000 can also be used for other products or materials.

Sampling, transport and storage of materials under test, as well as preparation of test specimens are described in ISO 16000-11.

### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 554, *Standard atmospheres for conditioning and/or testing — Specifications*

ISO 16000-9, *Indoor air — Part 9: Determination of the emission of volatile organic compounds from building products and furnishing — Emission test chamber method*

ISO 16000-11, *Indoor air — Part 11: Determination of the emission of volatile organic compounds from building products and furnishing — Sampling, storage of samples and preparation of test specimens*

EN 13725, *Air quality — Determination of odour concentration by dynamic olfactometry*

### 3 Terms, definitions, symbols, units and abbreviated terms

#### 3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

##### 3.1.1

##### **odour**

pleasant or unpleasant smell caused by chemical compounds emitting to indoor air from a building product or material

##### 3.1.2

##### **acceptability**

assessment of an odour emission to indoor air which can be ascertained according to a scale ranging from “clearly acceptable” to “clearly unacceptable” set by value on a defined evaluation scale

**ISO 16000-28:2012(E)****3.1.3****perceived intensity**

parameter to assess odour intensity based on a comparable scale

NOTE See 5492:2008, 2.8, 2.9 and 4.30.

**3.1.4****hedonic tone**

odour effect, which can be ascertained according to a scale ranging from “extremely pleasant” to “extremely unpleasant”

**3.1.5****panel selection**

procedure to determine which persons are qualified to serve as panel members

**3.1.6****sensory fatigue**

form of sensory adaptation in which a decrease in sensitivity occurs

**3.1.7****sensory adaptation**

temporary modification of the sensitivity of a sense organ due to continued and/or repeated stimulation, which is reversible

[ISO 5492:2008, definition 2.6]

**3.1.8****anosmia**

lack of sensitivity to some olfactory stimulus due to physiological defects, which is not reversible

NOTE Adapted from ISO 5492:2008, 2.32.

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)

[SIST ISO 16000-28:2013](https://standards.iteh.ai/catalog/standards/sist/2a0e0fd8-d7cf-4fcc-8baf-8ce169920530/sist-iso-16000-28-2013)

<https://standards.iteh.ai/catalog/standards/sist/2a0e0fd8-d7cf-4fcc-8baf-8ce169920530/sist-iso-16000-28-2013>

**3.1.9****sensory odour panel**

group of trained or untrained assessors performing the sensory assessment of the odour emission from building products or materials

NOTE See ISO 5492:2008, definition 1.9.

**3.1.10****panel leader**

person whose primary duties are to manage panel activities and recruit, train and monitor the assessors

**3.1.11****panel member**

person who is accepted to assess the odours

**3.1.12****untrained panel**

panel consisting of members who assess the odour emission without any training on odorous references

**3.1.13****trained panel**

panel consisting of members who are trained to judge the intensity of odour emission

**3.1.14****air exchange rate**

ratio of the volume of clean air brought into the test chamber hourly and the free test chamber volume measured in identical units

**3.1.15****outlet air flow rate**

air volume per time at the chamber outlet

NOTE The outlet air flow rate is expressed as volume per second.

**3.1.16****air velocity**

air speed over the surface of the test specimen

**3.1.17****area specific air flow rate**

ratio between the supply air flow rate and the area of the test specimen

**3.1.18****building product**

building material or component produced for incorporation in a permanent manner in construction works

NOTE A building product can be solid, liquid or combined (see ISO 16000-11).

EXAMPLE 1 Examples of solid building products include flooring, wall covering, ceiling materials.

EXAMPLE 2 Examples of liquid building products include paints, varnishes, oils, waxes, levelling compounds, plasters, mortars, concrete, adhesives, sealants, caulks, putties and surface coatings.

EXAMPLE 3 Examples of combined building products include glued applications, such as floor and wall coverings, which are fixed on the building site on to surfaces using adhesives.

**3.1.19****diffuser**

funnel-shaped device for assessing the odour from the test chamber or from an odour sample container

**3.1.20****mask**

auxiliary odour-assessment device for cases where the exhaust air volumes required by the diffuser cannot be reached

**3.1.21****test chamber**

enclosure with controlled operational parameters for the determination of volatile organic compounds and odours emitted from test specimens prepared from building products

**3.1.22****test room**

room where the odour test takes place

**3.1.23****clean air**

odourless air

See 3.1.29.

**3.1.24****product loading factor**

ratio of exposed surface area of the test specimen and the free test chamber volume

**3.1.25****sample container**

device for containing or carrying used for transporting the odour sample from the test chamber to the test room and for introducing the sample to the panel members

EXAMPLE A container may be a carton, can, tube, bag or packaging.