



Designation: D1240 – 02 (Reapproved 2006)

Standard Test Methods for Rosin Acids Content of Naval Stores, Including Rosin, Tall Oil, and Related Products¹

This standard is issued under the fixed designation D1240; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 These test methods cover the determination of rosin acids in tall oil, tall oil fatty acid, tall oil rosin, and other naval stores products.

1.2 These test methods may not be applicable to adducts or derivatives of rosin, fatty acid, or other naval stores products.

1.3 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D1585 Test Methods for Fatty Acids Content of Naval Stores, Including Rosin, Tall Oil, and Related Products

E70 Test Method for pH of Aqueous Solutions With the Glass Electrode

E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

3. Summary of Test Method

3.1 The rosin acids content is determined by one of three procedures; by selective esterification of fatty acids to form methyl esters followed by titration of the unreacted rosin acids, by selective esterification of fatty acids to form butyl esters followed by titration of the unreacted rosin acids, or by

selective esterification of fatty acids to form methyl esters followed by extraction of the sulfuric acid catalyst and titration of the unreacted rosin acids.

4. Significance and Use

4.1 This is revision of the method for measuring rosin acids content combines the three major ways of determining the rosin acids content of naval stores products into a single method.

4.1.1 For materials containing less than 15 % rosin, the modified Glidden procedure has gained acceptance over the Herrlinger-Compeau. For materials containing more than 15 % rosin the modified Wolfe Method is preferred. The modified Wolfe and modified Glidden procedures differ only in their details. They have been combined here into a single procedure. This procedure can be run using either a potentiometer or an internal indicator to determine the end point of the titration. Use of a potentiometer is preferred and is the referee method. Use of an internal indicator is the principal alternative method. They will be referred to as the Potentiometric Method and the Internal Indicator Method to distinguish them from the Herrlinger-Compeau and Linder-Persson methods.

4.1.2 The Herrlinger-Compeau Method is limited in application to materials containing less than 15 % rosin. It is little used in the industry today. Much early work is based on this test method so it is included here to provide a historical basis for the overall test method.

4.1.3 The Linder-Persson Method is also little used in the industry today. It is applicable for measuring the rosin acids content of naval stores products containing greater than 60 % rosin. Like the Herrlinger-Compeau, it is included here to provide a historical basis for the test method. In those instances where they are used, the Herrlinger-Compeau and Linder-Persson methods are often in conjunction to cover the whole range of rosin content.

5. Reagents

5.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society

¹ These test methods are under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and are the direct responsibility of Subcommittee D01.34 on Naval Stores.

Current edition approved Nov. 1, 2006. Published November 2006. Originally approved in 1952. Last previous edition approved in 2002 as D1240 – 02. DOI: 10.1520/D1240-02R06.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

where such specifications are available.³ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

5.2 Unless otherwise indicated, references to water shall be understood to mean deionized or distilled water.

6. Preparation of Sample

6.1 Homogeneous liquid materials may be used without further preparation.

6.2 Nonhomogeneous liquid materials should be heated until they are homogeneous, then a portion taken for analysis.

6.3 Solid samples are subject to surface oxidation which may affect the results. Prepare the sample for analysis by chipping small pieces from a freshly exposed surface of a lump or lumps and crush to a coarse powder to facilitate weighing and solution. Prepare fresh on the same day, prior to weighing, in order to avoid changes due to surface oxidation of crushed rosin on exposure to the air.

ROSIN ACIDS CONTENT BY THE POTENTIOMETRIC METHOD (Referee Method)

7. Scope

7.1 This test method covers the determination of rosin acids content of tall oil rosin, tall oil fatty acid, and other naval stores products, where the most reproducible results are desired. By using the potentiometric inflection end points, the error due to colorimetric end points is avoided.

8. Summary of Test Method

8.1 A sample is refluxed with methyl sulfuric acid to esterify the fatty acids. The rosin acids and sulfuric acid are then titrated potentiometrically, and the rosin acids content calculated from the difference between the two inflection points obtained.

9. Apparatus

9.1 *pH Meter*—An indicating potentiometer having a limit of error not greater than ± 0.1 pH over a range from pH 1 to pH 13, using an alkali-resistant glass electrode and a saturated calomel half-cell. The pH meter shall conform to the requirements of Test Method E70. Alternatively, an automatic potentiometric titrator may be used.

9.2 *Stirrer*, magnetic, equipped with poly(tetrafluoroethylene)-coated stir bar.

9.3 *Buret*, 50-mL capacity, with 0.1-mL divisions. The so-called automatic buret is preferable as its use minimizes

errors due to evaporation. The automatic buret should be guarded with soda-lime tubes against the absorption of CO₂ from the air.

9.4 *Erlenmeyer Flask*, 250-mL or larger of a chemically resistant glass with a standard-taper 24/40 joint.

9.5 *Condenser*, water-cooled, equipped with a joint fitting the flask described in accordance with 9.4.

10. Reagents

10.1 *Alcoholic Alkali, Standard Solution (0.5 N)*—Dissolve 33 g of potassium hydroxide (KOH), preferably in pellet form, in methanol (CH₃OH) and dilute to 1 L with methanol. Standardize to ± 0.001 N with potassium acid phthalate (C₆H₄COOKCOOH) in 60 mL of water followed by 40 mL of methanol; 2.553 g of potassium acid phthalate will be neutralized by 25.00 mL of 0.5 N KOH solution. Protect the standardized solution against evaporation and absorption of carbon dioxide (CO₂) from the air. Restandardize the solution frequently, either potentiometrically or colorimetrically, using phenolphthalein as the indicator.

10.1.1 For fatty acids containing low concentrations of rosin acids, 0.1 N alcoholic potassium hydroxide may give superior results.

10.2 *Ethanol (95 %)*—Denatured alcohol conforming to Formula No. 3A or No. 30 of the U.S. Bureau of Internal Revenue, neutralized by the addition of KOH.

10.3 *Methanol (99.5 %)*.

10.4 *Methyl Sulfuric Acid Solution*—Slowly pour 100 g of concentrated sulfuric acid (H₂SO₄ sp gr 1.82 to 1.84), while stirring constantly, into 400 g of methanol. Extreme caution should be taken while preparing the methyl sulfuric acid. Adding sulfuric acid too rapidly may cause the methanol to flash out of its container. Store the methyl sulfuric acid in a glass-stoppered bottle.

10.5 *Toluene*.

11. Procedure

11.1 Weigh the sample to the nearest 0.001 g in a 250-mL flask. Choose the amount of sample so that the second titration will consume between 10 and 30 mL of KOH solution. For rosin acids, this will be about 5 g of material. For fatty acids containing less than 15 % rosin, this will be about 40 g of material. For fatty acids containing less than 3 % rosin acids titrating with 0.1 N KOH may give superior results. Table 1 gives suggested amounts of material to use.

11.2 Dissolve the sample in 100 mL of methanol in a 250-mL flask. If the sample has a high rosin content it may be helpful first to dissolve it in 25 mL of toluene before adding the

TABLE 1 Sample Size and Titrant

| Material | Sample Size, g | Reflux Time, min | KOH Normality, N |
|-------------------------|----------------|------------------|------------------|
| Rosin | 5 | 2 | 0.5 |
| Fatty acid, <15 % rosin | 40 | 20 | 0.5 |
| Fatty acid, <3 % rosin | 40 | 20 | 0.1 |

³ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmaceutical Convention, Inc. (USPC), Rockville, MD.

methanol. For material believed to contain less than 15 % fatty acid, that is, high in rosin, add 5 mL of methyl sulfuric acid, connect the flask assembly, and reflux the solution for 2 min. (Solid samples must be in solution before beginning reflux.) For materials believed to contain concentrations of fatty acid higher than 15 %, that is, low in rosin, use 10 mL of methyl sulfuric and reflux for 20 min. Measure reflux time from the moment the first drop of solvent returns to the flask from the condenser. Cool and transfer to a 400-mL beaker, using a total of 100 mL of methanol (**Note 1**) in three successive rinsings.

NOTE 1—Ethanol is preferable when an automatic titrator is used.

11.3 Turn the pH meter on and allow a few minutes for it to come to equilibrium. Balance the meter using a standard buffer solution as described in Test Method **E70**; then rinse the electrodes thoroughly with water and then with alcohol.

11.4 Immerse the electrode in the sample solution. Start the stirrer and adjust its speed for vigorous stirring without splattering.

11.5 Titrate the sample solution with 0.5 *N* KOH to a fixed pH of 4.0, the first end point. If it appears that the buret does not contain sufficient KOH to continue the titration to the second end point, refill the buret at this point. Continue the titration to the fixed pH of 10.8, the second point. Record the amount of KOH required for the titration between the first and second end point. If an automatic titrator is used, the end points shall be taken at the inflection points or at the fixed pH of 4.0 and 10.8.

12. Calculation

12.1 Calculate the percentage of rosin acids as follows:

12.1.1 For materials containing less than 15 % rosin:

$$\text{Rosin acids, \%} = [(A/N/B) \times 30.24] - 1.1 \quad (1)$$

where:

- A* = KOH solution required for titration between the first and second end points, mL,
N = normality of the KOH solution,
B = sample used, g, and
 30.24 = (mol weight of abietic acid × 100)/1000

12.1.2 For materials containing greater than 15 % rosin:

$$\text{Rosin acids, \%} = (A/N/B) \times 30.24 \quad (2)$$

where:

- A* = KOH solution required for titration between the first and second end points, mL,
N = normality of the KOH solution,
B = sample used, g, and
 30.24 = (mol wt of abietic acid × 100)/1000

12.2 Report the percentage of rosin acids calculated by either **12.1.1** or **12.1.2** to the first decimal place.

ROSIN ACIDS CONTENT BY THE INTERNAL INDICATOR METHOD (Alternative Method)

13. Scope

13.1 This test method covers the determination of rosin acids content of tall oil rosin, tall oil fatty acid, and other naval

stores products, using an internal indicator for the determination of the end point. It gives good results when routinely applied by a skilled analyst. However, where the most reproducible results by different analysts and laboratories are desired, the referee method (Sections **6** to **11**) should be used.

14. Summary of Test Method

14.1 A sample is refluxed with methyl sulfuric acid to esterify the fatty acids. The rosin acids and sulfuric acid are then titrated in the presence of thymol blue indicator. The rosin acids content is then calculated from the difference between the two color end points obtained.

15. Apparatus

15.1 The apparatus for the esterification and titration of the sample shall consist of the flask, condenser, and buret described in Section **9**.

16. Reagents

16.1 *Alcoholic Alkali, Standard Solution*—See **10.1**.

16.2 *Methanol*—See **10.3**

16.3 *Methyl Sulfuric Acid Solution*—See **10.4**.

16.4 *Thymol Blue Indicator Solution (1 g/L)*—Dissolve 1 g of thymol blue in 1000 mL of methanol.

16.5 *Toluene*.

17. Procedure

17.1 Weigh the sample to the nearest 0.001 g in a 250-mL flask. Choose the amount of sample so that the titration will consume between 10 and 30 mL of 0.5 *N* KOH. For rosin acids, this will be about 5 g of material. For fatty acids containing less than 15 % rosin, this will be about 40 g of material. For fatty acids containing less than 3 % rosin acids, titrating with 0.1 *N* KOH may give superior results. **Table 1** gives suggested amounts of material to use.

17.2 Dissolve the sample in 100 mL of methanol in a 250-mL flask. If the sample has a high-rosin content it may be helpful first to dissolve it in 25 mL of toluene before adding the methanol. For material believed to contain less than 15 % fatty acid, add 5 mL of methyl sulfuric acid, connect the flask assembly, and reflux the solution for 2 min. (Solid samples must be in solution before beginning reflux.) For materials believed to contain concentrations of fatty acid higher than 15 %, use 10 mL of methyl sulfuric and reflux for 20 min. Measure reflux time from the moment the first drop of solvent returns to the flask from the condenser. Cool, add 1 mL of thymol blue indicator.

17.3 Titrate with the KOH solution to the first end point, about pH 4.0, when the solution changes color from red to yellow. Record the reading or refill the buret. Continue the titration to the second end point, about pH 10.8, when the solution changes color from yellow to blue. Record to the nearest 0.1 mL the millilitres of KOH solution required for titration between the two end points.

NOTE 2—These end points approximate the inflection points under the nonaqueous conditions employed.