



Designation: D 1239 – 98 (Reapproved 2006)^{ε1}

Standard Test Method for Resistance of Plastic Films to Extraction by Chemicals¹

This standard is issued under the fixed designation D 1239; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Editorially revised 7.2 in November 2006.

1. Scope

1.1 This test method for resistance of plastic films to chemicals covers the measurement of the weight loss of film after immersion in chemicals.

NOTE 1—There is no ISO standard similar or equivalent to test method.

NOTE 2—Film is defined as sheeting having nominal thickness not greater than 0.25 mm [0.010 in.], in accordance with Terminology D 883.

1.2 The values stated in SI units are to be regarded as standard. The values stated in other units are nominal values given for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D 543 Practices for Evaluating the Resistance of Plastics to Chemical Reagents

D 618 Practice for Conditioning Plastics for Testing

D 882 Test Method for Tensile Properties of Thin Plastic Sheeting

D 883 Terminology Relating to Plastics

3. Terminology

3.1 Definitions—For definitions of technical terms pertaining to plastics used in this test method, see Terminology D 883.

4. Significance and Use

4.1 This test method is intended to be a rapid empirical test to determine the loss of the plasticizer or other extractable

components from the plastic film when immersed in liquids commonly used in households.

5. Apparatus

5.1 *Balance*—An accurate analytical balance.

5.2 *Containers*—Pint jars or cans with a diameter of at least 65 mm [2.5 in.] (one container for each specimen).

6. Materials

6.1 *Distilled Water*—Freshly prepared distilled or deionized water.

6.2 *Soap Solution (1 %)*—Dissolve 12 g of dehydrated pure white soap flakes (dried for 1 h at 105°C) in 1200 mL of distilled water. This is sufficient solution to test three specimens.

6.3 *Cottonseed Oil*—Household cooking grade.

6.4 *Mineral Oil, USP*—Heavy grade, sp gr 0.875 to 0.905.

6.5 *Kerosine*.

6.6 *Ethyl Alcohol (50 %)* as described in Test Method D 543.

6.7 Any other standard or supplementary reagent listed in Test Method D 543.

7. Test Specimen

7.1 The test specimens for plastic films shall be in the form of squares 50 ± 0.25 mm [2 in.] on each side. At least three specimens of each sample shall be tested with each chemical reagent.

7.2 Nothing in this test method precludes the use of specimens of other dimensions or the making of other tests on the same specimens after they have been exposed to the chemicals. Another acceptable specimen is a disk 50 ± 0.25 mm [2 in.] in diameter (total area 41.5 cm²), or a tension specimen 100 by 25 mm [4 by 1 in.] as prescribed in Test Methods D 882. For such specimens, use a proportionate amount of chemical and container of appropriate dimensions so that the specimen can be immersed in a completely vertical position during the test. The amount of chemical used shall be approximately 8 mL/cm², counting the area of both sides of the specimen.

¹ This test method is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials.

Current edition approved Nov. 1, 2006. Published November 2006. Originally approved in 1952. Last previous edition approved in 1998 as D 1239 – 98.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.