

SLOVENSKI STANDARD SIST EN ISO 2811-2:2002

01-september-2002

6 Uf j Y']b``U_]'!'8 c`c Yj Ub 1 [cghchY'!'&"XY'. A Yhc XU'g dchUd`1 b14 if HGC'&, %4 &%-+Ł

Paints and varnishes - Determination of density - Part 2: Immersed body (plummet) method (ISO 2811-2:1997)

Beschichtungsstoffe - Bestimmung der Dichte - Teil 2: Tauchkörper-Verfahren (ISO 2811 -2:1997) **iTeh STANDARD PREVIEW**

Peintures et vernis - Détermination de la masse volumique - Partie 2: Méthode par immersion d'un corps (plongeur) (ISO 2811-2:1997)2002

https://standards.iteh.ai/catalog/standards/sist/04901708-7b9d-4099-

Ta slovenski standard je istoveten z: EN ISO 2811-2-2002 EN ISO 2811-2-2001

ICS:

87.040 Barve in laki Paints and varnishes

SIST EN ISO 2811-2:2002

en

iTeh STANDARD PREVIEW (standards.iteh.ai)

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN ISO 2811-2

August 2001

ICS 87.040

English version

Paints and varnishes - Determination of density - Part 2: Immersed body (plummet) method (ISO 2811-2:1997)

Peintures et vernis - Détermination de la masse volumique - Partie 2: Méthode par immersion d'un corps (plongeur) (ISO 2811-2:1997) Beschichtungsstoffe - Bestimmung der Dichte - Teil 2: Tauchkörper-Verfahren (ISO 2811-2:1997)

This European Standard was approved by CEN on 29 June 2001.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

SIST EN ISO 2811-2:2002 https://standards.iteh.ai/catalog/standards/sist/04901708-7b9d-4099-84bc-0e79e204fb58/sist-en-iso-2811-2-2002



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

© 2001 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members. Ref. No. EN ISO 2811-2:2001 E

Foreword

The text of the International Standard from Technical Committee ISO/TC 35 "Paints and varnishes" of the International Organization for Standardization (ISO) has been taken over as an European Standard by Technical Committee CEN/TC 139 "Paints and varnishes", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2002, and conflicting national standards shall be withdrawn at the latest by February 2002.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 2811-2:1997 has been approved by CEN as a European Standard without any modification.

NOTE: Normative references to International Standards are listed in annex ZA (normative).

iTeh STANDARD PREVIEW (standards.iteh.ai)

Annex ZA (normative) Normative references to international publications with their relevant European publications

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of -any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

NOTE Where an International Publication has been modified by common modifications, indicated by (mod.), the relevant EN/HD applies.

| Publication | <u>Year</u> | Title | <u>EN</u> | <u>Year</u> |
|-------------|-------------|---|-------------|-------------|
| ISO 1513 | 1992 | Paints and varnishes - Examination and preparation of samples for testing | EN ISO 1513 | 1994 |

iTeh STANDARD PREVIEW (standards.iteh.ai)

iTeh STANDARD PREVIEW (standards.iteh.ai)

INTERNATIONAL STANDARD



First edition 1997-12-15

Paints and varnishes — Determination of density —

Part 2: Immersed body (plummet) method

iTeh Speintures et vernis — Détermination de la masse volumique — Partie 2: Méthode par immersion d'un corps (plongeur) (standards.iteh.ai)



Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

iTeh STANDARD PREVIEW

International Standard ISO 2811-2 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

SIST EN ISO 2811-2:2002

Together with the other parts, his/part/of/ISO 2811 cancels rands replaces 8-769d-4099-ISO 2811:1974, which has been technically revised 04fb58/sist-en-iso-2811-2-2002

ISO 2811 consists of the following parts, under the general title *Paints and varnishes* — *Determination of density*:

- Part 1: Pyknometer method
- Part 2: Immersed body (plummet) method
- Part 3: Oscillation method
- Part 4: Pressure cup method

Annex A forms an integral part of this part of ISO 2811. Annex B is for information only.

© ISO 1997

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization Case postale 56 • CH-1211 Genève 20 • Switzerland Internet central@iso.ch

X.400 c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

Paints and varnishes — Determination of density —

Part 2: Immersed body (plummet) method

1 Scope

This part of ISO 2811 is one of a series of standards dealing with the sampling and testing of paints, varnishes and related products.

It specifies a method for determining the density of paints, varnishes and related products using balls or other round bodies as immersion bodies (plummets).

The method is limited to materials of low or medium viscosity, and is particularly suitable for production control. (standards.iteh.ai)

2 Normative references

SIST EN ISO 2811-2:2002

https://standards.iteh.ai/catalog/standards/sist/04901708-7b9d-4099-

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 2811. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 2811 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 1512:1991, Paints and varnishes — Sampling of products in liquid or paste form.

ISO 1513:1992, Paints and varnishes — Examination and preparation of samples for testing.

3 Definition

For the purposes of this part of ISO 2811, the following definition applies.

3.1 density, ρ : The mass divided by the volume of a portion of a material, expressed in grams per millilitre (g/ml).

4 Principle

The method is based on Archimedes' principle. A container is filled with the product under test and placed on the analytical balance. The plummet is attached to a tripod and is immersed in the product under test. The density is calculated from the balance readings before the plummet is immersed in the material under test and after it is immersed.