
**Elastomeric seismic-protection
isolators —**

**Part 3:
Applications for buildings —
Specifications**

*Appareils d'appuis structuraux en élastomère pour protection
sismique —
Partie 3. Applications pour bâtiments — Spécifications*

ISO 22762-3:2010

<https://standards.iteh.ai/catalog/standards/sist/5387adf6-4bd6-4ae2-81a3-7db606b0f1fc/iso-22762-3-2010>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 22762-3:2010

<https://standards.iteh.ai/catalog/standards/sist/5387adf6-4bd6-4ac2-81a3-7db606b0f1fc/iso-22762-3-2010>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols.....	4
5 Classification	7
6 Requirements.....	9
7 Design rules	20
8 Manufacturing tolerances.....	25
9 Marking and labelling.....	31
10 Test methods	32
11 Quality assurance.....	32
Annex A (normative) Tensile stress in reinforcing steel plate.....	33
Annex B (informative) Determination of ultimate property diagram based on experimental results	35
Annex C (informative) Minimum recommended physical properties of rubber material	38
Annex D (informative) Effect of inner hole diameter and second shape factor on shear properties	39
Annex E (informative) Determination of compressive properties of elastomeric isolators	42
Annex F (informative) Determination of shear properties of elastomeric isolators.....	45
Annex G (informative) Method of predicting buckling limit at large deformations.....	50
Annex H (informative) Design of fixing bolts and flanges	57
Bibliography.....	60

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 22762-3 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 4, *Products (other than hoses)*.

This second edition cancels and replaces the first edition (ISO 22762-3:2005), which has been technically revised. It also incorporates the Technical Corrigendum ISO 22762-3:2005/Cor.1:2006.

ISO 22762 consists of the following parts, under the general title *Elastomeric seismic-protection isolators*:

- *Part 1: Test methods* <https://standards.iteh.ai/catalog/standards/sist/5387adf6-4bd6-4ae2-81a3-7db606b0f1fc/iso-22762-3-2010>
- *Part 2: Applications for bridges — Specifications*
- *Part 3: Applications for buildings — Specifications*

Introduction

ISO 22762 (all parts) consists of two parts related to specifications for isolators, i.e. ISO 22762-2 for bridges and ISO 22762-3 for buildings. This is because the isolator requirements for bridges and buildings are quite different, although the basic concept of the two products is similar. Therefore, ISO 22762-2 and the relevant clauses in ISO 22762-1 are used when ISO 22762 (all parts) is applied to the design of bridge isolators whereas this part of ISO 22762 and the relevant clauses of ISO 22762-1 are used when it is applied to building isolators.

The main differences to be noted between isolators for bridges and isolators for buildings are the following.

- a) Isolators for bridges are mainly rectangular in shape and those for buildings are circular in shape.
- b) Isolators for bridges are designed to be used for both rotation and horizontal displacement, while isolators for buildings are designed for horizontal displacement only.
- c) Isolators for bridges are designed to perform on a daily basis to accommodate length changes of bridges caused by temperature changes as well as during earthquakes, while isolators for buildings are designed to perform only during earthquakes.
- d) Isolators for bridges are designed to withstand dynamic loads caused by vehicles on a daily basis as well as earthquakes, while isolators for buildings are mainly designed to withstand dynamic loads caused by earthquakes only.

For structures other than buildings and bridges (e.g. tanks), the structural engineer uses either ISO 22762-2 or ISO 22762-3, depending on the requirements of the structure.

<https://standards.iteh.ai/catalog/standards/sist/5387adf6-4bd6-4ac2-81a3-7db606b0f1fc/iso-22762-3-2010>

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

ISO 22762-3:2010

<https://standards.iteh.ai/catalog/standards/sist/5387adf6-4bd6-4ae2-81a3-7db606b0f1fc/iso-22762-3-2010>

Elastomeric seismic-protection isolators —

Part 3: Applications for buildings — Specifications

1 Scope

This part of ISO 22762 specifies minimum requirements and test methods for elastomeric seismic isolators used for buildings and the rubber material used in the manufacture of such isolators.

It is applicable to elastomeric seismic isolators used to provide buildings with protection from earthquake damage. The isolators covered consist of alternate elastomeric layers and reinforcing steel plates. They are placed between a superstructure and its substructure to provide both flexibility for decoupling structural systems from ground motion, and damping capability to reduce displacement at the isolation interface and the transmission of energy from the ground into the structure at the isolation frequency.

iTeh STANDARD PREVIEW

2 Normative references (standards.iteh.ai)

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 630, *Structural steels — Plates, wide flats, bars, sections and profiles*

ISO 1052, *Steels for general engineering purposes*

ISO 22762-1:2010, *Elastomeric seismic-protection isolators — Part 1: Test methods*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

breaking

rupture of elastomeric isolator due to compression (or tension)-shear loading

3.2

buckling

state when elastomeric isolators lose their stability under compression-shear loading

3.3

compressive properties of elastomeric isolator

K_v

compressive stiffness for all types of rubber bearings

3.4

compression-shear testing machine

machine used to test elastomeric isolators, which has the capability of shear loading under constant compressive load

3.5

cover rubber

rubber wrapped around the outside of inner rubber and reinforcing steel plates before or after curing of elastomeric isolators for the purposes of protecting the inner rubber from deterioration due to oxygen, ozone and other natural elements and protecting the reinforcing plates from corrosion

3.6

design compressive stress

long-term compressive force on the elastomeric isolator imposed by the structure

3.7

effective loaded area

area sustaining vertical load in elastomeric isolators, which corresponds to the area of reinforcing steel plates

3.8

effective width

(rectangular elastomeric isolator) the smaller of the two side lengths of inner rubber to which direction shear displacement is not restricted

3.9

elastomeric isolator

rubber bearing, for seismic isolation of buildings, bridges and other structures, which consists of multi-layered vulcanized rubber sheets and reinforcing steel plates

EXAMPLE High-damping rubber bearings, linear natural rubber bearings and lead rubber bearings.

3.10

first shape factor

ratio of effectively loaded area to free deformation area of one inner rubber layer between steel plates

3.11

high-damping rubber bearing

HDR

elastomeric isolator with relatively high damping properties obtained by special compounding of the rubber and the use of additives

3.12

inner rubber

rubber between multi-layered steel plates inside an elastomeric isolator

3.13

lead rubber bearing

LRB

elastomeric isolator whose inner rubber with a lead plug or lead plugs press fitted into a hole or holes of the isolator body to achieve damping properties

3.14

linear natural rubber bearing

LNR

elastomeric isolator with linear shear force-deflection characteristics and relatively low damping properties, fabricated using natural rubber

NOTE Any bearing with relatively low damping can be treated as an LNR bearing for the purposes of isolator testing.

3.15**maximum compressive stress**

peak stress acting briefly on elastomeric isolators in compressive direction during an earthquake

3.16**nominal compressive stress**

long-term stress acting on elastomeric isolators in compressive direction as recommended by the manufacturer for the isolator, including the safety margin

3.17**roll-out**

instability of an isolator with either dowelled or recessed connection under shear displacement

3.18**routine test**

test for quality control of the production isolators during and after manufacturing

3.19**second shape factor**

(circular elastomeric isolator) ratio of the diameter of the inner rubber to the total thickness of the inner rubber

3.20**second shape factor**

(rectangular or square elastomeric isolator) ratio of the effective width of the inner rubber to the total thickness of the inner rubber

3.21**shear properties of elastomeric isolators**

comprehensive term that covers characteristics determined from isolator tests:

- shear stiffness, K_h , for LNR;
<https://standards.iteh.ai/catalog/standards/sist/5387adf6-4bd6-4ae2-81a3-7db606b0f1fc/iso-22762-3-2010>
- shear stiffness, K_h , and equivalent damping ratio, h_{eq} , for HDR and LRB;
- post-yield stiffness, K_d , and characteristic strength, Q_d , for LRB

3.22**structural engineer**

engineer who is in charge of designing the structure for base-isolated bridges or buildings and is responsible for specifying the requirements for elastomeric isolators

3.23**type test**

test for verification either of material properties and isolator performances during development of the product or that project design parameters are achieved

3.24**ultimate properties**

properties at either buckling, breaking, or roll-out of an isolator under compression-shear loading

3.25**ultimate property diagram****UPD**

diagram giving the interaction curve of compressive stress and buckling strain or breaking strain of an elastomeric isolator

4 Symbols

For the purposes of this document, the symbols given in Table 1 apply.

Table 1 — Symbols and descriptions

Symbol	Description
A	effective plan area; plan area of elastomeric isolator, excluding cover rubber portion
A_b	effective area of bolt
A_e	overlap area between the top and bottom elastomer area of isolator
A_{free}	load-free area of isolator
A_{load}	loaded area of isolator
A_p	area of the lead plug for a lead rubber bearing
a	side length of square elastomeric isolator, excluding cover rubber thickness, or length in longitudinal direction of rectangular isolator, excluding cover rubber thickness
a_e	length of the shorter side of the rectangular isolator, including cover rubber thickness
a'	length in longitudinal direction of the rectangular isolator, including cover rubber thickness
B	effective width for bending of flange
b	length in transverse direction of the rectangular isolator, excluding cover rubber thickness
b'	length in transverse direction of the rectangular isolator, including cover rubber thickness
c	distance from centre of bolt hole to effective flange section
D'	outer diameter of circular isolator, including cover rubber
D_f	diameter of flange
d_i	inner diameter of reinforcing steel plate
d_k	diameter of bolt hole
d_0	outer diameter of reinforcing steel plate
E_{ap}	apparent Young's modulus of bonded rubber layer
E_c	apparent Young's modulus corrected, if necessary, by allowing for compressibility
E_c^s	apparent Young's modulus corrected for bulk compressibility depending on its shape factor (S_1)
E_∞	bulk modulus of rubber
E_0	Young's modulus of rubber
F_u	tensile force on isolator by uplift
G	shear modulus
$G_{\text{eq}}(\gamma)$	equivalent linear shear modulus at shear strain
H	height of elastomeric isolator, including mounting flange
H_n	height of elastomeric isolator, excluding mounting flange
h_{eq}	equivalent damping ratio
$h_{\text{eq}}(\gamma)$	equivalent damping ratio as a function of shear strain

Table 1 (continued)

Symbol	Description
K_d	post-yield stiffness (tangential stiffness after yielding of lead plug) of lead rubber bearing
K_h	shear stiffness
K_i	initial shear stiffness
K_p	shear stiffness of lead plug inserted in lead rubber bearing
K_r	shear stiffness of lead rubber bearing before inserting lead plug
K_t	tangential shear stiffness
K_v	compressive stiffness
L_f	length of one side of a rectangular flange
M	resistance to rotation
M_f	moment acting on bolt
M_r	moment acting on isolator
n	number of rubber layers
n_b	number of fixing bolts
P	compressive force
P_0	design compressive force
P_{\max}	maximum compressive force
P_{\min}	minimum compressive force
P_{Tb}	tensile force at break of isolator
Q	shear force
Q_b	shear force at break
Q_{buk}	shear force at buckling
Q_d	characteristic strength
S_1	first shape factor
S_2	second shape factor
T	temperature
T_0	standard temperature, 23 °C or 27 °C; where specified tolerance is ± 2 °C, T_0 is standard laboratory temperature
T_r	total rubber thickness, given by $T_r = n \times t_r$
t_r	thickness of one rubber layer
t_{r1}, t_{r2}	thickness of rubber layer laminated on each side of plate
t_s	thickness of one reinforcing steel plate
t_0	thickness of outside cover rubber
$U(\gamma)$	function giving ratio of characteristic strength to maximum shear force of a loop
V	uplift force

Table 1 (continued)

Symbol	Description
v	loading velocity
W_d	energy dissipated per cycle
X	shear displacement
X_0	design shear displacement
X_b	shear displacement at break
X_{buk}	shear displacement at buckling
X_s	shear displacement due to quasi-static shear movement
X_{max}	maximum shear displacement
X_d	shear displacement due to dynamic shear movement
Y	compressive displacement
Z	section modulus of flange
α	coefficient of linear thermal expansion
γ	shear strain
γ_0	design shear strain
γ_a	upper limit of the total of design strains on elastomeric isolators
γ_b	shear strain at break
γ_c	local shear strain due to compressive force
γ_d	shear strain due to dynamic shear movement
γ_{max}	maximum design shear strain during earthquake
γ_r	local shear strain due to rotation
γ_s	shear strain due to quasi-static shear movement
γ_u	ultimate shear strain
δ_H	horizontal offset of isolator
δ_v	difference in isolator height measured between two points at opposite extremes of the isolator
ε	compressive strain of rubber
ε_{cr}	creep strain
ε_T	tensile strain of isolator
ε_{Tb}	tensile-break strain of isolator
ε_{Ty}	tensile-yield strain of isolator
ζ	ratio of total height of rubber and steel layers to total rubber height
θ	rotation angle of isolator about the diameter of a circular bearing or about an axis through a rectangular bearing
θ_a	rotation angle of isolator in the longitudinal direction (a)
θ_b	rotation angle of isolator in the transverse direction (b)

Table 1 (continued)

Symbol	Description
λ	correction factor for calculation of stress in reinforcing steel plates
η	correction factor for calculation of critical stress
κ	correction factor for apparent Young's modulus according to hardness
$\Sigma\gamma$	total local shear strain
ρ_R	safety factor for roll-out
ρ_T	safety factor for tensile force
σ	compressive stress in isolator
σ_0	design compressive stress
σ_B	tensile stress in bolt
σ_b	bending stress in flange
σ_{bf}	allowable bending stress in steel
σ_{cr}	critical stress in isolator
σ_f	allowable tensile stress in steel
σ_{max}	maximum compressive stress
σ_{min}	minimum compressive stress
σ_{nom}	for building: nominal long-term compressive stress recommended by manufacturer
σ_s	tensile stress in reinforcing steel plate
σ_{sa}	allowable tensile stress in steel plate
σ_{sy}	yield stress of steel for flanges and reinforcing steel plates
σ_{su}	tensile strength of steel for flanges and reinforcing steel plates
σ_t	tensile stress
σ_{te}	allowable tensile stress in isolator
τ_B	shear stress in bolt
τ_f	allowable shear stress in steel
ϕ	factor for computation of buckling stability
ξ	factor for computation of critical stress

5 Classification

5.1 General

Elastomeric isolators are classified by construction, their ultimate properties and tolerances on their performance.






5.2 Classification by construction

Elastomeric isolators are classified by construction, as shown in Table 2.

Other methods not listed in Table 2 may be used to fix flanges to the laminated rubber, if the resulting construction has adequate strength to resist the shear forces and bending moments due to shear deflection.

Furthermore, such constructions shall be capable of resisting tension if the elastomeric isolator is designed for uplift.

Table 2 — Classification by construction

Type	Construction	Illustration
Type I	Mounting flanges are bolted to connecting flanges, which are bonded to the laminated rubber. Cover rubber is added before curing of isolator.	
	Mounting flanges are bolted to connecting flanges, which are bonded to the laminated rubber. Cover rubber is added after curing of isolator.	
Type II	Mounting flanges are directly bonded to the laminated rubber.	
Type III	Isolators without mounting flanges, connected to base by either recess rings or dowell pins.	 Recess connection
		 Dowell connection

5.3 Classification by tolerance on shear properties

Elastomeric isolators are classified by tolerance on shear properties, as shown in Table 3.

Table 3 — Classification by tolerance of shear properties

Class	Individual	Global
S-A	$\pm 15 \%$	$\pm 10 \%$
S-B	$\pm 25 \%$	$\pm 20 \%$

6 Requirements

6.1 General

Elastomeric isolators for buildings and the materials used in manufacture shall meet the requirements specified in this clause. For test items (see Table 4) that have no specific required values, the manufacturer shall define the values and inform the purchaser prior to production.

The standard temperature for determining the properties of elastomeric isolators is 23 °C or 27 °C in accordance with prevailing International Standards. However, it is advisable to establish a range of working temperatures taking into consideration actual environmental temperatures and possible changes in temperatures at the work site where the elastomeric isolators are installed.

Table 4 — Test pieces for type testing

Properties	Test item	Test piece
Compressive properties	Compressive stiffness	Full-scale only
Shear properties	Shear stiffness	Full-scale only
	Equivalent damping ratio	
	Post-yield stiffness (for LRB)	
	Characteristic strength (for LRB)	
Tensile properties	Tensile fracture strength	Scale B
	Tensile yield strength	
Dependency of shear properties	Shear strain dependency	Full-scale only
	Compressive stress dependency	Full-scale only
	Frequency dependency	Scale A, STD, SBS
	Repeated loading dependency	Scale B
	Temperature dependency	Scale A, STD, SBS
Dependency of compressive properties	Shear strain dependency	Scale B
	Compressive stress dependency	
Ultimate properties	Shear displacement capacity	Scale B
Durability	Ageing	Scale A, STD, SBS
	Creep	Scale A

Scale A: Scaling such that, for a circular bearing, diameter ≥ 150 mm, for a rectangular bearing, side length ≥ 100 mm and, for both types, rubber layer thickness $\geq 1,5$ mm and thickness of reinforcing steel plates $\geq 0,5$ mm.

Scale B: Scaling such that, for a circular bearing, diameter ≥ 500 mm, for a rectangular bearing, side length ≥ 500 mm and, for both types, rubber layer thickness $\geq 1,5$ mm and thickness of reinforcing steel plates $\geq 0,5$ mm. Minimum scale factor 0,5.

STD = standard test piece (see Tables 10 and 11 of ISO 22762-1:2010).

SBS = shear-block test piece specified in ISO 22762-1:2010, 5.8.3. With LRB, SBS shall only be used for ageing tests.