
**Paints and varnishes — Determination of
density —**

**Part 2:
Immersed body (plummet) method**

Peintures et vernis — Détermination de la masse volumique —

Partie 2: Méthode par immersion d'un corps (plongeur)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 2811-2:2011

<https://standards.iteh.ai/catalog/standards/sist/7d42b42e-a01b-4f23-ae8a-ea8efe145757/iso-2811-2-2011>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 2811-2:2011

<https://standards.iteh.ai/catalog/standards/sist/7d42b42e-a01b-4f23-ae8a-ea8efe145757/iso-2811-2-2011>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Temperature	1
6 Apparatus	2
7 Sampling	3
8 Procedure	3
8.1 General	3
8.2 Determination	3
9 Calculation	4
10 Precision	5
10.1 General	5
10.2 Repeatability limit, r	5
10.3 Reproducibility limit, R	5
11 Test report	5
Annex A (informative) Example of a calibration method	7
Annex B (informative) Temperature variation	8

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2811-2 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

This second edition cancels and replaces the first edition (ISO 2811-2:1997), which has been technically revised.

The main changes are the following.

- a) The unit for the density has been changed from grams per millilitre to grams per cubic centimetre, because this is the more common SI unit.
- b) The determination in duplicate has been changed to a single determination.
- c) The information on calibration procedure has been changed to an example only and the status of Annex B has been changed from normative to informative.
- d) The precision data has been updated by an interlaboratory test.
- e) The normative references have been updated.

ISO 2811 consists of the following parts, under the general title *Paints and varnishes — Determination of density*:

- *Part 1: Pyknometer method*
- *Part 2: Immersed body (plummet) method*
- *Part 3: Oscillation method*
- *Part 4: Pressure cup method*

Paints and varnishes — Determination of density —

Part 2: Immersed body (plummet) method

1 Scope

This part of ISO 2811 specifies a method for determining the density of paints, varnishes and related products, using balls or other round bodies as immersion bodies (plummetts).

The method is limited to materials of low or medium viscosity, and is particularly suitable for production control.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1513, *Paints and varnishes — Examination and preparation of test samples*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

density

ρ

mass divided by the volume of a portion of a material

NOTE It is expressed in grams per cubic centimetre.

4 Principle

The method is based on Archimedes' principle. A container is filled with the product under test and placed on the analytical balance. The plummet is attached to a tripod and is immersed in the product under test. The density is calculated from the balance readings before the plummet is immersed in the material under test and after it is immersed.

5 Temperature

The effect of temperature on density is highly significant with respect to filling properties, and varies with the type of product.

For international reference purposes, it is essential to standardize one test temperature, and $(23,0 \pm 0,5) ^\circ\text{C}$ is specified in this part of ISO 2811. However, it can be more convenient to carry out comparative testing at some other agreed temperature, for example $(20,0 \pm 0,5) ^\circ\text{C}$, as specified by relevant weights and measures legislation (see B.2).


The test sample and plummet shall be conditioned to the specified or agreed temperature, and it shall be ensured that the temperature variation does not exceed $0,5 ^\circ\text{C}$ during testing.

6 Apparatus

Ordinary laboratory apparatus and glassware, together with the following.

6.1 Plummet, of non-corrodible metal, e.g. copper-zinc alloy (brass), stainless steel or aluminium, as illustrated in Figure 1. The type illustrated is available with a volume of 10 cm^3 or 100 cm^3 .

Dimensions in millimetres



Key

- 1 volume 100 cm^3 or 10 cm^3 to the centre of the constriction in the stem
- d 3 mm for the 100 cm^3 plummet or 1 mm for the 10 cm^3 plummet

Figure 1 — Plummet

Each plummet shall be marked with its volume, the reference temperature and the surface tension and density of the reference liquid in the following form:

100 cm^3 $23 ^\circ\text{C}$ 25 mN/m $1,2 \text{ g/cm}^3$

6.2 Analytical balance, accurate to 10 mg.

6.3 Thermometer, accurate to $0,2 ^\circ\text{C}$ and graduated at intervals of $0,2 ^\circ\text{C}$ or finer.

6.4 Temperature-controlled chamber, capable of accommodating the balance, plummet and sample and maintaining them at the specified or agreed temperature (see Clause 5).

6.5 Tripod or other suitable device, for suspending the plummet and accurately adjusting its depth of immersion.

7 Sampling

Take a representative sample of the product under test, as described in ISO 15528. Examine and prepare the sample, as described in ISO 1513.

8 Procedure

8.1 General

Carry out a single determination on a fresh test sample.

The volume of the plummet shall be calibrated.

8.2 Determination

8.2.1 Selection of procedure

There are two procedures, one for all paints in general and one for those products containing fast-evaporating solvents.

8.2.2 Procedure A — For all paints in general

Ensure the plummet (6.1) is thoroughly clean before use. Place the plummet and the test sample next to the balance (6.2) in the temperature-controlled chamber (6.4) for approximately 30 min.

Place a sufficient volume of the test sample in a vessel of suitable size and capacity, e.g. 400 cm³ for a 100 cm³ plummet and 100 cm³ for a 10 cm³ plummet.

Using the thermometer (6.3), measure the temperature of the test sample. Check throughout the determination that the temperature of the chamber remains within the specified limits.

Place the vessel plus test sample on the balance and record the mass, m_1 (uncorrected for buoyancy), to the nearest 10 mg. Clamp the plummet onto the tripod (6.5) in such a way that it can be immersed in the sample without touching the sides of the vessel (see Figure 2).

Immerse the plummet in the sample until the surface of the liquid reaches the middle of the constriction in the plummet stem and record the mass, m_2 , to the nearest 10 mg.

NOTE If the balance is tared between weighings, mass $m_1 = 0$.




Figure 2 — Determination of density by the plummet method

8.2.3 Procedure B — For paints containing fast-evaporating solvents

Ensure that the plummet (6.1) is thoroughly clean before use. Place the plummet and the test sample next to the balance (6.2) in the temperature-controlled chamber (6.4) for approximately 30 min.

Using the thermometer (6.3), measure the temperature, t_T , of the test sample. Check throughout the determination that the temperature of the chamber remains within the specified limits.

Place a vessel of suitable size, containing a sufficient volume of test sample, on a laboratory jack.

Clamp the plummet onto a retort stand and place the stand on the balance in such a way that the plummet can be immersed in the sample by raising the laboratory jack without the plummet touching the sides of the vessel. Record the mass, m_2 , of the stand plus plummet.

Raise the laboratory jack until the surface of the liquid reaches the middle of the constriction in the plummet stem and record the mass, m_1 .

Equation (1) can be used to calculate the density, except that m_1 and m_2 are as follows:

m_1 is the mass of the retort stand and plummet after immersion of the plummet in the sample;

m_2 is the mass of the retort stand and plummet before immersion of the plummet.

9 Calculation

Calculate the density, ρ , of the product, in grams per cubic centimetre, at the test temperature, t_T , using Equation (1):

$$\rho = \frac{m_2 - m_1}{V_t} \quad (1)$$

where

m_1 is the mass, in grams, of the vessel containing the sample before immersion of the plummet;

m_2 is the mass, in grams, of the vessel after immersion of the plummet;

V_t is the volume, in cubic centimetres, of the plummet up to the middle of the constriction in the stem at the test temperature, t_T , determined in accordance with Annex B.

NOTE The result is not corrected for air buoyancy because the uncorrected value is required by most filling-machine control procedures and the correction (0,001 2 g/cm³) is negligible in relation to the precision of the method.

If the test temperature used is not the reference temperature, the density may be calculated using Equation (B.2).

10 Precision

10.1 General

The precision of the method depends on the characteristics of the product to be tested. For materials which contain no entrapped air, the values in 10.2 and 10.3 are valid.

10.2 Repeatability limit, r

The value below which the absolute difference between two single test results, obtained on identical material by one operator in one laboratory, within a short interval of time using the standardized test method, may be expected to lie, with a 95 % probability using the same equipment is

- 0,002 g/cm³ for solvents,
- 0,011 g/cm³ for coating materials using the 10 cm³ plummet, and
- 0,003 g/cm³ for coating materials using the 100 cm³ plummet.

10.3 Reproducibility limit, R

The value below which the absolute difference between two test results, obtained on identical material by operators in different laboratories using the standardized test method, may be expected to lie, with a 95 % probability, is

- 0,004 g/cm³ for solvents,
- 0,030 g/cm³ for coating materials using the 10 cm³ plummet, and
- 0,004 g/cm³ for coating materials using the 100 cm³ plummet.

11 Test report

The test report shall include at least the following information:

- a) all details necessary to identify the product tested;
- b) a reference to this part of ISO 2811, i.e. ISO 2811-2:2011;
- c) the type of plummet used and its volume (e.g. 100 cm³ ball);